



Designation: D 1468 – 93 (Reapproved 1996)

AMERICAN SOCIETY FOR TESTING AND MATERIALS
100 Barr Harbor Dr., West Conshohocken, PA 19428
Reprinted from the Annual Book of ASTM Standards. Copyright ASTM

Standard Test Method for Volatile Matter in Tricresyl Phosphate¹

This standard is issued under the fixed designation D 1468; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This test method covers a procedure for determining the volatile matter in tricresyl phosphate.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* For specific hazard statements, see Section 4.

1.3 For hazard information and guidance, see the supplier's Material Safety Data Sheet.

2. Significance and Use

2.1 This test method provides a measurement of volatile matter in tricresyl phosphate. The results of this measurement can be used for specification acceptance and determining performance in plasticizer use.

3. Apparatus

3.1 *Oven*, thermostatically controlled at $105 \pm 5^\circ\text{C}$.

3.2 *Petri Dish*, 100-mm diameter, or equivalent.

4. Hazards

4.1 Tricresyl phosphate is hazardous through inhalation or skin absorption. Take care in handling the material.

4.2 Ortho-isomer of tricresyl phosphate is considered toxic.

¹ This test method is under the jurisdiction of ASTM Committee D-1 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.35 on Solvents, Plasticizers, and Chemical Intermediates.

Current edition approved Oct. 15, 1993. Published December 1993. Originally published as D 1468 – 57 T. Last previous edition D 1468 – 84 (1988) ϵ ¹

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.

Trace amounts may be present in tricresyl phosphate specimens.

5. Procedure

5.1 Place a flat aluminum, glass, or porcelain dish in an oven at $105 \pm 5^\circ\text{C}$ for 1 h. Cool in a desiccator and weigh to 10 mg. Spread evenly over the bottom of the dish approximately 25 g of the sample. Weigh the dish and the specimen to 10 mg and place in an oven at $105 \pm 5^\circ\text{C}$ for 3 h. Cool the dish and specimen in a desiccator, and reweigh to 10 mg.

6. Calculation

6.1 Calculate the volatile matter in tricresyl phosphate as follows:

$$\text{Volatile matter, \%} = [(S - R)/S] \times 100 \quad (1)$$

where:

S = weight of specimen used, g, and

R = weight of specimen after heating, g.

7. Precision and Bias

7.1 *Precision*—Results should not differ from the mean by more than the following amounts:

	Within laboratory	Between laboratories
Volatile matter, weight %	0.05	0.1

7.2 *Bias*—Bias has not been determined for this test method.

8. Keywords

8.1 tricresyl phosphate; volatile matter