



# Standard Specification for Melamine-Formaldehyde Molding Compounds<sup>1</sup>

This standard is issued under the fixed designation D 704; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope \*

1.1 This specification covers compression molding, thermo-setting, melamine-formaldehyde molding compounds as further defined in 4.1, resin binder, with or without other resins, intimately combined with fillers, pigments, and any chemical agents needed.

1.2 The values stated in SI units are to be regarded as the standard.

NOTE 1—The properties included in this specification are those required to identify the types of molding compounds covered. There may be other requirements necessary to identify particular characteristics. These will be added to the specification as their inclusion becomes generally desirable and the necessary test data and methods become available. Transfer or injection molding will usually result in different physical and electrical characteristics than compression molding.

NOTE 2—ISO 2122-1977(E) is similar but not equivalent to this specification. Product classification and characterization are not equivalent.

## 2. Referenced Documents

### 2.1 ASTM Standards:

- D 149 Test Method for Dielectric Breakdown Voltage and Dielectric Strength of Solid Electrical Insulating Materials at Commercial Power Frequencies<sup>2</sup>
- D 150 Test Methods for A-C Loss Characteristics and Permittivity (Dielectric Constant) of Solid Electrical Insulating Materials<sup>2</sup>
- D 256 Test Method for Determining the Pendulum Impact Resistance of Notched Specimens of Plastics<sup>3</sup>
- D 495 Test Method for High-Voltage, Low-Current, Dry Arc Resistance of Solid Electrical Insulation<sup>2</sup>
- D 570 Test Method for Water Absorption of Plastics<sup>2</sup>
- D 618 Practice for Conditioning Plastics for Testing<sup>3</sup>
- D 648 Test Method for Deflection Temperature of Plastics Under Flexural Load<sup>3</sup>
- D 731 Test Method for Molding Index of Thermosetting Molding Powder<sup>3</sup>

- D 790 Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials<sup>3</sup>
- D 792 Test Methods for Density and Specific Gravity (Relative Density) of Plastics by Displacement<sup>3</sup>
- D 883 Terminology Relating to Plastics<sup>2</sup>
- D 1895 Test Methods for Apparent Density, Bulk Factor, and Pourability of Plastic Materials<sup>3</sup>
- D 1896 Practice for Transfer Molding Test Specimens of Thermosetting Compounds<sup>3</sup>
- D 3638 Test Method for Comparative Tracking Index of Electrical Insulating Materials<sup>4</sup>
- D 3795 Test Method for Thermal Flow and Cure Properties of Thermosetting Plastics by Torque Rheometer<sup>5</sup>
- D 3892 Practice for Packaging/Packing of Plastics<sup>6</sup>
- D 5224 Practice for Compression Molding Test Specimens of Thermosetting Molding Compounds<sup>7</sup>
- D 6289 Test Method for Measuring Shrinkage from Mold Dimensions of Molded Thermosetting Plastics<sup>7</sup>
- 2.2 ASTM Special Technical Publication:  
STP 15 D Manual on Quality Control of Materials<sup>8</sup>
- 2.3 ISO Standard:  
ISO 2122-1977(E) Plastics—Aminoplastic Molding Materials—Specification<sup>9</sup>

## 3. Terminology

3.1 *Definitions*—For definitions of technical terms pertaining to plastics used in this specification see Terminology D 883.

## 4. Classification

4.1 The molding compounds covered by this specification shall be designated by types, based upon their principal characteristics and the fillers used.

4.1.1 *Type 1*—General-purpose compound with cellulose filler, available in colors, white, and black. Suitable for general, mechanical, and electrical applications.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D-20 on Plastics and is the direct responsibility of Subcommittee D20.16 on Thermosetting Materials.

Current edition approved Nov. 10, 1999. Published February 2000. Originally published as D 704 – 43 T. Last previous edition D 704 – 94.

<sup>2</sup> Annual Book of ASTM Standards, Vol 10.01.

<sup>3</sup> Annual Book of ASTM Standards, Vol 08.01.

<sup>4</sup> Annual Book of ASTM Standards, Vol 10.02.

<sup>5</sup> Annual Book of ASTM Standards, Vol 10.03.

<sup>6</sup> Annual Book of ASTM Standards, Vol 08.02.

<sup>7</sup> Annual Book of ASTM Standards, Vol 08.03.

<sup>8</sup> Available from ASTM Headquarters. Request PCN 04-015030-34.

<sup>9</sup> Available from American National Standards Institute, 11 W. 42nd St., 13th Floor, New York, NY 10036.

\*A Summary of Changes section appears at the end of this standard.

4.1.2 *Type 2*—A mineral- and flock-filled compound for industrial uses involving elevated-temperature and electrical applications.

4.1.3 *Type 3*—A compound with chopped cotton-cloth filler, having greater impact strength than the other Types 1 through 7.

4.1.4 *Type 5*—Unreinforced molding compound with high translucency, particularly suited for small pearlescent moldings.

4.1.5 *Type 6*—A wood-filled compound for general industrial uses involving mechanical and electric applications.

4.1.6 *Type 7*—Similar to Type 6, but with cellulose filler and improved insert-holding properties.

4.1.7 *Type 8*—A glass-fiber-reinforced compound with high impact strength and good electrical properties.

4.1.8 *Type 9*—Short-fiber, glass-filled compound with good dimensional stability and mechanical properties.

4.1.9 *Type 10*—A glass fiber-filled compound, with medium impact strength.

4.1.10 *Type 11*—A glass-filled, chopped strand compound with extremely high impact strength and good arc resistance.

4.1.11 *Type 12*—A fabric-filled compound with medium impact strength.

NOTE 3—Melamine molding compounds are of a limited storage stability. Melamine resins advance rapidly when stored at elevated temperatures.

## 5. Ordering Information

5.1 The order for the compound shall specify name, type, color, and plasticity.

NOTE 4—Compounds with a higher bulk factor than specified in Table 1 may be available.

## 6. Property Requirements

6.1 The molding compounds covered by this specification, when molded in accordance with Practice D 5224, shall conform to the requirements prescribed in Table 1.

6.2 The required plasticity shall be agreed upon between the purchaser and producer or supplier. Test Methods D 731 and D 3795 are suggested for measuring plasticity and rate of cure.

6.3 The requirements in Table 1 shall be considered as minimum or maximum average values. Individual test results may vary  $\pm 10\%$  from the average, in most cases (Note 5). In

the case of arc resistance, all test results must be averaged, when practicable, and the range of test results must always be reported. For all other tests, a single result beyond the range of four times the estimated standard deviation must be discarded, retests made, and the resulting value substituted for the discarded value (Note 6).

NOTE 5—The moisture content of the molding compound and the molded part, as well as mold design, molding process, and molding conditions, also influence test results.

NOTE 6—A method for determining 99 % confidence limits is given in STP 15 D.

## 7. Sampling

7.1 A batch or lot shall be considered as a unit of manufacture and may consist of a blend of two or more production runs of compound.

7.2 Adequate statistical sampling shall be used.

## 8. Test Specimen Preparation

8.1 Where molded specimens are required, Practice D 5224 shall be followed as applicable (Note 7). Molds shall be constructed in accordance with Practice D 1896.

NOTE 7—Some melamine compounds may not feed, plasticize, or mold satisfactorily at the designated temperatures of Practice D 5224. In such cases the recommendation of the manufacturer shall be followed.

## 9. Conditioning

9.1 Measure the plasticity on compounds in the “as received” condition. However, for referee tests, store and condition the samples as described in Test Method D 731.

9.2 Condition molded test specimens in accordance with Procedure B of Practice D 618.

9.3 Conduct all testing in the Standard Laboratory Atmosphere as specified in Practice D 618, unless otherwise specified in the referenced test methods or in this specification.

## 10. Test Methods

10.1 Determine the properties enumerated in this specification in accordance with the following methods:

10.1.1 *Bulk Factor*—Test Methods D 1895, using the appropriate method for the compound involved.

**TABLE 1 Requirements for Compression-Molded Test Specimens<sup>A</sup>**

Property	Types											
	1	2	3	5	6	7	8	9	10	11	12	
Bulk factor, max	2.7	3.0	...	...	2.9	...	...	4.0	5.0	10.0	14.0	
Specific gravity, max	1.60	1.80	1.60	1.55	1.60	1.55	2.00	1.90	2.20	2.00	1.55	
Water absorption, max, weight gain %	0.40	0.25	0.60	0.35	0.60	0.60	0.20	0.15	0.20	0.20	0.50	
Impact resistance, min, J/m of notch	13.3	16.0	29.4	7.5	16.0	16.0	170.8	32.0	48.0	1066	53.3	
Flexural strength, min, MPa	68.9	51.0	82.7	65.5	44.8	40.0	68.9	96.5	82.7	137.8	96.5	
Deflection temperature, min, °C	177	168	162.7	148.8	166	166	204	196	166	204	202	
Dielectric strength, min, S/S, kV/mm	9.8	9.8	3.9	...	7.9	7.9	6.7	9.45	9.06	...	6.89	
Dissipation factor, max, 1 MHz	0.05	0.060	...	...	0.055	...	...	0.02	0.02	...	0.07	
Arc resistance, min, s	120	180	125	...	180	70	180	180	180	180	140	
Shrinkage, max, m/m	0.008	0.006	0.005	0.012	0.008	0.008	0.003	0.004	0.003	0.004	0.005	
CTI, min, V	500	...	600	...	400	...	...	...	...	700	...	

<sup>A</sup> The values shown herein were obtained under specified conditions. Any other conditions may significantly alter these values.

10.1.2 *Specific Gravity*—Method A of Test Methods D 792. A 3.2 by 51-mm disk is a recommended specimen for compounds containing long-fiber fillers that are subject to resin-squeeze-out and flow under pressure.

10.1.3 *Water Absorption*—Test Method D 570, 24-h immersion procedure.

10.1.4 *Impact Resistance (Izod)*—Method A of Test Methods D 256, using a 12.7 by 12.7 by 63.5-mm bar.

10.1.5 *Flexural Strength*—Method I, Procedure A of Test Methods D 790, using a 6.4 by 12.7 by 127-mm bar, tested parallel to molding pressure.

10.1.6 *Deflection Temperature*—Test Method D 648, at a fiber stress of 1.82 MPa on a 12.7 by 12.7 by 127-mm bar, loaded perpendicular to molding pressure at a 102-mm span.

10.1.7 *Dielectric Strength*—Test Methods D 149, using specimens 3.2 by 102 mm or larger, tested under transformer oil between cylindrical brass electrodes 25.4 mm in diameter, with edges next to specimen rounded to a radius of 3.2 mm and a length of 25.4 mm. The rate of rise for the short-time test shall be 0.5 kV/s (Note 8). For the step-by-step test the

increment of voltage increase shall be 2 kV and shall be applied for a period of 1 min.

NOTE 8—The short-time test determines the initial voltage for the step-by-step test.

10.1.8 *Permittivity and Dissipation Factor*—Test Method D 150, using a 3.2 by 102-mm specimen for all frequencies up to and including 1 MHz.

10.1.9 *Arc Resistance*—Test Method D 495, using tungsten electrodes.

10.1.10 *Shrinkage*—Test Method D 6289.

10.1.11 *Comparative Tracking Index (CTI)*—Test Method D 3638.

## 11. Packaging and Package Marking

11.1 All packing, packaging, and marking provisions of Practice D 3892 shall apply to this specification.

## 12. Keywords

12.1 formaldehyde; melamine-formaldehyde; molding compounds (thermosetting)

## SUMMARY OF CHANGES

This section identifies the location of selected changes to this specification. For the convenience of the user, Committee D-20 has highlighted those changes that may impact the use of this specification. This section also may include descriptions of the changes or reasons for the changes, or both.

### *D 704–94:*

- (1) ISO equivalency statement was included.
- (2) Keywords were editorially incorporated.
- (3) Removal of sections regarding purchaser/producer agreements outside Practice D 1898.
- (4) Removal of quality assurance (QA) provisions for government/military procurement.

### *D 704–99:*

- (1) Editorial change to clarify scope in 1.1.

- (2) Removed inch-pound units throughout.
- (3) Deleted references to Practice D 1898 as Practice D 1898 has been discontinued with no replacement.
- (4) Practice D 647 has been replaced by Practice D 1896; Method D 955 has been replaced by Practice D 6289; and, Practice D 956 has been replaced by Practice D 5224.
- (5) Revised 6.1, 6.3, 7.2, 8.1 and Notes 6 and 7 reflecting discontinued and replacement standards.
- (6) Added Summary of Changes.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).*