



Designation: D 1766 – 9601

Standard Test Method for Rubber Chemicals—Solubility¹

This standard is issued under the fixed designation D 1766; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

- 1.1 This test method covers a practical test for the solubility of commercial chemicals used in rubber products.
- 1.2 It is not a true measure of solubility, since equilibrium is not approached from both sides, that is, higher temperature and lower temperature.
- 1.3 The test method indicates the total solubility, under the conditions of the test, of all components in the presence of each other and in the proportions present in the sample.
- 1.4 This test method does not measure the solubility of a rubber chemical in rubber.
- 1.5 The values stated in SI units are to be considered standard.
- 1.6 *This standard does not purport to address the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

- 2.1 *ASTM Standards:*

¹ This test method is under the jurisdiction of ASTM Committee D-11 on Rubber and is the direct responsibility of Subcommittee D11.11 on Chemical Analysis. Current edition approved Jan. 10, 1996. 2001. Published February 1996. January 2002. Originally issued 1960. Replaces D 1766 – 60 T. Last previous edition D 1766 – 90 (1995) ϵ . D 1766 – 96.

E 145 Specification for Gravity-Convection and Forced-Ventilation Ovens²

3. Summary of Test Method

3.1 The test specimen is shaken in a specified volume of a desired solvent at a specified time and temperature. Solids are allowed to settle and a specified aliquot of the clear supernatant solvent is quantitatively removed, the solvent evaporated, and the mass of the residue obtained. From the masses of the residue and original specimen, the solubility of the specimen is obtained by calculation.

4. Significance and Use

4.1 This test method may be used as a raw material quality-control tool.

5. Apparatus

5.1 *Containers*, capacity approximately 100 cm³ (4-oz), glass, screw caps with metal foil liners.

5.2 *Weighing Bottles*, 50-cm³, ground-glass, low-form, with covers.

5.3 *Mechanical Shaker*.

5.4 *Steam Bath*.

5.5 *Oven*, constant-temperature, controllable, 110°C max in accordance with Type B of Specification E 145.

6. Procedure

6.1 Place 50 cm³ of the desired solvent in each of two suitable containers described in 5.1. Add, with shaking, a sufficient test specimen of the organic chemical in the “as-received” condition to each of the bottles to give apparent saturation, and then add about 25 % more. Close both bottles tightly and place in a mechanical shaker, at room temperature, for a minimum of 4 h.

6.2 Hold at $25 \pm 0.5^\circ\text{C}$ with occasional shaking for a minimum of an additional 4 h. If a significant quantity of solids is not in evidence at this point in both bottles, add 25 % more of the organic chemical to each bottle and repeat both shaking cycles.

6.3 Allow the solids to settle and while maintaining the temperature of the solution at $25 \pm 0.5^\circ\text{C}$, remove this solution by pipetting 25-cm³ aliquots from each of the bottles through a suitable filter stick (Note 1). Transfer the contents of the pipets into each of two tared, ground-glass, low-form, 50-cm³, covered weighing bottles. Call the tare masses *A*. Cover the weighing bottles immediately. Weigh the bottles and solution. Call these masses *B*.

NOTE 1—A filter stick may be made by wiring a small piece of medium grade filter paper over the end of a pipet with fine wire. The filter paper should be removed before emptying the pipet. A pressure-type apparatus may also be used to fill the pipet.

6.4 Remove the covers and evaporate the solvent on a steam bath. Then place the bottles in an oven maintained at a temperature at least 10°C below the melting point of the product (but in no case higher than 110°C), and dry to constant mass. Place the bottles in a covered desiccator until cool, and then weigh. Call these masses *C*.

7. Calculation

7.1 The solubility may be calculated as follows:

$$\text{Mass of } 25 \text{ cm}^3 \text{ of solution at } 25^\circ\text{C} = B - A \quad (1)$$

$$\text{Mass of } 25 \text{ cm}^3 \text{ of solution at } 23^\circ\text{C} = B - A \quad (1)$$

$$\text{Mass of solute in } 25 \text{ cm}^3 \text{ solution at } 25^\circ\text{C} = C - A \quad (2)$$

$$\text{Mass of solute in } 25 \text{ cm}^3 \text{ solution at } 23^\circ\text{C} = C - A \quad (2)$$

(see Section 7).

$$\text{Solubility in grams of solute per } 100 \text{ cm}^3 \text{ of solution} \quad (3)$$

$$\text{at } 25^\circ\text{C} = (C - A) \times 4$$

$$\text{at } 23^\circ\text{C} = (C - A) \times 4$$

NOTE 2—Solubility may also be expressed as follows:

$$\text{Mass of solvent in } 25 \text{ cm}^3 \text{ of solution at } 25^\circ\text{C} = B - C \quad (4)$$

$$\text{Mass of solvent in } 25 \text{ cm}^3 \text{ of solution at } 23^\circ\text{C} = B - C \quad (4)$$

Let *D* = density of solvent at 25/4°C. Then:

Let *D* = density of solvent at 23/4°C. Then:

² Annual Book of ASTM Standards, Vol 14.024.

$$\frac{\text{Solubility in grams solute per 100 g of solution at } 25^{\circ}\text{C}}{\times 100} = \quad (5)$$

$$\frac{\text{Solubility in grams solute per 100 g of solution at } 23^{\circ}\text{C}}{\times 100} = \quad (5)$$

$$\frac{\text{Solubility in grams solute per } 100 \text{ cm}^3 \text{ of solvent at } 25^{\circ}\text{C}}{\times D \times 100} = \quad (6)$$

$$\frac{\text{Solubility in grams solute per } 100 \text{ cm}^3 \text{ of solvent at } 23^{\circ}\text{C}}{\times D \times 100} = \quad (6)$$

$$\frac{\text{Solubility in grams solute per 100 g of solvent at } 25^{\circ}\text{C}}{\times 100} = \quad (7)$$

$$\frac{\text{Solubility in grams solute per 100 g of solvent at } 23^{\circ}\text{C}}{\times 100} = \quad (7)$$

8. Report

8.1 Solubility shall be reported as indicated in Table 1.

8.2 The solvent used shall be specified.

9. Precision and Bias

9.1 *Precision*—The two net masses of solute should agree within 10 % of each other. If not, the test should be repeated. If agreement within 10 % is obtained, the average mass of solute should be used.

9.2 *Bias*—No statement about bias is being made at this time.

10. Keywords

10.1 rubber chemicals; solubility

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).

TABLE 1 Code for Reporting Solubility Test Results

Descriptive Code	Description	Range of Solubility, Kg/m ³
P Ins	practically insoluble	<0.1
SS	slightly soluble	0.1 to <1.0
MS	moderately soluble	1.0 to < 5.0
S	soluble	5.0 to <10.0
VS	very soluble	10.0 and over