



## Standard Specification for Poly(Vinyl Chloride) Insulation for Wire and Cable, 75°C Operation<sup>1</sup>

This standard is issued under the fixed designation D 2220; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This specification covers a thermoplastic insulation of poly(vinyl chloride) or the copolymer of vinyl chloride and vinyl acetate.

1.2 This insulation is recommended for use at conductor temperatures not in excess of 75°C in dry locations at a maximum voltage rating of 300 V for power and control circuits with an insulation at temperatures not higher than 75°C. At a thickness of 15 mils (0.38 mm), application is recommended at conductor temperatures not in excess limited to voltage ratings below 300 V, and to dry locations. At a thickness of 75°C in wet or 30 mils, the application range is widened to dry-1 or wet applications, and to a maximum voltage rating of 600 V for power and control circuits.

1.2 The V.

1.3 Whenever two sets of values stated are presented, in inch-pound units different units, the values in the first set are the standard, except while those in cases where SI units are more appropriate. The values in parentheses are for information only.

1.34 In many instances the insulation material cannot be tested unless it has been formed around a conductor or cable. Therefore, tests are done on insulated wire or cable in this specification solely to determine the relevant property of the insulation material and not to test the conductor or completed cable.

### 2. Referenced Documents

2.1 *ASTM Standards:*

D 1711 Terminology Relating to Electrical Insulation<sup>2</sup>

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D-9 D09 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.18 on Solid Insulations, Non-metallic Shieldings, and Coverings for Electrical and Telecommunications Wires and Cables.

Current edition approved Sept. March 10, 1997; 2002. Published February 1998; May 2002. Originally published as D 2220 – 63T. Last previous edition D 2220 – 937.

**3. Terminology**

3.1 *Definitions:*

3.1.1 For definitions of terms used in this specification, refer to Terminology D 1711.

3.2 *Definition of Term Specific to This Standard:*

3.2.1 *aging (act of), n*—exposure of materials to air or oil at a temperature and a time as specified in Table 1.

**4. Physical Properties**

4.1 The insulation shall conform to the requirements for physical properties prescribed in Table 1.

**5. Electrical Requirements**

5.1 Perform the ac voltage, insulation resistance, and dc voltage tests in that order when any of these tests are required. The sequence for other testing is not specified.

5.2 *AC Voltage Test*—Test the insulated conductor at the ac withstand voltage as specified in Table 2. This test may be omitted if the dc withstand voltage test described in 5.4 is performed.

5.3 *Insulation Resistance:*

5.3.1 Insulated conductors in sizes AWG 14 ~~(1.63 mm)~~ (2.08 mm<sup>2</sup>) and larger shall have an insulation resistance of at least that corresponding to a constant of 2000 ~~M Ω-1000 ft~~ at 60°F (15.6°C).

5.3.2 If the temperature at the time measurement was made differs from 60°F (15.6°C), correct the insulation resistance to 60°F by multiplying the measured value by the proper correction factor from Table 1, Temperature Correction Factors for Insulation Resistance at 60°F, of Methods D 2633.

5.4 *DC Voltage Test*—Upon completion of the insulation resistance test, test each non-shielded insulated conductor for 5 min at a dc withstand voltage which is three times the ac test voltage specified in Table 2. This test may be omitted if the ac withstand voltage test described in 5.2 is performed.

5.5 *Accelerated Water Absorption*—The insulation shall meet the requirements in Table 3.

5.6 *Dielectric Strength Retention*— The insulation shall be capable of meeting a dielectric strength retention of at least 60 % of the original dielectric strength when tested at a temperature of 75 ± 1°C.

**6. Thickness of Insulation**

6.1 The average thickness of the insulation shall be at least that prescribed in Table 2. The minimum thickness shall be at least 90 % of the thickness prescribed in Table 2.

<sup>2</sup> Annual Book of ASTM Standards, Vol 10.01.

<sup>3</sup> Annual Book of ASTM Standards, Vol 10.02.

**TABLE 1 Physical Properties Requirements for Insulation**

<b>Physical properties requirements:</b>	
<b>Unaged Requirements:</b>	
Tensile strength, min, psi (MPa)	2000 (13.8)
Elongation at rupture, min, %	150
<b>Air Oven Aging Requirements:</b>	
<b>Aged Requirements:</b>	
After air oven test at 121 ± 1°C for 168 h:	
Tubular Specimens—up to size AWG 6 (13.3 mm <sup>2</sup> )	
Tensile strength, min, % of unaged value	80
Elongation, min, % of unaged value	75
Buffed die-cut Specimens—sizes AWG 6 and larger	
Tensile strength, min, % of unaged value	50
Tensile strength, min, % of unaged value	75
Elongation, min, % of unaged value	75
Elongation, min, % of unaged value	50
Heat shock, 121 ± 1°C	no cracks
Heat distortion, 121 ± 1°C, max, % decrease	25
Vertical flame test, max burning time after	passes
Vertical flame test, after	passes
five 15-s applications	
<b>Oil resistance test:</b>	
After oil immersion at 70 ± 1°C for 4 h:	
Tubular Specimens—up to size AWG 6 (13.3 mm <sup>2</sup> )	
Tensile strength, min, % of unaged value	85
Elongation, min, % of unaged value	85
Buffed die-cut Specimens—sizes AWG 6 and larger	
Tensile strength, min, % of unaged value	80
Elongation, min, % of unaged value	60
Cold bend test, -30 ± 1°C for 1 h	no cracks

**TABLE 2 Conductor Sizes, Insulation Thicknesses, and Test Voltages for Poly(Vinyl Chloride)-Insulated Control and Power Cables**

NOTE 1—For cables or conditions of service where mechanical stresses govern, such as in submarine cables or long vertical risers, these minimum conductor sizes may not be strong enough.

NOTE 2—The thicknesses given in Table 2 apply to aerial cables and to single conductors installed in conduits above ground and to the individual conductors of all multiple-conductor cables having a common jacket, metallic sheath, or protective covering over the assembly, with the following exceptions: For single-conductor cables for installation in underground ducts or direct earth burial, and for all submarine cables, add 15 mils (0.39 mm) to the insulation thicknesses given in Table 2, when such cables do not have a thermoplastic jacket or metallic sheath over the assembly.

NOTE 3—Where the thickness of the insulation is increased for mechanical reasons or for special service conditions, determine the test voltage by the size of the conductor and the rated voltage and not by the apparent thickness of insulation.

NOTE 4—Do not use single conductor cables in size AWG 9 (6.63 mm<sup>2</sup>) and smaller for direct earth burial.

Rated Circuit Voltage, Phase-to-Phase, V	Conductor Size, AWG or cmil (mm <sup>2</sup> )	Insulation Thickness, mils (mm)	AC Test Voltage, kV
0 to 300	26 to 16 (0.13 to 1.31)	15 (0.38)	1.0
0 to 300	26 to 16 (0.13 to 1.31)	15 (0.38)	1.0
0 to 600	26 to 16 (0.13 to 1.31)	30 (0.76)	1.5
0 to 600	26 to 16 (0.13 to 1.31)	30 (0.76)	1.5
	14 to 9 (2.08 to 6.63)	45 (1.14)	3.0
	14 to 9 (2.08 to 6.63)	45 (1.14)	3.0
	8 to 2 (8.37 to 33.6)	60 (1.52)	3.5
	8 to 2 (8.37 to 33.6)	60 (1.52)	3.5
	1 to 0000 (42.4 to 10.7)	80 (2.03)	4.0
	1 to 0000 (42.4 to 10.7)	80 (2.03)	4.0
	225 000 to 500 000 (140 to 253)	95 (2.41)	5.0
	225 000 to 500 000 (140 to 253)	95 (2.41)	5.0
	501 000 to 1 000 000 (254 to 507)	110 (2.79)	6.0
	501 000 to 1 000 000 (254 to 507)	110 (2.79)	6.0
	Over 1 000 000 (507)	125 (3.18)	7.0
	Over 1 000 000 (507)	125 (3.18)	7.0

**TABLE 3 Accelerated Water Absorption Requirements**

Electrical method 60 Hz at 75 ± 1°C:	
Permittivity after 24 h, max	10.0
Increase in capacitance, max, %:	
1 to 14 days	4.0
7 to 14 days	2.0

## 7. Workmanship, Finish, and Appearance

7.1 Apply the insulation directly to the surface of the conductor or conductor covering and obtain a tight fit to that surface.

7.2 *Repairs and Joints*—When making repairs or joints in the insulation, do the work in such a manner that the repaired part of the joint, and all parts affected by the process, meet the same electrical tests as the remainder of the insulation and maintain the limitations on the thickness specified in Section 6.

## 8. Sampling

8.1 Sample the insulation in accordance with Methods D 2633.

## 9. Test Methods

9.1 Test the insulation in accordance with Methods D 2633.

## 10. Keywords

10.1 accelerated water absorption; ac voltage test; dc voltage test; insulation resistance; poly (vinyl chloride) insulation; 75°C Poly (Vinyl Chloride) Insulation; thickness

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)).*