



Designation: D 4016 – 9302

Standard Test Method for Viscosity of Chemical Grouts by Brookfield Viscometer (Laboratory Method)¹

This standard is issued under the fixed designation D 4016; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

¹ This test method is under the jurisdiction of ASTM Committee D18 on Soil and Rock and is the direct responsibility of Subcommittee D18.15 on Stabilization With Admixtures.

Current edition approved May 15, 1993; Nov. 10, 2002. Published September 1993; January 2003. Originally published as D 4016 – 81. Originally approved in 1993. Last previous edition approved in 1993 as D 4016 – 8493.

1. Scope *

1.1 This test method covers the determination of viscosity of catalysed chemical grouts with the Brookfield viscometer (laboratory method), over the range from 1.0 to 1000 cP (0.001 to 1 Pa·s).

1.2 *This standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Terminology—Referenced Documents

2.1 ASTM Standards:

D 653 Terminology Relating to Soil, Rock, and Contained Fluids²

D 3740 Practice for Minimum Requirements for Agencies Engaged in the Testing and/or Inspection of Soil and Rock as Used in Engineering Design and Construction²

3. Terminology

3.1 For common definitions of terms used in this standard, refer to Terminology D 653.

3.2 Definitions of Terms Specific to This Standard:

~~2.1.1~~

3.2.1 coefficient of viscosity—the ratio between the applied shear stress and the rate of shear. This coefficient is a measure of the resistance to flow of the liquid. It is commonly called the viscosity of the liquid. The cgs unit of viscosity is 1 g/cm·s (1 dyn/s cm²) and is called a poise (P). Viscosities of thin liquids are normally given in hundredths of a poise or centipoises (cP). The SI unit of viscosity is 1 Pa·s (1 N·s/m²) and is equal to 10 P, or 1000 cP.

~~2.1.2~~

3.2.2 Newtonian liquid—a liquid in which the shear stress is proportional to the rate of shearing strain. This constant ratio is the viscosity. Non-Newtonian behavior can be determined with the Brookfield instrument by taking measurements at different spindle speeds.

3. Summary of Test Method

~~3.1 A rotating spindle is immersed in a container of catalysed chemical grout. An index to the viscosity is read directly on the instrument scale.~~

4. Significance and Use

~~4.1 This test~~ Summary of Test Method

~~4.1 A rotating spindle is intended for materials that will penetrate soil voids and rock fissures. Viscosity alone is not necessarily an exact index immersed in a container of catalysed chemical grout pe. An index to the viscosity is read directly on the instyrumnt scale.~~

² Annual Book of ASTM Standards Vol 04.08.

*A Summary of Changes section appears at the end of this standard.

5. Significance and Use

5.1 This test is intended for materials that will penetrate soil voids and rock fissures. Viscosity alone is not necessarily an exact index of grout penetrability.

NOTE 1—The quality of the result produced by this test method is dependent on the competence of the personnel performing it and the suitability of the equipment and facilities used. Agencies that meet the criteria of Practice D 3740 are generally considered capable of competent and objective testing/sampling/inspection/etc. Users of this standard are cautioned that compliance with of Practice D 3740 does not in itself assure reliable results. Reliable results depend on many factors; of Practice D 3740 provides a means of evaluating some of those factors.

6. Apparatus

56.1 *Brookfield Viscometer*—Any model whose lower limit of effective measurement is less than the value of the sample. Models LVF and LVT should be used for measurements above 20 cP (20 mPa-s), and for measurements from 1 to 20 cP (1 to 20 mPa-s) with the addition of a Model UL adapter. Models RV, RT, HA, and HB may be used for measurements above 100 cP (100 mPa-s).

NOTE 12—The UL adapter may be used for better accuracy in the 20 to 100-cP (20 to 100-mPa-s) range also.

56.2 *Griffin Beaker*, 600-cm³, low-form used as the container for the sample. Beaker material must not react with the grout. Glass beakers are not acceptable for silicates. Stainless steel beakers are acceptable for all materials.

56.3 *Calibrated Liquid-in-Glass Thermometers*, accurate to $\pm 1.0^\circ\text{F}$ (0.5°C), or any other thermometric device of equal accuracy.

NOTE 23—Glass thermometers should not be used with silicates.

56.4 *Temperature-Control Bath*, for work at other than ambient temperature, and large enough to hold the sample container. Any bath that will maintain its temperature within $\pm 1.0^\circ\text{F}$ (0.5°C) during the test period is adequate.

NOTE 34—Grout temperature must equal bath temperature at the start of the test. Temperature rise due to chemical reaction does not invalidate the test data.

67. Sample Preparation

67.1 The temperature of the grout components at time of testing shall be $68 \pm 1^\circ\text{F}$ ($20 \pm 0.5^\circ\text{C}$).

NOTE 45—Alternatively, three or more tests at various temperatures may be taken to define a viscosity versus temperature relationship. It is desirable to have such tests span the anticipated ground temperature.

67.2 Viscosity data should be taken on catalysed grout solution that contains all of the components normally used for field application.

78. Procedure

78.1 Prepare the grout components separately and bring them to the required temperature.

78.2 When not using the UL adapter attach the No. 1 spindle to the lower shaft.

78.2.1 When using the UL adapter attach the locating channel to the viscometer. Assemble the spindle, extension link, and coupling nut. Thread the coupling nut onto the viscometer spindle coupling. Guide the tube over the spindle. Thread the lower mounting screw into the tube collar.

NOTE 56—For more detailed assembly instructions, refer to the manufacturer's operation manual.

78.3 Catalyse the grout in a 600-cm³ beaker. For materials whose gel time range is between 10 and 30 min, gel time should be set at about 20 min. Instrument readings of viscosity (versus time) should be taken at approximately every two minutes.

78.3.1 For materials whose gel time range is less than 10 min, a gel time should be set between 50 and 100 % of gel time range, and readings taken at least every 2 min or, if possible, at 1-min intervals.

78.3.2 For materials whose gel time range is over 30 min, a gel time should be selected at least 25 % above minimum, and readings taken at approximately equal time intervals to permit at least five readings prior to gelation.

NOTE 67—For materials whose normal setting time is modified by prolonged agitation (this includes many silicate and acrylamide grouts) only one reading per sample should be taken, and multiple samples used to define the viscosity-time data.

78.4 Insert the spindle or UL adapter into the group up to the reference mark and level the viscometer.

78.5 Select the highest spindle speed that will give a viscometer reading between 20 % and 80 % of scale. The following table may be used as a selection guide.

With Model UL Adapter	
rpm	Range, cP or mPa-s
50 to 100	0 to 10
20 to 50	10 to 30
10 to 20	20 to 50

1 to 10	Without UL Adapter	50 to 100
rpm		Range, cP or mPa-s
2 to 30		20 to 100
0.5 to 20		50 to 200
0.5 to 12		100 to 500
0.5 to 6		200 to 1000

78.5.1 For all samples whose gel time permits more than one reading, at least one shall be taken at a different spindle speed, from that originally selected. If apparent viscosities differ by more than 20 % at different spindle speeds, the grout shall be reported as non-Newtonian.

NOTE 78—For non-Newtonian fluids it is recommended that, where possible, sufficient readings be taken so that a chart of spindle speed versus “effective” viscosity may be reported.

78.6 Depress the clutch and turn on the motor. Release the clutch and allow the dial to rotate until the pointer stabilizes.

NOTE 89—At speeds above 4 rpm, 20 to 30 s will generally be required. At slower speeds, it may take longer.

89. Report

89.1 The following data shall be included in the report:

89.1.1 Composition of the grout, listing each component, and its weight percentage of the total solution. Composition by volume is also acceptable, if pertinent solution concentrations and densities are noted.

89.1.2 Temperature of the test sample, just prior to the viscosity measurement.

89.1.3 Gel time of the sample.

NOTE 910—For the purpose of this test, change from liquid to gel may be considered to occur when the liquid becomes too thick to pour out of the sample container.

89.1.4 Sample viscosity in cP (mPa-s) for grouts with very short gel times, or preferably, a plot of viscosity versus time.

910. Precision

910.1 Precision—Data are being evaluated to determine the precision of this test method. In addition Subcommittee D18.165 is seeking pertinent data from users of this test method.

910.2 Bias—There is no accepted reference value for this test method, therefore, bias cannot be determined.

101. Keywords

101.1 Brookfield viscometer; chemical grout; coefficient of viscosity; grouting; Newtonian fluids; non-Newtonian fluids

SUMMARY OF CHANGES

In accordance with Committee D18 policy, this section identifies the location of changes to this standard since the last edition (1993) that may impact the use of this standard.

(1) Added Referenced Document Section and renumbered subsequent sections. Included Terminology D 653 and Practice D 3740 to section.

(2) Added reference to Terminology D 653 in Terminology section.

(3) Added Note 1 for the Practice D 3740 statement.

(4) Renumbered subsequent notes.

(5) Added Summary of Changes section.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).