



Designation: D 293 – 93 (Reapproved 1999)

Standard Test Method for the Sieve Analysis of Coke¹

This standard is issued under the fixed designation D 293; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method describes the separation of a coke sample into defined size fractions and expressing said fractions as a weight percent of the gross sample.

1.2 The values stated in SI units are to be regarded as the standard. Inch-pound units shall be accepted on an equivalent basis.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

D 346 Practice for Collection and Preparation of Coke Samples for Laboratory Analysis²

D 4621 Guide for Accountability and Quality Control in the Coal Analysis Laboratory²

E 11 Specification for Wire-Cloth Sieves for Testing Purposes³

E 323 Specification for Perforated-Plate Sieves for Testing Purposes³

3. Significance and Use

3.1 This test method determines the size distribution of coke for conformance to specifications of percentages retained on designated screen sizes.

4. Apparatus

4.1 *Sieves*—Use square-hole sieves conforming to Specification E 11. Where sieves larger than 100 mm (4 in.) are required, the specifications for same shall be by mutual agreement between interested parties. Permissible variations in sieve openings and spacings shall be in accordance with Specification E 11.

4.1.1 For complete characterization of the size range of a coke sample, the number and size of the selected sieves should be such that no more than 25 % of the gross sample weight will be retained on any given sieve.

4.1.2 For coke 38.1 mm (1½ in.) and larger in size, sieves of heavy double-cripped wire and square or rectangular frames with 0.56 to 0.84 m² (6 to 9 ft²) of sieve area are satisfactory. For coke smaller than 38.1 mm (1½ in.) in size, sieves of double-cripped wire and square or circular frames with 0.19 to 0.37 m² (2 to 4 ft²) of sieve area are usually more convenient.

4.2 *Weighing Balance*, preferably of the platform type, having a sensitivity of 0.025 kg (0.05 lbs) or better, at rated capacity and with graduations such that 0.05 kg (0.1 lb) can be read without interpolation.

5. Test Sample

5.1 The test sample shall be taken in accordance with Practice D 346.

6. Procedure

6.1 Starting with the sieve having the largest opening, sieve the sample of coke in quantities small enough to prevent plugging and clogging of the sieve.

6.1.1 Hand-fit each piece of coke retained on the 38.1-mm (1½-in.) or larger sieve. A piece is considered undersize, if in some position and without forcing, it passes the sieve opening.

6.1.2 Shake vigorously on each succeeding sieve coke pieces passing the 38.1-mm (1½-in.) sieve. This shaking may be performed manually or mechanically provided mechanical shaking yields results equivalent to manual shaking. Note that the objectives of shaking, either manual or mechanical, are to place all of the naturally occurring pieces of a given size range on the appropriate sieve and to avoid degradation of the naturally occurring sizes.

6.2 Record to the nearest 0.05 kg (0.1 lb) the weight of coke retained on each sieve and that which passes the smallest sieve used. For routine testing, the sum of all the size-fraction weights may be taken as the total weight of coke tested.

6.2.1 Samples containing pieces retained on 50-mm (2-in.) sieves and larger, need not be dried. However, when a higher degree of accuracy is desired, dry the gross sample to less than 1 % moisture and accurately weigh before sieving. Dry all

¹ This test method is under the jurisdiction of ASTM Committee D-5 on Coal and Coke and is the direct responsibility of Subcommittee D05.15 on Metallurgical Properties of Coal and Coke.

Current edition approved Jan. 15, 1993. Published April 1993. Originally published as D 293–28. Last previous edition D 293 – 93.

² *Annual Book of ASTM Standards*, Vol 05.06.

³ *Annual Book of ASTM Standards*, Vol 14.02.

samples of coke containing only pieces which pass a 50-mm sieve to less than 1 % moisture before testing.

7. Report

7.1 Report the weights of the size fractions as a percentage of the weight of the gross sample. Calculate percentage to the nearest 0.1 %. Record the results starting with the fraction of largest sieve size, which may be shown for separate fractions or cumulatively.

7.2 For those tests in which the gross sample is weighed before sieving, the sum of the weights of all size fractions should equal the measured gross weight. In cases in which the cumulative weight of size fractions differs from the initial gross weight by 0.5 % or less of the gross weight, adjustment can be made in the weight of the size fraction passing the smallest sieve size. With careful procedure, this difference should not exceed 0.5 %.

8. Precision and Bias

8.1 *Reproducibility*—No precision statement has been developed for this test method because of the impracticality of obtaining, transporting, and handling representative splits of the materials in the quantities that would be needed to establish the precision statement.

8.2 *Repeatability*—The precision of this test method is being investigated by a task group. At this time the values have not been determined.

8.3 *Bias*—The lack of a reference material precludes a bias statement.

9. Keywords

9.1 breakage; coke; degradation; increments

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).