



# Standard Specification for Propylene Glycol Monomethyl Ether Acetate<sup>1</sup>

This standard is issued under the fixed designation D 4835; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope\*

1.1 This specification covers propylene glycol monomethyl ether acetate (PMA).

NOTE 1—Propylene glycol monomethyl ether acetate (PMA) is a mixture of 1-methoxy-2-acetoxypropane and 2-methoxy-1-acetoxypropane.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 The following applies to all specified limits in this standard; for purposes of determining conformance with this standard, an observed value or a calculated value shall be rounded off “to the nearest unit” in the last right-hand digit used in expressing the specification limit, in accordance with the rounding-off method of Practice E 29.

1.4 For specific hazard information and guidance, consult the supplier’s Material Safety Data Sheet for materials listed in this standard.

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

- D 1078 Test Method for Distillation Range of Volatile Organic Liquids
- D 1209 Test Method for Color of Clear Liquids (Platinum-Cobalt Scale)
- D 1364 Test Method for Water in Volatile Solvents (Karl Fischer Reagent Titration Method)
- D 1613 Test Method for Acidity in Volatile Solvents and Chemical Intermediates Used in Paint, Varnish, Lacquer, and Related Products
- D 4773 Test Method for Purity of Propylene Glycol Monomethyl Ether, Dipropylene Glycol Monomethyl Ether, and Propylene Glycol Monomethyl Ether Acetate
- E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.35 on Solvents, Plasticizers, and Chemical Intermediates.

Current edition approved Oct. 1, 2003. Published October 2003. Originally approved in 1988. Last previous edition approved in 1993 as D 4835 – 93 (1998).

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

E 300 Practice for Sampling Industrial Chemicals

### 2.2 U.S. Federal Specification:

PPP-C-2020 Chemicals, Liquid, Dry, and Paste: Packaging of<sup>3</sup>

## 3. Properties

3.1 Propylene glycol monomethyl ether acetate (PMA) shall conform to the following requirements:

Purity, min, weight %	99
Color, platinum-cobalt scale, max	15
Water, max, weight %	0.05
Distillation range, °C:	
Initial boiling point, min	140
Dry boiling point, max	150
Acidity (free acid as acetic acid), max, weight %	0.02 <sup>4</sup>
Glycol ether, max, weight %	0.5

<sup>4</sup>Equivalent to 0.2 mg of potassium hydroxide (KOH) per gram of specimen.

## 4. Sampling

4.1 The material shall be sampled in accordance with Practice E 300.

## 5. Test Methods

5.1 The properties enumerated in this specification shall be determined in accordance with the following ASTM test methods:

- 5.1.1 *Gas Chromatographic Method*—Test Method D 4773.
- 5.1.2 *Color*—Test Method D 1209.
- 5.1.3 *Water*—Test Method D 1364.
- 5.1.4 *Acidity*—Test Method D 1613.
- 5.1.5 *Distillation Range*—Test Method D 1078.

## 6. Packaging and Package Marking

6.1 Package size shall be as agreed upon between the purchaser and the supplier.

6.2 Packaging shall conform to applicable carrier rules and regulations or when specified shall conform to Fed. Spec. PPP-C-2020.

## 7. Keywords

7.1 PM acetate; propylene glycol monomethyl ether acetate; solvent

<sup>3</sup> Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098.

\*A Summary of Changes section appears at the end of this standard.

## SUMMARY OF CHANGES

Committee D01.35 has identified the location of selected changes to this standard since the last issue (D 4835 - 93 (1998)) that may impact the use of this standard.

- (1) Added reference to Practice E 29 in Scope section.
- (2) Added Practice E 29 to list of Referenced Documents.
- (3) Added keywords.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)).*