

Steel Thickness Conversion Table (gauge - inch - mM)

Gauge No.	B.W.G		U.S.G	
	inch	mm	inch	mm
6	.203	5.156	.2031	5.16
7	.180	4.572	.1875	4.76
8	.165	4.191	.1719	4.37
9	.148	3.759	.1563	3.97
10	.134	3.404	.1406	3.57
11	.120	3.048	.1250	3.18
12	.109	2.769	.1094	2.78
13	.095	2.413	.0938	2.38
14	.083	2.108	.0781	1.98
15	.072	1.829	.0703	1.79
16	.065	1.651	.0625	1.59
17	.058	1.473	.0563	1.43
18	.049	1.245	.0500	1.27
19	.042	1.067	.0438	1.11
20	.035	.889	.0375	.953

Gauge No.	B.W.G		U.S.G	
	inch	mm	inch	mm
21	.032	.813	.0344	.873
22	.028	.711	.0313	.794
23	.025	.635	.0281	.714
24	.022	.559	.0250	.635
25	.020	.508	.0219	.556
26	.018	.457	.0188	.478
27	.016	.406	.0172	.437
28	.014	.356	.0156	.396
29	.013	.330	.0141	.358
30	.012	.305	.0125	.318
31	.010	.254	.0109	.277
32	.009	.229	.0102	.259
33	.008	.203	.0094	.239
34	.007	.178	.0086	.218
35	.005	.127	.0078	.198

BWG - Birmingham Wire Gauge for Iron & Steel Wire
 USG - US Standard Gauge for Stainless Steel