



Standard Specification for Copper-Alloy Die Castings¹

This standard is issued under the fixed designation B 176; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification establishes the requirements for copper-alloy die castings. The alloys specified are Copper Alloy UNS Nos. C85700, C85800, C86500, C 87800, C99700, and C99750.²

1.2 *Units*—Values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units, which are provided for information only and are not considered standard.

2. Referenced Documents

2.1 *ASTM Standards:*³

B 824 Specification for General Requirements for Copper Alloy Castings

E 8 Test Methods for Tension Testing of Metallic Materials

E 23 Test Methods for Notched Bar Impact Testing of Metallic Materials

E 255 Practice for Sampling Copper and Copper Alloys for the Determination of Chemical Composition

E 527 Practice for Numbering Metals and Alloys (UNS)

2.2 *American Die Casting Institute:*

“E” Series Product Standards⁴

2.3 *Federal Standard:*

Fed. Std. No. 123 Marking for Shipment (Civil Agencies)⁵

2.4 *Military Standards:*

MIL-STD-129 Marking for Shipment and Storage (Military Agencies)⁵

MIL-P-116 Methods of Preservation⁵

¹ This specification is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.05 on Castings and Ingots for Remelting.

Current edition approved May 1, 2004. Published May 2004. Originally approved in 1942. Discontinued January 2004 and reinstated in 2004 as B 176 – 04.

² The UNS system for copper and copper alloys (see Practice E 527) is a simple expansion of the former standard designation system accomplished by the addition of a prefix “C” and a suffix “00”. The suffix can be used to accommodate composition variations of the base alloy.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

⁴ Available from the American Die Casting Institute, 2340 Des Plaines Ave., Des Plaines, IL 60018.

⁵ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, ATTN: NPODS.

3. General Requirements

3.1 The following sections of Specification B 824 constitute a part of this specification.

3.1.1 Terminology (Section 3),

3.1.2 Number of Tests and Retests (Section 10) (Note to users: Paragraph 10.3 of Specification B 824 applies only when mechanical requirements are specified in the purchase order.),

3.1.3 Test Methods (Section 12),

3.1.4 Significance of Numerical Limits (Section 13),

3.1.5 Inspection (Section 14),

3.1.6 Rejection and Rehearing (Section 15),

3.1.7 Certification (Section 16),

3.1.8 Test Report (Section 17),

3.1.9 Product Marking (Section 18), and

3.1.10 Supplementary Requirements.

3.2 In addition, when a section with a title identical to that referenced in 3.1, above, appears in this specification, it contains additional requirements which supplement those appearing in Specification B 824.

4. Terminology

4.1 For general terms related to copper and copper alloys, refer to Terminology B 846.

5. Ordering Information

5.1 Include the following information when placing orders for die castings under this specification as applicable:

5.1.1 Specification title, number, and year of issue,

5.1.2 Part name and number,

5.1.3 Copper Alloy UNS Number,

5.1.4 Quantity and delivery schedule, as required,

5.1.5 Engineering drawing of die casting, when required, giving all necessary dimensions and tolerances and showing latest revisions and allowances for machining, if any. Location of ejector pin marks or parting lines shall be at the option of the manufacturer unless specifically designated on the drawing.

5.1.6 When die castings are purchased for agencies of the U.S. government the Supplementary Requirements of Specification B 824 may be specified.

5.2 The following requirements are optional and should be specified in the purchase order when required.

5.2.1 Inspection lot sampling (Section 8),

5.2.2 Chemical analysis of residual elements (Section 4),

*A Summary of Changes section appears at the end of this standard.

TABLE 1 Chemical Requirements

Composition, % max (unless shown as a range or min)																	
Copper Alloy UNS No.	Major Elements										Residual Elements						
	Copper	Tin	Lead	Zinc	Iron	Nickel including Cobalt	Aluminum	Manganese	Silicon	Iron	Antimony	Nickel Cobalt	Sulphur	Phosphorous	Aluminum	Manganese	Silicon
C85700	58.0–64.0 ^A	0.50–1.5	0.8–1.5	32.0–40.0	0.7	...	1.0	...	0.8	0.05
C85800	57.0 min ^A	1.5	1.5	31.0–41.0	0.50	0.05	0.50	0.05	0.01	0.55	0.25	0.25 ^B
C86500	55.0–60.0 ^A	1.0	0.40	36.0–42.0	0.40–2.0	...	0.50–1.5	0.10–1.5	1.0
C87800	80.0 min ^A	0.25	0.15	12.0–16.0	3.8–4.2	0.15	0.05	0.20	0.05	0.01	0.15	0.15	...	^{B,C}
C99700	54.0 min ^A	1.0	2.0	19.0–25.0	...	4.0–6.0	0.50–3.0	11.0–15.0	...	1.0
C99750	55.0–61.0	...	0.50–2.5	17.0–23.0	...	5.0	0.25–3.0	17.0–23.0	...	1.0 ^D

^A In determining copper min, copper may be determined as copper plus nickel.

^B Arsenic 0.05 max.

^C Magnesium 0.01 max.

^D Iron content above the nickel content may cause hard spots resulting in decreased machinability.

- 5.2.3 Soundness requirements (Section 9),
- 5.2.4 Mechanical requirements (Section 5),
- 5.2.5 Special requirements (Section 9),
- 5.2.6 Certification (Specification B 824),
- 5.2.7 Foundry test report (Specification B 824),
- 5.2.8 Witness inspection (Specification B 824),
- 5.2.9 Product marking (Specification B 824), and
- 5.2.10 Packaging requirements (Section 12).

6. Chemical Composition

6.1 The castings shall conform to the requirements for major elements as shown in Table 1.

6.2 These specification composition limits do not preclude the presence of other elements. Limits may be established and analysis required for unnamed elements agreed upon between the manufacturer or supplier and the purchaser. Copper or zinc may be given as remainder and may be taken as the difference between the sum of all elements analyzed and 100 %. When all named elements in Table 1 are analyzed, their sum shall be as specified in Table 2.

6.3 It is recognized that residual elements may be present in cast copper-base alloys. Analysis shall be made for residual elements only when specified in the purchase order.

6.4 If the producer's or supplier's method of composition control is acceptable, sampling for chemical analysis may be waived at the discretion of the purchaser.

7. Mechanical Property Requirements

7.1 Unless specified in the purchase order, acceptance of die castings under this specification shall not depend on mechanical properties determined by tension or impact tests. Table X1.1 shows typical mechanical properties.

7.2 When minimum mechanical properties are specified in the purchase order the mechanical properties shall be agreed upon between the manufacturer or supplier and the purchaser.

8. Dimensions, Mass, and Permissible Variations

8.1 Permissible variations in dimensions shall be within the limits specified on the drawings or in the contract or purchase order.

8.1.1 Any dimensions for which a tolerance is not specified shall be in accord with ADCI Product Standard Series E 1 to E 16 inclusive.

9. Sampling

9.1 An inspection lot shall consist of the production from each die or compound die on each machine for each 24 h during the first week of normal operation and the production for each 48 h thereafter of normal operation. Any significant change in the machine, composition, die or continuity of operation shall be considered as the start of a new lot. Die castings inspected by this method shall be so marked or handled during the finishing operations as not to lose their identity.

9.2 Each die casting of a randomly selected sample shall be examined to determine conformance to the requirements with respect to general quality, dimensions and identification marking. The producer or supplier may use a system of statistical quality control for such examinations.

9.3 *Sampling for Chemical Analysis*—Refer to the Sampling section of Specification B 824 and Practice E 255 for sampling methodology.

10. Special Requirements

10.1 *Internal Soundness*—When specified, the soundness of die castings shall conform to standards or requirements agreed upon between the producer or supplier and the purchaser. The number and extent of imperfections shall not exceed those specified by the purchaser. The standards or requirements may consist of radiographs, photographs or sectioned die castings.

10.2 Imperfections inherent in the die castings shall not be cause for rejection provided it is demonstrated that the die castings are in accordance with the requirements and standards agreed upon.

TABLE 2 Sum of All Named Elements Analyzed

Copper Alloy UNS No.	Copper Plus Named Elements, % min
C85700	98.7
C85800	98.7
C86500	99.0
C87800	99.5
C99700	99.7
C99750	99.7

10.3 *Workmanship*—Die castings shall be of uniform quality, free of injurious discontinuities that will adversely affect their serviceability.

10.4 *Finish*—When specified in the contract or purchase order the as-cast surface finish required shall conform to standards agreed upon between the purchaser and the producer or supplier, or as prescribed in ADCI Product Standard E 18.

10.5 *Pressure Tightness*—When specified in the contract or purchase order the pressure tightness of die castings shall conform to standards agreed upon between the purchaser and the producer or supplier, or as prescribed in ADCI Product Standard E 17.

11. Test Methods

11.1 Analytical chemical methods are given in Specification B 824 (Section 13).

11.2 When tension or impact tests are made, the tension test specimen shown in Fig. 18, Standard Tension Test Specimens for Die Castings, of Test Methods E 8 and the impact test specimen shown in Fig. 6, Charpy (Simple-Beam) Impact Test Specimens, Types A, B, and C, of Test Methods E 23, shall be used.

12. Packaging and Package Marking

12.1 *Packaging*—Unless otherwise specified, the die castings shall be packaged to provide adequate protection during

normal handling and transportation. Each package shall contain only one type of item unless otherwise agreed upon. The type of packaging and gross weight of containers shall, unless otherwise agreed upon, be at the producer’s discretion, provided they are such as to ensure acceptance by common or other carriers for safe transportation at the lowest rate to the delivery point.

12.2 *Marking*—Each shipping container shall be legibly marked with the purchase order number, gross and net weights, and the supplier’s name or trademark. Marking for shipment shall be in accordance with Fed. Std. No. 123 for civil agencies and MIL-STD-129 for Military agencies.

12.3 *Preservation*—Material intended for prolonged storage in unheated locations shall be adequately packed and protected to avoid deterioration and damage. When specified in the contract or purchase order, material shall be preserved, packaged, and packed in accordance with the requirements of MIL-P-116. The applicable levels shall be as specified in the contract or order.

13. Keywords

13.1 copper-alloy castings; die castings; UNS No. C85700; UNS No. C85800; UNS No. C86500; UNS No. C87800; UNS No. C99700; UNS No. C99750

APPENDIXES

(Nonmandatory Information)

X1. TYPICAL MECHANICAL PROPERTIES

X1.1 The data in Table X1.1 do not constitute a part of this specification. They will indicate to the purchaser the mechanical properties that may be expected of test specimens when made in a die, the test specimens being cast in a test bar die and conforming to the chemical composition specified. It should be thoroughly understood that the following figures represent die-cast test specimens and not specimens cut from commercial

die-cast parts. In the tension testing of die-cast brass specimens, the rate of stressing up to the yield strength shall not exceed 100 ksi (700 MPa)/min. Exceedingly slow rates of testing may result in creep and hence are to be avoided. Beyond the yield strength, the rate of straining shall not exceed 0.25 in./in.·min measured on the gage length of the specimen.

TABLE X1.1 Typical Mechanical Properties of Test Specimens^A

Copper Alloy UNS No.	Tensile Strength, ksi (MPa)	Yield Strength psi (0.2% Offset), ksi (MPa)	Elongation in 2 in., (50 mm) %	Impact Strength Charpy, ft-lbf (J)	Hardness, Rockwell B	Modulus of Elasticity ($\times 10^3$) ksi (GPa)
C85800	55 (379)	30 (207)	15	40 (54)	55 to 60	15 000 (103)
C87800	85 (586)	50 (345)	25	70 (95)	85 to 90	20 000 (138)

^A ksi = 1000 psi. For explanation of SI unit MPa, see X3.1.

X2. CHARACTERISTICS

X2.1 Table X2.1 shows certain casting and other outstanding characteristics which are usually considered when selecting a die casting alloy for a specific application.

TABLE X2.1 Die Casting and Other Characteristics

NOTE—*Rating System*—the various alloys are rated 1 to 5 according to the positive to negative qualities in the listed categories. A rating of 1 gives the best performance, 5 the poorest performance. No one alloy is best in all categories. A rating of 5 in any one or more categories does not rule an alloy out of commercial usefulness if its other attributes are especially favorable. However, ratings of 5 may present manufacturing difficulties.

Copper Alloy UNS No.	Die Casting Characteristics						Other Characteristics				
	Approximate Melting Point	Resistance to Hot Cracking	Pressure Tightness	Die Filling Capacity	Anti-Solder to Die	^A	Corrosion Resistant	Machining	Polishing	Electroplating	High Temperature Strength
C85800	1600–1650	2	3	3	2	4	3	1	3	1	3
C87800	1510–1680	2	2	2	1	1	1	5	4	2	1

^A Surface smoothness-as cast.

X3. METRIC EQUIVALENTS

X3.1 The SI unit for strength properties (MPa) is in accordance with the International System of Units (SI). The derived SI unit for force is the newton (N), which is defined as that force which when applied to a body having a mass of one kilogram gives it an acceleration of one metre per second squared ($N = \text{kg}\cdot\text{m}/\text{s}^2$). The derived SI unit for pressure or

stress is the newton per square metre (N/m^2), which has been named the pascal (Pa) by the General Conference on Weights and Measures. Since $1 \text{ ksi} = 6\,894\,757 \text{ Pa}$ the metric equivalents are expressed as megapascal (MPa), which is the same as MN/m^2 and N/mm^2 .

SUMMARY OF CHANGES

Committee B05 has identified the location of selected changes to this standard since the last issue (B 176 – 95) that may impact the use of this standard. (Approved May 1, 2004)

- | | |
|--|--|
| <ul style="list-style-type: none"> (1) Simplified scope section alloy listings for clarity. (2) Instituted usage of Terminology B 846 (see Section 4). (3) Instituted usage of Practice E 255 in (see Sections 2 and 9). (4) Made corrections to specification and table cross-references. | <ul style="list-style-type: none"> (5) Modified several sections to accommodate current form and style practices. |
|--|--|

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).