



Standard Specification for Aluminum and Aluminum-Alloy Bar, Rod, and Wire [Metric]¹

This standard is issued under the fixed designation B 211M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope *

1.1 This specification covers rolled or cold-finished bar, rod, and wire in alloys (Note 1) and tempers as shown in Table 2.

NOTE 1—Throughout this specification use of the term *alloy* in the general sense includes aluminum as well as aluminum alloy.

NOTE 2—The term *cold finished* is used to indicate the type of surface finish, sharpness of angles, and dimensional tolerances produced by drawing through a die.

NOTE 3—See Specification B 221M for aluminum and aluminum-alloy extruded bars, rods, wire, shapes, and tubes; and Specification B 316M for aluminum and aluminum-alloy rivet and cold-heading wire and rods.

1.2 Alloy and temper designations are in accordance with ANSI H35.1M. The equivalent Unified Numbering System alloy designations are those of Table 1 preceded by A9, for example, A91100 for aluminum 1100 in accordance with Practice E 527.

1.3 This specification is the metric counterpart of Specification B 211.

1.4 For acceptance criteria for inclusion of new aluminum and aluminum alloys in this specification, see Annex A2.

2. Referenced Documents

2.1 The following documents of the issue in effect on date of material procurement form a part of this specification to the extent referenced herein.

2.2 ASTM Standards:

B 557M Test Methods of Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products [Metric]²

B 594 Practice for Ultrasonic Inspection of Aluminum-Alloy Wrought Products for Aerospace Applications²

B 597 Practice for Heat Treatment of Aluminum Alloys²

B 660 Practices for Packaging/Packing of Aluminum and Magnesium Products²

B 666/B 666M Practice for Identification Marking of Aluminum and Magnesium Products²

E 29 Practice for Using Significant Digits in Test Data to

Determine Conformance with Specifications³

E 34 Test Methods for Chemical Analysis of Aluminum and Aluminum-Base Alloys⁴

E 55 Practice for Sampling Wrought Nonferrous Metals and Alloys for Determination of Chemical Composition⁴

E 227 Test Method for Optical Emission Spectrometric Analysis of Aluminum and Aluminum Alloys by the Point-to-Plane Technique⁴

E 290 Test Method for Semi-Guided Bend Test for Ductility of Metallic Materials⁵

E 527 Practice for Numbering Metals and Alloys (UNS)⁶

E 607 Test Method for Optical Emission Spectrometric Analysis of Aluminum and Aluminum Alloys by the Point-to-Plane Technique, Nitrogen Atmosphere⁷

E 716 Practices for Sampling Aluminum and Aluminum Alloys for Spectrochemical Analysis⁷

E 1004 Test Method for Electromagnetic (Eddy-Current) Measurements of Electrical Conductivity⁸

E 1251 Test Method for Optical Emission Spectrometric Analysis of Aluminum and Aluminum Alloys by the Argon Atmosphere, Point-to-Plane, Unipolar Self-Initiating Capacitor Discharge⁷

G 47 Test Method for Determining Susceptibility to Stress-Corrosion Cracking of High-Strength Aluminum-Alloy Products⁹

2.3 ANSI Standards:

H35.1M Alloy and Temper Designation Systems for Aluminum¹⁰

H35.2M Dimensional Tolerances for Aluminum Mill Products¹⁰

2.4 Federal Standard:

Fed. Std. No. 123 Marking for Shipment (Civil Agencies)¹¹

2.5 Military Standard:

MIL-STD-129 Marking for Shipment and Storage¹¹

¹ This specification is under the jurisdiction of ASTM Committee B07 on Light Metals and Alloys and is the direct responsibility of Subcommittee B07.03 on Aluminum Alloy Wrought Products.

Current edition approved June 10, 2001. Published September 2001. Originally published as B 211M-79. Last previous edition B 211M-95a.

² *Annual Book of ASTM Standards*, Vol 02.02.

³ *Annual Book of ASTM Standards*, Vol 14.02.

⁴ *Annual Book of ASTM Standards*, Vol 03.05.

⁵ *Annual Book of ASTM Standards*, Vol 03.01.

⁶ *Annual Book of ASTM Standards*, Vol 01.01.

⁷ *Annual Book of ASTM Standards*, Vol 03.06.

⁸ *Annual Book of ASTM Standards*, Vol 03.03.

⁹ *Annual Book of ASTM Standards*, Vol 03.02.

¹⁰ Available from ANSI, 25 W. 43rd St., 4th Floor, New York, NY 10036.

¹¹ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

***A Summary of Changes section appears at the end of this standard.**



TABLE 1 Chemical Composition Limits^{A,B,C}

Alloy	Silicon	Iron	Copper	Manganese	Magnesium	Chromium	Zinc	Bismuth	Lead	Titanium	Other Elements ^D		Aluminum
											Each	Total ^E	
1060	0.25	0.35	0.05	0.03	0.03	...	0.05	0.03	0.03 ^F	...	99.60 min ^G
1100 ^H	0.95 Si + Fe		0.05–0.20	0.05	0.10	0.05	0.15	99.00 min ^G
2011	0.40	0.7	5.0–6.0	0.30	0.20–0.6	0.20–0.6	...	0.05	0.15	remainder
2014	0.50–1.2	0.7	3.9–5.0	0.40–1.2	0.20–0.8	0.10	0.25	0.15	0.05	0.15	remainder
2017	0.20–0.8	0.7	3.5–4.5	0.40–1.0	0.40–0.8	0.10	0.25	0.15	0.05	0.15	remainder
2024	0.50	0.50	3.8–4.9	0.30–0.9	1.2–1.8	0.10	0.25	0.15	0.05	0.15	remainder
2219	0.20	0.30	5.8–6.8	0.20–0.40	0.02	...	0.10	0.02–0.10	0.05 ^I	0.15 ^I	remainder
3003	0.6	0.7	0.05–0.20	1.0–1.5	0.10	0.05	0.15	remainder
5052	0.25	0.40	0.10	0.10	2.2–2.8	0.15–0.35	0.10	0.05	0.15	remainder
5056	0.30	0.40	0.10	0.05–0.20	4.5–5.6	0.05–0.20	0.10	0.05	0.15	remainder
Alclad 5056	5056 alloy clad with 6253 alloy	
5154 ^H	0.25	0.40	0.10	0.10	3.1–3.9	0.15–0.35	0.20	0.20	0.05	0.15	remainder
6061	0.40–0.8	0.7	0.15–0.40	0.15	0.8–1.2	0.04–0.35	0.25	0.15	0.05	0.15	remainder
6110	0.7–1.5	0.8	0.20–0.7	0.20–0.7	0.50–1.1	0.04–0.25	0.30	0.15	0.05	0.15	remainder
6253 ^J	^K	0.50	0.10	...	1.0–1.5	0.04–0.35	1.6–2.4	0.05	0.15	remainder
6262	0.40–0.8	0.7	0.15–0.40	0.15	0.8–1.2	0.04–0.14	0.25	0.40–0.7	0.40–0.7	0.15	0.05	0.15	remainder
7075	0.40	0.50	1.2–2.0	0.30	2.1–2.9	0.18–0.28	5.1–6.1	0.20	0.05	0.15	remainder

^A Limits are in mass percent maximum unless otherwise shown.

^B Analysis shall be made for the elements for which limits are shown in this table.

^C For purposes of determining conformance to these limits, an observed value or a calculated value obtained from analysis shall be rounded to the nearest unit in the last right-hand place of figures used in expressing the specified limit, in accordance with the rounding-off method of Practice E 29.

^D *Others* includes listed elements for which no specific limit is shown as well as unlisted metallic elements. The producer may analyze samples for trace elements not specified in the specification. However, such analysis is not required and may not cover all metallic *Others* elements. Should any analysis by the producer or the purchaser establish that an *Others* element exceeds the limit of *Each* or that the aggregate of several *Others* elements exceeds the limit of *Total*, the material shall be considered non-conforming.

^E Other elements—Total shall be the sum of unspecified metallic elements 0.010 % or more each, rounded to the second decimal before determining the sum.

^F Vanadium 0.05 % max.

^G The aluminum content is the difference between 100.00 % and the sum of all the other metallic elements and silicon present in amounts of 0.010 % or more each, rounded to the second decimal before determining the sum.

^H Beryllium 0.0003 maximum for welding electrode and welding rod only.

^I Vanadium 0.05–0.15 % zirconium 0.10–0.25 %. The total for other elements does not include vanadium and zirconium.

^J Composition of cladding alloy as applied during the course of manufacture. Samples from finished wire shall not be required to conform to these limits.

^K 45 to 65 % of actual magnesium content.

2.6 Aerospace Material Specification:

AMS-H-6088 Heat Treatment of Aluminum Alloys¹²

3. Terminology

3.1 Definitions:

3.1.1 *bar*—a solid product that is long in relation to cross section, which is square or rectangular (excluding plate and flattened wire) with sharp or rounded corners or edges, or is a regular hexagon or octagon, and in which at least one perpendicular distance between parallel faces is over 10 mm.

3.1.2 *cold-finished bar*—bar brought to final dimensions by cold working to obtain improved surface finish and dimensional tolerances.

3.1.3 *rod*—a solid round section over 10 mm in diameter, whose length is great in relation to its diameter.

3.1.4 *cold-finished rod*—rod brought to final dimensions by cold working to obtain improved surface finish and dimensional tolerances.

3.1.5 *wire*—a solid section long in relation to its cross-sectional dimensions, having a cross section that is round, hexagonal, or octagonal and whose diameter, width, or greatest

distance between parallel faces is up through 10 mm, or having a symmetrical cross section that is square or rectangular (excluding flattened wire) with sharp or rounded corners or edges.

3.1.6 *drawn wire*—wire brought to final dimensions by drawing through a die.

3.1.7 *alclad wire*—wire having on its surface a metallurgically bonded aluminum or aluminum-alloy coating that is anodic to the core alloy to which it is bonded, thus electrolytically protecting the core alloy against corrosion.

3.1.8 *flattened wire*—a solid section having two parallel flat surfaces and rounded edges produced by roll-flattening round wire.

3.1.9 *flattened and slit wire*—flattened wire which has been slit to obtain square edges.

3.1.10 *producer*—the primary manufacturer of the material.

3.1.11 *supplier*—includes only the category of jobbers and distributors as distinct from producers.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *capable of*—The term *capable of* as used in this specification means that the test need not be performed by the producer of the material. However, should subsequent testing by the purchaser establish that the material does not meet these requirements, the material shall be subject to rejection.

¹² Available from the Society of Automotive Engineers (SAE), 400 Commonwealth Drive, Warrendale, PA 15096-0001.



TABLE 2 Mechanical Property Limits^{A,B}

Temper	Specified Diameter or Thickness, mm		Tensile Strength, MPa		Yield Strength ^C (0.2 % offset), MPa		Elongation, ^{C,D} min, %	
	over	through	min	max	min	max	in 50 mm	in 5 × diameter (5.65 √ <i>A</i>)
Aluminum 1060								
O	...	3.20	55
	3.20	...	55	...	15	...	25	22
H14	...	10.00	85	...	70
H18	...	10.00	110	...	90
Aluminum 1100								
O	...	3.20	75	105
	3.20	...	75	105	20	...	25	22
H12	...	10.00	95
H14	...	10.00	110
H16	...	10.00	130
H18	...	10.00	150
H112	all	...	75	...	20
F	all	...	^E	...	^E
Alloy 2011								
T3	3.20	40.00	310	...	260	...	10	9
	40.00	50.00	295	...	235	10
	50.00	90.00	290	...	205	12
T4 and T451 ^F	3.20	200.00	275	...	125	...	16	14
T8	3.20	80.00	370	...	275	...	10	9
Alloy 2014 ^G								
O	...	3.20	...	240
	3.20	200.00	...	240	12	10
T4, T42 ^H , and T451 ^F	...	3.20	380
	3.20	200.00 ^I	380	...	220	...	16	14
T6, T62 ^H , and T651 ^F	...	3.20	450
	3.20	200.00 ^I	450	...	380	...	8	7
Alloy 2017 ^G								
O	...	3.20	...	240
	3.20	200.00	...	240	16	14
T4, T42 ^H , and T451 ^F	...	3.20	380
	3.20	200.00 ^{I,J}	380	...	220	...	12	10
Alloy 2024 ^G								
O	...	3.20	...	240
	3.20	200.00	...	240	16	14
T36	...	3.20	475
	3.20	10.00	475	...	360	...	10	...
T4 ^K	...	3.20	425
	3.20	12.50	425	...	310 ^K	...	10	...
	12.50	120.00 ^L	425	...	290	9
	120.00	160.00 ^M	425	...	275	9
	160.00	200.00 ^M	425	...	260	9
T42 ^H	...	3.20	400
	3.20	25.00	425	...	275	...	10	9
	25.00	160.00 ^L	425	...	275	9
T351 ^F	12.50	160.00 ^L	425	...	310	9
T6	...	3.20	425
	3.20	160.00 ^L	425	...	345	...	5	4
T62 ^H	...	3.20	415
	3.20	160.00 ^L	415	...	315	...	5	4
T851 ^F	12.50	160.00 ^L	455	...	400	4
Alloy 2219								
T851 ^F	12.50	50.00	400	...	275	3
	50.00	100.00	395	...	270	3
Alloy 3003								
O	...	3.20	95	130
	3.20	...	95	130	35	...	25	22
H12	...	10.00	115
H14	...	10.00	140

ASTM B 211M

TABLE 2 *Continued*

Temper	Specified Diameter or Thickness, mm		Tensile Strength, MPa		Yield Strength ^C (0.2 % offset), MPa		Elongation, ^{C,D} min, %	
	over	through	min	max	min	max	in 50 mm	in 5 × diameter (5.65 √A)
H16	...	10.00	165
H18	...	10.00	185
H112	all	...	95	...	35
F	all	...	^E	...	^E
Alloy 5052								
O	...	3.20	170	220
	3.20	...	170	220	65	...	25	22
H32	...	3.20	215
	3.20	10.00	215	...	160
H34	...	3.20	235
	3.20	10.00	235	...	180
H36	...	3.20	255
	3.20	10.00	255	...	200
H38	...	10.00	270
F	all	...	^E	...	^E
Alloy 5056								
O	...	3.20	...	320
	3.20	320	20	18
H111	...	10.00	300
H12	...	10.00	315
H32	...	10.00	300
H14	...	10.00	360
H34	...	10.00	345
H18	...	10.00	400
H38	...	10.00	380
H192	...	10.00	415
H392	...	10.00	400
Alclad Alloy 5056								
H192	...	10.00	360
H392	...	10.00	345
H393	3.20	5.00	375	...	325
Alloy 5154								
O	...	3.20	205	285
	3.20	...	205	285	75	...	25	22
H32	...	10.00	250
H34	...	10.00	270
H36	...	10.00	290
H38	...	10.00	310
H112	all	...	205	...	75
Alloy 6061 ^G								
O	...	3.20	...	155
	3.20	200.00	...	155	18	16
T4 and T451 ^F	...	3.20	205
	3.20	200.00 ^J	205	...	110	...	18	16
T42 ^H	...	200.00 ^J	205	...	95	...	18	16
T6, T62 ^H , and T651 ^F	...	3.20	290
	3.20	200.00 ^J	290	...	240	...	10	9
T89 and T94	...	10.00	370	...	325
Alloy 6110								
T9	...	10.00	450	...	435	...	2	...
Alloy 6262								
T6 and T651 ^F	3.20	200.00 ^L	290	...	240	...	10	9
T9	3.20	50.00	360	...	330	...	5	4
	50.00	80.00	345	...	315	4
Alloy 7075 ^G								
O	...	3.20	...	275
	3.20	200.00	...	275	10	9
T6, T62 ^H	...	3.20	530	...	455
	3.20	100.00 ^N	530	...	455	...	7	6



TABLE 2 *Continued*

Temper	Specified Diameter or Thickness, mm		Tensile Strength, MPa		Yield Strength ^C (0.2 % offset), MPa		Elongation, ^{C,D} min, %		
	over	through	min	max	min	max	in 50 mm	in 5 × diameter (5.65 √A)	
T651 ^F	...	3.20	530	...	455	
	3.20	100.00 ^N	530	...	455	...	7	...	
	100.00	160.00	515	...	440	...	7	...	
	160.00	200.00	505	...	425	...	7	...	
T73 and T7351 ^F	...	3.20	470	
	3.20	100.00	470	...	425	...	10	9	
	100.00	120.00	455	...	380	...	8	9	
Temper	Specified Diameter or Thickness, mm						Bend Diameter Factor, N		
	over	through							
Alloy 2017									
T4, T42, and T451	...	3.20							3 ^O
	3.20	200.00 ^J							6 ^O
Alloy 2024									
0	...	3.20							1
T351, T4, T42	...	3.20							3
	3.20	160.00							6
Alloy 3003									
0	all								0
H12	...	10.00							2
H14	...	10.00							2
H16	...	10.00							8

^A To determine conformance to this specification, each value for tensile strength and for yield strength shall be rounded to the nearest 1 MPa and each value for elongation to the nearest 0.5 %, both in accordance with the rounding-off method of Practice E 29.

^B The basis for establishment of tensile property limits is shown in Annex A1.

^C The measurement of yield strength and elongation is not required for wire up through 3.20 mm in thickness or diameter.

^D Elongations in 50 mm apply to rectangular bar up through 12.5 mm thickness from which a standard rectangular tension test specimen is machined. The 5 × diameter (5.65 √A) requirements, where *D* and *A* are diameter and cross-sectional area of the specimen, respectively, apply to round specimens tested in full-section or to standard or proportional, round-machined, tension test specimens.

^E There are no tensile requirements for material in the F temper but it usually can be expected that material 40 mm or less in thickness or diameter (except sections over 100 mm in width) will have a strength about equivalent to the H14 or H34 temper. As size increases the strength decreases to nearly that of the O temper.

^F For stress-relieved tempers, characteristics and properties other than those specified may differ somewhat from the corresponding characteristics and properties of material in the basic tempers.

^G Also available in the F temper for which no properties are specified and no tension tests are performed but for which tests are performed for confirmation of heat-treat response as required by Section 10.

^H Material in the T42 or T62 tempers is not available from the materials producers. These properties can usually be obtained by the user when material is properly solution heat treated or solution and precipitation heat treated from O or F temper. These properties also apply to samples of material in the O or F temper that are solution heat treated or solution and precipitation heat treated by the producer to determine that the material will respond to proper heat treatment. Properties attained by the user, however, may be lower than those listed if the material has been formed or otherwise cold or hot worked, particularly in the O temper, prior to solution heat treatment.

^I For rounds, maximum diameter is 200 mm; for square, rectangular, hexagonal, or octagonal bar, maximum thickness is 100 mm and maximum cross-sectional area is 23 000 mm².

^J For bar, maximum cross-sectional area is 32 000 mm².

^K Minimum yield strength for 2024-T4 wire and rod over 3.20 mm in thickness or diameter, produced in coil form for both straight length and coiled products, is 275 MPa.

^L Properties listed for this size increment are applicable to rod with a maximum diameter of 160 mm and to square, rectangular, hexagonal or octagonal bar having a maximum thickness of 100 mm and maximum cross-sectional area of 23 000 mm².

^M Properties listed for this size increment are listed for rod only.

^N For rounds, maximum diameter is 100 mm; for square, hexagonal, or octagonal bar, maximum thickness is 90 mm; for rectangular bar, maximum thickness is 80 mm, with corresponding maximum width of 150 mm; for rectangular bar less than 80 mm in thickness, maximum width is 250 mm.

^O Bend diameter factor values stated for this full size increment apply to T4 product only. Values listed also apply to T451 produce in the 12.2-200 mm size range.

4. Ordering Information

4.1 Orders for material to this specification shall include the following information:

- 4.1.1 This specification number,
- 4.1.2 Quantity in pieces or kilograms,
- 4.1.3 Alloy (Section 7),
- 4.1.4 Temper (Section 9),
- 4.1.5 *Product Form*—Rolled or cold-finished bar, rolled or cold-finished rod, or wire.

4.1.6 *Geometry and Dimensions*—Diameter for rounds; distance across flats for square-cornered squares, hexagons, or octagons; width and depth for square-cornered rectangles

(orders for squares, hexagons, octagons, or rectangles with rounded corners usually require a drawing),

4.1.7 Length,

4.1.8 Tensile property limits and dimensional tolerances for sizes not covered in Table 2 and in ANSI H35.2M, respectively.

4.2 Additionally, orders for material to this specification shall include the following information when required by the purchaser:

4.2.1 Whether heat treatment in accordance with Practice B 597 is required (8.2),

4.2.2 Whether 7075-O material is required to develop requirements for T73 temper (see 10.1.2),



4.2.3 Whether bend testing is required for 2017, 2024, or 3003 (Section 12),

4.2.4 When specified finish of bar and rod is not required (Section 16),

4.2.5 Whether marking for identification is required (Section 17),

4.2.6 Whether ultrasonic inspection is required (Section 18, Table 3),

4.2.7 Whether inspection or witness of inspection and tests by the purchaser's representative is required prior to material shipment (Section 20),

4.2.8 Whether certification is required (Section 22), and

4.2.9 Whether Practices B 660 applies, and if so, the levels of preservation, packaging, and packing required (Section 23).

5. Manufacture

5.1 The products covered by this specification shall be produced either by hot extruding and cold finishing or by hot rolling with or without cold finishing, at the option of the producer.

6. Quality Assurance

6.1 *Responsibility for Inspection and Tests*—Unless otherwise specified in the contract or purchase order, the producer is responsible for the performance of all inspection and test requirements specified herein. The producer may use his own or any other suitable facilities for the performance of the inspection and test requirements specified herein, unless disapproved by the purchaser in the order at the time of contract signing. The purchaser shall have the right to perform any of the inspections and tests set forth in this specification where such inspections are deemed necessary to assure that material conforms to prescribed requirements.

6.2 *Lot Definition*—An inspection lot shall be defined as follows:

6.2.1 For heat-treated tempers, an inspection lot shall consist of an identifiable quantity of material of the same mill form, alloy, temper, and nominal dimensions traceable to a heat-treat lot or lots, and subjected to inspection at one time.

6.2.2 For nonheat-treated tempers, an inspection lot shall consist of an identifiable quantity of material of the same mill form, alloy, temper, and nominal dimensions subjected to inspection at one time.

7. Chemical Composition

7.1 *Limits*—The bar, rod, and wire shall conform to the chemical composition limits specified in Table 1. Conformance

shall be determined by the producer by analyzing samples taken at the time the ingots are cast, or samples taken from the finished or semifinished product. If the producer has determined the chemical composition of the material during the course of manufacture, additional sampling and analysis of the finished product shall not be required.

NOTE 4—It is standard practice in the United States aluminum industry to determine conformance to the chemical composition limits prior to further processing of ingots into wrought products. Due to the continuous nature of the process, it is not practical to keep a specific ingot analysis identified with a specific quantity of finished material.

7.2 *Number of Samples*—The number of samples taken for determination of chemical composition shall be as follows:

7.2.1 When samples are taken at the time the ingots are cast, at least one sample shall be taken for each group of ingots cast simultaneously from the same source of molten metal.

7.2.2 When samples are taken from the finished or semifinished product, a sample shall be taken to represent each 2000 kg, or fraction thereof, in the lot, except that no more than one sample shall be required per piece.

7.3 *Methods of Sampling*—Samples for determination of chemical composition shall be taken in accordance with one of the following methods:

7.3.1 Samples for chemical analysis shall be taken from the material by drilling, sawing, milling, turning, clipping, etc., a representative piece or pieces to obtain a mass of prepared sample not less than 75 g. Sampling shall be in accordance with Practice E 55.

7.3.2 Sampling for spectrochemical analysis shall be in accordance with Practices E 716. Samples for other methods of analysis shall be suitable for the form of material being analyzed and the type of analytical method used.

NOTE 5—It is difficult to obtain a reliable analysis of each of the components of clad materials using material in its finished state. A reasonably accurate determination of the core composition can be made if the cladding is substantially removed prior to analysis. The cladding composition is more difficult to determine because of the relatively thin layer and because of diffusion of core elements to the cladding. The correctness of cladding alloy used can usually be verified by a combination of metallographic examination and spectrochemical analysis of the surface at several widely separated points.

7.4 *Method of Analysis*—The determination of chemical composition shall be made in accordance with suitable chemical (Test Methods E 34), or spectrochemical (Test Methods E 227, E 607, and E 1251), methods. Other methods may be used only when no published ASTM method is available. In case of dispute, the methods of analysis shall be agreed upon between the producer and the purchaser.

8. Heat Treatment

8.1 Unless otherwise specified in 8.2, producer or supplier heat treatment for the applicable tempers designated in Table 2 shall be in accordance with AMS-H-6088.

8.2 When specified, heat treatment of applicable tempers in Table 2 shall be in accordance with Practice B 597.

9. Tensile Properties of Material as Supplied

9.1 *Limits*—The bar, rod, and wire shall conform to the tensile requirements in Table 2.

TABLE 3 Ultrasonic Discontinuity Limits for Rolled or Cold-Finished Bar^A

Alloys	Size		Maximum Mass per Piece, kg	Discontinuity Class ^B
	Thickness, mm			
	over	through		
2014, 9221 } 2024, 7075 }	12.50	35.00	300	B
	35.00	80.00	300	A
	80.00	155.00	500	B

^A Discontinuities in excess of those listed in this table shall be allowed if it is established that they will be removed by machining or that they are in noncritical areas.

^B The discontinuity class limits are defined in Section 11 of Practice B 594.



9.2 *Number of Specimens:*

9.2.1 For material having a nominal mass up through 1.7 kg/linear m, one tension test specimen shall be taken for each 500 kg or fraction thereof in the lot. Only one specimen shall be taken from any one piece when more than one piece is available.

9.2.2 For material having a nominal mass over 1.7 kg/linear m, one tension test specimen shall be taken for each 300 m or fraction thereof in the lot. Only one specimen shall be taken from any one piece when more than one piece is available.

9.3 *Test Specimens*—Geometry of test specimens and the location in the product from which they are taken shall be as specified in Test Methods B 557M.

9.4 *Test Methods*—The tension tests shall be made in accordance with Test Methods B 557M.

10. Producer Confirmation of Heat-Treat Response

10.1 In addition to the requirements of 9.1, material in Alloys 2014, 2017, 2024, and 6061 produced in the O or F temper (within the size limits specified in Table 2) shall, after proper solution heat treatment and natural aging for not less than 4 days at room temperature, conform to the properties specified in Table 2 for T42 temper material. The heat-treated samples may be tested prior to 4 days natural aging but if they fail to conform to the T42 temper properties, the tests may be repeated after completion of 4 days natural aging without prejudice.

10.1.1 Alloy 7075 material produced in the O or F temper (within the size limits specified in Table 2) shall, after proper solution heat treatment and precipitation heat treatment, conform to the properties specified in Table 2 for T62 temper material.

10.1.2 When specified, 7075-O material (within the size limits specified in Table 2) shall, after proper solution and precipitation heat treatment, conform to the properties specified for T73 temper in Table 2 and Section 13.

10.2 *Number of Specimens*—The number of specimens from each lot of O temper material and F temper material to verify conformance with 10.1 shall be as specified in 9.2.

11. Heat Treatment and Reheat Treatment Capability

11.1 As-received material in the O or F temper and in Alloys 2014, 2017, 2024, and 6061 (within the size limitation specified in Table 2 and without the imposition of cold work) shall, after proper solution heat treatment and natural aging for not less than 4 days at room temperature, conform to the properties specified in Table 2 for T42 temper material.

11.2 As-received Alloy 7075 material in the O or F temper (within the size limitations specified in Table 2 and without the imposition of cold work) shall, after proper solution and precipitation heat treatment, conform to the properties specified in Table 2 for T6 and T62 tempers.

11.3 Material in Alloys and Tempers 2014-T4, T451, T6, T651; 2017-T4, T451; 2024-T4, T6, T351, and T851 shall, after proper resolution heat treatment and natural aging for not less than 4 days at room temperature, conform to the properties specified in Table 2 for the T42 temper.

NOTE 6—6061-T4, T6, T451, and T651 are deleted from this paragraph because experience has shown the reheat-treated material tends to develop

large recrystallized grains and may fail to develop the expected levels of properties.

11.4 Alloy 7075 material in T6, T651, T73, and T7351 tempers shall, after proper resolution heat treatment and precipitation heat treatment, conform to the properties specified in Table 2 for T6 and T62 tempers.

11.5 Material in T3, T4, T42, T351, and T451 tempers shall, after proper precipitation heat treatment, conform to the properties specified in Table 2 for the T8, T6, T62, T851 and T651 tempers, respectively.

12. Bend Properties

12.1 When bend testing is specified for the alloys, tempers and dimensions listed with the Bend Diameter Factor, N , values in Table 2; bend test specimens shall be prepared and tests shall be made in accordance with applicable requirements of Test Method E 290. Bend test samples shall be bent cold without cracking through an angle of 180° around a pin having a diameter equal to N times the product diameter or least thickness of the specimen.

13. Stress-Corrosion Resistance

13.1 Alloy 7075 in the T73-type tempers shall be capable of exhibiting no evidence of stress-corrosion cracking when subjected to the test specified in 13.2.

13.1.1 For lot acceptance purposes, resistance to stress-corrosion cracking for each lot of material shall be established by testing the previously selected tension-test samples to the criteria shown in Table 4.

13.1.2 For surveillance purposes, each month the producer shall perform at least one test for stress-corrosion resistance in accordance with 13.2 in the T73 type temper, for each thickness range 20.00 mm and over listed in Table 2, produced that month. Each sample shall be taken from material considered acceptable in accordance with lot-acceptance criteria of Table 4. A minimum of three adjacent replicate specimens shall be taken from each sample and tested. The producer shall maintain records of all lots so tested and make them available for examination at the producer's facility.

13.2 The stress-corrosion cracking test shall be performed on material 20.00 mm and over in thickness as follows:

13.2.1 Specimens shall be stressed in tension in the short transverse direction with respect to grain flow and held at constant strain. The stress level shall be 75 % of the specified minimum yield strength.

13.2.2 The stress-corrosion test shall be made in accordance with Test Method G 47.

13.2.3 There shall be no visual evidence of stress-corrosion cracking in any specimen, except that the retest provisions of 21.2 shall apply.

14. Cladding Thickness

14.1 The aluminum-alloy coating of Alclad 5056 wire shall have a minimum average thickness corresponding to 16 % of the total cross-sectional area of the wire.

14.2 When the area of the coating is to be determined on finished wire, transverse cross sections of at least three wires from the lot shall be mounted to expose a transverse cross section and polished for examination with a metallurgical



TABLE 4 Lot Acceptance Criteria for Resistance to Stress Corrosion

Lot Acceptance Criteria			
Alloy and Temper	Electrical Conductivity ^A , IACS	Level of Mechanical Properties	Lot Acceptance Status
7075-T73 and T7351	40.0 or greater	per specified requirements	acceptable
	38.0 through 39.9	per specified requirements and yield strength does not exceed minimum by more than 82 MPa	acceptable
	38.0 through 39.9	per specified requirements but yield strength exceeds minimum by more than 82 MPa	unacceptable ^B
	Less than 38.0	any level	unacceptable ^B

^A The electrical conductivity shall be determined in accordance with Test Method E 1004 in the following locations:

^B When material is found to be unacceptable, it shall be reprocessed (additional precipitation heat treatment or re-solution heat treatment, stress relieving and precipitation heat treatment, when applicable).

Product	Thickness, mm	Location
Rolled or cold finished from rolled stock Cold finished from extruded stock	All	surface of tension-test sample
	Up through 2.50	surface of tension-test sample
	Over 2.50 through 12.50	subsurface after removing approximately 10 % of the thickness by machining
	Over 12.50 through 40.00	subsurface at approximate center of thickness on a plane parallel to the longitudinal centerline of the material
	Over 40.00	subsurface of tension-test sample surface that is closest to the center of the material and on a plane parallel to the extrusion surface

microscope. Using at least 100× magnification, the coating area in each sample shall be measured by use of a planimeter on the projected image, and the average of the measurements shall be taken as the area.

15. Dimensional Tolerances

15.1 Variations from specified dimensions for the material ordered shall not exceed the permissible variations specified in the following tables of ANSI H35.2M.

Table No.	Title
9.1	Diameter—Round Wire and Rod
9.5	Thickness and Width—Rectangular Wire and Bar
9.6	Distance across Flats—Square Hexagonal and Octagonal Wire and Bar
9.7	Thickness and Width—Flattened Wire (Round Edge)
9.8	Thickness and Width—Flattened and Slit Wire
9.9	Length—Specific and Multiple
9.10	Twist—Bar and Straight Lengths
9.11	Straightness—Rod and Bar in Straight Lengths Other than Screw Machine Stock
9.13	Flatness—Flat Surfaces
9.14	Angularity
9.15	Squareness of Saw Cuts

15.2 *Sampling for Inspection*—Examination for dimensional conformance shall be made to ensure conformance to the tolerance specified.

16. Finish

16.1 Unless otherwise specified, rod up to and including 75 mm in diameter and bar up to and including 50 mm thick (with maximum width for rectangles of 100 mm) shall be supplied cold finished. Rod and bar in larger sizes may be furnished either as rolled or cold finished, at the producer’s or supplier’s discretion.

17. Identification Marking of Product

17.1 When specified in the contract or purchase order all material shall be marked in accordance with Practice B 666M. In addition, 2000 and 7000 series alloys furnished in the T6, T651, T73, T7351 or T851 tempers shall also be marked with the lot number in at least one location on each piece.

18. Internal Quality

18.1 When specified by the purchaser at the time of placing the order, each bar over 12.50 mm in thickness or smallest dimension in Alloys 2014, 2024, 2219, and 7075 shall be tested in accordance with Practice B 594 to the discontinuity acceptance limits of Table 3.

19. General Quality

19.1 Unless otherwise specified, the material shall be supplied in the mill finish and shall be uniform as defined by the requirements of this specification and shall be commercially sound. Any requirement not so covered is subject to negotiation between the producer and the purchaser.

19.2 Each inspection lot of bar, rod, and wire shall be examined to determine conformance to this specification with respect to general quality and identification marking. On approval of the purchaser, however, the producer may use a system of statistical quality control for such examinations.

20. Source Inspection

20.1 If the purchaser desires that his representative inspect or witness the inspection and testing of the material prior to shipment, such agreement shall be made by the purchaser and producer as part of the purchase contract.

20.2 When such inspection or witness of inspection and testing is agreed upon, the producer shall afford the purchaser’s representative all reasonable facilities to satisfy him that the material meets the requirements of this specification. Inspection and tests shall be conducted so there is no unnecessary interference with the producer’s operations.

21. Rejection and Retest

21.1 If any material fails to conform to all of the applicable requirements of this specification, it shall be cause for rejection of the inspection lot.

21.2 When there is evidence that a failed specimen was not representative of the inspection lot and when no other sampling plan is provided or approved by the purchaser through the



contract or purchase order, at least two additional specimens shall be selected to replace each test specimen that failed. All specimens so selected for re-test shall meet the requirements of the specification or the lot shall be subject to rejection.

21.3 Material in which defects are discovered subsequent to inspection may be rejected.

21.4 If material is rejected by the purchaser, the producer or supplier is responsible only for replacement of the material to the purchaser. As much as possible of the rejected material shall be returned to the producer or supplier.

22. Certification

22.1 The producer or supplier shall, on request, furnish to the purchaser a certificate of inspection stating that each lot has been sampled, tested, and inspected in accordance with this specification, and has been found to meet the requirements.

23. Packaging and Package Marking

23.1 The material shall be packaged to provide adequate protection during normal handling and transportation, and each package shall contain only one size, alloy, and temper of

material unless otherwise agreed. The type of packing and gross mass of containers shall, unless otherwise agreed upon, be at the producer's discretion, provided they are such as to ensure acceptance by common or other carriers for safe transportation at the lowest rate to the delivery point.

23.2 Each shipping container shall be marked with the purchase order number, material size, specification number, alloy and temper, gross and net masses, and the producer's name or trademark.

23.3 When specified in the contract or purchase order, material shall be preserved, packaged, and packed in accordance with the requirements of Practices B 660. The applicable levels shall be as specified in the contract or order. Marking for shipment of such material shall be in accordance with Fed. Std. No. 123 for civil agencies and MIL-STD-129 for military agencies.

24. Keywords

24.1 aluminum alloy; rolled or cold-finished bar; rolled or cold-finished rod; rolled or cold-finished wire

ANNEXES

(Mandatory Information)

A1. BASIS FOR INCLUSION OF PROPERTY LIMITS

A1.1 Limits are established at a level at which a statistical evaluation of the data indicates that 99 % of the population obtained from all standard material meets the limit with 95 % confidence. For the products described, mechanical property limits for the respective size ranges are based on the analyses of at least 100 data from standard production material with no more than ten data from a given lot. All tests are performed in accordance with the appropriate ASTM test methods. For

informational purposes, refer to "Statistical Aspects of Mechanical Property Assurance" in the Related Material section of the *Annual Book of ASTM Standards*, Vol 02.02. Mechanical property limits in this metric issue were derived from the inch-pound system limits that were developed under the above principles. As test data on metric dimensioned specimens are accumulated, some refinement of limits, particularly for elongations measured in 5D, can be anticipated.

A2. ACCEPTANCE CRITERIA FOR INCLUSION OF NEW ALUMINUM AND ALUMINUM ALLOYS IN THIS SPECIFICATION

A2.1 Prior to acceptance for inclusion in this specification, the composition of wrought or cast aluminum or aluminum alloy shall be registered in accordance with ANSI H35.1(M). The Aluminum Association¹³ holds the Secretariat of ANSI H35 Committee and administers the criteria and procedures for registration.

A2.2 If it is documented that the Aluminum Association could not or would not register a given composition, an alternative procedure and the criteria for acceptance shall be as follows:

A2.2.1 The designation submitted for inclusion does not utilize the same designation system as described in ANSI

H35.1(M). A designation not in conflict with other designation systems or a trade name is acceptable.

A2.2.2 The aluminum or aluminum alloy has been offered for sale in commercial quantities within the prior twelve months to at least three identifiable users.

A2.2.3 The complete chemical composition limits are submitted.

A2.2.4 The composition is, in the judgment of the responsible subcommittee, significantly different from that of any other aluminum or aluminum alloy already in the specification.

A2.2.5 For codification purposes, an alloying element is any element intentionally added for any purpose other than grain refinement and for which minimum and maximum limits are specified. Unalloyed aluminum contains a minimum of 99.00 % aluminum.

A2.2.6 Standard limits for alloying elements and impurities

¹³ The Aluminum Association, 900 19th Street, NW, Washington, DC 20006.



are expressed to the following decimal places:

Less than 0.001 %	0.000X
0.001 to but less than 0.01 %	0.00X
0.01 to but less than 0.10 %	
Unalloyed aluminum made by a refining process	0.0XX
Alloys and unalloyed aluminum not made by a refining process	0.0X
0.10 through 0.55 %	0.XX
(It is customary to express limits of 0.30 through 0.55 % as 0.X0 or 0.X5.)	
Over 0.55 %	0.X, X.X, etc.
(except that combined Si + Fe limits for 99.00 % minimum aluminum must be expressed as 0.XX or 1.XX)	

are expressed in the following sequence: Silicon; Iron; Copper; Manganese; Magnesium; Chromium; Nickel; Zinc (Note A2.1); Titanium; Other Elements, Each; Other Elements, Total; Aluminum (Note A2.2).

NOTE A2.1—Additional specified elements having limits are inserted in alphabetical order of their chemical symbols between zinc and titanium, or are specified in footnotes.

NOTE A2.2—Aluminum is specified as *minimum* for unalloyed aluminum and as a *remainder* for aluminum alloys.

A2.2.7 Standard limits for alloying elements and impurities

SUMMARY OF CHANGES

Committee B07 has identified the location of selected changes to this standard since B 211M–95a that may impact the use of this standard.

- (1) Updated Referenced Documents (Section 2).
- (2) Expanded Ordering Information (Section 4).
- (3) Section 12, Bend Properties, was added.
- (4) Table 1, Footnotes F, H, K were revised; Footnote D was added.
- (5) Table 2, bend test factor values were added for 2017, 2024, and 3003 products.
- (6) Table 2, Footnotes L and O added.
- (7) Table 2, 2011-T3 thickness range was revised.
- (8) Table 2, 7075-T6, T62, T651, T73, and T7351 thickness ranges and properties were revised.

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).