



Designation: B 231/B 231M – 99

## Standard Specification for Concentric-Lay-Stranded Aluminum 1350 Conductors<sup>1</sup>

This standard is issued under the fixed designation B 231/B 231M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 This specification covers aluminum 1350-H19 (extra hard), 1350-H16 or -H26 ( $\frac{3}{4}$  hard), 1350-H14 or -H24 ( $\frac{1}{2}$  hard), and 1350-H142 or -H242 ( $\frac{1}{2}$  hard), bare concentric-lay-stranded conductors constructed with a straight round central wire surrounded by one or more layers of helically layed wires. The conductors are for general use for electrical purposes (Explanatory Note 1 and Note 2).

1.2 The values stated in inch-pound or SI units are to be regarded separately as standard. The values in each system are not exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

1.2.1 For density, resistivity and temperature, the values stated in SI units are to be regarded as standard.

NOTE 1—Prior to 1975, aluminum 1350 was designated as EC aluminum.

NOTE 2—The aluminum and temper designations conform to ANSI Standard H35.1/H35.1M. Aluminum 1350 corresponds to Unified Numbering System A91350 in accordance with Practice E 527.

NOTE 3—Sealed conductors that are intended to prevent longitudinal water propagation and are further covered/insulated are also permitted within the guidelines of this specification.

### 2. Referenced Documents

2.1 The following documents of the issue in effect on date of material purchase form a part of this specification to the extent referenced herein:

#### 2.2 ASTM Standards:

- B 193 Test Method for Resistivity of Electrical Conductor Materials<sup>2</sup>
- B 230/B 230M Specification for Aluminum 1350-H19 Wire for Electrical Purposes<sup>2</sup>
- B 263 Test Method for Determination of Cross-Sectional Area of Stranded Conductors<sup>2</sup>
- B 354 Terminology Relating to Uninsulated Metallic Electrical Conductors<sup>2</sup>

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B-1 on Electrical Conductors and is the direct responsibility of Subcommittee B01.07 on Conductors of Light Metals.

Current edition approved April 10, 1999. Published June 1999. Originally published as B 231 – 48 T. Last previous edition B 231 – 95.

<sup>2</sup> Annual Book of ASTM Standards, Vol 02.03.

B 609/B 609M Specification for Aluminum 1350 Round Wire, Annealed and Intermediate Tempers, for Electrical Purposes<sup>2</sup>

B 682 Specification for Standard Metric Sizes of Electrical Conductors<sup>2</sup>

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications<sup>3</sup>

E 527 Practice for Numbering Metals and Alloys (UNS)<sup>4</sup>

#### 2.3 ANSI Documents:

ANSI H35.1 American National Standard Alloy and Temper Designation System for Aluminum<sup>5</sup>

ANSI H35.1M American National Standard Alloy and Temper Designation Systems for Aluminum [Metric]<sup>5</sup>

#### 2.4 NIST Document:

NBS Handbook 100—Copper Wire Tables<sup>6</sup>

#### 2.5 Aluminum Association Document:

Publication 50, Code Words for Overhead Aluminum Electrical Conductors<sup>7</sup>

### 3. Classification

3.1 For the purpose of this specification, conductors are classified as follows (Explanatory Note 1 and Note 2):

3.1.1 *Class AA*—For bare conductors usually used in overhead lines.

3.1.2 *Class A*—For conductors to be covered with weather-resistant materials, and for bare conductors where greater flexibility than is afforded by Class AA is required. Conductors intended for further fabrication into tree wire or to be insulated and laid helically with or around aluminum or ACSR messengers, shall be regarded as Class A conductors with respect to direction of lay only (see 7.4).

3.1.3 *Class B*—For conductors to be insulated with various materials such as rubber, paper, varnished cloth, etc., and for the conductors indicated under Class A where greater flexibility is required.

<sup>3</sup> Annual Book of ASTM Standards, Vol 14.02.

<sup>4</sup> Annual Book of ASTM Standards, Vol 01.01.

<sup>5</sup> Available from American National Standards Institute, 11 West 42nd St., 13th Floor, New York, NY 10036.

<sup>6</sup> Available from the National Technical Information Service, 5285 Port Royal Rd, Springfield, VA 22161.

<sup>7</sup> Available from the Aluminum Association, Inc., 900 19th Street, NW, Suite 300, Washington, DC 20006.

3.1.4 *Classes C and D*—For conductors where greater flexibility is required than is provided by Class B conductors.

**TABLE 1 Construction Requirements and Recommended Reel Sizes and Shipping Lengths of Aluminum Conductors, Concentric-Lay-Stranded, Class AA, and Class A**

NOTE 1—Metric values listed represent a soft conversion and as such they may not be the same as those masses which are calculated from the basic metric density.

Conductor Size				Required Construction		Mass		Rated Strength		Recommended Package Sizes <sup>A</sup>			
cmils <sup>B</sup> or AWG	mm <sup>2</sup>	Code Words <sup>C</sup>	Class	Number of Wires	Diameter of Wire		Per 1000 ft, lb	Per km, kg	kips	kN	Reel Designation <sup>D</sup>	Nominal Length of Each Piece, ft <sup>B</sup>	Nominal Mass of Each Length, lb <sup>B</sup>
					in.	mm							
3 500 000	1 773	Bluebonnet	A	127	0.1660	4.22	3 345	4 977	58.7	261	RMT 90.45	2 840	9 530
3 000 000	1 520	Trillium	A	127	0.1537	3.90	2 840	4 226	50.3	223	RMT 90.45	3 350	9 530
2 750 000	1 393	Bitterroot	A	91	0.1738	4.42	2 602	3 872	46.1	205	RMT 90.45	3 490	9 100
2 500 000	1 267	Lupine	A	91	0.1657	4.21	2 365	3 519	41.9	186	RMT 90.45	3 840	9 100
2 250 000	1 140	Sagebrush	A	91	0.1572	3.99	2 128	3 166	37.7	167	RMT 90.45	4 270	9 100
2 000 000	1 013	Cowslip	A	91	0.1482	3.77	1 873	2 787	34.2	153	RMT 90.45	4 850	9 100
1 750 000	886.7	Jessamine	AA	61	0.1694	4.30	1 641	2 442	29.7	132	RMT 90.45	5 940	9 760
1 590 000	805.7	Coreopsis	AA	61	0.1614	4.10	1 489	2 216	27.0	120	RMT 90.45	6 540	9 760
											RM 68.38	3 270	4 880
1 510 500	765.4	Gladiolus	AA, A	61	0.1574	4.00	1 417	2 108	25.6	114	RMT 90.45	6 880	9 760
											RM 68.38	3 440	4 880
1 431 000	725.1	Carnation	AA, A	61	0.1532	3.89	1 342	1 997	24.3	108	RMT 90.45	7 270	9 760
											RM 68.38	3 635	4 880
1 351 000	694.8	Columbine	AA, A	61	0.1488	3.78	1 266	1 884	23.4	104	RMT 90.45	7 690	9 760
											RM 68.38	3 845	4 880
1 272 000	644.5	Narcissus	AA, A	61	0.1444	3.67	1 192	1 774	22.0	98.1	RMT 90.45	8 170	9 760
											RM 68.38	4 085	4 880
1 192 500	604.2	Hawthorn	AA, A	61	0.1398	3.55	1 117	1 662	21.1	93.5	RMT 90.45	9 340	9 760
											RM 68.38	4 360	4 880
1 113 000	564.0	Marigold	AA, A	61	0.1351	3.43	1 044	1 553	19.7	87.3	RMT 90.45	9 340	9 760
											RM 68.38	4 670	4 880
1 033 500	523.7	Bluebell	AA	37	0.1671	4.25	968.4	1 441	17.7	78.8	RMT 84.45	7 630	7 400
											RM 66.32	3 815	3 700
											NR 48.28	1 910	1 850
1 033 500	523.7	Larkspur	A	61	0.1302	3.31	969.2	1 442	18.3	81.3	RMT 90.45	10 060	9 760
											RM 68.38	5 030	4 880
1 000 000	506.7	Hawkweed	AA	37	0.1644	4.18	937.3	1 395	17.2	76.2	RMT 84.45	7 880	7 400
											RM 66.32	3 940	3 700
											NR 48.28	1 970	1 850
1 000 000	506.7	Camellia	A	61	0.1280	3.25	936.8	1 394	17.7	78.3	RMT 90.45	10 400	9 760
											RM 68.38	5 200	4 880
954 000	483.4	Magnolia	AA	37	0.1606	4.08	894.5	1 331	16.4	72.6	RMT 84.45	8 260	7 400
											RM 66.32	4 130	3 700
											NR 48.28	2 065	1 850
954 000	483.4	Goldenrod	A	61	0.1251	3.18	894.8	1 331	16.9	75.0	RMT 90.45	10 900	9 760
											RM 68.38	5 450	4 880
900 000	456.0	Cockscomb	AA	37	0.1560	3.96	844.0	1 256	16.4	68.4	RMT 84.45	8 760	7 400
											RM 66.32	4 390	3 700
											NR 48.28	2 190	1 850
900 000	456.0	Snapdragon	A	61	0.1215	3.09	844.0	1 256	15.9	70.8	RMT 90.45	11 550	9 760
											RM 68.38	5 775	4 880
795 00	402.8	Arbutus	AA	37	0.1466	3.72	745.3	1 109	13.9	61.8	RMT 84.45	9 920	7 400
											RM 66.32	4 960	3 700
											NR 48.28	2 480	1 850
795 000	402.8	Lilac	A	61	0.1142	2.90	745.7	1 110	14.3	63.8	RMT 90.45	13 080	9 760
											RM 68.38	6 540	4 880
750 000	380.0	Petunia	AA	37	0.1424	3.62	703.2	1 046	13.1	58.6	RMT 84.45	10 510	7 400
											RM 66.32	5 255	3 700
											NR 48.28	2 630	1 850
750 000	380.0	Cattail	A	61	0.1109	2.82	703.2	1 046	13.5	60.3	RMT 90.45	13 860	9 760
											RM 68.38	6 930	4 880
715 500	362.6	Violet	AA	37	0.1391	3.53	671	998.5	12.8	56.7	RTM 84.45	11 020	7 400
											RM 66.32	5 510	3 700
											NR 48.28	2 755	1 850
715 500	362.6	Nasturtium	A	61	0.1083	2.75	671	998.5	13.1	58.4	RMT 90.45	14 530	9 760
											RM 68.38	7 265	4 880
700 000	354.7	Verbena	AA	37	0.1375	3.49	655.7	975.7	12.5	55.4	RMT 84.45	11 260	7 400
											RM 66.32	5 630	3 700
											NR 48.28	2 815	1 850

**TABLE 1** *Continued*

Conductor Size		Required Construction				Mass		Rated Strength		Recommended Package Sizes <sup>A</sup>			
cmils <sup>B</sup> or AWG	mm <sup>2</sup>	Code Words <sup>C</sup>	Class	Number of Wires	Diameter of Wire		Per 1000 ft, lb	Per km, kg	kips	kN	Reel Designation <sup>D</sup>	Nominal Length of Each Piece, ft <sup>E</sup>	Nominal Mass of Each Length, lb <sup>E</sup>
					in.	mm							
700 000	354.7	Flag	A	61	0.1071	2.72	655.8	975.8	12.9	57.1	RMT 90.45	14 850	9 760
											RM 68.38	7 425	4 880
650 000	329.4	Heuchera	AA	37	0.1326	3.37	609.8	907.4	11.6	51.7	RMT 84.45	12 130	7 400
											RM 66.32	6 065	3 700
											NR 48.28	3 035	1 850
636 000	322.3	Orchid	AA, A	37	0.1311	3.33	596.0	886.9	11.4	50.4	RMT 84.45	12 400	7 400
											RM 66.32	6 200	3 700
											NR 48.28	3 100	1 850
600 000	304.0	Meadowsweet	AA, A	37	0.1273	3.23	562.0	836.3	10.7	47.5	RMT 84.45	13 140	7 400
											RM 66.32	6 570	3 700
											NR 48.28	3 285	1 850
556 500	282.0	Dahlia	AA	19	0.1711	4.35	521.4	775.8	9.75	43.3	RM 66.32	7 270	3 800
											NR 48.28	3 635	1 900
											NR 42.28	2 425	1 265
556 500	282.0	Mistletoe	A	37	0.1226	3.12	521.3	775.7	9.94	44.3	RMT 84.45	14 170	7 400
											RM 66.32	7 085	3 700
											NR 48.28	3 545	1 850
500 000	253.3	Zinnia	AA	19	0.1622	4.12	468.5	697.1	8.76	38.9	RM 66.32	8 100	3 800
											NR 48.28	4 050	1 900
											NR 42.28	2 700	1 265
500 000	253.3	Hyacinth	A	37	0.1162	2.95	468.3	696.8	9.11	40.5	RMT 84.45	15 760	7 400
											RM 66.32	7 880	3 700
											NR 48.28	3 940	1 850
477 000	241.7	Cosmos	AA	19	0.1584	4.02	446.8	664.8	8.36	37.0	RM 66.32	8 490	3 800
											NR 48.28	4 245	1 900
											NR 42.28	2 830	1 265
477 000	241.7	Syringa	A	37	0.1135	2.88	446.8	664.8	8.69	38.6	RMT 84.45	16 530	7 400
											RM 66.32	8 265	3 700
											NR 48.28	4 135	1 850
450 000	228.0	Goldentuft	AA	19	0.1539	3.91	421.8	627.6	7.89	35.0	RM 66.32	9 000	3 800
											NR 48.28	4 500	1 900
											NR 42.28	3 000	1 265
397 500	201.4	Canna	AA, A	19	0.1447	3.67	372.9	554.9	7.11	31.6	RM 66.32	10 180	3 800
											NR 48.28	5 090	1 900
											NR 42.28	3 395	1 265
350 000	177.3	Daffodil	A	19	0.1357	3.45	327.9	487.9	6.39	28.4	RM 66.32	11 560	3 800
											NR 48.28	5 780	1 900
											NR 42.28	3 855	1 265
336 400	170.5	Tulip	A	19	0.1331	3.38	315.5	469.5	6.15	27.3	RM 66.32	12 030	3 800
											NR 48.28	6 015	1 900
											NR 42.28	4 010	1 265
300 000	152.0	Peony	A	19	0.1257	3.19	281.4	418.3	5.48	24.3	RM 66.32	13 490	3 800
											NR 48.28	6 745	1 900
											NR 42.28	4 495	1 265
266 800	135.2	Daisy	AA	7	0.1953	4.96	250.2	372.3	4.83	21.4	NR 42.28	5 590	1 400
											NR 36.22	2 795	700
266 800	135.2	Laurel	A	19	0.1185	3.01	250.1	372.2	4.97	22.1	RM 66.32	15 170	3 800
											NR 48.28	7 585	1 900
											NR 42.28	5 055	1 265
250 000	126.7	Sneezewort	AA	7	0.1890	4.80	234.4	348.8	4.52	20.1	NR 42.28	5 970	1 400
											NR 36.22	2 985	700
250 000	126.7	Valerian	A	19	0.1147	2.91	234.3	348.6	4.66	20.7	RM 66.32	16 190	3 800
											NR 48.28	8 095	1 900
											NR 42.28	5 395	1 265
4/0	107.2	Oxlip	AA, A	7	0.1739	4.42	198.4	295.2	3.83	17.0	NR 42.28	7 050	1 400
											NR 36.22	3 525	700
3/0	85.0	Phlox	AA, A	7	0.1548	3.93	157.2	233.9	3.04	13.5	NR 42.28	8 890	1 400
											NR 36.22	4 445	700
2/0	67.4	Aster	AA, A	7	0.1379	3.50	124.8	185.7	2.51	11.1	NR 42.28	11 210	1 400
											NR 36.22	5 605	700

**TABLE 1** *Continued*

Conductor Size				Required Construction		Mass		Rated Strength		Recommended Package Sizes <sup>A</sup>			
cmils <sup>B</sup> or AWG	mm <sup>2</sup>	Code Words <sup>C</sup>	Class	Number of Wires	Diameter of Wire		Per 1000 ft, lb	Per km, kg	kips	kN	Reel Designation <sup>D</sup>	Nominal Length of Each Piece, ft <sup>B</sup>	Nominal Mass of Each Length, lb <sup>B</sup>
					in.	mm							
1/0	53.5	Poppy	AA, A	7	0.1228	3.12	98.9	147.2	1.99	8.84	NR 42.28	14 130	1 400
1	42.4	Pansy	AA, A	7	0.1093	2.78	78.4	116.6	1.64	7.30	NR 36.22	7 065	700
2	33.6	Iris	AA, A	7	0.0974	2.47	62.2	92.6	1.35	5.99	NR 36.22	8 915	700
4	21.1	Rose	A	7	0.0772	1.96	39.1	58.2	0.881	3.91	NR 42.28	22 470	1 400
6	13.3	Peachbell	A	7	0.0612	1.56	24.6	36.6	0.563	2.53	NR 36.22	11 235	700
											NR 42.28	35 710	1 400
											NR 36.22	17 855	700
											NR 42.28	56 910	1 400
											NR 36.22	28 455	700

<sup>A</sup> For information only.

<sup>B</sup> Conversion factors: 1 cmil = 5.067 E-04 mm<sup>2</sup>, 1 mil + 2.54 E-02 mm, 1 lb/1000 ft = 1.488 E+00 kg/km, 1 ft = 3.048 E-01 m, 1 lb = 4.536 E-01 kg, 1 lbf = 4.448 E-03 kN.

<sup>C</sup> Code words shown in this column are from, "Publication 50, Code Words for Overhead Aluminum Electrical Conductors," by the Aluminum Association. They are provided here for information only.

<sup>D</sup> See Table 9 for dimensions of standard reels.

#### 4. Ordering Information

4.1 Orders for material under this specification shall include the following information:

4.1.1 Quantity,

4.1.2 Conductor size: square millimetres, if cross-sectional area is specified as a requirement (Section 8 and Tables 1-4),

4.1.2.1 Conductor size, number and diameter of wires for Class B, C, or D conductors, if cross-sectional area is not specified as a requirement (see 8.2),

4.1.3 Class (see 3.1),

4.1.4 Temper (see 5.1),

4.1.5 Details of special-purpose lays, when required (see 7.2 through 7.5),

4.1.6 Special tension tests if required (see 14.1 and 15.1),

4.1.7 Package size and type (see 17.1 and Table 1 or Table 2),

4.1.8 Special package marking, if required (Section 19),

4.1.9 Heavy wood lagging if required (see 18.2),

4.1.10 Place of inspection (Section 17), and

4.1.11 Method of cross-sectional area determination if not optional (see 12.1).

#### 5. Requirements for Wires

5.1 Aluminum wire employed in Classes AA and A conductors shall be 1350-H19, unless otherwise specified. The purchaser shall designate the temper of conductors of Classes B, C, and D.

5.1.1 For conductor tempers other than 1350-H19, when temper designations are not more specific in the inquiry and purchase order, the manufacturer shall have the following options on manufacturing method:

5.1.1.1 Strand the conductor from wires drawn to final temper;

5.1.1.2 Strand the conductor from wires drawn to H19 temper and annealed to final temper prior to stranding;

5.1.1.3 Strand the conductor from 1350-H19 wires and anneal the stranded conductor to final temper.

5.2 Before stranding, the aluminum wire used shall meet the requirements of Specifications B 230/B 230M or B 609/B 609M, whichever is applicable.

5.3 All wires in the conductor shall be of the same temper.

#### 6. Joints

6.1 Only cold-pressure joints or electric-butt, cold-upset joints may be made in the six outer finished wires of (1) Class AA conductors composed of seven wires or (2) Class A conductors composed of seven wires used in overhead lines. In other conductors, electric-butt welds, cold-pressure welds, or electric-butt, cold-upset welds may be made in the finished wires composing conductors, but such welds shall not be closer than prescribed in Table 5 (Explanatory Note 3).

#### 7. Lay

7.1 For Class AA conductors composed of seven wires or more the preferred lay of a layer of wires is 13.5 times the outside diameter of that layer, but the lay shall be not less than 10 nor more than 16 times this diameter.

7.2 For all other classes the lay of a layer of wires shall be not less than 8 nor more than 16 times the outside diameter of that layer, except that for conductors composed of 37 wires or more, this requirement shall apply only to the two outer layers. The lay of the layers other than the two outer layers shall be at the option of the manufacturer, unless otherwise agreed upon.

7.2.1 For conductors to be used in covered or insulated wires or cables, the lay length of the wires shall not be less than 8 nor more than 16 times the outer diameter of the finished conductor. For conductors of 37 wires or more, this requirement shall apply to the wires in the outer two layers. The lay of the layers other than the outer two layers shall be at the option of the manufacturer, unless otherwise agreed upon.

7.3 Other lays for special purposes shall be furnished by special agreement between the manufacturer and the purchaser (Explanatory Note 4).

7.4 The direction of lay of the outer layer shall be right-hand for Classes AA and A and left-hand for other classes, unless the direction of lay is specified otherwise by the purchaser.

**TABLE 2 Construction Requirements and Recommended Reel Sizes and Shipping Lengths of Aluminum Conductors, Concentric Lay-Stranded, Classes AA and A**

NOTE 1—Sizes selected from Specification B 682.

Conductor Size, mm <sup>2</sup>	Class	Stranding			Rated Strength 1350-H19, kN	Recommended Package Sizes <sup>A</sup>		
		Number of Wires	Diameter, mm	Mass, kg/km		Reel Designation <sup>B</sup>	Nominal Length of Each Piece, m	Nominal Mass of Each Length, kg
2000	A	127	4.48	5 632	294	RMT 90.45	770	4325
1600	A	127	4.01	4 512	236	RMT 90.45	960	4325
1250	A	91	4.18	3 479	183	RMT 90.45	1185	4130
1120	A	91	3.96	3 123	165	RMT 90.45	1320	4130
1000	A	91	3.74	2 785	151	RMT 90.45	1495	4130
900	AA	61	4.33	2 478	133	RMT 90.45	1785	4425
800	AA, A	61	4.09	2 211	119	RMT 90.45	2000	4425
						RM 68.38	1000	2215
710	AA, A	61	3.85	1 959	105	RMT 90.45	2260	4425
						RM 68.38	1130	2215
630	AA, A	61	3.63	1 742	96.6	RMT 90.45	2540	4425
						RM 68.38	1270	2215
560	AA, A	61	3.42	1 546	85.7	RMT 90.45	2860	4425
						RM 68.38	1430	2215
500	AA	37	4.15	1 381	75.1	RMT 84.45	2430	3355
						RM 66.32	1215	1680
						NR 48.28	610	840
500	A	61	3.23	1 379	76.5	RMT 90.45	3210	4425
						RM 68.38	1605	2215
450	AA	37	3.94	1 245	67.7	RMT 84.45	2695	3355
						RM 66.32	1350	1680
						NR 48.28	675	840
450	A	61	3.06	1 238	68.6	RMT 90.45	3575	4425
						RM 68.38	1790	2215
400	AA	37	3.71	1 104	61.9	RMT 84.45	3040	3355
						RM 66.32	1520	1680
						NR 48.28	760	840
400	A	61	2.89	1 104	63.0	RMT 90.45	4010	4425
						RM 68.38	2005	2215
355	AA	37	3.50	982	55.1	RMT 84.45	3415	3355
						RM 66.32	1710	1680
						NR 48.28	855	840
355	A	61	2.72	978	57.4	RMT 90.45	4525	4425
						RM 68.38	2265	2215
315	AA, A	37	3.29	868	48.7	RMT 84.45	3865	3355
						RM 66.32	1935	1680
						NR 48.28	970	840
280	AA	19	4.33	772	42.9	RM 66.32	2235	1725
						NR 48.28	1115	860
						NR 42.28	745	575
280	A	37	3.10	771	43.2	RMT 84.45	4350	3355
						RM 66.32	2180	1680
						NR 48.28	1090	840
250	AA	19	4.09	689	38.3	RM 66.32	2505	1725
						NR 48.28	1250	860
						NR 42.28	835	575
250	A	37	2.93	688	39.7	RMT 84.45	875	3355
						RM 66.32	2440	1680
						NR 48.28	1220	840
224	AA	19	3.87	617	34.3	RM 66.32	2795	1725
						NR 48.28	1395	860
						NR 42.28	930	575
200	AA, A	19	3.66	552	31.6	RM 66.32	3125	1725
						NR 48.28	1560	860
						NR 42.28	1040	575
180	A	19	3.47	496	28.4	RM 66.32	3480	1725
						NR 48.28	1730	860
						NR 42.28	1160	575
160	A	19	3.27	440	25.2	RM 66.32	3920	1725
						NR 48.28	1955	860
						NR 42.28	1305	575
140	AA	7	5.05	387.0	22.2	NR 42.28	1640	635
						NR 36.22	830	320
140	A	19	3.06	386	22.1	RM 66.32	4470	1725
						NR 48.28	2230	860
						NR 42.28	1490	575
125	AA	7	4.77	345	19.8	NR 42.28	1840	635
						NR 36.22	930	320

**TABLE 3 Construction Requirements of Aluminum Conductors, Concentric-Lay-Stranded, Class B, C, and D**

Conductor Size		Hard-Drawn Copper Equivalent		Stranding						Reverse Concentric Compressed Class B Diameter, in.	Unilay Compressed Class B Diameter, in.	Direct Current Resistance at 20°C	
cmils <sup>A</sup>	AWG	cmils <sup>A</sup>	AWG	Class B		Class C		Class D				Ω/1000 ft	Ω/km
				Number of Wires	Diameter of Wire, mils <sup>B</sup>	Number of Wires	Diameter of Wire, mils <sup>A</sup>	Number of Wires	Diameter of Wire, mils <sup>A</sup>				
4 000 000	...	2 520 000	...	217	135.8	271	121.5	271	121.5	...	...	0.00442	0.0145
3 500 000	...	2 200 000	...	169	143.9	217	127.0	271	113.6	...	...	0.00505	0.0166
3 000 000	...	1 890 000	...	169	133.2	217	117.6	271	105.2	...	...	0.00584	0.0192
2 500 000	...	1 570 000	...	127	140.3	169	121.6	217	107.3	...	...	0.00701	0.0229
2 000 000	...	1 260 000	...	127	125.5	169	108.8	217	96.0	1.583	1.533	0.00867	0.0284
1 900 000	...	1 195 000	...	127	122.3	169	106.0	217	93.6	1.542	1.494	0.00913	0.0299
1 800 000	...	1 132 000	...	127	119.1	169	103.2	217	91.1	1.502	1.454	0.00963	0.0316
1 750 000	...	1 101 000	...	127	117.4	169	101.8	217	89.8	1.480	1.434	0.0099	0.0325
1 700 000	...	1 069 000	...	127	115.7	169	100.3	217	88.5	1.459	1.413	0.0102	0.0335
1 600 000 <sup>C</sup>	...	1 006 000	...	127	112.2	169	97.3	217	85.9	1.415	1.371	0.0109	0.0357
1 500 000	...	943 000	...	91	128.4	127	108.7	169	94.2	1.370	1.327	0.0116	0.0380
1 400 000	...	880 000	...	91	124.0	127	105.0	169	91.0	1.323	1.282	0.0124	0.0407
1 300 000	...	818 000	...	91	119.5	127	101.2	169	87.7	1.275	1.236	0.0133	0.0436
1 250 000 <sup>C</sup>	...	786 000	...	91	117.2	127	99.2	169	86.0	1.250	1.212	0.0138	0.0453
1 200 000	...	755 000	...	91	114.8	127	97.2	169	84.3	1.225	1.187	0.0144	0.0472
1 100 000	...	692 000	...	91	109.9	127	93.1	169	80.7	1.173	1.137	0.0158	0.0518
1 000 000 <sup>B</sup>	...	629 000	...	61	128.0	91	104.8	127	88.7	1.117	1.084	0.0173	0.0568
900 000	...	566 000	...	61	121.5	91	99.4	127	84.2	1.060	1.028	0.0193	0.0633
800 000 <sup>C</sup>	...	503 000	...	61	114.5	91	93.8	127	79.4	1.000	0.969	0.0217	0.0712
750 000	...	472 000	...	61	110.9	91	90.8	127	76.8	0.968	0.939	0.0231	0.0758
700 000	...	440 000	...	61	107.1	91	87.7	127	74.2	0.935	0.907	0.0248	0.0814
650 000	...	409 000	...	61	103.2	91	84.5	127	71.5	0.901	0.874	0.0267	0.0876
636 000	...	400 000	...	...	...	...	...	...	...	...	...	...	...
600 000	...	377 000	...	61	99.2	91	81.2	127	68.7	0.866	0.840	0.0289	0.0948
550 000	...	346 000	...	61	95.0	91	77.7	127	65.8	0.829	0.804	0.0315	0.103
500 000	...	314 000	...	37	116.2	61	90.5	91	74.1	0.789	0.766	0.0347	0.114
477 000	...	300 000	...	...	...	...	...	...	...	...	...	...	...
450 000	...	283 000	...	37	110.3	61	85.9	91	70.3	0.749	0.727	0.0385	0.126
400 000 <sup>C</sup>	...	252 000	...	37	104.0	61	81.0	91	66.3	0.706	0.685	0.0434	0.142
350 000	...	220 000	...	37	97.3	61	75.7	91	62.0	0.661	0.641	0.0495	0.162
336 400	...	...	0000	...	...	...	...	...	...	...	...	...	...
300 000	...	188 700	...	37	90.0	61	70.1	91	57.4	0.611	0.594	0.0578	0.187
266 800	...	...	000	...	...	...	...	...	...	...	...	...	...
250 000	...	157 200	...	37	82.2	61	64.0	91	52.4	0.558	0.542	0.0694	0.228
211 600	0000	...	00	19	105.5	37	75.6	61	58.9	0.512	0.498	0.0820	0.269
167 800	000	...	0	19	94.0	37	67.3	61	52.4	0.456	0.443	0.103	0.338
133 100	00	...	1	19	83.7	37	60.0	61	46.7	0.405	0.395	0.130	0.427
105 600	0	...	2	19	74.5	37	53.4	61	41.6	0.362	0.352	0.164	0.538
83 690	1	...	3	19	66.4	37	47.6	61	37.0	0.322	0.313	0.207	0.679
66 360	2	...	4	7	97.4	19	59.1	37	42.4	0.283	...	0.261	0.856
52 620	3	...	5	7	86.7	19	52.6	37	37.7	0.252	...	0.330	1.08
41 740	4	...	6	7	77.2	19	46.9	37	33.6	0.225	...	0.416	1.36
33 090	5	...	7	7	68.8	19	41.7	37	29.9	0.200	...	0.523	1.72
26 240	6	...	8	7	61.2	19	37.2	37	26.6	0.178	...	0.661	2.17
20 820	7	...	9	7	54.5	19	33.1	37	23.7	0.159	...	0.834	2.74
16 510	8	...	10	7	48.6	19	29.5	37	21.1	0.142	...	1.05	3.44
13 090	9	...	11	7	43.2	19	26.2	37	18.8	0.126	...	1.32	4.33
10 380	10	...	12	7	38.5	19	23.4	37	16.7	0.113	...	1.67	5.48
	11	...	...	...	...	...	...	...	...	0.100	...	2.11	6.92
6 530	12	...	14	7	30.5	19	18.5	37	13.3	0.089	...	2.67	8.76
	13	...	...	...	...	...	...	...	...	0.080	...	3.34	10.96
4 110	14	...	16	7	24.2	19	14.7	37	10.5	0.071	...	4.22	13.8
2 580	16	...	18	7	19.2	19	11.7	...	...	...	...	6.71	22.0
1 620	18	...	20	7	15.2	...	...	...	...	...	...	10.7	35.1
1 020	20	...	22	7	12.1	...	...	...	...	...	...	16.9	55.4

<sup>A</sup> See Footnote B of Table 1.

<sup>B</sup> This size is sensibly equivalent to size 1 033 500 cmils within a difference of 3.24 %.

<sup>C</sup> These sizes are sensibly equivalent to sizes 1 590 000; 1 272 000; 795 000; and 397 500 cmil respectively within the cross-sectional area tolerances stipulated by this specification and associated Specifications B 230/B 230M and B 609/B 609M.

**TABLE 4 Construction Requirements of Conductors Classes B, C, and D**

NOTE 1—Sizes selected from Specification B 682.

Conductor Size, mm <sup>2</sup>	Stranding						Nominal Diameter (mm)		
	Class B		Class C		Class D		Reverse Con- centric Com- pressed Class B	Unilay Com- pressed Class B	Direct Current Resistance Ω/km
	Number of Wires <sup>A</sup>	Diameter, mm	Number of Wires <sup>A</sup>	Diameter, mm	Number of Wires <sup>A</sup>	Diameter, mm			
2000	217	3.43	271	3.07	271	3.07	56.56	54.74	0.01437
1800	169	3.68	217	3.25	271	2.91	53.54	51.93	0.01596
1600	169	3.47	217	3.06	271	2.74	50.49	48.96	0.01796
1400	169	3.25	217	2.87	271	2.56	47.29	45.79	0.02053
1250	127	3.54	169	3.07	217	2.71	44.64	43.27	0.02299
1200 <sup>B</sup>	127	3.47	169	3.01	217	2.65	43.76	42.40	0.02395
1120	127	3.35	169	2.90	217	2.56	42.24	40.96	0.02566
1000	127	3.17	169	2.74	217	2.42	39.97	38.70	0.02874
900	127	3.00	169	2.60	217	2.30	37.83	36.72	0.03193
800	91	3.35	127	2.83	169	2.46	35.74	34.62	0.03592
710	91	3.15	127	2.67	169	2.31	33.61	32.61	0.04047
630	91	2.97	127	2.51	169	2.18	31.69	29.98	0.04561
560	91	2.80	127	2.37	169	2.05	29.88	28.96	0.05131
500	61	3.23	91	2.64	127	2.24	28.20	27.37	0.05747
450	61	3.06	91	2.51	127	2.12	26.71	25.96	0.06386
400	61	2.89	91	2.37	127	2.00	25.23	24.48	0.07184
355	61	2.72	91	2.23	127	1.89	23.75	23.06	0.08094
315	61	2.56	91	2.10	127	1.78	22.35	21.72	0.09122
300 <sup>B</sup>	61	2.50	91	2.05	127	1.73	21.83	21.20	0.09578
280	61	2.42	91	1.98	127	1.68	21.13	20.48	0.10263
250	37	2.93	61	2.28	91	1.87	19.89	19.35	0.11494
240 <sup>B</sup>	37	2.87	61	2.24	91	1.83	19.49	18.96	0.11973
224	37	2.78	61	2.16	91	1.77	18.88	18.32	0.12828
200	37	2.62	61	2.04	91	1.67	17.79	17.31	0.14368
185 <sup>B</sup>	37	2.52	61	1.97	91	1.61	17.11	16.65	0.15532
180	37	2.49	61	1.94	91	1.59	16.90	16.42	0.15964
160	37	2.35	61	1.83	91	1.50	15.96	15.48	0.17959
150 <sup>B</sup>	37	2.27	61	1.77	91	1.45	15.41	14.99	0.19157
140	37	2.19	61	1.71	91	1.40	14.87	14.48	0.20525
125	37	2.07	61	1.62	91	1.32	14.06	13.68	0.22988
120 <sup>B</sup>	37	2.03	61	1.58	91	1.30	13.78	13.41	0.23946
100	19	2.59	37	1.86	61	1.44	12.56	12.24	0.28735
95.0 <sup>B</sup>	19	2.52	37	1.81	61	1.41	12.22	11.93	0.30247
80.0	19	2.32	37	1.66	61	1.29	11.25	10.95	0.35919
70.0 <sup>B</sup>	19	2.17	37	1.55	61	1.21	10.52	10.24	0.4105
63.0	19	2.05	37	1.47	61	1.15	9.94	9.71	0.45611
50.0	19	1.83	37	1.31	61	1.02	8.88	8.65	0.5747
40.0	19	1.64	37	1.17	61	0.914	7.95	7.74	0.71838
35.0 <sup>B</sup>	7	2.52	19	1.53	37	1.10	7.33	...	0.821
31.5	7	2.39	19	1.45	37	1.04	6.95	...	0.91222
25.0	7	2.13	19	1.29	37	0.928	6.20	...	1.1494
20.0	7	1.91	19	1.16	37	0.830	5.56	...	1.4368
16.0	7	1.71	19	1.04	37	0.742	4.98	...	1.7959
12.5	7	1.51	19	0.915	37	0.656	4.39	...	2.2988
10.0	7	1.35	19	0.819	37	0.587	3.93	...	2.8735
8.00	7	1.21	19	0.732	37	0.525	3.52	...	3.5919
6.30	7	1.07	19	0.650	37	0.466	3.11	...	4.5611
6.00 <sup>B</sup>	7	1.04	19	0.634	37	0.454	3.03	...	4.7892
5.00	7	0.954	19	0.579	37	0.415	2.78	...	5.747
4.00	7	0.853	19	0.518	37	0.371	2.48	...	7.1838
3.15	7	0.757	19	0.459	37	0.329	2.20	...	9.1222
2.50	7	0.674	19	0.409	37	0.293	1.96	...	11.494
2.00	7	0.603	19	0.366	37	0.262	1.75	...	14.368
1.50 <sup>B</sup>	7	0.522	19	0.317	37	0.227	1.52	...	19.157
1.00	7	0.426	19	0.259	...	...	1.24	...	28.735
0.800	7	0.381	...	...	...	...	1.11	...	35.919
0.750 <sup>B</sup>	7	0.369	...	...	...	...	1.07	...	38.313
0.500	7	0.302	...	...	...	...	0.88	...	57.47

<sup>A</sup> For unidirectional/unilay stranded conductors, the number of wires shown are a minimum.

<sup>B</sup> Additional sizes shown as third preference sizes in Specification B 682.



**TABLE 5 Minimum Distance Between Joints in the Completed Conductor**

Number of Wires in Conductor <sup>A</sup>	Distance Between Joints, min ft [m]					
	Class AA		Class A		Classes B, C, and D	
	ft	[m]	ft	[m]	ft	[m]
7	50 <sup>B</sup>	[15] <sup>B</sup>	50 <sup>C</sup>	[15] <sup>C</sup>	1	[0.3]
12	50	[15]	50	[15]	1	[0.3]
19	50	[15]	50	[15]	1	[0.3]
37	25	[7.5]	25	[7.5]	1 <sup>D</sup>	[0.3] <sup>D</sup>
61 and over	25	[7.5]	5	[1.5]	1 <sup>D</sup>	[0.3] <sup>D</sup>

<sup>A</sup> Conductors of an intermediate number of wires shall conform to those having the next smaller number.

<sup>B</sup> Only cold-pressure welds and electric-butt, cold-upset welds are permitted in the six outer wires of conductors composed of seven wires; no welds are permitted in the center or core wire.

<sup>C</sup> For bare overhead conductors only cold-pressure welds and electric-butt, cold-upset welds are permitted in the six outer wires, no welds are permitted in the center or core wire. For other uses, electric-butt welds, cold-pressure welds, and electric-butt, cold-upset welds may be used in any wire.

<sup>D</sup> In a layer.

7.5 The direction of lay for conductors having a nominal cross-sectional area larger than No. 8 AWG (8 mm<sup>2</sup>) shall be reversed in successive layers, unless otherwise specified by the purchaser.

7.5.1 For conductors to be used in covered or insulated wires or cables, the direction of lay of the outer layer shall be left hand and may be reversed or unidirectional/unilay in successive layers, unless otherwise agreed upon with the purchaser.

**8. Construction**

8.1 The areas of cross section, numbers, and diameters of wires in the various classes of concentric-lay-stranded conductors shall conform to the requirements prescribed in Tables 1-4.

8.2 The diameters of the wires listed in Tables 3 and 4 are nominal. Where “combination strand” is required in order to insulate the conductor properly (strands in the outer layer having a larger diameter than those in the inner layers) the diameters shall be subject to a tolerance of ±5 % provided that the area of cross section after stranding is in accordance with Section 12.

8.3 Where compressed stranding is required in order to insulate the conductor properly, one or more layers of any stranded conductor consisting of 7 wires or more may be slightly compressed, thereby reducing the outside diameter of the conductor to the nominal values shown in Table 3 or Table 4, provided that the area of cross section after compressing is in accordance with Section 12.

8.3.1 The average diameter of the conductor in 8.3 shall vary by not more than +1 or –2 % from the diameter specified in Table 3 or Table 4.

**9. Rated Strength of Conductor**

9.1 The rated strength of 1350-H19 conductors shall be taken as the percent, indicated in Table 6, of the sum of the strengths of the component wires, calculated using the nominal wire diameters and the specified minimum average tensile strength given in Specification B 230/B 230M for 1350-H19 wire. In the case of compressed conductors, the nominal wire

**TABLE 6 Rating Factors**

Stranding		Rating Factor, %
Number of Wires in Conductor	Number of Layers	
7	1	96
19	2	93
37	3	91
61	4	90
91 and above	5 and above	89

diameter should be that of the corresponding non-compressed construction as listed in Tables 1-4.

9.2 Calculations for rated strengths of 1350-H16, -H26, -H14, -H24, -H142, and -H242 conductors shall be made on the basis of the strengths of the component wires using the nominal wire diameters and the specified maximum and minimum tensile strengths for the appropriate temper of the respective component wires given in Specification B 609/B 609M. The minimum rated strengths of the conductors shall be taken as the sum of the calculated minimum strengths of the component wires multiplied by the rating factor given in Table 6. The maximum rated strength of the conductors shall be taken as the sum of the calculated maximum strengths of the component wires.

9.3 Rated-strength and breaking-strength values shall be rounded to three significant figures, in the final value only, in accordance with the rounding method of Practice E 29.

9.4 Rated strengths of conductors are given in Table 1 or Table 2.

**10. Density**

10.1 For the purpose of calculating mass, cross sections, etc., the density of aluminum 1350 shall be taken as 2705 kg/m<sup>3</sup> [0.0975 lb/in.<sup>3</sup>] at 20°C.

**11. Mass and Electrical Resistance**

11.1 The mass and electrical resistance of a unit length of a stranded conductor are a function of the length of lay. The approximate mass and electrical resistance may be determined using the standard increments shown in Table 7. When greater accuracy is desired, the increment based on the specific lay of the conductor may be calculated (Explanatory Note 5).

11.2 The maximum electrical resistance of a unit length of stranded conductor shall not exceed 2 % over the nominal d-c resistance shown in Tables 3 and 4 (Explanatory Note 8). When the d-c resistance is measured at other than 20°C, it is to be corrected by using the multiplying factor given in Table 8.

**TABLE 7 Standard Increments Due to Stranding**

Size of Conductor, All Classes, cmils [mm <sup>2</sup> ]	Increment (Increase) of Mass and Electrical Resistance, %
4 000 000 to 3 000 001, incl [2000–1500, incl]	4
3 000 000 to 2 000 001, incl [Under 1500–1000, incl]	3
2 000 000 and under [Under 1000]	2

**TABLE 8 Temperature Correction Factors for Conductor Resistance**

Temperature °C	Multiplying Factor for Conversion to 20°C
0	1.088
5	1.064
10	1.042
15	1.020
20	1.000
25	0.980
30	0.961
35	0.943
40	0.925
45	0.908
50	0.892
55	0.876
60	0.861
65	0.846
70	0.832
75	0.818
80	0.805
85	0.792
90	0.780

11.3 For conductors to be used in covered or insulated wires or cables d-c resistance measurement may be used in lieu of the method outlined in Section 12, to determine compliance with this specification; however, the referee method shall be that outlined in Section 12.

## 12. Variation in Area

12.1 The area of cross section of the completed conductor shall not be less than 98 % of the area of cross section of the conductor size listed in Column 1 of Tables 1-4. The manufacturer may have the option of determining the cross-sectional area by either of the following methods, except that in case of question regarding area compliance, the method of 12.1.2 shall be used.

12.1.1 The area of cross section of a conductor may be determined by calculations from diameter measurements, expressed to four decimal places, of its component wires at any point when measured perpendicularly to their axes.

12.1.2 The area of cross section of a conductor may be determined by Test Method B 263. In applying that test method, the increment in mass resulting from stranding may be

the applicable value specified in 11.1 or may be calculated from the measured component dimensions of the sample under test. In case of question regarding area compliance, the actual mass increment due to stranding shall be calculated.

## 13. Finish

13.1 The conductor shall be free of all imperfections not consistent with good commercial practice.

## 14. Mechanical and Electrical Tests of Conductors NOT Annealed After Stranding

14.1 Wires composing the conductors shall be tested prior to stranding in accordance with the applicable specification (see 5.2), and tests on the completed conductor are not required. However, when requested by the purchaser and agreed to by the manufacturer at time of ordering, the tension tests of wires before stranding may be waived and the completed conductor tested in accordance with 14.2, or wires removed from the completed conductor tested in accordance with 14.3.

14.2 When the completed conductor is tested as a unit, the breaking strength shall be not less than the rated strength of 1350-H19 conductors or the minimum rated strength of 1350-H16, -H26, -H14, -H24, -H142, and -H242 conductors if failure occurs in the free length at least 1 in. [25 mm] beyond the end of either gripping device, or shall be not less than 95 % of the rated or minimum rated strength if failure occurs inside, or within 1 in. [25 mm] of the end of either gripping device. The breaking strength of 1350-H16, -H26, -H14, -H24, -H142, and -H242 conductors shall be not greater than their maximum rated strengths. The free length between grips of the test specimen shall be not less than 24 in. [600 mm] and care shall be taken to ensure that the wires in the conductor are evenly gripped during the test (Explanatory Note 6).

14.3 Routine production testing of the aluminum wires after stranding is not required. However, when such tests are requested by the purchaser and agreed upon by the manufacturer at the time of ordering (or made for other reasons), the 1350-H19 wires removed from the completed conductor shall have tensile strengths of not less than 95 % of the minimum tensile strength specified for the individual tests in Specification B 230/B 230M. The 1350-H16, -H26, -H14, -H24, -H142,

**TABLE 9 Dimensions of Standard Reels (For Information Only)**

Reel Designation <sup>A,B,C</sup>	Reel Capacity, in. <sup>3</sup> [m <sup>3</sup> ]	Nominal Reel Dimensions				
		Flange Diameter, in. [m]	Drum Diameter, in. [m]	Width, in. [m]		Arbor Hole Diameter, in. [mm]
				Inside	Outside	
NR 36.22	16 800 [0.275]	36 [0.91]	18 [0.46]	22 [0.56]	25 [0.64]	3 to 3/4 [76–83]
NR 42.28	29 100 [0.477]	42 [1.07]	21 [0.53]	28 [0.71]	32½ [0.83]	3 to 3/4 [76–83]
NR 48.28	38 000 [0.623]	48 [1.22]	24 [0.61]	28 [0.71]	32½ [0.83]	3 to 3/4 [76–83]
RM 66.32 <sup>D</sup>	76 900 [1.260]	66 [1.68]	36 [0.91]	32 [0.81]	38 [0.97]	3 to 3/4 [76–83]
RM 68.38 <sup>D</sup>	99 300 [1.627]	68 [1.73]	36 [0.91]	38 [0.97]	44 [1.12]	3 to 3/4 [76–83]
RMT 84.45 <sup>E</sup>	152 700 [2.502]	78 (84) [1.98 (2.13)]	42 [1.07]	45 [1.14]	52 [1.32]	5 to 5/4 [127–133]
RMT 90.45 <sup>E</sup>	187 000 [3.064]	84 (90) [2.13 (2.29)]	42 [1.07]	45 [1.14]	52 [1.32]	5 to 5/4 [127–133]

<sup>A</sup> Prefix "NR" denotes wooden nonreturnable reel, "RM" metal returnable reel, and "RMT" metal returnable reel with I-beam tires.

<sup>B</sup> Pay-off equipment for reels NR 48.28 and smaller should be a minimum of 2 in. [50 mm] wider than the nominal outside reel width to provide for extension of bolts and for possible flange distortion. For reels 66.32 and larger, either wood or metal, pay-off equipment should not be less than 4 in. [100 mm] wider than the reel width.

<sup>C</sup> Reels are not designed to withstand the forces required for braking during tension stringing operations.

<sup>D</sup> Reels RM 66.32 and RM 68.38 have flat rims.

<sup>E</sup> Reels RMT 84.45 and RMT 90.45 have 3-in. [76-mm] I-beam tires. Indicated flange diameters are diameters under the tire; values in parentheses are diameters over the tire. Reels with similar dimensions except without I-beam tires are sometimes used.

and -H242 wires shall have tensile strengths not less than 95 % of the minimum tensile strengths nor more than 105 % of the maximum tensile strengths prescribed in Specification B 609/B 609M. The electrical resistivity shall meet the minimum resistivity specified for the wire before stranding. Elongation tests may be made for information purposes only and no minimum values are assigned (Explanatory Note 7). The frequency of these tests shall be decided upon between the purchaser and the manufacturer.

14.4 All wires composing the conductors shall be capable of meeting the bending properties stated in Specification B 230/B 230M after stranding.

## **15. Mechanical and Electrical Tests of Conductors ANNEALED After Stranding**

15.1 Tensile properties and electrical resistivity shall be determined on samples taken from 10 % of the reels or coils of conductor, but from not less than five (or all if the lot is less than five) reels or coils. Resistivity shall be determined as prescribed in Section 7 of Specification B 230/B 230M on one wire from each conductor sample except this test is not required if performed previously on the 1350-H19 wire. At the manufacturer's option, tension tests shall be made either on one of the inner 7 wires and one wire from each additional layer of each conductor sample to determine conformance with 15.2 or on the conductor as a unit to determine conformance with 15.3.

15.2 When wires removed from the completed conductor are tested, 1350-H26, -H24, and -H242 wires shall have tensile strengths not less than 95 % of the minimum tensile strength nor more than 105 % of the maximum tensile strength prescribed in Specification B 609/B 609M, as applicable (Explanatory Note 7).

15.3 When the completed conductor is tested as a unit, the breaking strengths of 1350-H26, -H24, and -H242 conductors shall conform with 9.2 through 9.4.

15.4 All wires composing the conductors shall be capable of meeting the bending properties stated in Specification B 230/B 230M after stranding. Routine production testing after stranding is not required unless requested by the purchaser and agreed upon by the manufacturer at the time of ordering.

## **16. Retests**

16.1 If upon testing a sample from any reel or coil of conductor the results do not conform to the requirements of Sections 8 and 9, two additional samples shall be tested, and the average of the three tests shall determine the acceptance of the reel or coil.

## **17. Inspection**

17.1 Unless otherwise specified in the contract or purchase order, the manufacturer shall be responsible for the performance of all inspection and test requirements specified.

17.2 All inspections and tests shall be made at the place of manufacture unless otherwise especially agreed to between the manufacturer and the purchaser at the time of the purchase.

17.3 The manufacturer shall afford the inspector representing the purchaser all reasonable access to the manufacturer's facilities to satisfy him that the material is being furnished in accordance with this specification.

## **18. Packaging and Package Marking**

18.1 Package sizes and kind of package, reels or coils, shall be agreed upon by the manufacturer and the purchaser at the time of placing the order. Recommended package sizes for Classes AA and A are shown in Table 1 or Table 2.

18.2 There shall be only one length of conductor on a reel when the conductor on the reel will not undergo further manufacturing processes.

18.3 The conductor shall be protected against damage in ordinary handling and shipping. If heavy wood lagging is required, it shall be specified by the purchaser at the time of placing the order.

18.4 The net mass, length (and number of lengths if more than one is included in a package), size, kind of conductor, stranding, and any other necessary identification shall be marked on a tag attached to the end of the conductor inside the package. This same information, together with the purchase order number, the manufacturer's serial number (if any), and all shipping marks and other information required by the purchaser shall appear on the outside of each package.

NOTE 4—Multiple lengths per package are allowable only when the bare conductor is intended for remanufacture, such as adding a covering or insulation. In such cases the position of each end of a length is to be clearly marked and the length of each portion shall be shown on the tag attached to the end of the conductor.

## **19. Marking**

19.1 The net mass, length (and number of lengths, if more than one length is included in a package), size and kind of conductor, shall be marked on a tag attached to the end of each conductor inside the package. The same information, together with the manufacturer's serial number (if any) and all shipping marks and other information required by the purchaser shall appear on the outside of each package.

## **20. Keywords**

20.1 aluminum conductor; concentric-lay-stranded aluminum conductor; electrical conductors; electrical conductors, aluminum; stranded aluminum conductors

**EXPLANATORY NOTES**

NOTE 1—In this specification only concentric-lay-stranded conductor constructions manufactured from round aluminum 1350 wires are specifically designated.

NOTE 2—For definitions of terms relating to conductors, refer to Terminology B 354.

NOTE 3—The behavior of properly spaced wire joints in stranded conductors is related to both their tensile strength and elongation. Because of its higher elongation properties, the lower strength electric-butt weld gives equivalent overall performance to that of a cold-pressure weld or an electric-butt, cold-upset weld in stranded conductors with more than seven wires.

NOTE 4—Certain types of insulated conductors may require a shorter lay than other conductors. Special requirements regarding length of lay should be specified by the purchaser in such instances.

NOTE 5—The increment of mass or electrical resistance of a completed concentric-lay-stranded conductor,  $k$ , in percent is:

$$k = 100(m - 1)$$

where  $m$  is the stranding factor, and is also the ratio of the mass or electrical resistance of a unit length of stranded conductor to that of a solid conductor of the same cross-sectional area or of a stranded conductor with infinite length of stranding, that is, all wires parallel to the conductor axis. The stranding factor  $m$  for the completed stranded conductor is the numerical average of the stranding factors for each of the individual wires in the conductor, including the straight core wire, if any (for which the stranding factor is unity). The stranding factor (mind) for any given wire in a concentric-lay-stranded conductor is:

$$m_{ind} = \sqrt{1 + (9.8696/n^2)}$$

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).*

where  $n$  = length of lay/diameter of helical path of the wire. The derivation of the above is given in *NBS Handbook 100*.

NOTE 6—To test stranded conductors for breaking strength successfully as a unit requires an adequate means of gripping the ends of the test specimen without causing damage that may result in failure below the actual strength of the conductor. Various means are available such as compression sleeves, split sleeves, and preformed grips, but ordinary jaws or clamping devices usually are not suitable.

NOTE 7—Wires unlaidd from conductors may have different physical properties from those of the wire prior to stranding because of the deformation brought about by stranding and straightening for test.

NOTE 8—The d-c resistance on a given construction shall be calculated using the following formula:

Inch-Pound Units:

$$R = \left( \frac{k}{100} + 1 \right) \frac{\rho}{A}$$

or Metric Units:

$$R \left[ \left( \frac{K}{100} + 1 \right) \frac{\rho}{A} \right] 1000$$

where:

- $R$  = conductor resistance in  $\Omega/1000$  ft ( $\Omega/\text{km}$ ),
- $k$  = increment due to stranding from Table 7 and Explanatory Note 5,
- $\rho$  = volume resistivity in ohms-cmil/ft ( $\Omega\text{-mm}^2/\text{m}$ ), determined in accordance with Test Method B 193, and
- $A$  = cross-sectional area of conductor in kcmil ( $\text{mm}^2$ ) determined in accordance with Section 12 of this specification.