



Designation: B 778 – 97

Standard Specification for Shaped Wire Compact Concentric-Lay-Stranded Aluminum Conductors (AAC/TW)¹

This standard is issued under the fixed designation B 778; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers shaped wire compact concentric-lay-stranded aluminum conductor (AAC/TW) and its component wires for use as overhead electrical conductors (Explanatory Note 1 and Note 2).

1.2 The values stated in inch-pound units are to be regarded as the standard with the exception of temperature and resistivity. The SI equivalents of inch-pound units may be approximate.

NOTE 1—AAC/TW is designed to increase the aluminum area for a given diameter of conductor by the use of trapezoidally shaped wires (TW). The conductors consist of a central core of one round aluminum wire or a seven-strand compact round core surrounded by two or more layers of trapezoidal aluminum 1350-H19 wires. For the purposes of this specification, the sizes listed are tabulated on the basis of the finished conductor having an area equal to that of specific sizes of standard AAC (Table 1) or in fixed diameter increments (Table 2) so as to facilitate conductor selection.

NOTE 2—The aluminum and temper designations conform to ANSI Standard H 35.1. Aluminum 1350 corresponds to Unified Numbering System (UNS) A91350 in accordance with Practice E 527.

2. Referenced Documents

2.1 The following documents of the issue in effect on date of material purchase form a part of this specification to the extent referenced herein.

2.2 ASTM Standards:

- B 230 Specification for Aluminum 1350-H19 Wire for Electrical Purposes²
- B 263 Test Method for Determination of Cross-Sectional Area of Stranded Conductors²
- B 354 Terminology Relating to Uninsulated Metallic Electrical Conductors²
- E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications³
- E 527 Practice for Numbering Metals and Alloys (UNS)⁴

2.3 Other Documents:

¹ This specification is under the jurisdiction of ASTM Committee B-1 on Electrical Conductors and is the direct responsibility of Subcommittee B 01.07 on Conductors of Light Metals.

Current edition approved Oct. 10, 1997. Published December 1997. Originally published as B 778 – 87. Last previous edition B 778 – 92.

² Annual Book of ASTM Standards, Vol 02.03.

³ Annual Book of ASTM Standards, Vol 14.02.

⁴ Annual Book of ASTM Standards, Vol 01.01.

TABLE 1 Construction Requirements for Shaped Wire Compact Concentric-Lay-Stranded Aluminum Conductors Sized to Have Areas Equal to AAC Size

AAC/TW Conductor Size, kcmil	Nominal Outside Diameter, in. ^A	Number of Aluminum Wires	Number of Layers	Nominal Mass, lb/1000 ft	Rated Strength, 1000 lbf
336.4	0.612	17	2	315.3	6.02
397.5	0.661	17	2	372.6	6.96
477.0	0.720	17	2	447.1	8.36
500.0	0.736	17	2	468.7	8.76
556.5	0.775	17	2	521.6	9.75
600.0	0.803	17	2	562.4	10.52
636.0	0.825	17	2	596.1	11.1
700.0	0.864	17	2	656.1	12.3
750.0	0.893	17	2	702.1	13.1
795.0	0.919	17	2	745.1	13.6
900.0	0.990	31	3	843.6	15.4
954.0	1.018	31	3	894.2	16.4
1000.0	1.041	31	3	937.3	17.1
1033.5	1.057	31	3	968.7	17.7
1113.0	1.095	31	3	1043.2	19.1
1192.5	1.132	31	3	1117.7	20.4
1272.0	1.168	31	3	1192.2	21.8
1351.5	1.202	31	3	1266.3	23.2
1431.0	1.236	31	3	1341.3	24.0
1590.0	1.315	49	4	1490.3	27.0
1750.0	1.377	49	4	1640.3	29.7
2000.0	1.468	49	4	1893.0	33.9
2500.0	1.648	71	5	2366.2	41.9
3000.0	1.799	71	5	2839.5	50.3

^A 1 in. = 25.4 mm.

ANSI H35.1 American National Standard Alloy and Temper Designation Systems for Aluminum⁵
 NBS Handbook 100—Copper Wire Tables⁶

3. Ordering Information

3.1 Orders for material under this specification shall include the following information:

- 3.1.1 Quantity of each size,
- 3.1.2 Conductor size: kcmil area and diameter (Table 1 and Table 2),
- 3.1.3 Special tension test, if required (see 8.2),
- 3.1.4 Place of inspection (Section 15),
- 3.1.5 Package size and type (see 15.1),

⁵ Available from American National Standards Institute, 11 West 42nd Street, 13th Floor, New York, NY 10036.

⁶ Available from National Institute of Standards and Technology (NIST), Gaithersburg, MD 20899.

TABLE 2 Construction Requirements for Shaped Wire Compact Concentric-Lay-Stranded Aluminum Conductors, in Fixed-Diameter Increments

AAC/TW Conductor Size, kcmil	Nominal Outside Diameter, in.	Number of Aluminum Wires	Number of Layers	Nominal Mass, lb/1000 ft	Rated Strength, 1000 lbf
322.5	0.60	17	2	302.3	5.88
384.5	0.65	17	2	360.4	6.74
449.4	0.70	17	2	421.2	7.88
521.7	0.75	17	2	489.0	9.14
595.8	0.80	17	2	558.4	10.44
678.2	0.85	17	2	635.7	11.88
761.5	0.90	17	2	713.7	13.07
854.2	0.95	17	2	800.6	14.86
918.8	1.00	31	3	861.2	15.76
1020.0	1.05	31	3	956.0	17.50
1123.1	1.10	31	3	1052.7	19.26
1234.2	1.15	31	3	1156.8	21.17
1346.8	1.20	31	3	1262.3	23.10
1467.9	1.25	31	3	1375.9	24.65
1583.2	1.30	34	3	1483.9	26.59
1682.7	1.35	49	4	1577.5	28.55
1812.7	1.40	49	4	1699.0	30.74
1954.3	1.45	49	4	1832.1	33.16
2093.6	1.50	49	4	1981.6	35.51
2245.4	1.55	49	4	2125.7	37.30
2388.1	1.60	52	4	2260.3	39.67
2514.8	1.65	71	5	2379.5	42.17
2667.2	1.70	71	5	2524.5	44.74
2844.5	1.75	71	5	2692.2	47.70
3006.2	1.80	71	5	2873.0	50.43

3.1.6 Special package markings, if required (Section 15), and

3.1.7 Heavy wood lagging, if required (see 15.3).

4. Requirement for Wires

4.1 Before stranding, the trapezoidal aluminum wires shall conform to the requirements of Specification B 230 except for shape and diameter tolerance. The tensile strength and elongation requirements of trapezoidal wires shall be the same as for round wires of equal area. The area tolerances shall be such that the finished conductor conforms to Section 11.

5. Joints

5.1 Electric-butt welds, electric-butt cold-upset welds, or cold-pressure welds may be made in the individual aluminum wires during the stranding process. No weld shall occur within 50 ft (15 m) of any other weld in the completed conductor (Explanatory Note 3).

6. Lay

6.1 The preferred lay of the outside layer of aluminum wires of shaped wire aluminum conductors, having multiple layers of aluminum wires is 11 times the outside diameter of the conductor but the lay shall not be less than 10 nor more than 14 times that diameter (Explanatory Note 1).

6.2 The preferred lay of the layer immediately beneath the outside layer of aluminum wires is 13 times the outside diameter of such layer but the lay shall be not less than 10 nor more than 16 times that diameter.

6.3 The lay of the inner layers of aluminum wires shall be not less than 10 nor more than 17 times the outside diameter of such layer.

6.4 The direction of lay of the outside layer of aluminum wires shall be right-hand.

6.5 The direction of lay of the aluminum wires shall be reversed in successive layers.

6.6 For the purpose of this specification the lay factor is the length of lay of a given layer divided by its outside diameter.

7. Construction

7.1 The nominal aluminum cross-sectional area, the outside diameter, the nominal number of aluminum wires, the number of layers, the linear density, and the rated strength, of the shaped wire compact concentric-lay-stranded aluminum conductors, shall be as shown in Table 1 and Table 2.

NOTE 3—Exception to 7.1. Because the final design of a shaped wire compact conductor is contingent on several factors such as layer diameter, wire width and thickness, and the like, the actual configuration of a given size may vary between manufacturers. This might result in a slight variation in the number of wires and number of layers, from that shown in Table 1 and Table 2, and also in the dimensions of the individual wires.

8. Rated Strength of Conductor

8.1 The rated strength of a conductor, as shown in Table 1 and Table 2, shall be taken as the percentage, indicated in Table 3, in accordance with the number of aluminum layers, of the sum of the wire strengths calculated from the specified diameter of the round wires having the same area as the trapezoidal wires used in the manufacture of the conductor, and the appropriate minimum average tensile strength given in Specification B 230.

8.1.1 The rated strengths of conductors calculated in accordance with 8.1 and 8.3 are listed in Table 1 and Table 2.

8.2 Tests to confirm that the rated strength of the conductor is met are not required by this specification, but shall be made if agreed upon between the manufacturer and the purchaser at the time of placing an order. When tested, the breaking strength of the conductor shall be not less than the rated strength if failure occurs in the free length at least 1 in. (25 mm) beyond the end of either gripping device, or shall be not less than 95 % of the rated strength if failure occurs inside or within 1 in. of the end of either gripping device (Explanatory Note 2).

8.3 Rated strength and breaking strength values shall be rounded to three significant figures in the final value only, in accordance with Practice E 29.

9. Density

9.1 For the purpose of calculating mass per unit length, cross-sections, and the like, the density of aluminum 1350 shall be taken as 0.0975 lb/in.³ (2705 kg/m³) at 20°C.

10. Mass and Electrical Resistance

10.1 The mass per unit length and electrical resistance of a unit length of stranded conductor are a function of the length of

TABLE 3 Rating Factors

Number of Layers	Rating Factor, %
2	0.93
3	0.91
4	0.90
5 and above	0.89

lay. The approximate linear density and electrical resistance of a stranded conductor may be determined using the standard increments shown in Table 4. When greater accuracy is desired, the increment based on the actual lay of the conductor may be calculated (Explanatory Note 3).

11. Variations in Area

11.1 The area of cross-section of the aluminum wires of the conductor shall be not less than 98 % nor more than 102 % of the area specified in column 1 of Table 1 and Table 2. The area of each wire shall be determined by Test Method B 263. In applying this method, the increment in linear density resulting from stranding may be the applicable value specified in Table 4, or it may be calculated from the measured dimensions of the sample under test. In case of questions regarding area compliance, the actual linear density increment due to stranding shall be calculated.

11.2 The diameter of the finished conductor shall be not less than 99 % nor more than 101 % of that shown in Table 1 and Table 2 when measured with a diameter tape between the closing dies and the capstan of the strand.

12. Workmanship, Finish, and Appearance

12.1 The conductor shall be clean and free from imperfections not consistent with good commercial practice.

13. Mechanical and Electrical Tests

13.1 Tests for mechanical and electrical properties of aluminum wires shall be made before stranding (Explanatory Note 4).

14. Inspection

14.1 Unless otherwise specified in the contract or purchase order, the manufacturer shall be responsible for the performance of all inspection and test requirements specified.

14.2 All inspections and tests shall be made at the place of manufacture unless otherwise especially agreed upon between the manufacturer and the purchaser at the time of the purchase.

14.3 The manufacturer shall afford the inspector representing the purchaser all reasonable manufacturer's facilities to satisfy him that the material is being furnished in accordance with this specification.

15. Packaging and Package Marking

15.1 Package sizes and kind of package, reels, etc. shall be agreed upon between the manufacturer and the purchaser.

15.2 There shall be only one length of conductor on a reel.

15.3 The conductors shall be protected against damage in ordinary handling and shipping. If heavy wood lagging is required, it shall be specified by the purchaser at the time of placing the order.

15.4 The net mass, length, size, kind of conductor, stranding, and any other necessary identification shall be marked on a tag attached to the conductor inside the package. This same information, together with the purchase order number, the manufacturer's serial number (if any), and all shipping marks and other information required by the purchaser shall appear on the outside of the package.

16. Keywords

16.1 aluminum conductors; compact conductors; compact conductors, aluminum; concentric-lay-stranded aluminum conductors; electrical conductors; electrical conductors, aluminum; shaped wire compact conductors; shaped wire compact conductors, aluminum; shaped wire conductors; shaped wire conductors, aluminum

EXPLANATORY NOTES

NOTE 1—In this specification only shaped wire compact concentric-lay-stranded aluminum conductors are specifically designated. Conductor constructions not included in this specification should be agreed upon between the manufacturer and the purchaser when placing the order.

NOTE 2—For definitions of terms relating to conductors, refer to Terminology B 354.

NOTE 3—The behavior of properly spaced joints in aluminum wires in stranded conductors is related to both their tensile strength and elongation. Because of its higher elongation properties, the lower-strength electric-butt weld gives equivalent overall performance to that of a cold-pressure weld or an electric-butt, cold-upset weld in stranded conductors.

NOTE 4—The lay factor with respect to the outside diameter of a layer of wires varies for different layers and for different diameters of conductor, being larger for the inside layers than for the outside layer.

NOTE 5—To obtain the actual breaking strength of AAC/TW tested as a unit requires special devices for gripping the ends of the aluminum wires without causing damage thereto and resultant failure below the actual strength of the conductor. Various special dead-end devices are available for this purpose, such as compression sleeves. Ordinary jaws or clamping devices usually are not suitable.

NOTE 6—The increment of mass or electrical resistance of a completed concentric-lay-stranded conductor, k , in percent is given by the following equation:

$$k = 100(m - 1)$$

where m is the stranding factor, and is also the ratio of the mass or electrical resistance of a unit length of stranded conductor to that of a solid conductor of the same cross-sectional area or of a stranded conductor with infinite length of stranding, that is, all wires parallel to the conductor axis. The stranding factor (m) for the completed stranded conductor is the numerical average of the stranding factors for each of the individual wires in the conductor, including the straight core wire, if any (for which the stranding factor is unity). The stranding factor (m_{ind}) for any given wire in a concentric-lay-stranded conductor is:

$$m_{ind} = \sqrt{1 + (9.8696/n^2)}$$

where n = length of lay/diameter of helical path of the wire. This is assumed to be $ID + t$ for a given layer where t equals the thickness of the layer. To be more precise, for trapezoidal wire, this diameter should be that of the centroid (the center of mass of the wire) which is on a diameter slightly larger than the average layer diameter used in the above formula. Using the average layer diameter for the helical path of the wire introduces a small error which is considered to be negligible and may be ignored. The derivation of the above is given in the *NBS Handbook 100*.⁶

NOTE 7—Wires unlaidd from conductors may have different physical properties from those of the wire before stranding because of the deformation brought about by laying and again straightening for test.

TABLE 4 Standard Increments Due to Stranding

Size of Conductor, kcmil	Increment (Increase) of Mass per Unit Length and Electrical Resistance, %
Over 3 000 to 4 000	4
Over 2 000 to 3 000	3
2 000 and under	2



SUPPLEMENTARY REQUIREMENTS

The following supplementary requirements shall apply only when specified by the purchaser in the inquiry, contract, or order, for agencies of the U.S. Government.

S1. Referenced Documents

S1.1 The following documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation.

S1.2 *Military Specification:*⁷

MIL-C-12000 Cable, Cord and Wire, Electric Packaging of

S2. Inspection

S2.1 The government shall have the right to perform any of the inspections and tests set forth in this specification when such tests are deemed necessary to ensure that the material conforms to the prescribed requirements.

S3. Packaging

S3.1 Packaging shall be in accordance with MIL-C-12000.

⁷ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.