



Designation: D 558 – 9603

Standard Test Methods for Moisture-Density (Unit Weight) Relations of Soil-Cement Mixtures ¹

This standard is issued under the fixed designation D 558; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope *

1.1 These test methods cover the determination of the relationship between the water content and the density of soil-cement mixtures when compacted before cement hydration as prescribed.

1.2 A $\frac{1}{30}$ -ft³ (944-cm³) mold and a 5.5-lb (2.49-kg) rammer dropped from a height of 12.0 in. (304.8 mm) (30.5 cm) are used and two methods, depending on soil gradation, are covered, as follows:

	Sections
<u>Test Method A, using soil material passing a No. 4 (4.75-mm) sieve.</u>	-
<u>This method shall be used when 100 % of the soil sample passes the No. 4 (4.75-mm) sieve</u>	-
<u>Test Method A, using soil material passing a No. 4 (4.75-mm) sieve.</u>	5
<u>This method shall be used when 100 % of the soil sample passes the No. 4 (4.75-mm) sieve</u>	-
<u>Test Method B, using soil material passing a $\frac{3}{4}$-in. (19.0-mm) sieve.</u>	$\frac{7}{8}$
<u>This method shall be used when part of the soil sample is retained on the No. 4 (4.75-mm) sieve. This test method may be used only on materials with 30 % or less retained on the $\frac{3}{4}$-in. (19.0-mm) sieve</u>	-
<u>Test Method B, using soil material passing a $\frac{3}{4}$-in. (19.0-mm) sieve.</u>	6
<u>This method shall be used when part of the soil sample is retained on the No. 4 (4.75-mm) sieve. This test method may be used only on materials with 30 % or less retained on the $\frac{3}{4}$-in. (19.0-mm) sieve</u>	-
	$\frac{8}{8}$

1.3 ~~Th~~All observed and calculated values shall conform to the guidelines for significant digits and rounding established in Practice D 6026.

1.4 The values stated in inch-pound units are to be regarded as the standard, except as noted below. The SI units values given in parentheses are mathematical conversions to SI units, and are provided for information only and are not considered standard.

1.4.1 The gravitational system of inch-pound units is used when dealing with inch-pound units. In this system, the pound (lbf) represents a unit of force (weight), while the unit for mass is slugs.

1.4.2 The slug unit of mass is almost never used in commercial practice (density, scales, balances, etc.). Therefore, the standard unit for mass in this standard is either kilogram (kg) or gram (g) or both. Also, the equivalent inch-pound unit (slug) is not given.

1.4.3 It is common practice in the engineering/construction profession to concurrently use pounds to represent both a unit of mass (lbm) and of force (lbf). This implicitly combines two separate systems of units; that is, the absolute system and the gravitational system. It is scientifically undesirable to combine the use of two separate sets of inch-pound units within a single standard. As stated in 1.4.2, this standard includes the gravitational system of inch-pound units and does not use/present the slug unit for mass. However, the use of balances or scales recording pounds of mass (lbm) or recording density in lbm/ft³ shall not be regarded as nonconformance with this standard.

1.5 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

2.1 ASTM Standards:

¹ These test methods are under the jurisdiction of ASTM Committee D-18 on Soil and Rock and are the direct responsibility of Subcommittee D18.15 on Stabilization of Additives.

Current edition approved May Feb. 10, 1996; 2003. Published June 1996; April 2003. Originally published as D 558—38; approved in 1938. Last previous edition approved in 1996 as D 558 —82 (1990) ϵ 1, 96.

*A Summary of Changes section appears at the end of this standard.

- C 150 Specification for Portland Cement²
- C 595 Specification for Blended Hydraulic Cements²
- D 559 Test Methods for Wetting-and-Drying-Tests of Compacted Soil-Cement Mixtures³
- D 560 Test Methods for Freezing-and-Thawing-Tests of Compacted Soil-Cement Mixtures³
- ~~D 698 Test Methods for Moisture-Density Relations of Soils~~ 653 Terminology Relating to Soil, Rock, and Soil-Aggregate Mixtures Using 5.5-lb (2.49-kg) Rammer and 12-in. (305-mm) Drop³ Contained Fluids
- D 698 Test Methods for Laboratory Compaction Characteristics of Soil Using Standard Effort (12,400ft-lbf/ft³(600kN-m/m³))³
- D 2168 Test Methods for Calibration of Laboratory Mechanical-Rammer Soil Compactors³
- ~~D 3740 Practice 2216 Test Method for the Laboratory Determination of Water (Moisture) Content of Soil and Rock by Mass³~~
- D 3740 Practice for Minimum Requirements for Agencies Engaged in the Testing and/or Inspection of Soil and Rock as Used in Engineering Design and Construction³
- D 4753 Specification for Evaluating, Selecting, and Specifying Balances and Scales for Use in Soil, Rock, and Construction Materials Testing
- D 6026 Practice for Using Significant Digits in Geotechnical Data
- E 11 Specification for Wire-Cloth and Sieves for Testing Purposes⁴
- E 145 Specifications for Gravity-Convection and Forced-Ventilation Ovens

3. Terminology

3.1 For common definitions of terms used in this standard, refer to Terminology D 653.

4. Significance and Use

34.1 These tests determine the optimum water content and maximum density (unit weight) to be used for molding soil-cement specimens in accordance with Methods D 559 and D 560.

NOTE 1—Since these tests are used in conjunction with Methods D 559 and D 560 and the criteria referenced therein, the test differs in several aspects from Test Methods D 698. There are three main differences between this standard and Test Method D 698. Firstly, this standard allows a maximum particle size of $\frac{3}{4}$ -in. (19.0 mm) for a 4-in. (101.6-mm) mold while D 698 allows a maximum particle size of $\frac{3}{8}$ -in. (9.5-mm) for the same size mold. Secondly, this standard permits the material leftover after the water content specimen has been obtained to be mixed with the rest of the sample and reused for the next determination. Test Method D 698 does not permit the material to be reused. Thirdly, this standard allows the material that is retained on the $\frac{3}{4}$ -in. (19.0-mm) and passing the 3-in. (75-mm) to be discarded (scalping technique) and replaced with an equal mass of material that passes the $\frac{3}{4}$ -in. (19.0-mm) sieve and is retained on the No.4 (4.75-mm) sieve. Test Method D 698 does not permit the scalp and replacement technique.

NOTE 2—~~The agency performing these test methods can be evaluated in accordance with Practice D 3740. Notwithstanding statements on precision and bias contained in these test methods, the precision quality of these test methods the result produced by this standard is dependent on the competence of the personnel performing it, and the suitability of the equipment and facilities used. Agencies that meet the criteria of Practice D 3740 are generally considered capable of competent and objective testing/sampling/inspection/etc. Users of these test methods this standard are cautioned that compliance with Practice D 3740 does not, in itself, ensure reliable testing results. Reliable testing depends results depend on many factors; Practice D 3740 provides a means of evaluating some of these factors.~~

45. Apparatus

45.1 *Mold*—A cylindrical metal mold having a capacity volume of $\frac{1}{30} \pm 0.00040$ ft³ (944 ± 11 cm³) with an internal diameter of 4.0 ± 0.016 in. (101.60 ± 0.41 mm) and conforming to Fig. 1 to permit preparing compacted specimens of soil-cement mixtures of this size. The mold shall be provided with a detachable collar assembly approximately 2½-in. (63.5 mm) in height. The mold may be of the split type consisting of two half-round sections or section of pipe with one side split perpendicular to the pipe circumference and that can be securely locked in place to form a closed cylinder having the dimensions described above. The mold and collar assembly shall be so constructed that it can be fastened firmly to a detachable base (Fig. 1).

45.2 Rammer:

45.2.1 *Manual Rammer*—A manually operated metal rammer having a 2.000 ± 0.005 -in. (50.80 ± 0.13 -mm) diameter circular face and ~~weighing 5.5~~ a mass of 2.49 ± 0.02 lb (2.49 ± 0.01 kg). The rammer shall be equipped with a suitable guidesleeve to control the height of drop to a free fall of $12.0 \pm \frac{1}{16}$ in. (304.8 ± 1.6 mm) above the elevation of the soil-cement. The guidesleeve shall have at least four vent holes not smaller than $\frac{3}{8}$ in. (9.5 mm) spaced 90° apart and located with centers $\frac{3}{4} \pm \frac{1}{16}$ in. (19.0 ± 1.6 mm) from each end and shall provide sufficient clearance that free-falls of the rammer shaft and head will not be restricted.

45.2.2 *Mechanical Rammer*—A mechanically operated metal rammer having a 2.0 ± 0.005 -in. (50.80 ± 0.13 -mm) diameter face and a manufactured mass of ~~5.5~~ 2.49 ± 0.02 lb (2.49 ± 0.01 kg). The operating mass of the rammer shall be determined from a calibration in accordance with Methods D 2168. The rammer shall be equipped with a suitable arrangement to control the height of drop to a free-fall of $12.0 \pm \frac{1}{16}$ in. (304.8 ± 1.6 mm) above the elevation of the soil-cement.

45.2.3 *Rammer Face*—A sector face may be substituted with mechanical rammers provided the report shows that a sector face rammer was used. The sector face shall be a sector of a 4.0 ± 0.016 -in. (101.60 ± 0.41 -mm) diameter circle and shall have an

² Annual Book of ASTM Standards, Vols 04.01 and 04.02: Vol 04.01.

³ Annual Book of ASTM Standards, Vol 04.08.

⁴ Annual Book of ASTM Standards, Vols 04.01, 04.06, and Vol 14.02.

~~4.5.4~~ *Balances*—A balance or scale of at least 25-lb (11.3-kg) capacity sensitive conforming to 0.01-lb (0.005-kg) and the requirements of Class GP5 with a readability of 1g in Specification D 4753, except that a Class GP2 balance of at least 1000-g capacity sensitive to 0.1 g.

~~4.5~~ 0.1g readability is required for water content determination.

~~5.5~~ *Drying Oven*—A thermostatically controlled, preferably of the forced-draft type, meeting the requirements of Specification E 145 and capable of maintaining a uniform temperature of $230 \pm 110 \pm 9^\circ\text{F}$ ($110 \pm 5^\circ\text{C}$) for 5°C ($238 \pm 9^\circ\text{F}$) throughout the drying water content samples.

~~4.6~~ chamber.

~~5.6~~ *Straightedge*—A rigid stiff steel straight edge 12 in. (305 mm) in straightedge of any convenient length but not less than 10-in. (254-mm). The total length of the straightedge shall be machined straight to a tolerance of ± 0.005 -in. (± 0.1 -mm). The scraping edge shall be beveled edge.

~~4.7~~ if it is thicker than $\frac{1}{8}$ -in. (3-mm).

~~5.7~~ *Sieves*—3-in. (75-mm), $\frac{3}{4}$ -in. (19.0-mm), and No. 4 (4.75-mm) sieves conforming to the requirements of Specification E 11.

~~4.5.8~~ *Mixing Tools*—Miscellaneous tools such as mixing pan, spoon, trowel, and spatula, or a suitable mechanical device for thoroughly mixing the sample of soil with cement and with increments of water.

~~4.5.9~~ *Container*—A flat, round pan for moisture absorption by soil-cement mixtures, about 12 in. (305 mm) in diameter and 2 in. (50 mm) deep.

~~4.10~~ *Moisture*

~~5.10~~ *Water Content Cans*—Suitable containers made of material resistant to corrosion and change in mass upon repeated heating, cooling, exposure to materials of varying pH, and cleaning. Unless a desiccator is used, containers with close fitting lids shall be used for testing specimens having a mass of about 200g; while for specimens having a mass greater than about 200g, containers without lids may be used. One container is needed for each water content determination.

~~4.5.11~~ *Butcher Knife*—A butcher knife approximately 10 in. (250 mm) in length for trimming the top of the specimens.

6. Calibration

6.1 Perform calibrations before initial use, after repairs or other occurrences that might affect the test results, at intervals not exceeding 500 test specimens, or annually, whichever occurs first, for the following apparatus:

6.1.1 *Balance*—Evaluate in accordance with Specification D 3740.

6.1.2 *Molds*—Determine the volume as described in D 698, Annex 1.

6.1.3 *Manual Rammer*—Verify the free fall distance, rammer mass, and rammer force in accordance with 5.2. Verify the sleeve requirements in accordance with 5.2.1.

6.1.4 *Mechanical Rammer*—Calibrate and adjust the mechanical rammer in accordance with Test Method D 2168.

7. Test Method A, Using Soil Material Passing a No. 4 (4.75-mm) Sieve

7.1 *Sample:*

7.1.1 Prepare the sample for testing by breaking up the soil aggregations to pass the No. 4 (4.75-mm) sieve in such a manner as to avoid reducing the natural size of the individual particles. When necessary, first dry the sample until it is friable under a trowel. Drying may be accomplished by air drying or by the use of drying apparatus such that the temperature of the sample does not exceed 140°F (60°C).

7.1.2 Select a representative sample, weighing having a mass of approximately ~~6 lb (2.7 kg)~~ 2.7 kg or more, of the soil prepared as described in ~~5~~ 7.1.1.

7.2 *Procedure:*

7.2.1 Add to the soil the required amount of cement conforming to Specification C 150 or Specification C 595. Mix the cement and soil thoroughly to a uniform color.

7.2.2 When needed, add sufficient potable water to dampen the mixture to approximately four to six percentage points below the estimated optimum water content and mix thoroughly. At this ~~moisture~~ water content, plastic soils, tightly squeezed in the palm of the hand, will form a cast that will fracture with only slight pressure applied by the thumb and fingertips; nonplastic soils will bulk noticeably.

7.2.3 When the soil is a heavy-textured clayey material, compact the mixture of soil, cement, and water in the container to a depth of about 2 in. (50 mm) using the rammer described in ~~4.2~~ 5.2 or a similar hand tamper. Cover, and allow to stand for not less than 5 min but not more than 10 min to aid dispersion of the moisture and to permit more complete absorption by the soil-cement.

7.2.4 After the absorption period, thoroughly break up the mixture, without reducing the natural size of individual particles, until it will pass a No. 4 (4.75-mm) sieve and then remix.

7.2.5 Form a specimen by compacting the prepared soil-cement mixture in the mold, with the collar attached, in three equal layers so as to give a total compacted depth of about 5 in. (130 mm). Compact each layer by 25 blows from the rammer dropping free from a height of 12 in. (~~304.8~~ 305 mm) above the elevation of the soil-cement when a sleeve-type rammer is used, or from 12 in. (~~304.8~~ 305 mm) above the approximate elevation of each finally compacted layer when a stationary-mounted type rammer is used. The blows shall be uniformly distributed over the surface of the layer being compacted. During compaction, the mold shall

rest on a uniform, rigid foundation such as provided by a cylinder or a cube of concrete ~~weighing with a mass~~ not less than 200 lb (91 kg):

~~5.2.6 Following compaction, remove 91 kg.~~

~~7.2.6 Remove the extension collar, after compaction and carefully trim the compacted mixture even with the top of the mold by means of the a knife and straightedge. Determine and weigh.~~

~~5.2.7 Multiply record the mass of the compacted specimen mixture and mold, minus mold to four significant digits.~~

~~7.2.7 Remove the mass of the mold, by 30 (or divide by 942.95); record the result as the wet unit mass, γ_m , in pounds per cubic foot or grams per cubic centimetre, of the compacted soil-cement mixture.~~

~~5.2.8 Remove the material from the mold and slice vertically through the center. Take a representative sample of the material, weighing not less than 100 g, from the full height of one of the cut faces, weigh immediately, faces. Immediately, determine and record the mass of the moist material and container to four significant digits. Dry in an oven at $230 \pm 9^\circ\text{F} + 9^\circ\text{C}$ ($110 \pm 5^\circ\text{C}$) for at least 12 hours or to a constant mass.~~

~~5.2.9 Calculate mass. Determine the water content mass of the sample as directed in Section 7. Record the result as the moisture content, w , of the compacted soil-cement mixture.~~

~~5.2.10 Thoroughly dry soil and container to four significant digits.~~

~~7.2.8 Thoroughly break up the remainder of the material as before until it will pass a No. 4 (4.75-mm) sieve, as judged by eye, and add all other material remaining after obtaining the moisture sample.~~

~~5.2.11 Add~~

~~7.2.9 Add water in sufficient amount to increase the water content of the soil-cement mixture by one or two percentage points, mix, and repeat the procedure given in 5.2.5-5.2.10 7.2.5-7.2.8 for each increment of water added.~~

~~5.2.12 Continue this series of determinations until there is either a decrease or no change in the wet unit mass, γ_m , in pounds per cubic foot or grams per cubic centimetre mass of the compacted soil-cement mixture, moist material and mold.~~

NOTE 4—This procedure has been found satisfactory in most cases. However, in instances where the soil material is fragile in character and will reduce significantly in grain size due to repeated compaction, a separate and new sample shall be used for each moisture-density (unit weight) determination.

NOTE 5—To minimize the effect of cement hydration, perform the test expeditiously and continuously to completion.

68. Test Method B, Using Soil Material Passing a ¾-in. (19.0-mm) Sieve

68.1 Sample:

68.1.1 Prepare the sample for testing by segregating the aggregate retained on a No. 4 (4.75-mm) sieve and breaking up the remaining soil aggregations to pass the No. 4 (4.75-mm) sieve in such a manner as to avoid reducing the natural size of individual particles. When necessary, first dry the sample until it is friable under a trowel. Drying may be accomplished by air drying or by the use of drying apparatus such that the temperature of the sample does not exceed 140°F (60°C).

68.1.2 Sieve the prepared soil over the 3-in. (75-mm) (Note 2), ¾-in., (19.0-mm), and No. 4 (4.75-mm) sieves. Discard the material retained on the 3-in. (75-mm) sieve. Determine the percentage of material, by oven-dry mass, retained on the ¾-in. (19.0-mm) and No. 4 sieves.

68.1.3 Saturate the aggregate passing the ¾-in. (19.0-mm) sieve and retained on the No. 4 (4.75-mm) sieve by soaking in potable water; surface-dry the material as required for later testing.

NOTE 6—Most soil-cement construction specifications covering soil gradation limit maximum size material to 3 in. (75 mm) or less.

68.1.4 Select and maintain separate representative samples of soil passing the No. 4 (4.75-mm) sieve and of saturated, surface-dry aggregate passing the ¾-in. (19.0-mm) sieve and retained on the No. 4 sieve so that the total sample will weigh approximately ~~11 lb (4.99 kg)~~ 5 kg or more. The percentage, by oven-dry mass, of aggregate passing the ¾-in. (19.0-mm) sieve and retained on the No. 4 (4.75-mm) sieve shall be the same as the percentage passing the 3-in. (75-mm) sieve and retained on the No. 4 sieve in the original sample.

68.2 Procedure:

68.2.1 Add to the portion of the soil sample passing the No. 4 sieve, the amount of cement conforming to Specification C 150 or Specification C 595, required for the total sample specified in 6 8.1.4. Mix the cement and soil thoroughly to a uniform color.

68.2.2 When needed, add water to this soil-cement mixture and facilitate moisture dispersion as described for Method A in 5 7.2.2-5.7.2.4. After this preparation, add the saturated, surface-dry aggregate to the soil-cement mixture passing the No. 4 (4.75-mm) sieve and mix thoroughly.

68.2.3 Form a specimen by compacting the prepared soil-cement mixture in the mold (with the collar attached) and trim ~~and weigh~~ the compacted specimen as described for Method A in 5 7.2.5 and 5 7.2.6. During the trimming operation remove all particles that extend above the top level of the mold. Correct all irregularities in the surface by hand-tamping fine material into these irregularities and leveling the specimen again with the ~~straightedge~~.

~~6.2.4 Multiply straightedge. Determine and record the mass of the compacted specimen mixture and mold, minus the mass of mold to four significant digits.~~

~~8.2.4 Remove the mold, by 30 (or divide by 942.95); record the result as the wet unit mass, γ_m , in pounds per cubic foot or grams per cubic centimetre of the compacted soil-cement mixture.~~

~~6.2.5 Remove the material from the mold and take a sample for determining the water content as described for Method A in~~

5.2.8 and 5.2.9 7.2.7 except that the moisture water content sample shall weigh not less than have a mass of at least 500 g. Record the result as the water content, w , of the compacted soil-cement mixture.

68.2.65 Thoroughly break up the remainder of the material as before until it will pass a 3/4-in. (19.0-mm) sieve and at least 90 % of the soil particles smaller than a No. 4 (4.75-mm) sieve will pass a No. 4 sieve, as judged by eye, and add all other material remaining after obtaining the ~~moisture water content~~ sample.

68.2.76 Add sufficient water to increase the water content of the soil-cement mixture by one or two percentage points, mix, and repeat the procedure described in 6.2.3-6.2.6 8.2.3-8.2.5 for each increment of water added. Continue this series of determinations until there is either a decrease or no change in the wet unit mass, γ_m , in pounds per cubic foot or grams per cubic centimetre mass of the ~~compacted soil-cement mixture~~ moist material and the mold (Note 3 and Note 4).

79. Calculations

79.1 Calculate the volume of the mold used to compact the soil-cement mixture for each trial in accordance with Test Method D 698, Annex A1, to four significant digits.

9.2 Calculate the water content and dry unit mass, γ_d , in pounds per cubic foot or grams per cubic centimetre of the compacted soil-cement mixture for each trial in accordance with D 2216 to 0.1 %

9.3 Calculate the moist density (Eq 1), the dry density (Eq 2), and then the dry unit weight (Eq 3) for each trial as follows:

$$w = [(A - B)/(B - C)] \times 100 \quad (1)$$

$$\gamma = [\gamma_m / (w + 100)] \times 100$$

$$\gamma = [\gamma \rho_m = (M_m - M_{md}) / 1000 V$$

MmMmd γ V

where:

w - ρ_m = percentage moist density of w compacted soil-cement specimen, Mg/m³,

A - M_m = mass of moisture can moist specimen and wet soil-cement, mold, kg,

B = mass of moisture can and oven-dry soil-cement, compaction mold, kg, and

M_{md}
 C - V = mass volume of moisture can, compaction, m³(see D 698, Annex A1).

$$\rho_d = \rho_m / (1 + w/100) \quad (2)$$

where:

$\gamma \rho_d$ = dry unit mass density of compacted soil-cement specimen, lb Mg/ftm³ or g/cm,

ρ_m = moist density of compacted soil-cement specimen, Mg/m³, and

w = water content, %.

$$\gamma_d = 62.43 \rho_d \text{ in lbf/ft}^3 \quad (3)$$

or

$$\gamma_d = 9.087 \rho_d \text{ in kN/m}^3 \quad (4)$$

where:

γ_{md} = wet dry unit mass weight of compacted soil-cement; specimen

10. Moisture-Density (Unit Weight) Relationship

10.1 The values of water content and dry unit weight calculated in Section 9 for each compacted soil-cement specimen are then plotted. The dry unit weight in lbf/ft³ or g/cm shall be plotted to the nearest 0.1 lbf/ft³.

8. Moisture-Density Relationship

8.1 The calculations in Section 7 shall be made to determine on the water content ordinate scale and the corresponding dry unit mass, γ_d , in pounds per cubic foot or grams per cubic centimetre (density) for each of water content to the nearest 0.1 % on the abscissa scale. Draw the compaction curve as a smooth curve through the plotted points.

NOTE 7—Experience has shown that it is very important to use consistent scales when plotting these curves. † One satisfactory approach is to plot the dry unit mass, γ_d , in pounds per cubic foot or grams per cubic centimetre (densities) weight using a scale of 1" = 5 lbf/ft³ for the soil-cement mixture shall be plotted as ordinates ordinate and the corresponding moisture contents water content using a scale of 1" = 2 % as the abscissas.

810.2 Optimum Water Content, w_o —When the densities and corresponding moisture contents for the soil-cement mixture have been determined and plotted as indicated in 8.1 it will be found that by connecting the plotted points with a smooth line, a curve is produced. The—The water content corresponding to the peak of the curve plotted according to 10.1 shall be termed the “optimum moisture “ optimum water content” of the soil-cement mixture under the compaction process described in these methods.

~~810.3 *Maximum Density, Dry Unit Weight, γ_{dmax}* —The dry unit mass, γ_d , weight, in pounds per cubic foot or grams per cubic centimetre of lb/ft^3 corresponding to the soil-cement mixture at “optimum optimum water content” shall be termed “maximum density” dry unit weight” under the compaction process described in these test methods.~~

911. Report

911.1 The report shall include the following:

911.1.1 Sample identification (i.e., sample number, project, location, depth, etc.),

11.1.2 Procedure used (Method A or Method B),

11.1.3 Optimum water content, to the nearest 0.5 %,

11.1.4 Maximum dry unit weight, to the nearest 0.5 lb/ft^3 , and

911.1.25 ~~M~~Compaction curve plot showing compaction points used to establish the compaction curve, point of maximum dry unit weight and optimum water content.

102. Precision and Bias

102.1 *Precision*—~~Test data on precision are being sought by not presented due to the subcommittee for the preparation nature of a statement on the precision of materials being tested by this test procedure. Until method. It is either not feasible or too costly at this time to have ten or more laboratories participate in a statement round-robin testing program. Subcommittee D 18.15 is developed, seeking any data from the users of this test method that might be guided by the statement in Test Method D 698, for which the precision is expected used to b make a limited statement on precision.~~

102.2 *Bias*—There are no accepted reference values for this test method, therefore, bias cannot be determined.

113. Keywords

113.1 compaction; dry density; optimum water content; soil-cement; soil-stabilization; unit weight

SUMMARY OF CHANGES

In accordance with D 18 policy, this section identifies the principal location of changes to these test methods that have been incorporated this standard since the last issue.

- ~~(1) Added new sentence at edition (1996) that may impact the end use of Section 1.2, Test Method B, this standard.~~
- ~~(1) Changed title to clarify reflect definitions used in the applicable materials as required test method.~~
- ~~(2) Corrected typo in F section 1.2.~~
- ~~(3) Changed referenced sections for Method D 698 when using a 4-in. (101.60-mm) mold.~~
- ~~(2) Added safety caveat A and Method B in section 1.2.~~
- ~~(4) Added new paragraph section 1.3 to reference D 6026.~~
- ~~(5) Revised section 1.4 to comply with present policy.~~
- ~~(3) Added Practice D 3740 as a referenced document clarify units used in Section 2 the test method.~~
- ~~(6) Updated the standard titles and added D 653, D 2216, D 4753, D 6026 and E 145 to sectionf 2 on “Referenced Documents”.~~
- ~~(7) Added the recommended D-18 practice.~~
- ~~(4) Added term “unit weight” in sections 3.1, Note 4 and Section 10.~~
- ~~(8) Added new information to Note 1.~~
- ~~(9) Updated Note 2 statement on Practice D 3740.~~
- ~~(10) Added new Section 3 on “Terminology” and renumbered subsequent sections.~~
- ~~(11) Revised sections 5.1, 5.4, 5.5, 5.6, and 5.10 to reference Practice D 3740. Renumbered the remaining notes.~~
- ~~(5) Revised conform to D 18 guidelines and policies.~~
- ~~(12) Added new Section H 6 on Keywords.~~
- ~~(6) Added Summary of Changes “Calibration”. Renumbered subsequent sections.~~
- ~~(13) Revised 7.2.6 for clarity and to reflect include significant digits.~~
- ~~(14) Moved the changes made information in this revision.~~
- ~~(7) Changed “moisture content” Section 7.2.7 to Section 9 “w Calculations”. Renumbered subsequent sections.~~
- ~~(15) Revised Section 7.2.8 for clarity.~~
- ~~(16) Moved the informat²ion in Sections 1.1, 3.1, 4.5, 5.2.2, 5.2.9, 5.2.11, 6.2.5, 6.2.7, 7.1, 8.1, 8.2, 8.3, Section 7.2.9 to Section 9 “Calculations”. Renumbered subsequent sections.~~
- ~~(17) Revised wording of 7.2.10.~~
- ~~(18) Added new sentence to end of Section 8.2.3 to clarify instructions and include significant digits.~~
- ~~(19) Moved information in Section 8.2.4 to Section 9 “Calculations”. Renumbered subsequent sections.~~
- ~~(20) Revised Section 9 “Calculations” to agree include all calculations associated with the test method.~~

- (21) Revised Section 10 “Moisture-Density (Unit Weight) Relationship” to include additional instructions.
- (22) Revised Section 18-F1 “Report” to include additional items.
- (23) Revised Section 12.1 to conform to D 18 guidelines.
- (24) Corrected errors with respect to significant digits throughout standard.
- (25) Updated “Summary of Changes” section.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).