



# Standard Specification for Materials and Manufacture of Articulating Concrete Block (ACB) Revetment Systems<sup>1</sup>

This standard is issued under the fixed designation D 6684; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 The purpose of this Standard is to provide specifications for articulating concrete block (ACB) revetment system structural components, material composition and physical properties, manufacturing methods and testing requirements.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory requirements prior to use.*

## 2. Referenced Documents

### 2.1 ASTM Standards:

- C 33 Specification for Concrete Aggregates<sup>2</sup>
- C 39 Test Method for Compressive Strength of Cylindrical Concrete Specimens<sup>2</sup>
- C 42 Test Method for Obtaining and Testing Drilled Cores and Sawed Beams of Concrete<sup>2</sup>
- C 67 Test Methods for Sampling and Testing Brick and Structural Clay Tile<sup>3</sup>
- C 140 Test Methods of Sampling and Testing Concrete Masonry Units and Related Units<sup>3</sup>
- C 150 Specification for Portland Cement<sup>4</sup>
- C 207 Specification for Hydrated Lime for Masonry Purposes<sup>4</sup>
- C 331 Specification for Lightweight Aggregates for Concrete Masonry Units<sup>2</sup>
- C 595 Specification for Blended Hydraulic Cements<sup>4</sup>
- C 618 Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for use as a Mineral Admixture in Concrete<sup>2</sup>
- C 666 Test Method for Resistance of Concrete to Rapid Freezing and Thawing<sup>2</sup>
- C 1262 Test Method for Evaluating the Freeze-Thaw Durability of Manufactured Concrete Masonry Units and Related Concrete Units<sup>3</sup>

D 4533 Test Method for Trapezoid Tearing Strength of Geotextiles<sup>5</sup>

D 4632 Test Method for Grab Breaking Load and Elongation of Geotextiles<sup>5</sup>

D 4833 Test Method for Index Puncture Resistance of Geotextiles, Geomembranes, and Related Products<sup>5</sup>

### 2.2 Other Documents:

American Association of State Highway Transportation Officials (AASHTO), 1995, "Standard Specification for Geotextiles," AASHTO Designation M 288, February.

Koerner, R.M., 1998, "Designing With Geotextiles," 4th Edition, Prentice-Hall Publishers, Englewood Cliffs, N.J. p. 761.

## 3. Terminology

### 3.1 Definitions:

3.1.1 *articulating concrete block (ACB) revetment system, n*—a matrix of interconnected concrete block units sufficient for erosion protection. Units are connected by geometric interlock and/or cables, geotextiles, or geogrids, and typically include a geotextile underlay for subsoil retention.

## 4. Significance and Use

4.1 An articulating concrete block system is comprised of a matrix of individual concrete blocks placed together to form an erosion-resistant revetment with specific hydraulic performance characteristics. The system includes a filter layer compatible with the subsoil which allows infiltration and exfiltration to occur while providing particle retention. The filter layer may be comprised of a geotextile, properly graded granular media, or both. The blocks within the matrix shall be dense and durable, and the matrix shall be flexible and porous.

4.2 Articulating concrete block systems are used to provide erosion protection to underlying soil materials from the forces of flowing water. The term "articulating," as used in this Standard, implies the ability of individual blocks of the system to conform to changes in subgrade while remaining interconnected by virtue of geometric interlock and/or additional system components such as cables, ropes, geotextiles, or geogrids.

4.3 The definition of articulating concrete block systems

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D18 on Soil and Rock and is the direct responsibility of Subcommittee D18.25 on Erosion and Sediment Control Technology.

Current edition approved June 10, 2001. Published August 2001.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 04.02.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 04.05.

<sup>4</sup> *Annual Book of ASTM Standards*, Vol 04.01.

<sup>5</sup> *Annual Book of ASTM Standards*, Vol 04.13.

does not distinguish between interlocking and non-interlocking block geometries, between cable-tied and non-cable-tied systems, between vegetated and non-vegetated systems or between methods of manufacturing or placement. Furthermore, the definition does not restrict or limit the block size, shape, strength, or longevity; however, guidelines and recommendations regarding these factors are incorporated into this Standard. Block systems are available in either open-cell or closed-cell configurations.

**5. Materials and Manufacture**

5.1 *Materials Specifications: Cementitious Materials*—Materials shall conform to the following applicable ASTM standards:

Portland Cements	C 150
Blended Cements	C 595
Hydrated Lime Types	C 207
Pozzolans	C 618

5.2 Aggregates shall conform to the following ASTM specifications, except that grading requirements shall not necessarily apply:

Normal Weight	C 33
Light Weight	C 331

5.3 *Physical Properties*—At the time of delivery to the work site, the units shall conform to the physical requirements prescribed in Table 1.

5.3.1 In addition to Table 1, when freeze-thaw durability testing is required, such testing shall be performed in accordance with Test Methods C 67, C 666, or C 1262, at the direction of the Owner. The number of freeze-thaw cycles and the corresponding weight loss criterion for pass-fail determination shall be specified by the Owner along with the test method.

5.4 *Geotextile Filter*—The geotextile filter shall be in compliance with the project specifications, in consideration of its compatibility with the underlying soil subgrade. Minimum strength requirements are provided in Table 2.

5.4.1 *Geotextile*—Subsoil compatibility assessment shall include functional requirements for permeability, particle retention, and resistance to clogging. Physical property requirements for permittivity, aperture size, percent open area, and UV stability should be based on site-specific soil characteristics, site conditions, and construction techniques. Applicable references for conducting compatibility assessments include:

Koemer, R.M., 1998, “Designing With Geotextiles,” 4th Edition, Prentice-Hall Publishers, Englewood Cliffs, N.J. p. 761.

5.5 *Revetment Cable and Fittings:*

5.5.1 For cabled systems, the revetment cable or rope and fittings shall be designed to provide adequate strength and durability characteristics to facilitate lifting and placing of large mattresses.

5.5.2 Fittings such as sleeves, clamps and stops shall be as required by the manufacturer. Selection of cable or rope and fittings shall be made in a manner that insures a safe design factor for mats being lifted from one or both ends. Consideration shall be taken for the bending of the cables or ropes around hooks or pins during lifting. Revetment cable or rope, splice fittings, sleeves and stops shall be selected so that the cable or rope and all connections result in a minimum factor-of-safety of 5.0 with respect to lifting.

5.5.3 For those systems performance tested with, and that rely on cables, ropes, or other non-concrete components to maintain the block-to-block interconnection, the cables, ropes, and/or non-concrete components shall also meet the design life of the project.

5.6 *Block Production:*

5.6.1 Articulating concrete blocks may be produced at a block plant or onsite using either wet-cast or dry-cast production techniques, provided that the composition and physical characteristics of the furnished units meet the requirements of 5.1-5.3.

5.7 *Matrix Assembly:*

5.7.1 *Non-Cabled System*—Non-cabled articulating concrete block systems are typically palletized, cured, and shipped to the job site. Non-cabled systems may also be assembled on, and/or glued to, a high-strength geotextile fabric which is used to carry the articulated block mattress.

5.7.2 *Cabled System*—Cabled articulating concrete block revetment systems can be assembled into mattresses, typically up to 480 square feet (45 square meters). Whole mat production can occur at the block plant or at the project. The individual blocks are typically placed in their respective matrix positions on a work surface, and the cables or ropes are inserted through the core holes in the block. Once the blocks have been assembled into a mattress, the ends of the cable or rope are secured as necessary based on the characteristics of the system. Wetcast mattresses can be poured with the cables or ropes integral to the blocks both laterally and longitudinally at the time of production. With this method, cable-end sleeves are not necessary.

**6. Sampling and Testing**

6.1 Manufacturer shall provide test data showing that concrete products manufactured within the previous 24 months of anticipated ACB placement have met the requirements of this Standard.

6.2 Manufacturer shall provide access to lots ready for delivery to the purchaser or his authorized representative for sampling and testing in accordance with the procedures specified in this Standard prior to the commencement of ACB placement.

6.3 For the compressive strength, water absorption, and unit weight (density) determinations, three samples shall be taken

**TABLE 1 Physical Requirements**

Minimum Compressive Strength, lb/in <sup>2</sup>		Maximum Water Absorption, lb/ft <sup>3</sup>		Minimum Density (in air), lb/ft <sup>3</sup>	
Average of 3 units	Individual Unit	Average of 3 units	Individual Unit	Average of 3 units	Individual Unit
4,000	3,500	9.1	11.7	130	125

NOTE—For units produced by a wet-cast method, tests shall be conducted in accordance with Test Methods C 39 and C 42. For units produced by a dry-cast method, tests shall be conducted in accordance with Test Methods C 140.

**TABLE 2 Geotextile Strength Requirements (AASHTO M-288)**

Property	ASTM Test Methods	Units	Class 1		Class 2		Class 3	
			Elongation <50% <sup>A</sup>	Elongation >50% <sup>A</sup>	Elongation <50% <sup>A</sup>	Elongation >50% <sup>A</sup>	Elongation <50% <sup>A</sup>	Elongation >50% <sup>A</sup>
Grab Strength	D 4632	lb	315	200	250	160	180	110
Sewn Seam Strength <sup>B</sup>	D 4632	lb	270	180	220	140	160	100
Tear Strength	D 4533	lb	110	80	90 <sup>C</sup>	55	70	40
Puncture Strength	D 4833	lb	110	80	90	55	70	40

<sup>A</sup> As measured in accordance with Test Method D 4632.

<sup>B</sup> When seams are required.

<sup>C</sup> The required Minimum Average Roll Value (MARV) tear strength for woven monofilament geotextiles is 55 lb.

NOTE—Required geotextile class for permanent erosion control design is designated below for the indicated application. The severity of installation conditions generally dictates the required geotextile class.

Class 1 is recommended for harsh or severe installation conditions where there is a greater potential for geotextile damage, including irregular sections where repeated mattress lifting, realignment, and replacing is expected, or when vehicular traffic on the installation is anticipated.

Class 2 is recommended for installation conditions where mattress placement in regular, even reaches is expected and little or no vehicular traffic on the installation will occur, or when hand-placing on a graded surface of native soils.

Class 3 is specified for the least severe installation environments, typically hand-placed systems (zero drop height) on a bedding layer of graded sand, road base aggregate, or other select imported material.

from each lot of 50,000 units (i.e., individual blocks) or fraction thereof. Additional samples may be taken at the discretion of the purchaser.

6.4 For the compressive strength, water absorption, and unit weight (density) determinations, specimens shall be obtained from the samples and tested in accordance with Test Methods D 39 and D 42 for blocks produced by a wet cast method or in accordance with Test Methods C 140 for blocks produced by a dry-cast method.

6.5 Sample cylinders, cores or coupons shall use a height to thickness ratio of not less than 1:1 nor greater than 2:1 for purposes of compressive strength testing. The minimum thickness (or diameter) shall be 1.5 in. Care shall be taken to achieve square-cut ends and to ensure proper capping prior to testing.

6.6 Samples shall be 100 % solid and shall not contain cable holes or other voids.

6.7 The compressive strength of the sample shall be considered to be the net area compressive strength of the full size unit, as corrected for the height to thickness ratio of the sample in accordance with Test Methods C 140.

## 7. Compliance

7.1 In the event that a sample fails to conform to the specified requirements, the manufacturer may sort the ship-

ment and test new units, selected at random by the purchaser from the retained lot. If the second set of tests also fails to conform to the specified requirements, the entire lot may be rejected.

NOTE 1—Unless otherwise specified in the purchase order, the cost of tests is typically borne as follows: (1) if the results of the tests show that the units do not conform to the requirements of this Standard, the cost is typically borne by the seller; (2) if the results of the tests show that the units conform to the requirements of this Standard, the cost is typically borne by the purchaser.

## 8. Quality Assurance

8.1 All units shall be sound and free of defects that would interfere with proper placement or that would impair the strength or longevity of the installation.

8.2 Minor cracks incidental to the usual method of manufacture, or chipping that results from customary methods of handling in shipping, delivery and placement shall not be deemed grounds for rejection provided the requirements of 8.1 are met.

## 9. Keywords

9.1 articulating concrete block (ACB) revetment systems; channel; channel stability; erosion; erosion control; open-channel flow; revetments

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).*