



Standard Test Method for Measuring the Resiliency of Turf Reinforcement Mats (TRMs)¹

This standard is issued under the fixed designation D 6524; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method is used to measure the resiliency or recovery of turf reinforcement mats (TRMs) after they have been subjected to three cycles of loading at 689 kPa (100 psi) for 1 min/per cycle.

1.2 The values stated in SI units are to be regarded as the standard. The values are provided in inch-pound units for information only.

1.3 This test method does not provide resiliency values for TRMs under variable normal compressive stresses. This test method determines nominal resiliency.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

- D 123 Terminology Relating to Textiles²
- D 1776 Practice for Conditioning Textiles for Testing²
- D 1777 Test Method for Thickness of Textiles Materials²
- D 4354 Practice for Sampling of Geosynthetics for Testing³
- D 4439 Terminology for Geotextiles³
- D 5199 Test Method for Measuring Nominal Thickness of Geotextiles and Geomembranes³

3. Terminology

3.1 Definitions:

3.1.1 *pressure, n*—the force or load per unit area.

3.1.2 *thickness*—(1) the distance between one planar surface and its opposite parallel and planar surface; (2) for TRMs, the distance between the upper and lower surfaces of the material, measured under a specified pressure and time.

3.1.3 *turf reinforcement mat (TRM), n*—a long-term nondegradable rolled erosion control product composed of UV stabilized, nondegradable, synthetic fibers, nettings, or filaments, or combination thereof, processed into three-

dimensional reinforcement matrices.

3.2 For definitions of other textile terms used in this test method, refer to Terminology D 123.

3.3 For definitions of other terms relating to geotextiles and geomembranes used in this test method, refer to Terminology D 4439.

4. Summary of Test Method

4.1 The nominal resiliency of TRMs is determined by observing the thickness of the TRM before and after it is subjected to three cycles of loading at 689 kPa (100 psi) for 1 min/cycle.

5. Significance and Use

5.1 Resiliency may be used to control the quality of many TRMs. Resiliency may be indicative of a TRM's ability to retain original configuration after exposure to the stresses which may be exerted during manufacture, shipping, and installation. Resiliency is not generally indicative of field performance.

5.2 The resiliency of TRMs may vary considerably depending on the pressure applied to the specimen during loading cycles. To minimize variation, specific sample size and applied pressure are indicated in this test method to ensure all results are comparable.

5.3 To determine the effect of different pressure loadings on the final thickness of TRMs, use this test method.

5.4 This test method may be used for acceptance testing of commercial shipments of TRMs, but caution is advised since information on between-laboratory precision is incomplete. Comparative tests, in accordance with 5.4.1 may be advisable.

5.4.1 In a case of a dispute arising from differences in reported test results when using this test method for acceptance testing of commercial shipments, the purchaser and the supplier should conduct comparative tests to determine if there is a statistical bias between their laboratories. Competent statistical assistance is recommended for the investigation of bias. As a minimum, the two parties should take a group of test specimens that are as homogeneous as possible and that are formed from a lot of material of the type in question. The test specimens should be randomly assigned in equal numbers to each laboratory for testing. The average results from the two laboratories should be compared using Student's *t*-test for unpaired data and an acceptable probability level chosen by the

¹ This test method is under the jurisdiction of ASTM Committee D-35 on Geosynthetics and is the direct responsibility of Subcommittee D35.05 on Geosynthetic Erosion Control.

Current edition approved Feb. 10, 2000. Published April 2000.

² *Annual Book of ASTM Standards*, Vol 07.01.

³ *Annual Book of ASTM Standards*, Vol 04.09.

two begun. If bias is found, either its cause must be corrected, or the purchaser and the supplier must agree to the light of the known bias.

NOTE 1—The user should be aware that the compressibility of the materials, their rebound characteristics, and the like will also be affected by the thickness of the TRMs following the time when they are rolled up on rolls shipped and stored.

6. Apparatus

6.1 *Thickness Testing Instrument*—The thickness gage shall have a base (or anvil) and a free-moving presser foot plate whose planar faces are parallel to each other to <0.1 mm. A gage with a 150-mm (6-in.) diameter presser foot, the base shall extend at least 10 mm in all directions further than the edge of the approximately 17 500-mm² circular presser foot, shall be used for measurements of TRMs. The instruments must be capable of measuring a maximum thickness of at least 25 mm (1 in.) to an accuracy of +0.2 mm. The gages shall be constructed to permit gradual application of pressure to a specific force of 0.2 + 0.02 kPa (0.029 + 0.003 psi) for TRMs. Dead weight loading may be used.

NOTE 2—Due to compressibility of many TRMs, the cutting and handling preparation may change the thickness. Care should be exercised to minimize these effects.

7. Sampling

7.1 *Lot Sample*—In the absence of other guidelines, divide the product into lots and take lot samples in accordance with Practice D 4354.

7.2 *Laboratory Sample*—Consider the units in the lot sample as the units in the laboratory sample. For the laboratory sample, take a full-width sample of sufficient length along the selvage or edge of the roll so that the requirements of 7.3-7.5.2 can be met. Exclude the inner and outer wraps of the roll or any material containing folds, crushed areas, or other distortions not representative of the sampled lot.

7.3 Remove test specimens from the laboratory sample in a randomly distributed pattern across the width with no specimen taken nearer than 100 mm (4 in.) from the selvage or roll edge, unless otherwise specified.

7.4 *Test Specimens*—Cut ten 102 by 102-mm (4 by 4 in.) test specimens from the sample. Handle specimens in a manner to avoid the loss of loose filler and weaving components.

7.5 *Number of Specimens*—Unless otherwise agreed upon, as when provided in an applicable material specification, take a number of test specimens per laboratory sample such that the user may expect at the 95 % probability level that the test result is not more than 6.0 % of the average above or below the true average of the sample. Determine the number of specimens per sample as follows:

7.5.1 *Reliable Estimate of ν* —When there is a reliable estimate of ν based upon extensive part records for similar materials tested in the user's laboratory as directed in this test method, calculate the required number of specimens for the machine and cross-machine directions as follows:

$$n = (t/\nu A)^2 \quad (1)$$

where:

- n = number of test specimens (rounded upward to a whole number),
- ν = reliable estimate of the coefficient of variation of individual observations on similar materials in the user's laboratory under conditions of single-operation precision, %,
- t = value of Student's t for one-sided limits (see Table 1), a 95 % probability level, and the degrees of freedom associated with the estimate of ν , and
- A = 5.0 % of the average, the value of the allowable variation.

7.5.2 *No Reliable Estimate of ν* —When there is no reliable estimate of ν for the user's laboratory, Eq 1 should not be used directly. Instead, specify the fixed number (10) of specimens. The number of specimens is calculated using $\nu = 9.5$ % of the average. These values for ν are somewhat larger than usually found in practice. When a reliable estimate of ν for the user's laboratory becomes available, Eq 1 will usually require fewer than the fixed number of specimens.

8. Conditioning

8.1 Bring the specimens to the moisture and temperature equilibrium in the atmosphere for testing TRMs, that is a temperature of 21 ± 2°C (70 ± 4°F) and a relative humidity of 60 ± 10 %.

9. Procedure

9.1 Test the conditioned specimens in the standard atmosphere specified in 8.1

9.2 Handle the test specimens carefully to avoid altering the natural state of the material.

9.3 With force applied to the presser foot on the base (no test specimen present), zero the measuring scale or record the base reading. Lift the presser foot, center the test specimen on the base under the presser foot, and bring the presser foot into contact with the material. After the full force has been applied to the presser foot for 5 s against the specimen, record the thickness value to the nearest 0.002 mm and remove the specimen from the test device.

9.4 Place the specimen under a constant normal compressive load of 689 kPa (100 psi), assuming that the load is applied evenly over the entire surface area of the test specimen.

NOTE 3—Hydraulic presses have been found to be successful for load application.

TABLE 1 Values of Student's t for Two-Sided Limits and the 95 % Probability A

df	t 0.025	df	t 0.025	df	t 0.025
1	12.706	11	2.201	21	2.080
2	4.303	12	2.179	22	2.074
3	3.182	13	2.160	23	2.069
4	2.776	14	2.145	24	2.064
5	2.571	15	2.131	25	2.060
6	2.447	16	2.120	26	2.056
7	2.365	17	2.110	27	2.052
8	2.306	18	2.101	28	2.048
9	2.262	19	2.093	29	2.045
10	2.228	20	2.086	inf.	1.960

9.4.1 Apply three loading cycles that consist of one minute under load and one minute unloaded.

9.4.2 After the three loading cycles, allow the specimen to recover for 30 min.

9.5 Measure the final thickness, T_f (mm), in accordance with 9.3.

9.6 Repeat the test method for each of the remaining specimens.

10. Calculation

10.1 Calculate the percent thickness recovery, resiliency, for each specimen:

$$\text{Resiliency} = (T_f / T_i) \times 100 \quad (2)$$

10.2 Calculate the average resiliency for all specimens.

11. Report

11.1 Report the following information for nominal resiliency:

11.1.1 Project, type of TRM tested, and method of sampling,

11.1.2 Name or description of thickness and pressure loading apparatus used for testing,

11.1.3 Dimensions of the presser foot and of the specimen,

11.1.4 Loading time interval,

11.1.5 Number of tests,

11.1.6 Average nominal resiliency,

11.1.7 Coefficient of variation of thickness in the sample, in percent (optional), and

11.1.8 Any unusual or out-of-standard conditions or observations made during the tests.

12. Precision and Bias

12.1 *Precision*—The precision of this test method is being evaluated.

12.2 *Bias*—This test method has no bias because the value of that property can only be defined in terms of this test method.

13. Keywords

13.1 thickness; recovery; resiliency; turf reinforcement mat, TRM

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).