

Standard Specification for Vinyl Acetate¹

This standard is issued under the fixed designation D 2190; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers vinyl acetate.

1.2 For specific hazard information and guidance, see the supplier's Material Safety Data Sheet for materials listed in this specification.

2. Referenced Documents

2.1 ASTM Standards:

D 268 Guide for Sampling and Testing Volatile Solvents and Chemical Intermediates for Use in Paint and Related Coatings and Materials²

D 1078 Test Method for Distillation Range of Volatile Organic Liquids²

D 1209 Test Method for Color of Clear Liquids (Platinum-Cobalt Scale)²

D 1364 Test Method for Water in Volatile Solvents (Fischer Reagent Titration Method)²

D 2086 Test Method for Acidity in Vinyl Acetate and Acetaldehyde²

D 2191 Test Method for Acetaldehyde Content of Vinyl Acetate²

D 2193 Test Method for Hydroquinone in Vinyl Acetate²

D 4052 Test Method for Density and Relative Density of Liquids by Digital Density Meter³

E 1 Specification for ASTM Thermometers⁴

E 300 Practice for Sampling Industrial Chemicals⁵

2.2 U.S. Federal Standard:

PPP-C-2020 Chemicals, Liquid, Dry, and Paste: Packaging of⁶

3. Sampling

3.1 Sample the material in accordance with Practice E 300.

¹ This specification is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.35 on Solvents, Plasticizers, and Chemical Intermediates.

Current edition approved July 10, 1997. Published September 1997. Originally published as D 2190 – 63 T. Last previous edition D 2190 – 89 (1993)^{ε1}.

² Annual Book of ASTM Standards, Vol 06.04.

³ Annual Book of ASTM Standards, Vol 05.02.

⁴ Annual Book of ASTM Standards, Vol 14.03.

⁵ Annual Book of ASTM Standards, Vol 15.05.

⁶ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094.

4. Properties

4.1 The vinyl acetate shall conform to the following requirements:

Distillation range, °C	71.8 to 73.0
Apparent specific gravity, 20/20°C	0.9335 to 0.9345
Color (HQ grade only), Pt-Co scale, max	5
Water content, weight %, max	0.05
Acetaldehyde content, weight %, max	0.02
Acidity, as acetic acid, weight %, max	0.005
Inhibitor content (HQ)	A

^A As agreed upon between the purchaser and the manufacturer.

5. Test Methods

5.1 The properties enumerated in this specification shall be determined in accordance with the following ASTM methods:

5.1.1 *Apparent Specific Gravity*—Determine the apparent specific gravity by any convenient method that is accurate to the fourth decimal place, the temperature of both specimen and water being 20°C. (See Guide D 268 or Test Method D 4052.)

5.1.2 *Color*—Test Method D 1209.

5.1.3 *Distillation Range*—Test Method D 1078, using an ASTM Solvents Distillation Thermometer 39C having a range from 48 to 102°C, and conforming to the requirements in Specification E 1.

5.1.4 *Water*—Test Method D 1364.

5.1.5 *Acetaldehyde*—Test Method D 2191.

5.1.6 *Acidity*—Test Method D 2086.

5.1.7 *Inhibitor Content*—Test Method D 2193.

6. Packaging and Package Marking

6.1 Package size shall be agreed upon between the purchaser and the supplier.

6.2 Packaging shall conform to applicable carrier rules and regulations or, when specified, shall conform to Fed. Spec. PPP-C-2020.

7. Keywords

7.1 vinyl acetate

 **D 2190**

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).