



Designation: **D 4153 – 95a01**

Standard Performance Specification for Men’s, Women’s, and Children’s Woven Handkerchief Fabrics¹

This standard is issued under the fixed designation D 4153; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This performance specification covers woven fabrics to be used in the manufacture of men’s, women’s, and children’s handkerchiefs, both utilitarian and decorative.

1.2 This performance specification is not applicable to open-work fabrics such as lace which is used primarily to decorate handkerchiefs, or woven fabrics used for the manufacture of scarves.

1.3 These requirements apply to both the length and width directions for those properties where fabric direction is pertinent.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*

¹ This performance specification is under the jurisdiction of ASTM Committee D-13 on Textiles and is the direct responsibility of Subcommittee D13.561 on Performance Standards for Textile Fabrics—Apparel.

Current edition approved Dec. 10, 1995; 2001. Published May 1996; July 2001. Originally published as D 4153 – 82. Last previous edition D 4153 – 95a.

D 123 Terminology Relating to Textiles²

D 1424 Test Method for Tear-Resistance Strength of Woven Fabrics By Falling-Pendulum Type (Elmendorf) Apparatus²

D 2261 Test Method for Tearing Strength of Woven Fabrics by the Tongue (Single Rip) ~~Method~~ Procedure (Constant-Rate-of-Extension Tensile Testing Machine)²

D 2262 Test Method for Tearing Strength of Woven Fabrics by the Tongue (Single Rip) Method (Constant-Rate-of-Traverse Tensile Testing Machine)³

D 2905 Practice for Statements on Number of Specimens for Textiles²

D 5034 Test Method for Breaking-Force Strength and Elongation of Textile Fabrics (Grab Test)⁴

2.2 *AATCC Test Methods*:⁵

8 Colorfastness to Crocking: AATCC Crockmeter Method

15 Colorfastness to Perspiration

16 Colorfastness to Light

23 Colorfastness to Burnt Gas Fumes

61 Colorfastness to Washing, Domestic, and Laundering, Commercial: Accelerated

96 Dimensional Changes in Laundering of Woven and Knitted Textiles Except Wool

116 Colorfastness to Crocking: Rotary Vertical Crockmeter Method

124 Appearance of Durable Press Fabrics after Repeated Home Launderings

135 Dimensional Changes in Automatic Home Laundering of Woven or Knit Fabrics

172 Colorfastness to Non-chlorine Bleach in Home Laundering

188 Colorfastness to Chlorine Bleach in Home Laundering

2.3 *Federal Standard*:

16CFR—Code of Federal Regulations, Chapter II—Consumer Product Safety Commission, Subchapter D—Flammable Fabrics Act Regulations⁶

2.4 *Military Standard*:

MIL-STD—105 Sampling Procedures and Tables for Inspection by Attributes⁷

NOTE 1—Reference to test methods in this performance specification give only the permanent part of the designation of ASTM, AATCC, or other test methods. The current editions of each test method cited shall prevail.

3. Terminology

3.1 *Definitions*:

3.1.1 For definitions of textile terms used in this specification, refer to the individual ASTM and AATCC test methods and to Terminology D 123. Definitions found in a dictionary of common terms are suitable for terms used in this performance specification.

4. Specification Requirements

4.1 The properties of woven fabric for men's, women's, and children's handkerchiefs shall conform to the specification requirements in Table 1.

5. Significance and Use

5.1 Upon mutual agreement between the purchaser and the supplier, fabrics intended for this end use should meet all of the requirements listed in Table 1 of this specification.

5.2 It is recognized that for purposes of fashion or aesthetics the ultimate consumer of articles made from these fabrics may find acceptable fabrics that do not conform to all of the requirements in Table 1. Therefore, one or more of the requirements listed in Table 1 may be modified by mutual agreement between the purchaser and the supplier.

5.2.1 In such cases, any references to the specification shall specify that: "This fabric meets ASTM Specification D 4153 except for the following characteristic(s)."

5.3 Where no prepurchase agreement has been reached between the purchaser and the supplier, and in case of controversy, the requirements listed in Table 1 are intended to be used as a guide only. As noted in 5.2, ultimate consumer demands dictate varying performance parameters for any particular style of fabric.

² *Annual Book of ASTM Standards*, Vol 07.01.

³ Discontinued; see *1994 Annual Book of ASTM Standards*, Vol 07.021.

⁴ AATCC Technical Manual, available from the American Association

⁴ *Annual Book of Textile Chemists and Colorists*, PO Box 12215, Research Triangle Park, NC 27709; *ASTM Standards*, Vol 07.02.

⁵ AATCC Technical Manual, available from Superintendent the American Association of Documents, Government Printing Office, Washington, DC 20402; *Textile Chemists and Colorists*, PO Box 12215, Research Triangle Park, NC 27709.

⁶ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS; Superintendent of Documents, Government Printing Office, Washington, DC 20402.

⁷ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

TABLE 1 Specification Requirements

NOTE 1—The classes of colorfastness and DP rating are based on a numerical scale of 5 for negligible or no color change, color transfer, or wrinkle to 1 for very severe color change, color transfer, or wrinkle.

Characteristic	Requirements	Section
Breaking strength (load) (CRT) ^A	80 N (18 lbf), min	7.1
Tongue tear strength ^A	4.5 N (1 lbf)	7.2
Dimensional change:		
After 5 launderings	50 % max	7.3
Colorfastness to:		
Laundering:		7.4.1
Shade change	Class 4 ^B min	
Staining	Class 3 ^C min	
Burnt gas fumes:	Class 4 ^B min	7.4.2
Alteration in shade: 1 cycle on original and after 1 washing	Class 4 ^B min	7.4.2
Crocking:		7.4.3
Dry	Class 4 ^D min	
Wet	Class 3 ^D min	
Perspiration:		7.4.4
Shade change	Class 4 ^B min	
Staining	Class 3 ^C min	
Light (xenon arc) ^A		7.4.5
20 AATCC Fading units	Step 4 ^B min	
Chlorine Bleach	Class 4 ^B , min	7.4.6
Non-chlorine Bleach	Class 4 ^B , min	7.4.7
Fabric appearance (see 7.5.1.1)	DP 3.5 ^E min	7.5
Flammability	pass	7.6

^A More than one method can be used to measure these properties. These methods cannot be used interchangeably since there can be no overall correlation between them (see Note 2, Note 3, and Note 5).

^B AATCC Gray Scale for Color Change.

^C AATCC Gray Scale for Staining.

^D AATCC Chromatic Transference Scale.

^E For durable press fabrics only.

5.4 The uses and significance of particular properties and test methods are discussed in the appropriate sections of the specified test methods.

6. Sampling

6.1 *Lot Sample*—As a lot sample for acceptance testing, take at random the number of rolls as directed in an applicable specification or other agreement between the purchaser and the seller, such as an agreement to use MIL-STD-105.

6.2 *Laboratory Sample*—From each roll or piece in the lot sample, cut two laboratory samples the full width of the fabric, and at least 375 mm (15 in.) along the selvage.

6.2.1 If there has been no prior agreement and the test method does not specify the number of specimens, use the procedures in Practice D 2905 to determine the number of specimens, such that the user may expect at the 95% probability level that the test result is no more than 5% of the average above or below the lot average (that is, the average that would be obtained by applying this method to the entire lot) when using a reliable estimate of variability of individual observations on similar materials in the user's laboratory under conditions of single-operator precision.

7. Test Methods (see Note 1)

7.1 *Breaking Force*—Determine the dry breaking force, in the standard atmosphere for testing textiles, as directed in Test Method D 5034, using a constant rate of traverse (CRT) tensile testing machine with the speed of the pulling clamp at 300 ± 10 mm (12 ± 0.5 in.)/min.

NOTE 2—If preferred, the use of a constant-rate-of-extension (CRE) testing machine is permitted. The crosshead speed should be as agreed upon between the purchaser and the supplier. There may be no overall correlation between the results obtained with the CRT machine and the CRE machine. Consequently, these two breaking load testers cannot be used interchangeably. In case of controversy, the CRT machine shall prevail.

7.2 *Tear Strength*—Determine the tear strength as directed in Test Method D 2262.

NOTE 3—If preferred, the use of Test Method D 1424 or Test Method D 2261 is permitted with existing requirements as given in this performance specification. There may be no overall correlation between the results obtained with the tongue tear machines and the Elmendorf machine. Consequently, these three testers cannot be used interchangeably. In case of controversy, Test Method D 2262 shall prevail.

7.3 *Dimensional Change in Laundering*—Determine the maximum dimensional change after five launderings, or as agreed upon between the purchaser and the supplier, as directed in the applicable procedure in AATCC Test Method 135.

7.4 *Colorfastness*:

7.4.1 *Laundering*—Determine the colorfastness to laundering as directed in AATCC Test Method 61. The test conditions shall be as specified by the supplier.

7.4.2 *Burnt Gas Fumes*—Determine the colorfastness to burnt gas fumes on the original fabric and after one laundering as directed in AATCC Test Method 23.

NOTE 4—Washing conditions shall be the same as those used in 7.3.

7.4.3 *Crocking*—Determine the colorfastness to dry and wet crocking as directed in AATCC Test Method 8 for solid shades and AATCC Test Method 116 for prints or as agreed upon between the purchaser and the supplier.

7.4.4 *Perspiration*—Determine the colorfastness to perspiration as directed in AATCC Test Method 15.

7.4.5 *Light*—Determine the colorfastness to light as directed in AATCC Test Method 16.

NOTE 5—There are distinct differences in spectral distribution between the various types of machines listed in AATCC Test Method 16, with no overall correlations between them. Consequently, these machines cannot be used interchangeably. In case of controversy, results obtained with the water cooled xenon arc machine listed in Option E shall prevail.

7.4.6 *Colorfastness to Chlorine Bleach*—Determine colorfastness to light as directed in AATCC Test Method 16.

7.4.7 *Colorfastness to Non-chlorine Bleach*—Determine colorfastness to light as directed in AATCC Test Method 16.

7.5 *Fabric Appearance After Repeated Home Launderings*—Determine the fabric appearance as directed in AATCC Test Method 124 after laundering using the wash-and-wear cycle or the normal cycle as agreed upon between the purchaser and the supplier as specified in 7.3 for washable fabrics.

7.5.1 For fabrics not intended for use in “Durable Press” products, determine the fabric smoothness after pressing as specified in Section 5.12 of AATCC Test Method 96.

7.5.1.1 The fabric smoothness, or durable press (DP) rating of such fabrics shall have decreased no more than ½ durable press rating from that of the fabric before it is laundered.

7.6 *Flammability*—The flammability requirements shall be as agreed upon between the purchaser and the supplier, provided they met or exceed those of 16CFR–Part 1610 of the Flammable Fabrics Act Regulations.

8. Keywords

8.1 fabric; handkerchief; performance; specification; woven fabric

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).