



Standard Terminology Relating to Tire Cord, Bead Wire, Hose Reinforcing Wire, and Fabrics¹

This standard is issued under the fixed designation D 6477; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This terminology is the compilation of all definitions developed by Subcommittee D13.19 on Tire Cords and Fabrics.

1.2 The terminology, mostly definitions, is unique to the tire cord fabric industry. Meanings of the same terms used outside the tire cord fabric industry can be found in other compilations or in dictionaries of general usage.

1.3 In addition to being a specialized dictionary, this terminology is also a tool for managing the Subcommittee's terminology. This includes finding, eliminating, and preventing redundancies, that is, where two or more terms relating to the same concept are defined in different words.

2. Referenced Documents

2.1 ASTM Standards:

- D 123 Terminology Relating to Textiles²
- D 885 Test Methods for Tire Cords, Tire Cord Fabrics, and Industrial Filament Yarns Made from Manufactured Organic-Base Fibers²
- D 1871 Test Methods for Adhesion of Single-Filament Steel Wire to Rubber²
- D 2229 Test Method for Adhesion Between Steel Tire Cords and Rubber²
- D 2692 Test Method for Air Wicking of Tire Fabrics, Tire Cord Fabrics, Tire Cord, and Yarns²
- D 2969 Test Methods for Steel Tire Cords²
- D 2970 Test Methods for Tire Cords, Tire Cord Fabrics, and Industrial Yarns Made from Glass Filaments²
- D 4393 Test Method for Strap Peel Adhesion of Reinforcing Cords or Fabrics to Rubber Compounds³
- D 4776 Test Method for Adhesion of Tire Cords and Other Reinforcing Cords to Rubber Compounds by H-Test Procedure³
- D 4974 Test Method for Hot Air Thermal Shrinkage of Yarn and Cord Using a Thermal Shrinkage Oven³
- D 4975 Test Methods for Single-Filament Tire Bead Wire Made from Steel³

D 5591 Test Method for Thermal Shrinkage Force of Yarn and Cord with the Testrite Thermal Shrinkage Force Tester³

D 6320 Test Methods for Single Filament Hose Reinforcing Wire Made from Steel³

3. Terminology

adhesion, *n*—the property denoting the ability of a material to resist delamination or separation into two or more layers.

D 1871, D 4393, D 4776

adhesion, *n*—*in tire fabrics*, the force required to separate a textile material from rubber or other elastomer by a definite prescribed method.

D 2229, D 4393, D 4776

adhesive treated tire cord, *n*—a tire cord whose adhesion to rubber or other elastomer has been improved by the application of a dip followed by rapid drying and (normally) additional heat treatment.

D 5591

air wicking, *n*—*in tires*, the passage of air longitudinally along or through yarns in a fabric that has been encased and cured in rubber or other elastomer, that is, air permeability in the plane of the fabric.

D 2692

breaking force, *n*—the maximum force applied to a material carried to rupture.

DISCUSSION—Materials that are brittle usually rupture at the maximum force. Materials that are ductile are usually capable of withstanding the maximum force without rupturing. For many years, it has been the usual practice in the tire industry and related industries to use the term *breaking strength* to characterize yarn and cord of a specified size and type without consideration of their unit size. Numerically, *breaking strength* is equal to breaking force for the same specimen. The average of the breaking forces observed on two or more specimens of a specific sample is referred to as the sample breaking strength, which is the property used in engineering calculations for a specific textile material. *Tensile strength* and *breaking tenacity* are derived or calculated values for materials that include consideration of the unit size of the materials. These terms can be used to compare intrinsic strengths of yarns and cords of different sizes or different materials. The term *tensile strength*, in MPA (psi), is not synonymous with either *breaking force* or *breaking strength*, in N (lbf), or breaking tenacity, in mN/tex (gt/den).

breaking strength, *n*—a strength expressed in terms of breaking force.

DISCUSSION—Breaking strength is particularly significant as the characteristic of a sample as distinct from a specimen, and is usually expressed as newtons (N) or pounds-force (lbf). See discussion for *breaking force*.

¹ This terminology is under the jurisdiction of ASTM Committee D13 on Textiles and is the direct responsibility of Subcommittee D13.19 on Tire Cord and Fabrics.

Current edition approved May 10, 2003. Published June 2003. Originally approved in 1999. Last previous edition approved in 2002 as D 6477–02a.

² *Annual Book of ASTM Standards*, Vol 07.01.

³ *Annual Book of ASTM Standards*, Vol 07.02.

breaking tenacity, *n*—the tenacity at the breaking force.

DISCUSSION—See discussion for *breaking force*.

catenary length, *n*—the difference between the length of the shortest and the longest component in a plied yarn or cables cord after twisting. **D 2970**

chafer fabric, *n*—woven fabric, usually coated with unvulcanized rubber, which is laid around the bead of a tire before vulcanization.

DISCUSSION—Chafer fabric is used to reinforce the outer layer of rubber on the tire bead to provide an abrasion resistant surface in contact with the wheel rim. In the case of tubeless tires, the chafer fabric is usually made wickproof to prevent air leaking from the inflated tire. **D 2692, D 4393**

cord, *n*—a twisted or formed structure composed of one or more single or plied filaments, strands, or yarns of organic polymer or inorganic materials.

DISCUSSION—Cord, as used in these test methods, is used for the manufacture of pneumatic tires or other industrial fabrics. The direction of twist used to combine the single or plied yarn elements into a cord construction is in the direction opposite to that used in the yarns. Frequently, tire and other reinforcing cords consist of a single yarn strand having little or no twist. These cords as well as single monofilaments, are used synonymously with twisted and plied cords in this test method. **D 885, D 4776, D 5591**

cord twist, *n*—the number of turns per unit length in a cord made from two or more single or plied yarns.

cord twist, *n*—the amount of twist in a cord made from two or more single or plied yarns.

DISCUSSION—Cord twist is based on the initial length of a cord specimen. Cord twist is expressed as the number of turns divided by the length of the untwisted cord. **D 885, D 2970**

core, *n*—a filament or strand that serves as an extended axis about which other elements can be wound. **D 2969**

curing, *n*—see the preferred term **vulcanization**. **D 1871, D 4393, D 4776**

dip, *n*—a chemical composition that is applied to a textile cord or fabric to improve its adhesion to rubber or other elastomer. **D 885, D 2970**

dip pick-up, *n*—the amount of dip or dip components present in a textile cord or fabric after processing, expressed as a percentage of the mass of the oven-dried dip-free material. **D 2970**

direction of lay, *n*—the helical disposition of the components of a strand or cord.

DISCUSSION—The strand or cord has an “S” or left hand lay if, when held vertically, the spirals around the central axis of the strand or cord conform in the direction of slope to the central portion of the letter “S”; and “Z”, or righthand lay, if the spirals conform in direction of slope to the central portion of the letter “Z”. **D 2969**

direction of twist, *n*—see **direction of lay**. **D 2969**

elongation, *n*—the ratio of the extension of a material to the length of the material prior to stretching.

DISCUSSION—Elongation may be measured at any specified force or at rupture.

fabric, *n*—*in textiles*, a planar structure consisting of yarns or fibers.

DISCUSSION—In tire cord, fabrics are produced with tire cord warp yarns interlaced with widely spaced filling yarns.

fabric dip, *n*—for *tire fabrics*, a chemical composition which is applied to a textile cord or fabric to improve its adhesion to rubber compounds. **D 4393**

flare, *n*—the spreading of the filament ends or the strand ends at the cut end of a steel tire cord, expressed as the unraveled length. **D 2969**

greige cord, *n*—*in tire cords*, a cord that has not been adhesive treated, heat treated, or otherwise treated before use (see *cord*). **D 4974, D 5591**

greige tire cord, *n*—a tire cord that has not been dip treated or heat treated before use (see *tire cord*). **D 5591**

growth, *n*—the increase one or more dimensions of an object or a material.

DISCUSSION—The increase in length of a specimen caused by the application of a continuing load or force under specified conditions.

high elongation, *adj*—*in steel tire cord*, a cord with an average elongation at break greater than 3.0 %. **D 2969**

holland cloth, *n*—a completely filled woven fabric having a smooth gloss finish on both sides used as a separating medium for sheeted rubber compounds. **D 1871, D 4393**

hose reinforcing wire, *n*—a single filament of steel wire with a metallic coating (usually brass) used in the reinforcement of a rubber or other elastomer hose. **D 1871, D 6320**

H-test adhesion, *n*—the force to extract either end of a textile cord structure that is embedded in a rubber compound under specified conditions.

industrial yarn, *n*—a yarn composed of continuous filaments, usually of high breaking tenacity, produced with or without twist, and intended for applications in which functional properties are of primary importance; for example, in reinforcing material in elastomeric products (tires, hose, belting), in protective coverings, and in cordage and webbing, and so forth.

DISCUSSION—For example, in reinforcing material in elastomeric products (tire, hose, belting), in protective coverings, and in cordage and webbing, and so forth. **D 885, D 2970, D 4776**

initial modulus, *n*—the slope of the initial straight portion of a stress-strain (or force elongation) curve.

DISCUSSION—Modulus is the ratio of the change in tenacity, expressed in millinewtons per tex (mN/tex) or grams-force per denier (gf/den) to the change in strain, expressed as a fraction of the original length. In the case of a tenacity elongation curve, the following equation is used to calculate the initial modulus: $initial\ modulus = (tenacity/percent\ elongation) \times 100$ **D 885, D 2970**

length of lay, *n*—the axial distance required to make one complete revolution of any element of a strand or cord. **D 2969**

mill grain, *n*—*in rubber*, grain which is imparted to rubber sheeting while being mixed or conditioned in a rubber mill and which is parallel to the direction the rubber moves in the

mill. **D 1871**
moisture equilibrium for testing, *n*—for industrial yarns and tire cords, the condition reached when, after free exposure to a test atmosphere which is in motion, two successive weighings not less than 4 h apart, show not more than 0.1 % progressive change in mass of the specimen or sample. **D 885**

percent elongation, *n*—the increase in length of a specimen expressed as a percentage of the original length. **D 4975**

pneumatic tire, *n*—a hollow tire that becomes load-bearing upon inflation with air, or other gas, to a pressure above atmospheric. **D 885, D 5591**

reinforcing cord, *n*—a cord made from industrial yarns and used to provide added support to other materials, such as tires, hose, belting, protective coverings, webbings, and so forth. **D 4776**

residual torsion, *n*—revolutions made by a specified length of cord when one end is held in a fixed position and the other allowed to turn freely. **D 2969**

retraction, *n*—in yarns and cords, the reduction in length when previous restraint is removed and relaxation is allowed, thus causing a directionally proportional increase in linear density. **D 5591**

rubber, *n*—a material that is capable of recovering from large deformations quickly and forcibly, and can be, or already is, modified to a state in which it is essentially insoluble (but can swell) in boiling solvent, such as benzene, methylethyl ketone, and ethanol-toluene azeotrope. **D 1871, D 4393, D 4776**

rubber compound, *n*—as used in the manufacture of rubber articles, an intimate mixture of elastomer(s) with all the materials necessary for the finished article. **D 1871, D 2229, D 4393, D 4776**

rubberize, *v*—to impregnate or coat with rubber compound, or both. **D 4393**

single twist, *n*—the amount of twist in each individual single yarn element in a tire cord structure based on the length of the element after twist has been removed from the cord. **D 885**

standard atmosphere for testing textiles, *n*—laboratory conditions for testing fibers, yarns, and fabrics in which air and relative humidity are maintained at specific levels with established tolerances.

DISCUSSION—Air is maintained at a relative humidity of $55 \pm 2\%$ and at a temperature of $24 \pm 1^\circ\text{C}$ ($75 \pm 2^\circ\text{F}$) for this test method.

steel cord, *n*—a formed structure made of two or more steel filaments when used as an end product or a combination of strands or filaments and strands. **D 2229, D 2969, D 4393**

steel cord wrap, *n*—a steel filament wound helically around a steel cord. **D 2969**

steel filament, *n*—the individual element in a steel strand or cord. **D 2969**

steel strand, *n*—a group of steel filaments combined to form a unit product to be processed further.

DISCUSSION—A strand may be considered a cord if it is the finished product for tire reinforcement or it may be an element in a more

complex structure.

D 2969

stitch, *v*—in making rubberized articles, to press uncured rubber compound into or around yarns or cords to form a composite of the materials and to remove entrapped air.

DISCUSSION—Normally the yarns or cords in the article are parallel. The stitching tool is normally a rolling disk mounted on an axle for manipulation by hand or by machine. The outer edge of the disk is unsharpened but narrower than the intended space between parallel cords. Application of moderate force on this tool accomplishes high local pressure on the surface to which it is applied. **D 4393**

straightness, *n*—in steel cord, the property of a cord characterized by a lack of deviation from its central axis over short lengths of cord. **D 2969**

tabby, *n*—a plain weave fabric. In the context of tire cord fabric, it refers to sections of closely spaced weft yarns in a special section of fabric woven to provide as sample.

tabby sample, *n*—the section of tire cord fabric between two tabbies that have been woven separately with a distance of 0.5 to 1.0 m (18 to 36 in.) between them.

DISCUSSION—A tabby usually is woven 150 to 200 mm (6 to 8 in) in length using cotton filling yarn in the range from 750 to 2000 tex (675 to 1800 denier) and 30 to 50 picks/dm (8 to 12 picks/in). **D 885, D 2970**

tack, *n*—for rubber or rubber compounds, a property that causes two layers of these materials when pressed together to adhere at the area of contact. **D 4393**

test panel, *n*—for in air wicking tests, the composite structure of a rubber compound and fabric which is used to test the fabric for air wicking.

thermal shrinkage, *n*—of textile yarn and cords, contraction in length caused by heat. **D 4974**

thermal shrinkage force, *n*—that force induced when a restrained material is restricted from shrinking upon exposure to heat. **D 5591**

thermal shrinkage force tester, *n*—an apparatus that measures the force achieved when a yarn or similar specimen, held at a constant (fixed) length, is subjected to a temperature above that at which the specimen was mounted in the apparatus. **D 5591**

tire, *n*—a load-bearing ground-contacting circumferential attachment to a vehicle wheel. **D 885, D 5591**

tire bead, *n*—the part of a tire that comes in contact with the rim and is shaped to secure the tire to the rim. **D 1871, D 4975**

tire bead wire, *n*—a monofilament of steel wire with a metallic coating, usually bronze, used in the forming of a tire bead. **D 1871, D 4975**

tire cord, *n*—a twisted or formed structure composed of one or more single or plied filaments, strands, or yarns of organic polymer or inorganic material.

DISCUSSION—The direction of twist used to combine the single or plied yarn elements into a cord structure is in a direction opposite to that used in the yarn. Frequently, tire and other reinforcing cords consist of a single yarn strand having little or no twist. These cords are used synonymously with twisted and plied cords in this test method.

D 2692, D 2970, D 4393, D 4974

tire cord fabric, *n*—a fabric consisting of tire cord warp with widely spaced (usually 40 to 200 picks/m (1 to 5 picks/in.)) single yarn filling. **D 885, D 2692, D 2970, D 4393**

tire fabric, *n*—a textile fabric, other than tire cord fabric, which is used as a reinforcement in tires. **D 2692**

torsion resistance, *n*—*in tire bead wire*, the number of turns of twist in a short length of wire that causes rupture. **D 4975, D 6320**

vulcanization, *n*—an irreversible process, usually accomplished through the application of heat, during which a rubber compound, through a change in its chemical structure (for example, cross linking) becomes less plastic and more resistant to swelling by organic liquids while elastic properties are conferred, improved, or extended over a greater range of temperatures.

DISCUSSION—Although *vulcanization* is preferred to *curing*, the terms *cured* and *uncured* are widely used as synonyms for *vulcanized* and *unvulcanized*. **D 1871, D 2692, D 4393, D 4776**

weftless fabric, *n*—*as used in tire building*, a sheet of parallel cords surrounded by uncured rubber compound.

DISCUSSION—Fabric stability, sufficient to ensure that fabric can be moved and handled, is imparted by the unvulcanized rubber rather than by textile yarns (wefts or picks) as in woven tire cord fabric. **D 4393**

wickproof, *adj*— *in tire fabric, tire cord fabric, tire cord, or yarn*, a term used to describe a fabric or yarn that shows no air wicking by this prescribed test.

wildness, *n*—obsolete term, previously used to describe a number of steel tire cord properties including flare, straightness, and residual torsion. **D 2969**

work-to-break, *n*—the total energy required to rupture a specimen to the breaking force during a tensile test.

DISCUSSION—Work-to-break is proportional to the area under the stress-strain curve from the origin to the breaking force. **D 885**

yield strength, *n*—the stress at which a material exhibits a specified limiting deviation from the proportionality of stress to strain.

DISCUSSION—It is customary in this instance to express the deviation in terms of strain and to determine yield strength by the offset method where a strain of 0.2% is specified. **D 4975, D 6320**

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).