



Designation: D 1248 – 00a

Standard Specification for Polyethylene Plastics Extrusion Materials for Wire and Cable¹

This standard is issued under the fixed designation D 1248; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope *

1.1 This specification provides for the identification of polyethylene plastics extrusion materials for wire and cable in such a manner that the seller and the purchaser can agree on the acceptability of different commercial lots or shipments. The tests involved in this specification are intended to provide information for identifying materials according to the types, classes, categories, and grades covered. It is not the function of this specification to provide specific engineering data for design purposes.

1.2 This specification does not allow for the use of recycled plastics (see Note 3).

1.3 The values stated in SI units are to be regarded as the standard.

1.4 The following safety hazards caveat pertains only to the test method portion, Section 11, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—No ISO equivalent.

NOTE 2—This standard has undergone major revision from the reapproval of 1989 and now covers only polyethylene for wire and cable applications. For information regarding molding and extrusion materials, see Specification D 4976. For information regarding plastic pipe materials, see Specification D 3350.

NOTE 3—See Guide D 5033 for information and definitions related to recycled plastics.

2. Referenced Documents

2.1 ASTM Standards:

- D 150 Test Methods for A-C Loss Characteristics and Permittivity (Dielectric Constant) of Solid Electrical Insulating Materials²
- D 257 Test Methods for D-C Resistance or Conductance of Insulating Materials²
- D 470 Test Methods for Crosslinked Insulations and Jackets

- for Wire and Cable²
- D 618 Practice for Conditioning Plastics and Electrical Insulating Materials for Testing³
- D 638 Test Method for Tensile Properties of Plastics³
- D 746 Test Method for Brittleness Temperature of Plastics and Elastomers by Impact³
- D 792 Test Methods for Specific Gravity (Relative Density) and Density of Plastics by Displacement³
- D 1238 Test Method for Flow Rates of Thermoplastics by Extrusion Plastometer³
- D 1505 Test Method for Density of Plastics by the Density-Gradient Technique³
- D 1531 Test Method for Relative Permittivity (Dielectric Constant) and Dissipation Factor of Polyethylene by Liquid Displacement Procedure²
- D 1603 Test Method for Carbon Black in Olefin Plastics³
- D 1693 Test Method for Environmental Stress-Cracking of Ethylene Plastics³
- D 1898 Practice for Sampling of Plastics³
- D 1928 Practice for Preparation of Compression-Molded Test Sheets and Test Specimens³
- D 2565 Practice for Operating Xenon-Arc Type Light Exposure Apparatus With and Without Water for Exposure of Plastics⁴
- D 2633 Test Methods for Thermoplastic Insulations and Jackets for Wire and Cable⁵
- D 2839 Test Method for Use of a Melt Strand for Determining Density of Polyethylene⁴
- D 2951 Test Method for Resistance of Types III and IV Polyethylene Plastics to Thermal Stress-Cracking⁴
- D 3182 Practice for Rubber-Materials, Equipment, and Procedures for Mixing Standard Compounds and Preparing Standard Vulcanized Sheets⁶
- D 3349 Test Method for Absorption Coefficient of Carbon Black Pigmented Ethylene Plastic Film⁵
- D 3350 Specification for Polyethylene Plastics Pipe and Fittings Materials⁴
- D 3636 Practice for Sampling and Judging Quality of Solid Electrical Insulating Materials⁵
- D 3892 Practice for Packaging/Packing of Plastics⁴

¹ This specification is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.15 on Thermoplastic Materials.

Current edition approved Nov. 10, 2000. Published January 2001. Originally published as D 1248 – 52. Last previous edition D 1248 – 00.

² Annual Book of ASTM Standards, Vol 10.01.

³ Annual Book of ASTM Standards, Vol 08.01.

⁴ Annual Book of ASTM Standards, Vol 08.02.

⁵ Annual Book of ASTM Standards, Vol 10.02.

⁶ Annual Book of ASTM Standards, Vol 09.01.

*A Summary of Changes section appears at the end of this standard.

D 4329 Practice for Operating Light and Water Apparatus (Fluorescent UV Condensation Type) for Exposure of Plastics⁷

D 4976 Specification for Polyethylene Plastics Molding and Extrusion Materials⁷

D 5033 Guide for the Development of Standards Relating to the Proper Use of Recycled Plastics⁷

E 1131 Test Method for Compositional Analysis by Thermogravimetry⁸

G 53 Practice for Operating Light- and Water-Exposure Apparatus (Fluorescent UV-Condensation Type) for Exposure of Nonmetallic Materials⁸

G 151 Practice for Exposing Nonmetallic Materials in Accelerated Test Devices That Use Laboratory Light Sources⁸

G 153 Practice for Operating Enclosed Carbon-Arc Light Apparatus for Exposure of Nonmetallic Materials⁸

G 154 Practice for Operating Fluorescent Light Apparatus for UV Exposure of Nonmetallic Materials⁸

G 155 Practice for Operating Xenon Arc Light Apparatus for Exposure of Nonmetallic Materials⁸

2.2 Federal Specification:⁹

L-L-390 Plastic, Molding, and Extrusion Materials, Polyethylene and Copolymers (Low, Medium, and High Density)

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *polyethylene plastics, n*—plastics or resins prepared by the polymerization of no less than 50 % ethylene and no less than 95 weight % of total olefins.

3.2 Historical usage and user group conventions have resulted in inconsistent terminology used to categorize and describe polyethylene resins and compounds. The following terminology is in use in ASTM specifications pertaining to polyethylene:

3.2.1 Specification D 1248:

3.2.1.1 Type (0, I, II, III, IV) = density ranges (same, respectively, as Class in Specification D 4976).

3.2.1.2 Class (A, B, C, D) = composition and use.

3.2.1.3 Category (1, 2, 3, 4, 5) = melt index ranges (same as Grade in Specification D 4976).

3.2.1.4 Grade (E, J, D, or W followed by one or two digits) = specific requirements from tables.

3.2.2 Specification D 3350:

3.2.2.1 Type (I, II, III) = density ranges (same as Types I, II, and III in Specification D 1248 and Classes 1, 2, and 3 in Specification D 4976).

3.2.2.2 Class = a line callout system consisting of “PE” followed by six cell numbers from Table 1 plus a letter (A, B, C, D, E) denoting color and UV stabilizer.

3.2.2.3 Grade = simplified line callout system using “PE” followed by density and slow crack growth cell numbers from Table 1.

⁷ Annual Book of ASTM Standards, Vol 08.03.

⁸ Annual Book of ASTM Standards, Vol 14.02.

⁹ Available from Naval Publications and Forms Center, 5801 Tabor Ave., Philadelphia, PA 19120.

3.2.3 Specification D 4976:

3.2.3.1 Group (1, 2) = branched or linear polyethylene.

3.2.3.2 Class (5, 1, 2, 3, 4) = density ranges (same, respectively, as Type in Specification D 1248).

3.2.3.3 Grade (1, 2, 3, 4, 5) = melt index ranges (same as Category in Specification D 1248).

4. Classification

4.1 This specification recognizes that polyethylene plastics are identified primarily on the basis of two characteristics, namely, density and flow rate (previously identified as melt index). The former is the criterion for assignment as to type, the latter for designation as to category. Other attributes important to the user for certain applications are covered by three general classes and by specifying in greater detail, by grades, a minimum number of key characteristics covered too broadly or not at all by the type, class, and category designations.

4.1.1 Types:

4.1.1.1 This specification provides for the identification of five types of polyethylene plastics extrusion materials for wire and cable by density in accordance with 10.1 and 11.1.3 and the requirements prescribed in Table 1 and Note 4, Note 5, and Note 10.

NOTE 4—It is recognized that some high-density polyethylene plastics of very high molecular weight may have densities slightly less than 0.960 yet in all other respects they are characteristic of Type IV materials. Similarly, there are other polyethylene plastics of very high molecular weight having densities slightly less than 0.941 which in all other respects are more characteristic of Type III than of Type II materials.

NOTE 5—While the original Type III now has been divided into two ranges of density (Types III and IV), both are still described by the term *high density*.

4.1.1.2 Material supplied under these types shall be of such nominal density, within the ranges given, as agreed upon between the manufacturer and the purchaser subject to the tolerances specified in 4.1.1.3 (Note 10).

4.1.1.3 In view of production, sampling, and testing variables, a commercial lot or shipment for which a nominal density has been agreed upon between the seller and the purchaser shall be considered as conforming and commercially acceptable when the density value found on a sample from the lot or shipment falls within the tolerance range of ± 0.004 of the nominal value.

4.1.1.4 If the nominal value is unknown or unspecified, classification shall be based on the tested value without tolerance consideration.

4.1.2 *Classes*—Each of the five types is subdivided into four classes according to composition and use as follows:

4.1.2.1 *Class A*—Natural color only, without any or with

TABLE 1 Classification of Polyethylene Plastics Extrusion Materials for Wire and Cable According to Type

Type	Nominal Density, ^A g/cm ³
0	<0.910
I	0.910 to 0.925
II	>0.925 to 0.940
III	>0.940 to 0.960
IV	>0.960

^AUncolored, unfilled material (see Note 10).

such antioxidant or other additives in such proportions as agreed upon between the seller and the purchaser.

4.1.2.2 *Class B*—Colors including white and black, without any or with such antioxidant or other additives in such proportions as agreed upon between the manufacturer and the purchaser.

4.1.2.3 *Class C*—Black (weather-resistant), containing not less than 2 % carbon black of a kind and particle size (Note 6), dispersed by such means and to such degree, all as may be agreed upon between the seller and the purchaser; without any or with such antioxidant or other additives in such proportions as agreed upon between the seller and the purchaser.

NOTE 6—Carbon black 35 mm or less in average particle diameter is used as required in black electrical and jacketing materials (Grades E and J) to impart maximum weather resistance.

4.1.2.4 *Class D*—Colored (UV resistant), including black and white, with antioxidant and UV stabilizers to allow electrical insulation and jackets to meet the requirements outlined in 11.1.14. (**Warning**—The expected service lifetime of Class D materials is very dependent upon the specific material formulation including selected colorants. Contact your supplier for additional information regarding this issue.)

4.1.3 *Categories:*

4.1.3.1 The four classes of each type are divided into five categories on the basis of broad ranges of flow rate in accordance with the requirements prescribed in Table 2.

NOTE 7—Some Type II and Type III polyethylene plastics of very high molecular weight cannot be categorized by flow rate. Solution viscosity is recommended as a means of distinguishing such materials.

4.1.3.2 Material supplied under these categories shall be of such nominal flow rate, within the ranges given, as agreed upon between the seller and the purchaser subject to the tolerances specified in 4.1.3.3.

4.1.3.3 In view of production, sampling, and testing variables, a commercial lot or shipment for which a nominal flow rate has been agreed upon between the seller and the purchaser shall be considered as conforming and commercially acceptable when the flow rate value found on a sample from the lot or shipment falls within the tolerance range of $\pm 20\%$ of the nominal flow rate.

4.1.3.4 If the nominal value is unknown or unspecified, classification shall be based on the tested value without tolerance consideration.

4.1.4 *Grades:*

4.1.4.1 If further definition is necessary, one of the grades given in Tables 3-5 shall be selected.

NOTE 8—Tables 4 and 5, are included to correspond with the grades specified in Federal Specification L-P-390.

TABLE 2 Classification of Polyethylene Plastics Extrusion Materials for Wire and Cable According to Category

Category	Nominal Flow Rate, g/10 min (190°C, 2.16 kg load)
1	>25
2	>10 to 25
3	>1.0 to 10
4	>0.4 to 1.0
5	0.4 max

NOTE 9—The grade shall be associated with the appropriate type, class, and category designations; for example, IA5-E4 or IC5-J3 as required. Other grades may be added as necessary by revision of this specification in established manner. Also, it is anticipated that additional requirements may be added under a given grade designation by future revision to provide more meaningful characterization of the material covered by such designation.

4.1.4.2 Instead of such selection, additional requirements specific to the application may be specified by the purchaser with the agreement of the seller.

5. Basis of Purchase

5.1 The purchase order or inquiry for these materials shall state the specification number, type, class, category, and, if needed, the appropriate grade, for example, D1248-IA5-E4.

5.2 Further definition may be agreed upon between the seller and the purchaser as follows:

5.2.1 Nominal density.

NOTE 10—For Class B, Class C, and Class D material, the nominal density of the base resin will be identified by the manufacturer upon request.

5.2.2 Nominal flow rate.

5.2.3 *Antioxidant(s) or Other Additive(s) and Proportions:*

5.2.3.1 *Class A*—As stated in 4.1.2.1,

5.2.3.2 *Class B*—As stated in 4.1.2.2,

5.2.3.3 *Class C*—As stated in 4.1.2.3, and

5.2.3.4 *Class D*—As stated in 4.1.2.4.

5.2.4 Contamination level (see 6.2).

5.2.5 Other supplementary definition, unless grade is sufficient and is identified (see 4.1.4.1 and 4.1.4.2).

5.3 Inspection (see 12.1).

6. Materials and Manufacture

6.1 The extrusion material for wire and cable shall be polyethylene plastic in the form of powder, granules, or pellets.

6.2 The extrusion materials for wire and cable shall be as uniform in composition and size and as free of contamination as can be achieved by good manufacturing practice. If necessary, level of contamination may be agreed upon between the seller and the purchaser.

6.3 Unless controlled by requirements specified elsewhere (see 4.1.4.1 and 4.1.4.2), the color and translucence of extruded pieces formed under conditions recommended by the manufacturer of the material, shall be comparable within commercial match tolerances to the color and translucence of standard molded or extruded samples of the same thickness supplied in advance by the manufacturer of the material.

7. Physical Requirements

7.1 Test specimens of the material prepared as specified in 10.1, and tested in accordance with 11.1, shall conform to the requirements prescribed by the material designation for type in Table 1, for class in 4.1.2, for category in Table 2, and for grade in Tables 3-5.

8. Sampling

8.1 A batch or lot shall be considered as a unit of manufacture and may consist of a blend of two or more production runs of material.

TABLE 3 Detail Requirements for Molded Test Specimens

Property and Unit	Grade ^A									
	E1	E2	E3	E4	E5	E6	E7	E8	E9	E10
Tensile strength, min:										
MPa	5	10	10	12	12	17	17	19	19	22
(psi)	(1200)	(1500)	(1500)	(1800)	(1800)	(2400)	(2400)	(2800)	(2800)	(3200)
Elongation, min, %	300	400	400	500	500	400	400	400	400	400
Brittleness temperature, max, °C	-50	-60	-60	-75	-75	-45	-75	-75	-75	-75
Environmental stress-crack resistance, ^{B,C} min, t_{20} h	48	48	48	48	48
Thermal stress-crack resistance, h without cracking, min	96	96	168
Dissipation factor, ^D max:										
Class A										
Before milling	0.0005	0.0002	0.0005	0.0002	0.0005	0.0002	0.0005	0.0002	0.0005	0.0002
After milling	0.0005	0.0003	0.0005	0.0003	0.0005	0.0003	0.0005	0.0003	0.0005	0.0003
Class B	0.001	0.0005	0.001	0.0005	0.001	0.0005	0.001	0.0005	0.001	0.0005
Class C	0.01	0.005	0.01	0.005	0.01	0.005	0.01	0.005	0.01	0.005
Dielectric constant ^D max increase over nominal ^E :										
Class A	0.05	0.01	0.05	0.01	0.05	0.01	0.05	0.01	0.05	0.01
Class B	0.12	0.04	0.12	0.04	0.12	0.04	0.12	0.04	0.12	0.04
Class C	0.52	0.30	0.52	0.30	0.52	0.30	0.50	0.30	0.50	0.30
Volume resistivity, min, Ω -cm:										
Classes A, B	10^{15}	10^{15}	10^{15}	10^{15}	10^{15}	10^{15}	10^{15}	10^{15}	10^{15}	10^{15}
Water immersion stability	F	F	F	F	F	F	F	F	F	F
	E11	J1	J3	J4	J5					
Tensile strength, min:										
MPa	22	10	12	19	22					
(psi)	(3200)	(1500)	(1800)	(2800)	(3200)					
Elongation, min, %	400	400	500	400	400					
Brittleness temperature, max, °C	-75	-60	-75	-75	-75					
Environmental stress-crack resistance, ^{B,C} min, t_{20} h	48	...	24	24	24					
Thermal stress-crack resistance, h without cracking, min	168					
Dissipation factor, ^D max:										
Class A										
Before milling	0.0005					
After milling	0.0005					
Class B	0.001					
Class C	0.01	...	0.01	0.01	...					
Dielectric constant ^D max increase over nominal ^E :										
Class A	0.05					
Class B	0.12					
Class C	0.50	...	0.52	0.52	...					
Volume resistivity, min, Ω -cm:										
Classes A, B	10^{15}					
Water immersion stability	F					

^AThe letters associated with these grades identify areas of potential applicability as indicated below:

E = Electrical Insulation (in some instances these materials also may serve as jacketing).

J = Jacketing (in some instances these materials also may serve as primary insulation).

^B t_{20} is the time required for failure of 20 % of the samples tested in accordance with Test Method D 1693 as further directed by 11.1.8.1-11.1.8.4 of this specification.

^CRequirements for environmental stress-crack resistance apply only to Class B, Class C, and Class D compounds unless otherwise specified (see 5.2.5).

^DAt any frequency from 1 kHz through 1 MHz (see also 11.1.10.1-11.1.10.3).

^EDielectric constant is a function of density; hence, the nominal value will be different for each type. Based on published information, the nominal values for the five types covered by this specification are as follows: Type 0-2.28, Type 1-2.28, Type II-2.31, Types III and IV-2.35 (Lanza, V. L., and Herrmann, D. B., *Journal of Polymer Science*, JPSCA, Vol 28, 1958, p. 622). To illustrate the manner in which the maximum limit for the dielectric constant of a particular, grade is determined, assume that a Type I, Class A material is to be supplied under Grade E2, then its maximum limit for dielectric constant will be $2.28 + 0.01 = 2.29$.

^FDissipation factor and dielectric constant must not exceed the limits specified above after immersion of the test specimens in water as described in 10.1.11. However, because this test is lengthy, it need not be performed on every lot of material. Rather, the material is to be checked initially for compliance with this requirement and, after that, as often as necessary to assure continued compliance. This requirement is not applicable to weather resistant (Class C and Class D) compounds (see Note 12).

8.2 Unless otherwise agreed between the seller and the purchaser, the material shall be sampled in accordance with the procedure described in Practice D 1898. Adequate statistical sampling prior to packaging shall be considered an acceptable alternative.

9. Testing

9.1 The requirements identified by the material designation and otherwise specified in the purchase order (see 5.1 and 5.2)

shall be verified by tests made in accordance with the directions given in 11.1. For routine inspection, only those tests necessary to identify the material to the satisfaction of the purchaser shall be required. One sample shall be sufficient for testing each batch or lot provided that the average values for all of the tests made on that batch or lot comply with the specified requirements.

TABLE 4 Special Grades—Dielectric—Natural and Colors

	Very Low Density, Specification D 1248, Type 0	Low Density, Specification D 1248, Type I				Medium Density, Specification D 1248, Type II		High Density, ^A Specification D 1248, Types III & IV				
		Natural	Colors	Natural	Colors	Natural	Colors	D7	D8	D9	D10	D11
Grade	D0	D1	D2	D3	D4	D5	D6	D7	D8	D9	D10	D11
Tensile Strength, min:												
MPa	6.9	9.7	9.7	9.7	9.7	12.4	12.4	19.3	19.3	24.1	24.1	27.6
(psi)	1000	(1400)	(1400)	(1400)	(1400)	(1800)	(1800)	(2800)	(2800)	(3500)	(3500)	(4000)
Elongation, min, %	500	400	400	400	400	400	400	400	400	400	400	400
Brittleness temperature, max, °C	-60	-60	-55	-60	-55	-60	-55	-55	...	-55
Dielectric constant, max, 1 MHz	2.28	2.35	2.35	2.35	2.35	2.35	2.35	2.38	2.38	2.38	2.38	2.38
Dissipation factor, max, 1 MHz	0.0005	0.0005	0.0005	0.0005	0.0005	0.0005	0.0005	0.0005	0.0005	0.0005	0.0005	0.0005
Environmental stress crack resistance, min:												
f _{20h} (100 % Igepal)	24	24
f _{20h} (10 % Igepal)	>24
Thermal stress crack resistance, min, f _{45h}	96	...	96
Milling stability	...	0.0005	0.0005	0.0005	0.0005	0.0005	0.0005	0.0005	0.0005	0.0005	0.0005	0.0005
After milling, dissipation factor, max
L-P-390, type, class, grade		III1	III2	III3	III4	IIM1	IIM2	IIH1	IIH2	IIH3	IIH4	IIH5

^AGrades D7 through D11 apply to both natural and colors, including black.

TABLE 5 Special Grades—Weather Resistant—Black

	Very Low Density, Specification D 1248, Type 0	Low Density, Specification D 1248, Type 1				Medium Density, Specification D 1248, Type II			High Density, Specification D 1248, Types III & IV	
		W1	W2	W3	W4	W5	W6	W7	W8	W9
Grade	W0	W1	W2	W3	W4	W5	W6	W7	W8	W9
Tensile Strength, min:										
MPa	6.9	9.7	9.7	9.7	9.7	12.4	12.4	12.4	19.3	24.1
(psi)	1000	(1400)	(1400)	(1400)	(1400)	(1800)	(1800)	(1800)	(2800)	(3500)
Elongation, min, %	500	400	400	400	400	400	400	400	400	400
Brittleness temperature, max, °C	-60	-50	-50	-50	-50	-50	-50	-50	-55	-55
Dielectric constant, max, 1 MHz	2.28	2.50	2.75	2.75	2.80	2.50	2.75	2.80	2.75	2.75
Dissipation factor, max, 1 MHz	0.0005	0.003	0.007	0.007	0.01	0.003	0.007	0.01	0.005	0.007
Environmental stress crack resistance, min:										
f _{20h} (100 % Igepal)	24
f _{20h} (10 % Igepal)	>24	24
Thermal stress crack resistance, min, f _{45h}	96	96
Milling stability	...	0.003	0.007	0.007	0.01	0.003	0.007	0.01	0.005	0.007
After milling, dissipation factor, max
Carbon content, range, %	2.0-3.0	0.4-0.6	2.0-3.0	2.0-3.0	2.0-3.0	0.4-0.6	2.0-3.0	2.0-3.0	2.0-3.0	2.0-3.0
Absorption coefficient, min	320	...	320	320	320	...	320	320	320	320
L-P-390, type, class, grade		IIIL1	IIIL2	IIIL3	IIIL4	IIIM1	IIIM2	IIIM3	IIIH1	IIIH2

10. Specimen Preparation

10.1 Unless otherwise specified in 11.1, the test specimens shall be molded in accordance with Procedure C of Practice D 1928.

11. Test Methods

11.1 Determine the properties enumerated in this specification in accordance with the following test methods:

11.1.1 *Conditioning*—Unless otherwise specified in the test methods or in this specification, for those tests where conditioning is required, condition the molded test specimens in accordance with Procedure A of Practice D 618.

11.1.2 *Test Conditions*—Unless otherwise specified in the test methods or in this specification, conduct tests in the standard laboratory atmosphere of $23 \pm 2^\circ\text{C}$ ($73.4 \pm 3.6^\circ\text{F}$) and $50 \pm 5\%$ relative humidity.

11.1.3 *Density*—Test Method D 1505 or alternative methods of suitable accuracy, such as Test Method D 2839 or Methods A or B of Test Methods D 792. Make duplicate determinations using two separate portions of the same molding or from two moldings. The molded specimen thickness shall be 1.9 ± 0.2 mm (0.075 ± 0.008 in.). Condition only as specified in 11.1.1 and any departure from that conditioning shall be reported.

11.1.4 *Flow Rate*—Test Method D 1238, using Condition 190/2.16 unless otherwise directed (Note 11). Make duplicate determinations on the material in the form of powder, granules, or pellets. No conditioning is required.

NOTE 11—Although the flow rate of polyethylene plastics may be measured under any of the conditions listed for it in Test Method D 1238, only measurements made at Condition 190/2.16 (190°C , 2.16 kg load) may be identified as “melt index.” This method of test serves to indicate

the degree of uniformity of the flow rate of the polymer of a single manufacturer as made by an individual process and in this case may be indicative of the degree of uniformity of other properties. However, uniformity of flow rate among various polymers of various manufacturers as made by various processes does not, in the absence of other tests, indicate uniformity of other properties and vice versa. The melt viscosity of polyethylene plastics, in common with that of most high polymers, is non-Newtonian, that is, dependent on the rate of shear. The degree of departure from Newtonian behavior depends on the nature and molecular constitution of the individual sample. Additional characterization of the sample can be obtained if other conditions are used. Especially recommended as an adjunct to Condition 190/2.16 is Condition 190/10.0.

11.1.5 Carbon Black Content—Test Method D 1603 or E 1131. If Test Method D 1603 is used, it must be known that no inorganic pigments or fillers are present in the material. Make duplicate determinations from a sample of the material in the form of powder, granules, or pellets.

NOTE 12—If it is known or suspected that the material contains moisture, the sample should be dried prior to being tested, but otherwise no conditioning is required.

11.1.6 Tensile Strength; Elongation at Break—Test Method D 638, except that speed of grip separation shall be 500 mm (20 in.)/min for Types 0 and I and 50 mm (2 in.)/min for Types II, III, and IV. Specimens shall conform to the dimensions given for Type IV in Test Method D 638 with their thickness to be 1.9 ± 0.2 mm (0.075 ± 0.008 in.). Specimens may be either die cut or machined to the specified dimensions. Bench mark separation shall be 25.40 ± 0.38 mm (1.000 ± 0.015 in.) and initial grip separation shall be 62.5 ± 5 mm (2.5 ± 0.2 in.). Percentage elongation at break shall include the cold-drawing distance. Test results for specimens which break outside the gage-marks after extensive cold drawing need not be discarded unless the break occurs between the contact surfaces of a grip.

11.1.7 Brittleness Temperature—Procedure A of Test Method D 746.

11.1.8 Environmental Stress-Crack Resistance-Test—Test Method D 1693, with the following provisions:

11.1.8.1 Type 0 materials shall be tested under Condition B, as defined in Table 1 of Test Method D 1693.

11.1.8.2 Type I materials shall be tested under Condition A, as defined in Table 1 of Test Method D 1693.

11.1.8.3 Unless otherwise specified, test materials of Types II, III, and IV under Condition B, as defined in Table 1 of Test Method D 1693.

11.1.8.4 Test Grades E4, E5, E8, E9, E10, E11, and W3 in undiluted Igepal CO-630.¹⁰ Test Grades J3, J4, J5, and W4 in a solution of 10 weight % Igepal CO-630 in water.

11.1.9 Thermal Stress-Crack Resistance of Types III and IV Polyethylenes—Test Method D 2951.

11.1.10 Dissipation Factor and Dielectric Constant—Test Method D 1531 or Test Method D 150, with the former to be the referee method. The following additional instructions and the precautions of Note 12 shall be observed:

11.1.10.1 Milling Stability—This procedure is intended for application to materials to be used for electrical insulation. For

such materials, the milling procedure described in 11.1.10.2 may be performed as a preconditioning step prior to the determination of dissipation factor and dielectric constant as provided in 11.1.10. Its purpose is to establish that a suitable antioxidant is present in adequate quantity. After being milled as prescribed, the material shall meet the dielectric requirements prescribed in Table 3.

11.1.10.2 Process approximately 400 g of material for $3 \text{ h} \pm 5$ min on a two-roll laboratory mill meeting the requirements prescribed in Practice D 3182 at a temperature of $160 \pm 5^\circ\text{C}$ with the distance between the rolls so adjusted that the charge maintains a uniform rolling bank. Any other size two-roll laboratory mill may be used provided the charge is adequate to maintain a uniform rolling bank on the rolls and to furnish sufficient material for test specimens.

11.1.10.3 Due to the time-consuming nature of this preconditioning procedure, the frequency with which it is applied shall be established by sound statistical quality control practices by the individual manufacturer. However, the specified electrical tests shall be performed on every batch or run, using the normal conditioning procedure (11.1.1) plus the precautions of Note 12.

11.1.11 Water Immersion Stability—Immerse the test specimen in distilled water at $23 \pm 2^\circ\text{C}$ for 14 days after which remove, wipe dry, and immediately test for dissipation factor and dielectric constant in accordance with 11.1.10.

11.1.12 Volume Resistivity—Test Methods D 257, using the electrodes shown in Fig. 4 (Flat Specimen for Measuring Volume and Surface Resistances or Conductances) or Fig. 5 (Tubular Specimen for Measuring Volume and Surface Resistances or Conductances). Conditioning and test conditions shall be as specified in 11.1.1 and 11.1.2 plus the precautions of Note 13.

NOTE 13—Test specimens, particularly those molded of compounds containing carbon black, should be tested immediately after conditioning and their storage under humid conditions should be avoided.

11.1.13 Absorption Coefficient—Test Method D 3349.

11.1.14 Weatherability for Colored Materials (Including White and Black):

11.1.14.1 Carbon Arc—See Appendix X1 for this test.

11.1.14.2 Xenon Arc—The material shall retain a minimum of 50 % of its unexposed elongation after 4000 h (Note 14) of exposure in a xenon-arc apparatus. Prepare the specimens in accordance with Test Methods D 2633 for physical tests of insulations and jackets. Perform the tests in accordance with Practices D 2565, G 151 and G 155 using filters CIRA/C and an irradiance of $0.70 \text{ W/m}^2/\text{nm}$ at 340 nm (Note 15). The exposure cycle consists of a light cycle of 10 h with 18 minutes water spray on the front surface during each 2 h period followed by a dark period of 2 h with continuous water spray on the back surface. The insulated black panel temperature is $70 \pm 2^\circ\text{C}$ with the light on and $55 \pm 2^\circ\text{C}$ with the light off. The dry bulb is adjusted to $48 \pm 2^\circ\text{C}$ during the light cycle and $55 \pm 2^\circ\text{C}$ during the dark cycle. The relative humidity requirements are $50 \pm 5 \%$ during the light cycle and $95 \pm 5 \%$ when the light is off.

NOTE 14—The 4000 h exposure period specified cannot be extrapolated to service life under environmental conditions without data to estimate an

¹⁰ This method is based on the use of Igepal CO-630, a trademark for a nonylphenoxy poly(ethyleneoxy)ethanol, which may be obtained from Rhone-Poulenc CN7500, Prospect Plains Road, Cranbury, NJ 08512-7500.

acceleration factor for the materials exposed. A study has been initiated by an ICEA/TWCSTAC working group to determine the acceleration factors for several formulations of polyethylene wire and cable materials.

NOTE 15—Longer periods of exposure will be required for older xenon-arc machines operated at irradiance of 0.35 W/m²/nm at 340 nm.

11.1.14.3 *Fluorescent UV Condensation Device*—The material shall retain a minimum of 50 % of its unexposed elongation after 4000 h (Note 14) of exposure in a fluorescent UV condensation apparatus. Prepare the specimens in accordance with Methods D 2633 for physical tests of insulations and jackets. Perform the tests in accordance with Practices G 151, G 154, and D 4329 with the following changes: test conditions of 20 h UV exposure to UVA-340 fluorescent lamps with an irradiance of 0.70 W/m²/nm and the uninsulated black panel temperature controlled at 70 ± 3°C followed by 4 h darkness with condensation at 55 ± 3°C uninsulated black panel temperature.

12. Inspection

12.1 Inspection of the material shall be made as agreed upon by the purchaser and the seller as part of the purchase contract.

13. Retest and Rejection

13.1 If any failure occurs, the materials may be retested to

establish conformity in accordance with agreement between the purchaser and the seller.

14. Packaging and Package Marking

14.1 *Packaging*—The material shall be packaged in standard commercial containers, so constructed as to ensure acceptance by common or other carriers for safe transportation at the lowest rate to the point of delivery, unless otherwise specified in the contract or order.

14.2 *Package Marking*—Unless otherwise agreed between the seller and the purchaser, shipping containers shall be marked with the name of the material, type, and quantity contained therein, as defined by the contract or order under which shipment is made and the name of the manufacturer.

14.3 All packing, packaging, and marking provisions of Practice D 3892 shall apply to this specification.

15. Keywords

15.1 polyethylene classification system; polyethylene for wire and cable; polyethylene plastics; wire and cable insulations and jackets

QUALITY ASSURANCE PROVISIONS FOR GOVERNMENT/MILITARY PROCUREMENT

These requirements apply only to Federal/Military procurement, not domestic sales or transfers.

S1. Sampling for inspection and testing shall be carried out in accordance with the recommendations of Practice D 3636.

S2. Selection of acceptable quality level (AQL) and of inspection level (IL) shall be made, with consideration of the specific use requirements. This is discussed in Practice D 3636.

S3. In the absence of contrary requirements, the following values shall apply:

	IL	AQL
Defects of appearance and workmanship	II	2.5
Defects of preparation for delivery	S-2	2.5
Testing (products)	S-1	1.5
Testing (polymer, unfabricated)	S-1 ^A	...

^ASamples shall be drawn from the required number of units, and pooled for preparation of molded samples for mechanical properties evaluation.

APPENDIX

(Nonmandatory Information)

X1. CARBON-ARC APPARATUS

X1.1 The radiation from a twin enclosed carbon-arc has no similarity to solar radiation. Therefore, this type of unit is not recommended as a laboratory accelerated weathering test to qualify materials for outdoor applications. Agreement of the parties involved may allow use of this device. However, no information is available on the relation between exposure times and service life under use conditions for wire and cable.

X1.2 If a twin enclosed carbon-arc apparatus must be used, the following will apply.

X1.3 The material shall retain a minimum of 50 % of its

unexposed elongation after 4000 h (Note 14) of exposure in a twin enclosed carbon-arc apparatus, or a time agreed upon by the parties involved. Prepare the specimens in accordance with Test Methods D 2633 for physical tests of insulation and jackets. Perform the test in accordance with Practices G 151 and G 153 using an exposure cycle of 102 minutes light only at 63 ± 3°C (uninsulated black panel) and 55 ± 5 % relative humidity followed by 18 min of light plus water spray on the front surface of the specimen (air temperature not controlled).

SUMMARY OF CHANGES

This section identifies the location of selected changes to this specification. For the convenience of the user, Committee D20 has highlighted those changes that may impact the use of this specification. This section may also include descriptions of the changes or reasons for the changes, or both.

- | | |
|---|---------------------------------------|
| <i>D 1248 – 98:</i> | (I) Added recycle statement to Scope. |
| (I) Changed to a standard for polyethylene plastics for wire and cable. | <i>D 1248 – 00a:</i> |
| <i>D 1248 – 00:</i> | (I) Added 3.2. |

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).