



## Standard Guide for Writing Material Standards in the Classification D 4000 Format<sup>1</sup>

This standard is issued under the fixed designation D 5740; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### INTRODUCTION

This guide has been prepared to aid in the writing of material standards using the Classification D 4000 format. The following template is included which might be used directly for a draft document simply by filling in the blanks. See appendixes for additional explanatory information.

#### Standard Classification System for \_\_\_\_\_ Molding and Extrusion Materials (\_\_\_\_\_)

#### 1. Scope\*

1.1 This classification system covers \_\_\_ materials suitable for \_\_\_\_\_. The inclusion or exclusion of recycled plastics in this classification system must be addressed here.

1.2 The properties included in this standard are those required to identify the compositions covered. There may be other requirements necessary to identify particular characteristics important to specialized applications. These may be specified by using the suffixes as given in Section 5.

1.3 This classification system and subsequent line callout (specification) are intended to provide a means of calling out plastic materials used in the fabrication of end items or parts. It is not intended for the selection of materials. Material selection should be made by those having expertise in the plastic field after careful consideration of the design and the performance required of the part, the environment to which it will be exposed, the fabrication process to be employed, the costs involved, and the inherent properties of the material other than those covered by this standard.

NOTE 1—Insert Note 1 here to show the appropriate ISO equivalency statement.

1.4 The following precautionary caveat pertains only to the test method portion, Section 11, of this classification system: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

#### 2. Referenced Documents

##### 2.1 ASTM Standards:

<sup>1</sup> This guide is under the jurisdiction of ASTM Committee D-20 on Plastics and is the direct responsibility of Subcommittee D20.94 on Government/Industry Standardization.

Current edition approved July 10, ~~1997~~ 2003. Published ~~May 1998~~ October 2003. Originally published as D 5740—95; approved in 1995. Last previous edition approved in 1997 as D 5740 – 957.

\*A Summary of Changes section appears at the end of this standard.

- D 618 Practice for Conditioning Plastics and Electrical Insulating Materials for Testing<sup>2</sup>
- D 883 Terminology Relating to Plastics<sup>2</sup>
- D 1600 Terminology for Abbreviated Terms Relating to Plastics<sup>2</sup>
- D 1999 Guide for the Selection of Specimens and Test Parameters for International Commerce<sup>2</sup>
- D 3892 Practice for Packaging/Packing of Plastics<sup>3</sup>
- D 4000 Classification System for Specifying Plastic Materials<sup>3</sup>
- D 4066 Specification for Nylon Injection and Extrusion Materials (PA)<sup>3</sup>
- D 5033 Guide for the Development of ASTM Standards Relating to the Proper Recycling and Use of Recycled Plastics<sup>4</sup>

NOTE 2—Omit if use of recycled plastic is not allowed.

- D 5630 Test Method for Ash Content in Thermoplastics Plastics<sup>4</sup>
- D 6779 Classification System for Polyamide Molding and Extrusion Materials (PA)<sup>4</sup>
- E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications<sup>5</sup>

2.2 ISO Standards:<sup>6</sup>

ISO 3451-1 Plastics—Determination of Ash Content—Part 1: General Methods

**3. Terminology**

3.1 Except for the terms defined below, the terminology used in this classification system is in accordance with Terminologies D 883 and D 1600.

**4. Classification**

4.1 \_\_\_ materials are classified into groups according to their composition. These groups are subdivided into classes and grades as shown in the Basic Property Table (Table \_\_\_). An example of a basic property table can be found in Specification D 4066. The property table should contain a footnote referring to Section \_\_\_ for reference to specimen source and preparation.

NOTE 3—An example of this classification system is given as follows: The designation \_\_\_ indicates the following:

- = \_\_\_ as found in Terminology D 1600,
- = \_\_\_ (group),
- = \_\_\_ (class), and
- = requirements given Table \_\_\_ (grade).

4.1.1 ~~To facilitate incorporation of future or special materials the “other” category for group (00), class (0), and grade (0) is shown in Table \_\_\_. The basic properties of these materials can be obtained from Tables A or B as they apply. Cell tables found in Specification D 4066 can be used as examples.~~

**4.2 Reinforced;**

4.1.1 ~~Reinforced, filled, and lubricated versions of \_\_\_ materials that are not found in Table \_\_\_\_\_ are classified in accordance with Tables \_\_\_ and A or B. Table \_\_\_ is used according to specify the Group of \_\_\_ and Table A or B is reinforcement used to specify and the property requirements after the addition of reinforcements, pigments, fillers, or lubricants at the nominal level indicated (see 4.2.1):~~

4.2.1 ~~Reinforced versions level, by weight percent, of the basic materials are reinforcement. The grade is identified by a single letter that indicates the filler or reinforcement used and two digits, in multiples of 5, that indicate the nominal quantity in percent by weight. Thus, a letter designation G for glass-reinforced and 33 for percent of reinforcement, G33, specifies a filled material with a nominal grade containing 35 % glass-level of 33 %. The reinforcement letter designations and associated tolerance levels are shown in the following table: would be indicated by \_\_\_\_\_ G35. This designation indicates~~

- = = \_\_\_ as found in Terminology D 1600,
- = = \_\_\_ (group),
- = = \_\_\_ (class), and
- = = 35 % glass reinforcement and requirements given Table \_\_\_ (grade).

The reinforcement letter designations and associated tolerance levels are shown in the following table:

**TABLE 1 Reinforcement-Filler<sup>A</sup> Symbols<sup>B</sup> and Tolerances**

Symbol	Material	Tolerance
G	Carbon and graphite	carbon and graphite fiber reinforced ±2%

<sup>2</sup> Annual Book of ASTM Standards, Vol 08.01.

<sup>3</sup> Annual Book of ASTM Standards, Vol 08.02.

<sup>4</sup> Annual Book of ASTM Standards, Vol 08.03.

<sup>5</sup> Annual Book of ASTM Standards, Vol 14.02.

<sup>6</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036.

<u>C</u>	Carbon and graphite	±2 %
<u>D</u>	Alumina trihydrate	±2 %
<u>E</u>	Clay	±2 %
<u>F</u>	Cellulose	±2 %
<u>G</u>	glass-reinforced	±2 %
<u>H</u>	Glass	±2 %
<u>J</u>	Aramid	±2 %
<u>K</u>	Boron	±2 %
<u>L</u>	Calcium carbonate	±2 %
<u>L</u>	Lubricants (for example: PTFE, graphite)	lubricants (such as PTFE, graphite, silicone, and molybdenum disulfide)
<u>L</u>	Lubricants (for example: PTFE, graphite)	lubricants (such as PTFE, graphite, silicone, and molybdenum disulfide)
<u>M</u>	Mineral	mineral-reinforced ±2 %
<u>M</u>	Mineral	±2 %
<u>N</u>	Natural organic (for example: cotton, sisal, hemp, flax)	±2 %
<u>P</u>	Mica	±2 %
<u>Q</u>	Silica	±2 %
<u>R</u>	Combinations of reinforcements and/or fillers	combinations of reinforcements or fillers, or both ±2 %
<u>R</u>	Combinations of reinforcements and/or fillers	±2 %
<u>S</u>	Synthetic organic	± %
<u>S</u>	Synthetic organic	±2 %
<u>T</u>	Talcum	±2 %
<u>V</u>	Metal	±2 %
<u>W</u>	Wood	±2 %
<u>X</u>	Not specified	To be specified

<sup>A</sup>Ash content of filled and/or reinforced materials may be determined using either Test Method D 5630 or ISO 3451-1 where applicable.

<sup>B</sup>Additional symbols may be added to this table as required.

NOTE 4—This part of the classification system uses the percent of reinforcements or additives, or both, in the callout of the modified basic material. The types and percentages of reinforcements and additives should be shown on the supplier’s technical data sheet unless they are proprietary in nature. If necessary, additional callout of these reinforcements and additives can be accomplished by use of the suffix part of the system (see Section 5).

4.1.2 To facilitate incorporation of future or special materials the “other” category for group (00), class (0), and grade (0) is shown in Table \_\_\_.

4.2 Reinforced, filled, and lubricated versions of \_\_\_ materials that are not in Table \_\_\_ are classified in accordance with Tables \_\_\_ and A or B. Table \_\_\_ is used to specify the Group or the group and class of \_\_\_ and Table A or B is used to specify the property requirements.

4.2.1 Reinforced, filled, and lubricated variations of the basic materials are identified by a single letter from Table 1 that indicates the filler and/or reinforcement used and two digits that indicate the nominal quantity in percent by weight. A second letter, from Table 1a, when desired, is used to indicate the form or structure of the reinforcement and/or filler, but is not used for functional mixtures. Thus, a letter designation G for glass, E for beads or spheres or balls, and 33 for percent by weight, GE33, specifies a reinforced or filled material with 33 percent by weight in the form of glass beads, spheres, or balls. The reinforcement letter designations and associated tolerance levels are shown in the previous table. Form and structure letter designations are shown in the following table:

**TABLE 1a Symbols for the Form or Structure of Fillers and Reinforcing Materials**

<u>Symbol</u>	<u>Form or Structure</u>
<u>C</u>	Chips, cuttings
<u>D</u>	Fines, powders
<u>E</u>	Beads, spheres, balls
<u>F</u>	Fiber
<u>G</u>	Ground
<u>H</u>	Whisker
<u>K</u>	Knitted fabric
<u>L</u>	Layer
<u>M</u>	Mat (fabric, thick)
<u>N</u>	Non-woven (fabric, thin)
<u>P</u>	Paper
<u>R</u>	Roving
<u>S</u>	Flake
<u>T</u>	Cord

V  
W  
Y  
X

Veneer  
Woven fabric  
Yarn  
Not specified

4.2.2 Specific requirements for reinforced, filled, or lubricated \_\_\_ materials shall be shown by a six-character designation. The designation will consist of the letter “A” or “B” and the five digits comprising the cell numbers for the property requirements in the order as they appear in Tables A or B.

4.2.2.1 Although the values listed are necessary to include the range of properties available in existing materials, users should not infer that every possible combination of the properties exists or can be obtained.

4.2.3 When the grade of the basic material is not known, or is not important, the use of the “ø” “0” grade classification shall be used for the reinforced materials in this system.

NOTE 5—An example of this classification for a reinforced \_\_\_ material is given as follows. The designation \_\_\_ would indicate the following material requirements.

_____	= _____ from Table _____,
-	= _____,
-	= _____,
-	= _____,
-	= _____,
-	= _____, and
-	= _____.

If no properties are specified, the designation would be \_\_\_\_\_.

**5. Suffixes**

5.1 When additional requirements are needed that are not covered by the basic requirements or cell-table requirements, they shall be indicated through the use of suffixes.

5.2 A list of suffixes can be found in Classification System D 4000 (Table 3) and may be used for additional requirements as appropriate. Additional suffixes will be added to that standard as test methods and requirements are developed and requested.

**6. General Requirements**

6.1 Basic requirements from the property tables or cell tables are always in effect unless superseded by specific suffix requirements, which always take precedence.

6.2 The plastics composition shall be uniform and shall conform to the requirements specified herein.

**7. Detail Requirements**

7.1 The materials shall conform to the requirements in Tables \_\_\_, \_\_\_, \_\_\_, and suffix requirements as they apply.

7.2 For purposes of determining conformance, all specified limits for a specification (line callout) based on this classification system are absolute limits, as defined in Practice E 29.

7.2.1 With the absolute method, an observed value or a calculated value is not rounded, but is to be compared directly with the limiting value. Conformance or nonconformance is based on this comparison.

**8. Sampling**

8.1 Sampling shall be statistically adequate to satisfy the requirements of 12.4.

8.2 A batch or lot shall be constituted as a unit of manufacture as prepared for shipment and may consist of a blend of two or more “production runs.”

**9. Specimen Preparation**

9.1 ~~Indicate the source of the test specimens shall be molded for the relevant test methods.~~

9.2 Prepare the specimens by a \_\_\_ process in accordance with \_\_\_. An example is found in Classification System D 6779.

**10. Conditioning**

10.1 Test specimens shall be conditioned in the standard laboratory atmosphere in accordance with Procedure A of Practice D 618 before performing the required tests.

NOTE 6—If another conditioning procedure is used, replace the previous one.

10.2 Conduct those tests influenced by ambient conditions in the standard laboratory atmosphere of 23 ± 2°C and 50 ± 5 % relative humidity in accordance with Practice D 618.

**11. Test Methods**

11.1 Determine the properties enumerated in this classification system by means of the test methods referenced in Section 2.

Note 7—The test methods for international commerce in Guide D 1999 are recommended. However, any needed test method may be referenced.

11.1.1 The number of tests shall be consistent with the requirements of Section 8 and 12.4.

## **12. Inspection and Certification**

12.1 Inspection and certification of the material supplied with reference to a specification based on this classification system shall be for conformance to the requirements specified herein.

12.2 Lot-acceptance inspection shall be the basis on which acceptance or rejection of the lot is made. The lot-acceptance inspection shall consist of:

12.2.1 \_\_\_\_\_.

12.2.2 \_\_\_\_\_.

12.3 Periodic check inspection with reference to a specification based upon this classification system shall consist of the tests for all requirements of the material under the specification. Inspection frequency shall be adequate to ensure the material is certifiable in accordance with 12.4.

12.4 Certification shall be that the material was manufactured by a process in statistical control, sampled, tested, and inspected in accordance with this classification system, and that the average values for the lot meet the requirements of the specification (line callout).

12.5 A report of test results shall be furnished when requested. The report shall consist of results of the lot-acceptance inspection for the shipment and the results of the most recent periodic-check inspection.

**NOTE 87**—If recycled plastics are allowed in the standard, insert the following phrase after the word “shipment” in the last sentence of 12.5: “the percent by weight of recycled plastic, as defined in 3.1 of Guide D 5033, if requested.”

## **13. Packaging, Packing, and Marking**

13.1 The provisions of Practice D 3892 apply to packaging, packing, and marking of containers for plastic materials.

## **14. Keywords**

14.1 classification; classification system; line callout; plastic materials

# **APPENDIXES**

## **(Nonmandatory Information)**

### **X1. LIST BY SECTIONS/EXPLANATORY INFORMATION**

X1.1 *Scope*—Modify 1.1 for material and processing.

X1.2 *Referenced Documents*—Add documents as required and, if necessary, use footnotes in addition to those included and renumber footnotes as required.

X1.3 *Terminology*—Include new terms, definitions, and abbreviated terms as developed cooperatively between the writer of the standard and Subcommittee D20.92.

X1.4 *Classification*—Modify for material, 4.1. Consult current Classification D 4000 for listing.

X1.5 *Suffixes*—If suffixes are needed that are specific to the materials being classified, use the single-letter and two-digit system as found, for example, in accordance with Section 5 of Specification D 4066.

X1.6 *General Requirements*—Includes basic requirements as found in Classification D 4000.

X1.7 *Detail Requirements*.

X1.8 *Sampling*.

X1.9 *Specimen Preparation*—~~Can be expanded~~—Expand as required.

X1.10 *Conditioning*—Modify for material.

X1.11 *Test Methods*.

X1.12 *Inspection and Certification*.

X1.13 *Packaging, Packing, and Marking*.

X1.14 *Keywords.*

## X2. GENERAL INFORMATION

X2.1 Fill in the material and examples for which the standard applies.

X2.2 The basic property table is to use the abbreviations (symbols) from Classification D 4000. Table PA in Specification D 4066 can be used as an example of a basic property table.

X2.3 Develop Cell Tables A and B for the materials that are used. Cell tables found in Specification D 4066 can be used as examples.

X2.4 Certain thermoplastic and thermosetting materials will require a modification of the different sections, depending on the standard being drafted.

## SUMMARY OF CHANGES

This section identifies the location of selected changes to this guide. For the convenience of the user, Committee D-20 has highlighted those changes that may impact the use of this guide. This section may also include descriptions of the changes or reasons for the changes, or both.

### D 5740 - 03:

- (1) Addition of referenced documents D 6779 and ISO 3451-1.
- (2) Minor editorial changes in Sections 4.2.3, X1.5, and X1.9.
- (3) Revision of Table 1 to enable use of an expanded list of reinforcements and fillers.
- (4) Addition of Table 1a to enable use of structure or form of reinforcements and fillers.
- (5) Modification of Section 4.2.1 to describe the use of two letters to specify both filler or reinforcement and its form or structure.
- (6) Elimination of Note 7 referring to D 1999 and removal of the reference from Section 2.1. Note 8 becomes note 7.

### D 5740 – 97:

- (1) Guide D 5033 and Note 2 were added to 2.1.
- (2) Note-8 7 was added to 12.5.
- (3) “Recycled materials” was changed to “recycled plastics” in 1.1.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)).*