

This document is not an ASTM standard and is intended only to provide the user of an ASTM standard an indication of what changes have been made to the previous version. Because it may not be technically possible to adequately depict all changes accurately, ASTM recommends that users consult prior editions as appropriate. In all cases only the current version of the standard as published by ASTM is to be considered the official document.



Designation: D 4570 – 86 (Reapproved 1998)



Designation: D 4570 – 02

Standard Test Method for Rubber Chemicals—Determination of Particle Size of Sulfur by Sieving (Dry)¹

This standard is issued under the fixed designation D 4570; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

~~¹ NOTE—Section 10 was added editorially in June 1993.~~

¹ This test method is under the jurisdiction of ASTM Committee D11 on Rubber and is the direct responsibility of Subcommittee D11.20 on Compounding Materials and Procedures.

Current edition approved July 8, 1986; Dec. 10, 2002. Published September January 2003. Originally approved in 1986. Last previous edition approved in 1998 as D 4570 - 86 (1998).

1. Scope

1.1 This test method covers the particle size measurement of the coarse fraction of ground sulfurs. It is limited to measurement of particles greater than 45 μm (No. 325 sieve). If the sulfur is very fine and the screens become plugged by the caking of the sulfur, it may be necessary to use a wet sieve procedure instead.

1.2 The values stated in SI units are to be regarded as the standard.

1.3 *This standard does not purport to address all of the safety problems, concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*

E 11 Specification for Wire-Cloth Sieves for Testing Purposes²

E 145 Specification for Gravity-Convection and Forced-Ventilation Ovens³

3. Significance and Use

3.1 This test method is used to evaluate sulfur for suitability as a rubber vulcanizing agent. Sulfur particles must be significantly small enough to dissolve in rubber during cure and to produce a uniform network of cross-links. This test method is used as a quality control method to ensure that no excessively large particles are not present (and to determine if the sulfur follows a typical pattern for size distribution).

4. Apparatus

4.1 *Standard Sieves*, stainless steel, 203 mm in diameter conforming to Specification E 11. The stainless steel cloth shall range in mesh size from 45 to 250 μm . The sieve set should include a lid and a bottom pan.

4.2 *Mechanical Sieve Shakers*, such as a Tyler Ro-Tap⁴ or equivalent unit.

4.3 *Balance*, with a minimum capacity of 500 g sensitive to 0.1 g.

4.4 *Balance*, with a minimum capacity of 150 g sensitive to 0.001 g.

4.5 *Oven*, circulating air type, controlled to $70 \pm 2^\circ\text{C}$.

5. Reagent

5.1 *Tri-calcium Phosphate*, screened to a fineness of less than 45 μm .

6. Procedure

6.1 Assemble the sieves;

² Annual Book of ASTM Standards, Vol 14.02.

³ This unit may be purchased from the Fisher Scientific Co., 585 Alpha Dr., Pittsburgh, PA 15238.

⁴ Annual Book of ASTM Standards, Vol 14.04.

⁵ This unit may be purchased from the Fisher Scientific Co., 585 Alpha Dr., Pittsburgh, PA 15238.

6.1 Weigh each ~~weighed~~ sieve to the nearest 0.1 g, g and assemble in order of increasing mesh size from bottom to top and add to the top. Add a bottom pan. Choice of sieves depends on the information desired.

6.2 ~~Weigh into~~

6.2 Into a beaker or suitable container, weigh precisely 100.0 g of sulfur. If sulfur to the nearest 0.1 g. When the sulfur is very fine, add 2.0 g of the fine tri-calcium phosphate (see 5.1) and blend thoroughly using a spatula or glass stirring rod. spatula.

6.3 Transfer all the sulfur to the top sieve and add the lid. Fix the sieve vest firmly in the mechanical sieve shaker. Run the unit for 10 min, stop, remove the sieves, and weigh each sieve to the nearest 0.1 g. Return the sieves to the unit and run an additional 3 min. ~~Check~~ Reweigh each sieve again to the masses of the sieves, nearest 0.1 g. Repeat until sieving is complete and the sieves reach constant mass.

7. Calculation

7.1 Determine the residue remaining on each sieve by mass difference. For higher precision, transfer the small residue from the coarser screen to a weighing dish and weigh to the nearest 0.01 g.

7.2 The percent residue on each screen is equal to the amount in grams on each screen.

7.3 The percent residue passing through each screen is determined by accumulating the total percent material collected on that screen and the coarser screens used and subtracting the total from 100.

% residue through (for any screen) \equiv
 $\equiv 100 - \text{sumation of \% sulfur collected on that screen and on any coarser screens}$

8. Report

- 8.1 The report should include the following information:
 - 8.1.1 Proper identification of samples,
 - 8.1.2 Identification of each screen used,
 - 8.1.3 The percent residue on each screen, and
 - 8.1.4 The percent residue through for each screen.

9. Precision and Bias

9.1 Round robin testing will be conducted, and precision and bias statements will be balloted for inclusion upon the completion of this work.

10. Keywords

- 10.1 dry sieving; particle size; sulfur

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).