



Standard Specification for Poly(Vinyl Chloride) Jacket for Wire and Cable¹

This standard is issued under the fixed designation D 1047; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers a durable general-purpose thermoplastic jacket made from poly(vinyl chloride) or the copolymer of vinyl chloride and vinyl acetate suitable for a minimum installing temperature of -10°C .

1.2 The values stated in inch-pound units are the standard, except in cases where SI units are more appropriate. The values in parentheses are for information only.

2. Referenced Documents

2.1 ASTM Standards:

D 470 Test Methods for Crosslinked Insulations and Jackets for Wire and Cable²

D 1499 Practice for Filtered Open-Flame Carbon-Arc Exposures of Plastics³

D 2633 Methods of Testing Thermoplastic Insulations and Jackets for Wire and Cable⁴

G 23 Practice for Operating Light-Exposure Apparatus (Carbon-Arc Type) With and Without Water for Exposure of Nonmetallic Materials⁵

¹ This specification is under the jurisdiction of ASTM Committee D09 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.18 on Solid Insulations, Non-Metallic Shieldings and Coverings for Electrical and Telecommunications Wires and Cables.

Current edition approved Feb. 15, 1995. Published April 1995. Originally published as D 1047 – 49 T. Last previous edition D 1047 – 89.

² Annual Book of ASTM Standards, Vol 10.01.

³ Annual Book of ASTM Standards, Vol 08.01.

⁴ Annual Book of ASTM Standards, Vol 10.02.

⁵ Discontinued; see 1996 Annual Book of ASTM Standards, Vol 14.02.

3. Test Applicable for Sunlight and Weather Resistant Materials

3.1 The jacket shall retain a minimum of 80 % of its unexposed tensile strength and elongation after 720 h of exposure in a dual carbon-arc apparatus. Prepare the specimens in accordance with Test Methods D 470 for physical tests of insulations and jackets. Perform the test in accordance with Practice D 1499 using Method 1 of Practice G 23.

4. Physical Properties

4.1 The jacket shall conform to the requirements for physical properties prescribed in Table 1.

4.2 When used on single-conductor nonshielded cable rated 2001 to 5000 V phase to phase, the jacket shall also conform to the requirements for surface resistivity and U-bend discharge in Table 2.

5. Sampling

5.1 Sample the jacket in accordance with Methods D 2633 unless otherwise specified.

6. Test Methods

6.1 Unless otherwise specified, test the jacket in accordance with Methods D 2633.

7. Keywords

7.1 jacket for wire and cable; poly (vinyl chloride) jacket; thermoplastic jacket

TABLE 1 Physical Properties for Poly(Vinyl Chloride) Jacket^A

<i>Unexposed (Unaged) Requirements:</i>	
Tensile strength, min, psi (MPa)	1500 (10.3)
Elongation at rupture, min, %	100
<i>Exposed (Aged) Requirements:</i>	
After Air Oven Aging Test at 100 ± 1°C for 5 days:	
Tensile strength, min, % of unexposed (unaged) value	85
Elongation at rupture, min, % of unexposed (unaged) value	60
After Oil Immersion Test at 70 ± 1°C for 4 h:	
Tensile strength, min, % of unexposed (unaged) value	80
Elongation at rupture, min, % of unexposed (unaged) value	60
Heat distortion, 121 ± 1°C, max, %	50
Heat shock, 121 ± 1°C	no cracks
Cold bend, -35 ± 1°C	no cracks

^A The values specified are applicable only to jacket having a nominal wall thickness of 0.030 in. (0.76 mm) or greater.

TABLE 2 Requirements for Resisitivity and U-Bend Discharge

Surface resistivity, min, MΩ	200 000
U-bend discharge at the required cable insulation ac test voltage	no cable failures or cracks in the jacket

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).