



Standard Specification for Electrical Insulating Paper and Paperboard—Sulfate (Kraft) Layer Type¹

This standard is issued under the fixed designation D 1305; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers electrical grade unsized, unbleached sulfate paper and paperboard for use as layer insulation in coils, transformers, and similar apparatus. Other applications may include, but are not limited to, turn insulation, slot liners, wedges, phase insulation, and separator papers in stranded wire/cable constructions. Tissue for the manufacture of capacitors is not included in this specification. Other commonly used designations include:

- 1.1.1 *Soft Coil Wrap*,
- 1.1.2 *Dense Coil Wrap*,
- 1.1.3 *Kraft Coil Insulation*,
- 1.1.4 *Dry-Finished Kraft*, and
- 1.1.5 *Water-Finished Kraft*.

2. Referenced Documents

- 2.1 *ASTM Standards*:
 - D 202 Test Methods for Sampling and Testing Untreated Paper Used for Electrical Insulation²
 - D 1711 Terminology Relating to Electrical Insulation²

3. Terminology

3.1 *Definitions*—For definitions of terms used in this standard, refer to Terminology D 1711.

4. Classification

4.1 Four types of paper and paperboard are covered by this specification, as shown in Table 1. The material is available in sheets, pads, or rolls.

5. Ordering Information

5.1 Orders shall specify the type, including whether water finish or not (see Note 1), nominal thickness, form, width, length (for sheets), nominal outside diameter, and core inside diameter (for rolls).

TABLE 1 Types of Untreated Kraft Insulating Tissue, Paper, and Paperboard

Type	Density Range, g/cm ³	Nominal Thickness, mil (μ m)
I	less than 0.77	1 (25) to 30 (760)
II	0.77 to 0.86	0.5 (12) to 30 (760)
III	0.86 to 0.95	0.4 (10) to 30 (760)
IV	over 0.95	0.2 (5) to 30 (760)

NOTE 1—Water finish is not available with certain combinations of Kraft type and thickness. In general, water finish is restricted to paper and paperboard in the higher density ranges, that is, Types III and IV.

6. Materials

6.1 The material shall be natural unbleached sulfate paper or paperboard, free of dyes, pigments, fillers, or sizing. It may be furnished either with water-finish or without.

7. Detail Requirements

7.1 The material shall conform to the chemical, physical, and electrical requirements specified in Tables 1-4, when tested in accordance with the methods prescribed in Section 11.

8. Interpretation of Numerical Requirements

8.1 Unless otherwise stated, all specified limits in this specification apply to the average of determinations applicable to a sample as defined.

9. Workmanship, Finish, and Appearance

9.1 The material shall be uniform in thickness, density, formation, and texture. The material shall be as free of welts, wrinkles, creases, holes, slime spots, stains, shives, weak spots, blisters, tears, cuts, and other defects; and from resin, dirt, carbon, rubber, metal particles, corrosive substances, or other foreign material, as consistent with good manufacturing processes and in keeping with the requirements of this specification. Rolls and pads shall be compactly wound. Splices shall be kept to a minimum. Splicing compounds shall be noncorrosive and shall have no deleterious effect on the insulating or dielectric values of the paper.

¹ This specification is under the jurisdiction of ASTM Committee D-9 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.19 on Dielectric Sheet and Roll Products.

Current edition approved March 10, 1999. Published June 1999. Originally published as D1305 – 54 T. Last previous edition D1305 – 87 (1998).

² *Annual Book of ASTM Standards*, Vol 10.01.

TABLE 2 Chemical Requirements

Property	min	max
Ash, %	...	0.5
Alcohol-soluble material, %	...	1.0
Aqueous extract conductivity, mS/m ^A	...	1.0
Water-soluble chlorides, ppm	...	32
Fiber composition: unbleached sulfate, %	100	...
Moisture, as received, %	4	7
Moisture, as received, for water finished paper, %	4	9
Hydrogen ion concentration, pH	6.5	8.0

^A1 mS/m = 10 μΩ/cm.

10. Sampling

10.1 Sample the paper in accordance with Test Methods D 202.

11. Test Methods

11.1 The properties of the paper shall be determined in accordance with Test Methods D 202, except workmanship and appearance shall be visually judged.

12. Packaging and Package Marking

12.1 *Packaging*—The material shall be wound on a one-piece substantial core with inside diameter as specified. Ends of rolls shall be protected with suitable caps or roll end protectors to ensure against edge damage. The material shall be packed in moisture-proof wrappers, boxes, or cartons so constructed as to ensure acceptance by common or other carriers for safe transportation at the lowest rate to the point of delivery, unless otherwise specified in the contract or order.

12.2 *Package Marking*—Each container shall be marked on the side or on one end of the package, or on both the side and

end, with the name and type of material, specification number, purchase order number, manufacturer's name or trade mark, or both, manufacturer's roll number, lot number, and the date of manufacture. Each roll or pad shall be marked on one side with the manufacturer's name and lot number and the customer's purchase order number.

13. Retest and Rejection

13.1 If the results of any test do not conform to the requirements prescribed in this specification, at the option of the manufacturer that test shall be repeated on two additional sets of specimens from the same batch or shipment, each of which shall conform to the requirements specified. If either of these two additional sets of specimens fails, the material may be rejected at the option of the purchaser.

13.2 Notice of failure of material based on tests made in accordance with this specification shall be reported to the manufacturer within 3 weeks from receipt of the material by the purchaser. Any portion of an accepted shipment of material that is subsequently shown not to have been in accordance with this specification at the time of receipt may be rejected, provided the manufacturer is notified within 90 days from the date of receipt of the material by the purchaser.

14. Keywords

14.1 alcohol-soluble material; aqueous extract conductivity; ash; chlorides; conducting paths; density; dielectric breakdown voltage; paper; paperboard; pH; tensile strength; unbleached sulfate kraft

TABLE 3 Physical and Electrical Requirements

Nominal Thickness, mils (µm)	Tensile Strength, machine direction min, lbf/in. (N/mm) width	Conducting Paths, max, number per ft ² (per 929 cm ²) ^A	Dielectric Breakdown Voltage per Sheet, min, avg V rms	Nominal Thickness, mils (µm)	Tensile Strength, machine direction min, lbf/in. (N/mm) width	Conducting Paths, max, number per ft ² (per 929 cm ²) ^A	Dielectric Breakdown Voltage per Sheet, min, avg V ms
Type I ^B				0.75 (19)	9.1 (1.59)	2	375
1.0 (25)	8.0 (1.40)	1	350	1.0 (25)	12.6 (2.21)	1	430
1.5 (38)	12.5 (2.19)	1	400	1.5 (38)	17.1 (2.99)	1	570
1.7 (43)	15.0 (2.63)	5 × 10 ⁻²	435	1.7 (43)	18.9 (3.31)	5 × 10 ⁻²	630
2.0 (51)	17.0 (2.98)	4 × 10 ⁻²	495	2.0 (51)	22.1 (3.81)	4 × 10 ⁻²	720
2.5 (64)	21.0 (3.68)	3 × 10 ⁻²	575	2.5 (64)	26.1 (4.57)	3 × 10 ⁻²	780
3.0 (76)	26.0 (4.56)	2.0 × 10 ⁻²	650	3.0 (76)	30.6 (5.36)	2 × 10 ⁻²	800
4.0 (100)	34.5 (6.04)	2.0 × 10 ⁻²	735	4.0 (100)	39.6 (6.94)	2 × 10 ⁻²	1000
5.0 (130)	43.0 (7.53)	1.5 × 10 ⁻²	900	5.0 (130)	49.5 (8.67)	1.5 × 10 ⁻²	1200
6.0 (150)	52.0 (9.11)	1.5 × 10 ⁻²	1000	6.0 (150)	58.5 (10.24)	1.5 × 10 ⁻²	1350
7.0 (180)	60.0 (10.51)	1.3 × 10 ⁻²	1100	7.0 (180)	67.0 (11.73)	1.3 × 10 ⁻²	1500
10.0 (250)	81.0 (14.18)	1.0 × 10 ⁻²	1500	10.0 (250)	90.0 (15.76)	1.0 × 10 ⁻²	2000
15.0 (380)	115 (20.14)	0.5 × 10 ⁻²	2000	15.0 (380)	135 (23.64)	0.5 × 10 ⁻²	2500
20.0 (510)	144 (25.22)	0.5 × 10 ⁻²	2500	20.0 (510)	180 (31.52)	0.5 × 10 ⁻²	3000
30.0 (760)	180 (31.52)	0.5 × 10 ⁻²	3000	30.0 (760)	225 (39.40)	0.5 × 10 ⁻²	3750
Type II ^C				Type IV ^D			
0.5 (13)	4.6 (0.80)	4	225	0.20 (5)	1.5 (0.26)	9	250
0.55 (14)	5.2 (0.91)	4	230	0.25 (6)	2.3 (0.40)	7	300
0.6 (15)	5.8 (1.01)	3	240	0.3 (8)	3.1 (0.54)	7	320
0.75 (19)	7.2 (1.26)	2	260	0.35 (9)	3.8 (0.66)	7	330
1.0 (25)	10.0 (1.75)	1	360	0.4 (10)	4.6 (0.80)	6	340
1.5 (38)	15.0 (2.63)	1	470	0.45 (11)	5.4 (0.94)	5	350
1.7 (43)	20.0 (3.50)	5 × 10 ⁻²	510	0.5 (13)	6.2 (1.08)	4	355
2.0 (51)	23.0 (4.03)	4 × 10 ⁻²	575	0.55 (14)	7.0 (1.22)	4	360
2.5 (64)	24.5 (4.29)	3 × 10 ⁻²	640	0.6 (15)	7.7 (1.35)	3	365
3.0 (76)	29.0 (5.08)	2 × 10 ⁻²	690	0.75 (19)	10.1 (1.77)	2	380
4.0 (100)	38.5 (6.74)	2 × 10 ⁻²	790	1.0 (25)	14.0 (2.45)	1	430
5.0 (130)	48.0 (8.41)	1.5 × 10 ⁻²	900	1.5 (38)	19.0 (3.33)	1	600
6.0 (150)	58.0 (10.16)	1.5 × 10 ⁻²	1000	1.7 (43)	21.0 (3.68)	5 × 10 ⁻²	660
7.0 (180)	67.0 (11.73)	1.3 × 10 ⁻²	1100	2.0 (51)	24.5 (4.29)	4 × 10 ⁻²	750
10.0 (250)	90.0 (15.76)	1.0 × 10 ⁻²	1500	2.5 (64)	29.0 (5.08)	3 × 10 ⁻²	780
15.0 (380)	128 (22.42)	0.5 × 10 ⁻²	2000	3.0 (76)	34.0 (5.95)	2 × 10 ⁻²	800
20.0 (510)	160 (28.02)	0.5 × 10 ⁻²	2500	4.0 (100)	44.0 (7.70)	2 × 10 ⁻²	1000
30.0 (760)	200 (35.02)	0.5 × 10 ⁻²	3000	5.0 (130)	55.0 (9.63)	1.5 × 10 ⁻²	1200
Type III ^D				6.0 (150)	65.0 (11.38)	1.5 × 10 ⁻²	1350
0.4 (10)	4.1 (0.72)	6	340	7.0 (180)	74.0 (12.96)	1.3 × 10 ⁻²	1600
0.45 (11)	4.9 (0.85)	5	345	10.0 (250)	100 (17.51)	1.0 × 10 ⁻²	2000
0.5 (13)	5.6 (0.98)	4	350	15.0 (380)	150 (26.27)	0.5 × 10 ⁻²	2500
0.55 (14)	6.3 (1.10)	4	355	20.0 (510)	200 (35.02)	0.5 × 10 ⁻²	3000
0.6 (15)	6.9 (1.21)	3	360	30.0 (760)	250 (43.78)	0.5 × 10 ⁻²	3750

^ANote change in test method between 1.5 and 1.7 mils in thickness.

^BThickness tolerance for Type I shall be ±10 % on all thicknesses.

^CThickness tolerances for Type II shall be as follows:

2.0 mils and less ±7 %.

Over 2.0 mils ±10 %.

^DThickness tolerances for Types III and IV shall be as follows:

2.0 mils and less ±5 %.

Over 2.0 mils ±10 %.

TABLE 4 Dimensional Tolerances

Property	Types	Tolerances ± in. (mm)
Width (cross-machine direction)		
less than 2 in. (50 mm)	all	1/64 (0.4)
2 to 10 in. (51 to 254 mm), incl	all	1/32 (0.8)
over 10 in. (254 mm)	all	1/16 (1.6)
Length (sheets, machine direction)		
less than 18 in. (457 mm)	all	1/16 (1.6)
18 to 36 in. (457 to 915 mm), incl.	all	1/8 (3.2)
over 36 in. (915 mm)	all	3/16 (4.8)
Diameter (outer, of roll)	all	1/2 (13)

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).