



Designation: **D 1867 – 9601**

An American National Standard

## Standard Specification for Copper-Clad Thermosetting Laminates for Printed Wiring<sup>1</sup>

This standard is issued under the fixed designation D 1867; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This specification covers twelve grades of thermosetting laminate with copper foil bonded to one or both surfaces. These combination forms are intended primarily for use in fabrication of printed (etched) wiring or circuit boards.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

2.1 *ASTM Standards:*

---

<sup>1</sup> This specification is under the jurisdiction of the ASTM Committee ~~D-9~~ D09 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.07 on Flexible and Rigid Insulating Materials.

Current edition approved ~~March~~ Sept. 10, 1996; 2001. Published ~~May~~ November 2001. Originally published as D 1867 – 61 T. Last previous edition D 1867 – 946.

D 709 Specification for Laminated Thermosetting Materials<sup>2</sup>

D 1711 Terminology Relating to Electrical Insulation<sup>2</sup>

D 3636 Practice for Sampling and Judging Quality of Solid Electrical Insulating Materials<sup>3</sup>

D 5109 Test Methods for Copper-Clad Thermosetting Laminates for Printed Wiring Boards<sup>3</sup>

2.2 *Other Standards:*

MIL-P-13949 Plastic Sheet, Laminated, Metal Clad (for Printed Wiring Boards)<sup>4</sup>

NEMA Publication Number LI-1<sup>5</sup>

### 3. Terminology

3.1 For definitions of terms used in this standard, refer to Terminology D 1711.

### 4. Classification

34.1 *Base Laminate Grades*—Where applicable, the dielectric material forming the base of the copper-clad laminate of the types listed in Table 1 and Table 2 shall conform to the property requirements of that specific grade shown in Specification D 709.

34.2 *Copper Foil Surfaces*—The surfaces shall be copper foil, either rolled or electrodeposited, having a minimum purity of 99.50 % (silver considered as equal to copper). The thickness tolerances of the copper foil shall conform to the requirements of Table 3.

34.3 *Thickness Tolerance Classes*—Copper-clad laminates are available in two classes of thickness tolerance. Class I represents those tolerances of standard manufacturing practice. Class II represents a closer tolerance product than Class I. Any specified class shall conform to the requirements shown in Table 4.

34.3.1 For sheets of laminate equal to or greater than 18 by 18 in. (approximately 2.3 ft<sup>2</sup>) at least 90 % of all thickness test measurements made upon any sheet of laminate shall be within the limits specified in Table 4. For metric size sheets this 90 % requirement shall apply to sheet sizes of 0.5 by 0.5 m or 0.25 m<sup>2</sup> area.

34.3.2 The deviation of any single thickness test measurement value (see Practice D 3636) from the nominal overall thickness listed in Table 4 shall not exceed 125 % of the tolerance listed in Table 4.

34.3.3 Any overall laminate thickness not listed in Table 4 shall meet the tolerance requirements of the next highest nominal thickness listed in Table 4.

34.3.4 For cut panels (for example, laminate sheets cut to area less than 2.3 ft<sup>2</sup> or less than 0.25 m<sup>2</sup>) at least 98 % of all thickness test measurements shall be within the specified overall laminate thickness tolerance values of Table 4.

### 4. Ordering Information

4.1 ~~Orders for copper-clad laminates shall specify the grade of laminate base (see 3.1); the type of copper foil (either rolled or~~

<sup>2</sup> Annual Book of ASTM Standards, Vol 10.01.

<sup>3</sup> Annual Book of ASTM Standards, Vol 10.02.

<sup>4</sup> Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

<sup>5</sup> Available from National Electrical Manufacturers Association, 2101 L St., N.W., Washington, DC 20037.

**TABLE 1 Base Laminate Grades**

NOTE 1— A cross reference table of grade designations (see Table 2) appears here for reference purposes only. The ASTM grades shown are most closely associated with the NEMA and the military grades listed in this table. There is no requirement, stated or implied, in this ASTM specification that the ASTM grade must meet the specification requirements of the NEMA or the military standards listed.

ASTM Grade	Type
XXXP	Paper base, phenolic resin
XXXPC	Paper base, phenolic resin
FR-2	Paper base, phenolic resin, flammability rated
FR-3	Paper base, epoxy resin, flammability rated
FR-4	Glass woven fabric base, epoxy resin, general purpose, flammability rated
FR-5	Glass woven fabric base, epoxy resin, temperature resistant, flammability rated
FR-6	Random glass fiber base, polyester resin, flammability rated
G-10	Glass woven fabric base, epoxy resin, general purpose
G-11	Glass woven fabric base, epoxy resin, temperature resistant
CEM-1	Glass woven cloth surfaces, cellulose paper core, epoxy resin, flammability rated
CEM-3	Glass woven cloth surfaces, non-woven glass core, flammability rated
CFR-1	Glass polyester non-woven fabric base, epoxy resin, flammability rated

**TABLE 2 Grade Cross References**

ASTM Grade	NEMA LI-1 Grade	MIL-P-13949 Grade
XXXP	XXXP	PP
XXXPC	XXXPC	PP
FR-2	FR-2	...
FR-3	FR-3	PX
FR-4	FR-4	GF
FR-5	FR-5	GH
FR-6	FR-6	...
G-10	G-10	GE
G-11	G-11	GB
CEM-1	CEM-1	...
CEM-3	CEM-3	...
CFR-1	...	CF

**TABLE 3 Copper Foil Thickness<sup>A</sup>**

Nominal Weight, oz/ft <sup>2</sup>	Nominal Thickness, in.	Thickness Tolerance, in.	
		Plus	Minus
1/2	0.0007	0.00007	0.00007
1	0.0014	0.0004	0.0002
2	0.0028	0.0007	0.0003
3	0.0042	0.0004	0.0004
4	0.0056	0.0006	0.0006
5	0.0070	0.0007	0.0007

<sup>A</sup> Conversion factor: 0.001 in. = 0.0254 mm; 1 oz/ft<sup>2</sup> = 0.305 kg/m<sup>2</sup>.

**TABLE 4 Thickness Tolerance of Copper-Clad Sheet, ± in.<sup>A</sup>**

Nominal Overall Laminate Thickness, in. <sup>B</sup>	Class I			Class II	
	Grades			Grades	
	XXXP, XXXPC FR-2, FR-3		FR-4, FR-5 CEM-1, CEM-3 FR-6, G-10, G-11	XXXPC FR-2 FR-3	FR-4 FR-5 G-10 G-11 CFR-1
	1 oz, 1 Side	1 oz, 2 Sides 2, 3, 4, 5 oz 1 or 2 Sides	All Weights 1 or 2 Sides	All Weights 1 or 2 Sides	All Weights 1 or 2 Sides
1/32	0.004	0.0045	0.0065	0.003	0.004
3/64	0.005	0.0055	0.0075	0.0035	0.005
1/16	0.0055	0.006	0.0075	0.004	0.005
3/32	0.007	0.0075	0.009	0.005	0.007
1/8	0.0085	0.009	0.012	0.006	0.009
5/32	0.0095	0.010	0.015	0.007	0.010
3/16	0.010	0.011	0.019	0.008	0.012
7/32	0.011	0.012	0.021	0.009	0.012
1/4	0.012	0.012	0.022	0.009	0.012
CFR-1					
0.0085	NA <sup>C</sup>	NA	NA	NA	0.0015
0.015	NA	NA	NA	NA	0.002
0.020	NA	NA	NA	NA	0.002
0.030	NA	NA	NA	NA	0.003

<sup>A</sup> Conversion factor: 0.001 in. = 0.0254 mm; 1 oz = 28.349 g.

<sup>B</sup> CFR-1 laminate thickness as listed is without copper foil in accordance with MIL-P-13949. Tolerance values for CFR-1 apply to the dielectric layer only.

<sup>C</sup> Not applicable.

electrodeposited); the nominal weight of the copper foil (see 3.2); one- or two-side cladding; nominal overall laminate thickness; and the thickness tolerance class (see 3.3).

## 5. Ordering Information

5.1 Orders for copper-clad laminates shall specify the grade of laminate base (see 4.1); the type of copper foil (either rolled or electrodeposited); the nominal weight of the copper foil (see 4.2); one- or two-side cladding; nominal overall laminate thickness; and the thickness tolerance class (see 4.3).

## 6. Detailed Requirements

56.1 The laminate shall meet the requirements shown in Table 5.

**TABLE 5 Detailed Requirements: Copper-Clad Laminates for Printed Wiring<sup>A</sup>**

	XXXP	XXXPC	FR-2	FR-3	FR-4	FR-5	G-10	G-11	CEM-1	CEM-3	FR-6	CFR-1
Peel strength, min, lb/in. width: 1/2 oz copper after solder float condition A at elevated temperature condition E-1/125	...	...	...	...	6 4	6 2	6 4	6 2	...	6 4	...	...
1 oz copper after solder float condition A <sup>B</sup> at elevated temperature condition E-1/125	6	6	6	8	8	8	8	8	7	8	7	8
2-oz copper after solder float condition A at elevated temperature condition E-1/125	...	...	...	5	5	3	5	3	5	5	...	1
3, 4, 5 oz copper after solder float condition A at elevated temperature condition E-1/125	7	7	7	9	10	10	10	10	9	10	8	10
Flexural strength, avg, min at elevated temperature condition E-1/125	...	...	...	10	11	11	11	11	10	11	...	...
psi 1/32 to 3/32 in. only	...	...	...	7	7	5	7	5	7	7	...	...
lengthwise condition A	12000	12000	12000	20000	60000	60000	60000	60000	...	...	15000	...
crosswise condition A	10500	10500	10500	16000	50000	50000	50000	50000	40000	40000	15000	...
psi 1/8 and 1/4 in. only	12000	12000	12000	20000	55000	55000	55000	55000	...	...	...	...
lengthwise condition A	10500	10500	10500	16000	45000	45000	45000	45000	...	...	...	...
crosswise condition A	...	...	...	...	...	...	...	30000	...	...	...	...
Flexural strength test at 150°C lengthwise, all thicknesses, min lengthwise, min % retention of condition A	...	...	...	...	...	...	...	...	...	...	...	...
1/16 and 3/32 in.	...	...	...	...	...	40	...	40	...	...	...	...
1/32, 1/8, 1/4 in.	...	...	...	...	...	50	...	50	...	...	...	...
Flexural strength, avg, min psi condition A only	...	...	...	...	...	...	...	...	...	...	...	...
1/32 in. thick lengthwise	...	...	...	...	...	...	...	...	50000	50000	...	3000
1/16 in. thick lengthwise	...	...	...	...	...	...	...	...	35000	40000	...	...
3/32 in. thick lengthwise	...	...	...	...	...	...	...	...	30000	33000	...	...
1/16 in. thick crosswise	...	...	...	...	...	...	...	...	28000	32000	...	...
3/32 in. thick crosswise	...	...	...	...	...	...	...	...	25000	27000	...	...
Flammability Rating A and E-168/70	...	...	1	1	1	1	...	...	0	0	1	0
Water absorption, avg, max % condition D-24/23	1.30	1.30	1.30	1.00	0.50	0.50	0.50	0.50	0.50	0.50	...	1.00
1/32 in. thick	1.00	0.75	0.75	0.65	0.25	0.25	0.25	0.25	0.30	0.25	...	...
1/16 in. thick	0.85	0.65	0.65	0.60	0.20	0.20	0.20	0.20	0.25	0.20	0.40	...
3/32 in. thick	0.75	0.55	0.55	0.50	0.15	0.15	0.15	0.15	...	...	...	...
1/8 in. thick	0.60	0.40	0.40	0.25	0.13	0.13	0.13	0.13	...	...	...	...
1/4 in. thick	10 <sup>4</sup>	10 <sup>4</sup>	10 <sup>4</sup>	10 <sup>5</sup>	10 <sup>6</sup>	10 <sup>6</sup>	10 <sup>6</sup>	10 <sup>6</sup>	10 <sup>6</sup>	10 <sup>6</sup>	10 <sup>6</sup>	10 <sup>5</sup>
Volume resistivity, min MΩ-cm C-96/35/90	10 <sup>3</sup>	10 <sup>3</sup>	10 <sup>3</sup>	10 <sup>4</sup>	10 <sup>4</sup>	10 <sup>4</sup>	10 <sup>4</sup>	10 <sup>4</sup>	10 <sup>4</sup>	10 <sup>4</sup>	10 <sup>4</sup>	10 <sup>5</sup>
Surface resistivity, min MΩ/square C-96/35/90	15	15	15	30	40	40	40	40	40	40	30	30
Dielectric breakdown parallel to laminations, min, Kv condition D-48/50	...	...	...	...	...	...	...	...	...	...	...	...
Dissipation factor, avg, max at 1 MHz condition D-24/23	0.05	0.05	0.05	0.04	0.035	0.035	0.035	0.035	0.04	0.04	0.03	0.03
all thicknesses	...	...	...	...	...	...	...	...	...	...	...	...
thicknesses from 1/16 to 1/8 in.	0.05	0.05	0.05	...	...	...	...	...	...	...	...	...
Permittivity, avg, max at 1 MHz condition D-24/23	...	...	...	4.8	5.4	5.4	5.4	5.4	...	...	4.3	4.0
all thicknesses	...	...	...	...	...	...	...	...	...	...	...	...
1/32 and 1/8 in. thick only	5.3	5.3	5.3	...	...	...	...	...	5.2	5.4	...	...
1/16 in. thick only	...	...	...	...	...	...	...	...	5.0	5.4	...	...
3/32 in. thick only	...	...	...	...	...	...	...	...	4.8	5.4	...	...

<sup>A</sup> Conversion factors: 0.001 in. = 0.0254 mm; 1 oz = 28.349 g.

<sup>B</sup> See Table 9.

## 67. Warp or Twist

67.1 The warp or twist of copper-clad laminate shall meet the requirements of Table 6. The maximum values shown in Table 6 are percentage values applicable only to sheet sizes as manufactured and to sheets cut such that neither length nor width is less than 18 in. (457 mm). The values shown are percentages based upon 36-in. (914-mm) dimension sheets.

## 78. Blistering

78.1 No blistering shall occur due to exposure of specimens of the material to air at the temperatures and times shown in Table 7. This requirement applies to copper-clad specimens and to laminate from which all of the copper has been etched.

## 89. Workmanship and Surface Requirements

89.1 *Grades XXXP, XXXPC, FR-2 and FR-6 Only:*

89.1.1 Copper surfaces shall be free from defects which may affect serviceability of the laminate. Such defects in copper surfaces include blisters, wrinkles, cracks, dents, and scratches.

89.1.2 The copper shall not contain any pin holes having average diameter greater than 0.015 in. (0.381 mm).

89.1.3 Pin holes in the copper exceeding average diameter 0.005 in. (0.127 mm) shall not be present in concentration exceeding one per ft<sup>2</sup>.

89.1.4 The number of inclusions in copper which are larger than 0.020 in. (0.508 mm) in length shall be limited in a single ft<sup>2</sup> of laminate and in any single sheet of approximately 0.5 m<sup>2</sup> size. The limits are:

89.1.4.1 5 in any one ft<sup>2</sup>, and

89.1.4.2 10 in any one 0.5 m<sup>2</sup> size sheet.

89.1.5 The unclad laminate surface shall have a semi-gloss or dull finish.

89.2 *Grades FR-3, FR-4, FR-5, CEM-1, CEM-3, G-10, G-11, and CFR-1:*

89.2.1 Copper surfaces shall be free from defects which may affect serviceability. Such defects include blisters, wrinkles, and cracks. The copper surfaces shall be free from other defects as required in 89.2.2.

89.2.2 Pits are small holes occurring as imperfections that do not penetrate entirely through the copper foil. Dents are depressions in the copper foil that do not significantly decrease the thickness of the copper foil. Pits and dents are limited by a point count system in which the maximum total allowable point count for pits and dents is 35 per ft<sup>2</sup> (377/m<sup>2</sup>). Pits and dents carry various point counts depending upon the longest dimension of the pit or dent. Table 8 and Table 9 provides point count values for various dimensions.

89.2.3 Pinholes are small holes occurring as imperfections that penetrate entirely through the copper foil. A pinhole having an area equivalent to a 0.005-in. (0.127-mm) diameter circle is a defect. A maximum of one such pinhole is allowable in a 5-ft<sup>2</sup> (0.46-m<sup>2</sup>) area of laminate. Pinholes of smaller area are also defects and the aggregate sum of the areas of all smaller pinholes in a 5-ft<sup>2</sup> piece of laminate is limited to the equivalent area of a 0.005-in. diameter circle.

89.2.4 Inclusions are foreign particles which may or may not be enclosed in the mass of copper foil. Inclusions, having longest dimension 0.005 in. (0.127 mm) or more, are defects which are not allowed. Inclusions having longest dimension between 0.001 and 0.005 in. (0.0254 and 0.127 mm) are permitted providing the concentration of such minor defects does not exceed 5 per ft<sup>2</sup> of copper-clad laminate area.

89.2.5 Scratches are imperfections in the copper surface that do not extend through the entire thickness of the copper foil. A scratch is considered to be an imperfection in a copper surface if either the length or width dimension is between 0.2 and 4 in. (5 and 100 mm) and its depth dimension is between 5 and 20 % of the copper foil thickness. Imperfections with any depth greater than 20 % of the copper foil thickness are considered to be cracks.

89.2.5.1 An imperfection of any length or width that has a depth dimension smaller than 5 % of the copper foil thickness is considered not to be a nonconformity.

89.2.5.2 The concentration of scratches shall not exceed 5/ft<sup>2</sup> (54/m<sup>2</sup>) of the copper-clad laminate surface.

89.2.5.3 Do not include in the number of scratches any that appear within 0.5 in. (13 mm) of any sheet edge.

89.2.5.4 The laminate shall be free from any scratches that exceed 4-in. (100-mm) length. The laminate shall be free from any scratches having depths greater than 20 % of the copper foil thickness.

**TABLE 6 Maximum Warp or Twist for All Grades, % based on 36-in. dimension**

Range of Laminate Thickness, in.	Class I			Class II			
	Clad 1 Side, ½, 1, or 2 oz Copper	Clad 2 Sides ½, 1, or 2 oz Copper		Clad 1 or 2 Sides ½, 1, or 2 oz Copper CFR-1	Clad 1 Side ½, 1, or 2 oz Copper	Clad 2 Sides ½, 1, or 2 oz Copper	
		Glass	Paper			Glass	Paper
0.004 to 0.018	20	8	NA <sup>A</sup>	NA	15	6	NA
0.019 to 0.031	15	6	NA	NA	12	4	NA
1/32 to 3/64	12	5	6	NA	10	2	5
Over 3/64 to 1/16	10	5	6	NA	5	1	2.5
Over 1/16 to 1/8	8	3	3	NA	5	1	2.5
Over 1/8 to 1/4	5	1.5	1.5	NA	5	1	1.5

<sup>A</sup>Not Applicable.

**TABLE 7 Blistering Exposure Conditions**

Grade	Temperature, °C	min
XXXP, XXXPC, FR-2	118 to 122	30
FR-3	118 to 122	60
FR-4, FR-5, FR-6, G-10, G-11, CEM-1, CEM-3, CFR-1	138 to 142	60

**TABLE 8 Point Count Values for Pits and Dents**

	Longest Dimension		Point Value
	in.	mm	
0.005 to 0.010 inclusive	0.127 to 0.254		1
0.011 to 0.020 inclusive	0.279 to 0.508		2
0.021 to 0.030 inclusive	0.533 to 0.762		4
0.031 to 0.040 inclusive	0.787 to 1.016		7
greater than 0.040	greater than 1.016		30

**TABLE 9 Times and Temperatures for Solder Float Test**

Grades	Overall Composite Thickness, in. (mm)			
	up to 1/16 (1.6)		1/16 (1.6) and over	
	Time, s	Temperature, °F (°C)	Time, s	Temperature, °F (°C)
XPC, XXXPC, and FR-2	10	475 ± 4 (246.1 ± 2)	5	500 ± 4 (260 ± 2)
FR-3	5	500 ± 4 (260 ± 2)	5	500 ± 4 (260 ± 2)
FR-4, FR-5, CEM-1, CEM-3, FR-6, G-10, G-11, and CFR-1	20	500 ± 4 (260 ± 2)	20	500 ± 4 (260 ± 2)

89.2.6 Surface finish of the copper foil shall not exceed a roughness of 20 µm (0.0005 mm) arithmetic average.

89.2.7 The requirements of 89.2.1-89.2.6 do not apply to any portion of a laminate sheet which is within 0.5 in. (13 mm) of any edge of the sheet.

## 9. Sampling

9.1 Unless otherwise agreed upon by the purchaser and the seller, sample the laminate to be tested in accordance with Practice D 3636. The selection of inspection levels and acceptable quality level (AQL) shall be agreed upon between purchaser and seller.

## 10. Number of Tests

~~10.1 In case of failure under any of Sampling~~

~~10.1 Unless otherwise agreed upon by the tests specified, two additional sheets may be tested. If both additional sheets provide results in conformance to these specifications, purchaser and the lot or shipment of seller, sample the laminate shall to be judged tested in conformance to this specification. If any of the test results from the additional sheets are not in conformance accordance with this specification, the lot or shipment Practice D 3636. The selection of inspection levels and acceptable quality level (AQL) shall be regarded as not meeting the requirements of this specification. agreed upon between purchaser and seller.~~

## 11. Test Methods

~~11.1 Unless otherwise specified, determine all Number of Tests~~

~~11.1 In case of failure under any of the properties called for tests specified, two additional sheets may be tested. If both additional sheets provide results in conformance to these specifications, the lot or shipment of laminate shall be judged in accordance with Test Methods D 5109.~~

~~11.2 Unless otherwise specified, use only conformance to this specification. If any of the test results and from the additional sheets are not test measurements (see Practice D 3636) to judge in conformance with this specification, the lot or shipment shall be regarded as not meeting the requirements of the tables set forth in this specification.~~

## 12. Packaging and Product Marking

~~12.1 Package laminate in containers to ensure acceptance by common, or other, carriers for safe transportation at lowest rate to the point of delivery. Package the laminate so as to protect the copper surfaces from damage and to prevent the laminate from sliding or shifting position during transportation.~~

~~12.2 Unless Test Methods~~

~~12.1 Unless otherwise specified, mark each full size sheet determine all of laminate internally with the manufacturer's identification. Such marking shall appear at least once properties called for in any 3 by 3 in. (75 by 75 mm) section of the laminate. All grades of CFR 1 and grades FR-6 this specification in accordance with copper on two sides need not be so marked.~~

~~12.3 If the laminate is flammability rated, Test Methods D 5109.~~

~~12.2 Unless otherwise specified, use a red color for the internal marking of 12.2. If the laminate is only test results and not flammability rated, use some color other than red for test measurements (see Practice D 3636) to judge conformance to the marking requirements of 12.2.~~

~~12.4 Mark shipping containers with:~~

~~12.4.1 The ASTM grade (from Table 1);~~

~~12.4.2 The class of laminate (from Table 4);~~

~~12.4.3 The nominal overall laminate thickness;~~

~~12.4.4 The nominal weight of copper foil cladding;~~

~~12.4.5 The cladding: one or two sides;~~

~~12.4.6 The dimensions of the sheets;~~

~~12.4.7 The manufacturer's name;~~

~~12.4.8 The quantity of material, such quantity being defined by the purchase order or the contract for procurement, and;~~

~~12.4.9 The purchase order number or contract number, tables set forth in this specification.~~

### **13. Packaging and Product Marking**

13.1 Package laminate in containers to ensure acceptance by common, or other, carriers for safe transportation at lowest rate to the point of delivery. Package the laminate so as to protect the copper surfaces from damage and to prevent the laminate from sliding or shifting position during transportation.

13.2 Unless otherwise specified, mark each full size sheet of laminate internally with the manufacturer's identification. Such marking shall appear at least once in any 3 by 3 in. (75 by 75 mm) section of the laminate. All grades of CFR 1 and grades FR-6 with copper on two sides need not be so marked.

13.3 If the laminate is flammability rated, use a red color for the internal marking of 13.2. If the laminate is not flammability rated, use some color other than red for the marking of 13.2.

13.4 Mark shipping containers with:

13.4.1 The ASTM grade (from Table 1),

13.4.2 The class of laminate (from Table 4),

13.4.3 The nominal overall laminate thickness,

13.4.4 The nominal weight of copper foil cladding,

13.4.5 The cladding: one or two sides,

13.4.6 The dimensions of the sheets,

13.4.7 The manufacturer's name,

13.4.8 The quantity of material, such quantity being defined by the purchase order or the contract for procurement, and,

13.4.9 The purchase order number or contract number.

### **14. Keywords**

134.1 circuit board; copper-clad laminate; printed circuit board; printed wiring board; thermosetting laminate

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).*