



Standard Specification for General-Purpose Ethylene-Propylene Rubber Jacket for Wire and Cable¹

This standard is issued under the fixed designation D 2768; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers a weather and ozone-resisting crosslinked compound for use as the outer covering or jacket on insulated wires and cables. The polymer component of this material consists substantially of ethylenepropylene copolymer (EPM) or ethylene-propylene terpolymer (EPDM).

1.2 The values stated in inch-pound units are the standard, except in cases where SI units are more appropriate. The values in parentheses are for information only.

2. Referenced Documents

2.1 ASTM Standards:

D 257 Test Methods for D-C Resistance or Conductance of Insulating Materials²

D 470 Test Methods for Crosslinked Insulations and Jackets for Wire and Cable²

D 1499 Practice for Operating Light- and Water-Exposure Apparatus (Carbon-Arc Type) for Exposure of Plastics³

G 23 Practice for Operating Light-Exposure Apparatus (Carbon-Arc Type) With and Without Water for Exposure of Nonmetallic Materials⁴

3. Electrical Requirements

3.1 When used on single conductor nonshielded cables rated

2001 through 5000 V phase to phase, the jacket shall meet the following requirements of Test Methods D 470:

3.1.1 *Surface Resistivity*—The jacket shall have a surface resistivity equal to or greater than 200 000 M Ω .

3.1.2 *U-Bend Discharge*—There shall be no cable failure nor cracks in the jacket when a sample of completed cable is subjected to the U-bend discharge test at 150 V/mil (6 kV/mm) for at least 6 h.

4. Test Applicable for Sunlight and Weather Resistant Materials

4.1 The jacket shall retain a minimum of 80 % of its unaged tensile strength and elongation after 720 h of exposure in a dual carbon-arc apparatus. Prepare the specimens in accordance with Test Methods D 470 for physical tests of insulations and jackets. Perform the test in accordance with Practice D 1499 using Method 1 of Practice G 23.

5. Physical Requirements

5.1 The crosslinked jacket shall conform to the physical properties specified in Table 1.

6. Sampling

6.1 Sample the jacket in accordance with Test Methods D 470.

7. Test Methods

7.1 Unless otherwise instructed, test the jacket in accordance with Test Methods D 470.

8. Keywords

8.1 ethylene-propylene rubber; sunlight resistant; surface resistivity; U-bend discharge; weather resistant

¹ This specification is under the jurisdiction of ASTM Committee D-9 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.18 on Solid Insulations, Non-Metallic Shielding, and Coverings for Electrical and Telecommunications Wires and Cables.

Current edition approved Feb. 15, 1995. Published April 1995. Originally published as D 2768-68. Last previous edition D 2768-89.

² *Annual Book of ASTM Standards*, Vol 10.01.

³ *Annual Book of ASTM Standards*, Vol 08.01.

⁴ *Annual Book of ASTM Standards*, Vol 14.02.

TABLE 1 Physical Properties for General-Purpose EPM or EPDM Jacket^A

Unexposed (Unaged) Requirements:	
Tensile strength, min, psi	1500
(MPa)	(10.3)
Elongation at rupture, min, %	200
Exposed (Aged) Requirements:	
After air oven test at 121 ± 1°C for 168 h:	
Tensile strength, min, psi	1200
(MPa)	(8.3)
Elongation at rupture, min, %	175

^A The values specified are applicable only to jackets having a nominal thickness of .030 in. (0.76 mm) or more.

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).