



# Standard Specification for Ozone-Resisting Ethylene-Propylene Rubber Integral Insulation and Jacket for Wire and Cable<sup>1</sup>

This standard is issued under the fixed designation D 2770; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification covers a weather- and ozoneresisting vulcanized rubber integral insulation and jacket compound for electrical wires and cables. The rubber polymer shall consist substantially of ethylenepropylene copolymer (EPM) or of ethylenepropylene terpolymer (EPDM).

1.2 This type insulation is considered suitable for use on wire or cable which will be used for continuous operation at conductor temperatures up to 90°C in dry locations and 75°C in wet locations, and at operating voltages not exceeding 2000 V.

1.3 The values stated in inch-pound units, except for temperature, are regarded as the standard. The values in parentheses are for information only.

## 2. Referenced Documents

### 2.1 ASTM Standards:

D 470 Test Methods for Crosslinked Insulations and Jackets for Wire and Cable<sup>2</sup>

## 3. Physical Properties

3.1 The crosslinked integral covering shall conform to the requirements for physical properties specified in Table 1.

3.2 *Thickness of Insulation*—The average thickness of the insulation shall be not less than that given in Table 2. The minimum thickness shall be not less than 90 % of the specified thickness.

## 4. Electrical Requirements

4.1 *Order of Testing*—Perform the ac voltage withstand, insulation resistance, and dc voltage withstand tests in that order when any of these tests are required. The sequence for other testing is not specified.

4.2 *AC Voltage Withstand Test*—Each length of integrally covered conductor shall withstand for 5 min the ac voltage specified in Table 2, unless the dc test in 4.4 is performed.

4.3 *Insulation Resistance*—The integrally covered conduc-

**TABLE 1 Physical Test Requirements for EPM or EPDM Integral Insulation and Jacket**

Physical Requirements (original):	
Tensile stress at 100 % elongation, min, psi (MPa)	500 (3.4)
Tensile strength, min, psi (MPa)	1200 (8.3)
Elongation at rupture, min, %	150
Physical Requirements [After heat exposure (aging) in an air oven at 121 ± 1°C for 168 h]:	
Tensile strength, min, % of original	75
Elongation at rupture, min, % of original	75

tor shall have an insulation resistance not less than that corresponding to a constant of 10 000 at 60°F (15.6°C). Where the temperature of the water in which the insulation is tested differs from 60°F, the measured value obtained shall be multiplied by the proper correction factor for the particular compound as previously determined by the manufacturer.

4.4 *DC Voltage Withstand Test*—Upon completion of the insulation resistance test, each length of integrally covered conductor shall withstand for 5 min the d-c test voltage specified in Table 2 unless the a-c test described in 4.2 is performed.

4.5 *Accelerated Water Absorption*—The integral covering shall meet the requirements of Table 3. The Electrical Method Test shall be conducted at 60 Hz with the water temperature at 75 ± 1°C. The water temperature in the Gravimetric Method Test shall be 70 ± 1°C.

## 5. Ozone Resistance

5.1 The integral covering shall show no injury after exposure for 3 h to an ozone concentration of between 0.025 and 0.03 % volume.

## 6. Sampling

6.1 Sample the integral insulation and jacket in accordance with Test Methods D 470.

## 7. Test Methods

7.1 Test the integral insulation and jacket in accordance with Test Methods D 470.

## 8. Keywords

8.1 AC Voltage Withstand Test; DC Voltage Withstand Test; ethylene-propylene rubber; insulation resistance; ozone resisting; water absorption

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D-9 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.18 on Solid Insulations, Nonmetallic Shieldings and Coverings for Electrical and Telecommunications Wires and Cables.

Current edition approved June 15, 1993. Published August 1993. Originally published as D 2770 – 68. Last previous edition D 2770 – 80 (1987).

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 10.01.

**TABLE 2 Conductor Sizes, Insulation Thicknesses and Test Voltages**

Rated Circuit Voltage Phase to Phase, V <sup>A</sup>	Conductor Size, AWG or Kcmil (mm <sup>2</sup> )	Insulation Thickness		Test Voltage, kV	
		mils	(mm)	AC	DC
0 to 600	14 to 9 <sup>B</sup> (2.08 to 6.63)	45	(1.14)	4.0	12.0
	8 to 2 (8.37 to 33.6)	60	(1.52)	5.5	16.5
	1 to 4/0 (42.4 to 107)	80	(2.03)	7.0	21.0
	225 to 500 (140 to 523)	95	(2.41)	8.0	24.0
	501 to 1000 (254 to 507)	110	(2.79)	10.0	30.0
601 to 2000	14 to 9 <sup>C</sup> (2.08 to 6.63)	60	(1.52)	5.5	16.5
	8 to 2 (8.37 to 33.6)	70	(1.78)	7.0	21.0
	1 to 4/0 (42.4 to 107)	90	(2.29)	8.0	24.0
	225 to 500 (140 to 523)	105	(2.67)	9.5	28.5
	501 to 1000 (254 to 507)	120	(3.05)	11.5	34.5

<sup>A</sup> The actual operating voltage shall not exceed the rated circuit voltage by more than (1) 5 % during continuous operation or (2) 10 % during emergencies lasting not more than 15 min.

<sup>B</sup> In common with other electrical equipment, the use of cables is not recommended on systems where the ratio of the zero to positive reactance of the system at the point of cable application lies between -1 and -40 since excessively high voltages may be encountered in the case of ground faults.

<sup>C</sup> Single-conductor cables in sizes 9 AWG (6.63 mm<sup>2</sup>) and smaller shall not be used for direct burial.

**TABLE 3 Accelerated Water Absorption Test Requirements**

Electrical Method:	
Permittivity after 1 day, max	6.0
Increase in capacitance, %:	
1 to 14 days	5.0
7 to 14 days	3.0
Stability factor after 14 days, max	1.0
Gravimetric Method:	
Water absorption, max, mg/in. <sup>2</sup> (g/m <sup>2</sup> )	15.0 (23)

*The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).*