



Standard Test Method for Weight Loss of Solventless Varnishes¹

This standard is issued under the fixed designation D 3377; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of the percent weight loss of cured solventless electrical varnishes when exposed to elevated temperatures for prescribed periods of time.

1.2 Results of this test method are based on 6.4-mm ($\frac{1}{4}$ -in.) thick specimens and may not be applicable to specimens appreciably thinner or thicker than 6.4 mm.

1.3 The values stated in SI units are to be regarded as the standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*

D 5423 Specification for Forced-Convection Laboratory Ovens for Evaluation of Electrical Insulation²

3. Terminology

3.1 *Definition:*

3.1.1 *varnish, n*—*electrical insulating*, a liquid resin system that is applied to and cured on electrical components providing electrical, mechanical, and environmental protection.

3.1.1.1 *Discussion*—There are two types of electrical insulating varnish: solvent-containing and solventless. The solvent-containing varnish is a solution, dispersion, or emulsion of a polymer or mixture of polymers in a volatile, nonreactable liquid. The solventless type is a liquid resin system free of volatile, nonreactable solvents.

4. Significance and Use

4.1 The amount and composition of by-products produced by exposure of insulating varnishes to elevated temperatures can possibly:

4.1.1 Deteriorate other insulations in the system,

4.1.2 Cause cracking of insulation due to pressure, buildup in thick cross sections, or

4.1.3 Corrode other parts in the assembly.

4.2 Amount and rate of weight loss may affect the thermal rating of a varnish.

5. Apparatus

5.1 *Metal Mold*, consisting of two flat sheets 305 by 305 by 6.4 mm (12 by 12 by $\frac{1}{4}$ in.) separated by 6.4-mm ($\frac{1}{4}$ -in.) thick spacers along three sides. The spacers also seal the edges of the mold and the assembly is held together with “C” clamps or bolts. Aluminum or polished steel plates can be used.

5.2 *Laboratory Balance*, with accuracy of ± 1 mg.

5.3 *Forced-Convection Laboratory Oven*, meeting requirements of Specification D 5423, Type II for each test temperature.

5.4 *Screening Platform*, 6.4-mm ($\frac{1}{4}$ -in.) mesh, with 51-mm (2-in.) legs.

5.5 *Mold Release*.

NOTE 1—Fluorocarbon-type release agents are satisfactory.

5.6 Desiccator.

6. Procedure

6.1 Apply a thin, uniform coating of release agent to the contact surfaces of the mold.

6.2 Assemble the mold, taking precautionary measures to avoid leaks.

6.3 Pour the sample into the open edge of the mold, using care to avoid bubbles.

NOTE 2—In some cases, it may be necessary to prevacuum the sample before pouring.

6.4 Cure the sample using the recommended cure cycle.

6.5 After curing, remove the mold and contents from the oven and allow to cool to room temperature.

6.6 Carefully disassemble the mold and remove the cast sheet.

6.7 From the cast sheet, cut at least three specimens approximately 51 by 51 mm (2 by 2 in.) for each test temperature.

6.8 Dry the specimens for 1 h \pm 5 min at 110 \pm 2°C to remove surface moisture.

6.9 Remove specimens from the oven and place them immediately into the desiccator.

¹ This test method is under the jurisdiction of ASTM Committee D-9 on Electrical and Electronic Insulating Materials and is direct responsibility of Subcommittee D09.01 on Electrical Insulating Varnishes, Powders, and Encapsulating Compounds.

Current edition approved May 10, 1996. Published July 1996. Originally published as D 3377 – 75. Last previous edition D 3377 – 91.

² *Annual Book of ASTM Standards*, Vol 10.02.

TABLE 1 Standard Deviation and Weight Loss

Hours at Temperature	Weight Loss, %			Standard Deviation		
	Oven Aging Temperatures, °C					
	180	200	220	180	200	220
24	0.119	0.331	0.618	0.028	0.048	0.029
48	0.150	0.420	0.772	0.047	0.056	0.056
72	0.170	0.475	0.849	0.054	0.074	0.110
96	0.190	0.525	0.977	0.060	0.076	0.103
168	0.229	0.734	1.34	0.049	0.102	0.194

6.10 After cooling to room temperature in the desiccator, weigh each specimen to the nearest 1 mg.

6.11 Lay the specimens on the screen platform so that they are at least 3 mm (1/8 in.) apart.

6.12 Place the loaded platforms in the oven.

6.13 *Exposure Temperatures:*

Anticipated End Use Temperature, °C	Temperature Range, °C
105	125 to 180
130	150 to 200
155	175 to 225
180	200 to 250
200	220 to 275
220	250 to 300

Choose three temperatures within the above ranges at least 20°C apart.

6.14 *Exposure Times:*

Hours—24 48 72 96 168

NOTE 3—If desired, exposure times can be extended.

6.15 After each test period, remove the specimens from the oven and place immediately into the desiccator to cool to room temperature.

6.16 Weigh the specimens to the nearest 1 mg.

7. Calculation

7.1 Calculate the percent weight loss as follows:

$$\text{weight loss, \%} = [(A - B)/A] \times 100 \quad (1)$$

where:

A = initial weight, and

B = weight after aging.

8. Report

8.1 Report the following information:

8.1.1 Identity of compound,

8.1.2 Cure cycle used, and

8.1.3 Percent weight loss after each aging period and for each test temperature.

9. Precision and Bias

9.1 *Precision:*

9.1.1 The standard deviation of testing at five laboratories, for different times and temperatures, is shown in Table 1.³

9.1.2 A statement of bias is not applicable since a standard reference material is not available for this property.

9.2 *Bias*—This test method has no bias because the value for weight loss is defined solely in terms of this test method.

10. Keywords

10.1 solventless varnish; varnish; weight loss

³ Supporting data are available from ASTM Headquarters. Request RR: D-9-1014.

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).