



Standard Specification for Ozone-Resistant Thermoplastic Elastomer Insulation For Wire and Cable, 90°C Operation¹

This standard is issued under the fixed designation D 4246; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers an ozone-resistant insulating compound for electrical wire and cables 14 AWG and larger. This compound consists substantially of a thermoplastic elastomer.

1.2 This type of insulation is considered suitable for continuous operation at conductor temperatures not exceeding 90°C in dry locations. Operating voltages are not to exceed 2000 V. The minimum installation temperature is -40°C.

1.3 The values stated in inch-pound units are the standard, except in cases where SI units are more appropriate. The values in parentheses are for information only.

1.4 In many instances the insulation cannot be tested unless it has been formed around a conductor or cable. Therefore, tests are done on insulated wire or cable in this specification solely to determine the relevant property of the insulation and not to test the conductor or completed cable.

2. Referenced Documents

2.1 ASTM Standards:

D 470 Test Methods for Crosslinked Insulations and Jackets for Wire and Cable²

D 2633 Methods of Testing Thermoplastic Insulations and Jackets for Wire and Cable³

3. Terminology

3.1 Definition of Term Specific to This Standard.

3.1.1 *aging (act of), n*—the exposure of materials to air at 121°C for 168 h.

4. Physical Properties

4.1 Requirements for physical properties are listed in Table 1.

4.2 *Thickness of Insulation*—Table 1(a), (Conductor Sizes, Insulation Thicknesses, and AC Test Voltages for Rubber Insulations) of Test Methods D 470 lists the minimum average

¹ This specification is under the jurisdiction of ASTM Committee D-9 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.18 on Solid Insulations, Non-Metallic Shieldings, and Coverings for Electrical and Telecommunications Wires and Cables.

Current edition approved Jan. 10, 1997. Published February 1998. Originally published as D 4246 – 83. Last previous edition D 4246 – 89.

² *Annual Book of ASTM Standards*, Vol 10.01.

³ *Annual Book of ASTM Standards*, Vol 10.02.

TABLE 1 Requirements for Physical Properties

<i>Unaged Requirements:</i>	
Tensile strength, min, psi (MPa)	1000 (6.9)
Elongation at rupture, min, %	300
<i>Aged Requirements (after air oven test at 121 ± 1°C for 168 h):</i>	
Tensile strength and elongation, at rupture min, % of unaged value	75
<i>Heat Distortion (at 150 ± 1°C, max, % of unaged value):</i>	
4/0 AWG (107 m ²) and smaller (insulation on cable)	50
Larger than 4/0 AWG (107 mm ²) (buffed sample of insulation)	50

thickness for the insulation. The required minimum thickness is 90 % of the specified average thickness.

5. Electrical Requirements

5.1 *Order of Testing*—Perform the ac voltage, insulation resistance, and dc voltage tests in that order when any of these tests are specified. The sequence of other testing is not specified.

5.2 *AC Voltage Test*—Unless otherwise specified, omit this test if the dc voltage test described in 5.4 is to be performed. Test each insulated conductor for 5 min at the ac voltage given in Table 1(a) (Conductor Sizes, Insulation Thicknesses, and AC Test Voltages, for Rubber Insulations) of Methods D 470 under the columns labelled “Ozone-Resisting Insulations.”

5.3 *Insulation Resistance*—The insulated conductor shall have an insulation resistance value of at least that corresponding to a constant of 10 000 at 60°F (15.6°C).

5.3.1 If the water temperature at the time measurement was made differs from 60°F (15.6°C), correct the insulation resistance to 60°F. Table 2, (Temperature Correction Factors for Insulation Resistance at 60°F) of Test Methods D 470 contains the correction factors. Each insulation manufacturer can furnish the 1°F coefficient for the insulation material by using the procedure given in Test Methods D 470. Multiply the measured value by the correction factor to obtain the insulation resistance value corrected to 60°F.

5.3.2 If the insulated conductor is covered with a non-metallic sheath so that the insulation resistance can be measured only on the completed assembly, the required insulation resistance shall be at least 60 % of that required for the primary insulation based on the thickness of that insulation.

5.4 *DC Voltage Test*—Unless otherwise specified, omit this test if the ac voltage test described in 5.2 has been performed.

After completion of the insulation resistance test, test each insulated conductor for 5 min at the dc test voltage given in Table 1(b) (Conductor Sizes, and DC Test Voltages for Rubber Insulations) of Test Methods D 470 under the columns labelled “Ozone-Resisting Insulations.”

6. Cold Bend

6.1 The insulation shall not show any cracks when tested at a temperature of -55°C in accordance with the procedure and Table 7 (Mandrel Diameters for Cold Bend Test) in Methods D 2633.

7. Ozone

7.1 The insulation shall show no cracking or surface checking visible to the unaided eye after exposure to an ozone concentration of not less than 0.025 nor more than 0.030 % by volume, when tested in accordance with Test Methods D 470.

8. Heat Distortion

8.1 The insulation shall meet the requirements in Table 1 when tested in accordance with the procedure in Methods D 2633.

9. Sampling

9.1 Unless otherwise instructed, sample the insulation in accordance with Test Methods D 470.

10. Test Methods

10.1 Unless otherwise instructed, test the insulation in accordance with Test Methods D 470.

11. Keywords

11.1 ac voltage test; dc voltage test; insulation; insulation resistance; 90°C insulation; ozone-resistant; thermoplastic elastomer; thermoplastic elastomer insulation

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).