



Designation: **D 4514 – 9500**

An American National Standard

Standard Specification for Friction Tape¹

This standard is issued under the fixed designation D 4514; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

¹ This specification is under the jurisdiction of ASTM Committee ~~D-9~~ D09 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.07 on Flexible and Rigid Insulating Materials.

Current edition approved ~~Feb. 15, 1995~~; Apr. 10, 2000. Published ~~April 1995~~; June 2000. Originally published as D 4514 – 85. Last previous edition ~~D 4514 – 85 (1990)~~; D 4514 – 95.

1. Scope

1.1 This specification² covers friction tapes that are commonly used for protecting, and binding in place, insulation applied to joints of electrical wires and cables, and for other mechanical purposes.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values in parentheses are for information only.

2. Referenced Documents

2.1 *ASTM Standards:*

D 69 Test Methods for Friction Tapes³

D 1711 Terminology Relating to Electrical Insulation³

D 3636 Practice for Sampling and Judging Quality of Solid Electrical Insulating Materials⁴

2.2 *Federal Specifications:*

PPP-B-636 Box, Fiberboard⁵

2.3 *Federal Standards:*

Fed. Std. No. 123 Marking for Shipment (Civil Agencies)⁵

2.4 *Military Standards:*

MIL-STD-129 Marking for Shipment and Storage⁵

3. Terminology

3.1 *Definitions*— For definitions of terms used in this specification, refer to Terminology D 1711.

4. Materials and Manufacture

34.1 The tape shall consist of a woven fabric sheeting impregnated with an adhesive insulating compound, cut into rolls of narrow width and wound on a core.

34.2 The fabric sheeting shall be

evenly and firmly woven and as free of unsightly defects, dirt, knots, lumps and irregularities of twist as is consistent with the best manufacturing practices. The threads shall run in lines as straight as possible without weaving, to reduce to a minimum the raveling of the cloth when cut into tape.

34.3 The frictioning compound shall be a tacky adhesive insulating compound that will not have a deteriorating effect on copper or other metals or on the fabric.

34.4 The fabric shall be thoroughly impregnated and evenly covered on both sides with the frictioning compound. The compound shall adhere firmly to the fabric and shall not pull away from the fabric and leave bare spots when adjacent layers of tape are separated.

4.5. General Requirements

45.1 Friction tapes shall meet the requirements given in Table 1 when tested in accordance with Test Methods D 69.

TABLE 1 Requirements for Friction Tape

Property	Value
Adhesion	15 in./min (380 mm/min), max
Aged Adhesion	15 in./min (380 mm/min), max
Breaking Strength	40 lb/in. (170 N/25 mm), min
Breakdown Voltage	1000 V, min
Parallelism	1/8 in. (3.2 mm), max
Tackiness	pass in all combinations

45.2 When discoloration of the surface on which the tape is to be applied is an important consideration, the purchaser may request that the tape must pass the test for discoloration of copper in accordance with Test Methods D 69.

5.6. Dimensions and Permissible Variations

56.1 The nominal dimensions and their permissible variations when measured by the procedures of Test Methods D 69 are presented in Table 2.

6. Test Methods

6.1 The selection of the rolls, conditioning, and testing shall be in accordance with Test Methods D 69.

² This specification was formerly part of Test Method D 69.

³ *Annual Book of ASTM Standards*, Vol. 10.01.

⁴ *Annual Book of ASTM Standards*, Vol 10.02.

⁵ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

TABLE 2 Dimensions and Permissible Variations

Nominal width	¾ in. (19 mm)	1 in. (25 mm)	1½ in. (38 mm)	2 in. (51 mm)
Permissible variation for average	← ← ←	± 1/32 in. (± 0.8 mm)		→ → →
Permissible variation for individual	← ← ←	± 1/16 in. (± 1.6 mm)		→ → →
Nominal thickness	← ← ←	0.015 in. (0.38 mm)		→ → →
Permissible variation for average	← ← ←	± 0.003 in. (± 0.08 mm)		→ → →
Permissible variation for individual	← ← ←	± 0.004 in. (± 0.10 mm)		→ → →
Nominal length	← ← ←	82 ft (25 m)		→ → →
Permissible variation for length	← ← ←	+ 3 ft (+0.9 m) –0 ft (–0 m)		→ → →

7. Inspection

7.1 Inspection Test Methods

7.1 The selection of the material shall be made as agreed upon between the purchaser rolls, conditioning, and the seller as part of the purchase contract.

7.2 If it is required, the tape testing shall be tested and inspected either at the place of manufacture prior to shipment or at the place of delivery within four weeks from the date of delivery, in accordance with Test Methods D 69.

8. Rejection

8.1 The purchaser reserves the right to reject any part Inspection

8.1 Inspection of the shipment that does not comply with Section 10 of this specification.

8.2 The material shall be made as agreed upon between the purchaser reserves and the right to reject a shipment from which two or more sample rolls fail to meet the requirements seller as part of any individual test or measurement prescribed in this specification, without additional sampling. If only one sample roll fails an individual test or measurement or the average length of purchase contract.

8.2 If it is required, the sample rolls exceeds the prescribed value, a second set of samples tape shall be taken in accordance with Test Methods D 69; tested and all rolls in inspected either at the second sampling shall be subjected place of manufacture prior to that test shipment or measurement wherein at the failure occurred. The purchaser reserves place of delivery within four weeks from the right to reject the shipment if the second sampling fails to conform with the applicable requirement. date of delivery.

9. Aging and Storage Rejection

9.1 The tape shall at purchaser reserves the right to reject any time, within eight months after acceptance if stored in accordance part of the shipment that does not comply with Section 11 of this specification.

9.2; The purchaser reserves the right to reject a shipment from which two or more sample rolls fail to meet the adhesion requirements of any individual test or measurement prescribed in Test Methods D 69 except that a force of 3 lbf/in. (13.3 N/25 mm) shall be substituted for this specification, without additional sampling. If only one sample roll fails an individual test or measurement or the 4 lbf/in. (17.8 N/25 mm) during unwinding.

9.2 Proper storage average length of tape requires the use of sample rolls exceeds the original boxes and prescribed value, a cool, dark location. Tape second set of samples shall not be stored near steam pipes, radiators; taken in accordance with Test Methods D 69, and all rolls in the second sampling shall be subjected to that test or measurement wher-sein the failure occurred. The purchaser reserves the right to reject the shipment if the second sampling fails to conform with the applicable requirement.

10. Aging and Storage

10.1 The tape shall at any time, within eight months after acceptance if stored in accordance with 10.2, meet the adhesion test specified in Test Methods D 69 except that a force of 3 lbf/in. (13.3 N/25 mm) shall be substituted for the 4 lbf/in. (17.8 N/25 mm) during unwinding.

10.2 Proper storage of tape requires the use of the original boxes and a cool, dark location. Tape shall not be stored near steam pipes, radiators, or other sources of heat.

11. Packaging and Package Marking

101.1 Packaging—Each roll of tape shall be enclosed in a paper carton unless otherwise specified. If enclosed in a paper carton, either the roll of tape or the carton shall be wrapped in a moisture-proof material and sealed. The wrapping on the tape or carton shall be secure and shall protect the contents fully.

101.2 Package Marking—Each box shall be marked with the name of the manufacturer or trademark, and the nominal width and length of the tape.

112. Keywords

112.1 adhesion; aged adhesion; aging; breakdown voltage; breaking strength; dimensions; friction tape; parallelism; storage; tackiness

GOVERNMENT/MILITARY PROCUREMENT

These requirements apply *only* to Federal/Military procurement, not domestic sales or transfers.

S1.1 Quality Assurance Provisions

S1.1.1 *Responsibility for Inspection*—Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements, as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

S1.1.2 *Examination and Tests*—The examinations and tests shall be in accordance with this specification, and the additional examinations set forth herein.

S1.1.3 *Sampling for Examinations* —All insulation tape of the same width offered for delivery at one time shall be considered a lot for purposes of examination. Random samples of the insulation tape shall be selected from each lot in accordance with Practice D 3636. The samples, for purposes of determining the sample size in accordance with Practice D 3636, shall be expressed in units of rolls of tape, or in the case of preparation for delivery, in units of packed shipping containers. The inspection levels and acceptance quality level (AQL), expressed in defects per 100 units, shall be in accordance with Table ~~S1-1~~ S1.1.

S1.1.4 *Examination*—Each sample selected shall be examined for compliance with the specified requirements. Examinations shall be conducted as specified requirements. Examinations shall be conducted as specified in S1.1.4.1, S1.1.4.2, S1.1.4.3, S1.1.4.4, and S1.1.4.5. If the number of nonconformities in any sample exceeds the acceptance number for the sample, the lot represented by the sample shall be rejected.

S1.1.4.1 *Examination of the End Item for Nonconformities in Appearance and Workmanship* —The sample unit for this examination shall be two continuous yards, disregarding the first three units of each sample roll (see Table ~~S1-2~~ S1.2).

S1.1.4.2 *Examination of Assembly of Roll of Tape*—The assembly shall be in accordance with Table ~~S1-3~~ S1.3.

S1.1.4.3 *Examination of the End Item for Nonconformities in Dimensions*—Samples selected in accordance with S1.1.3 shall be inspected for thickness and width in accordance with Table ~~S1-4~~ S1.4.

S1.1.4.4 *Examination of the End Item for Average Length of Tape per Roll*—The sample unit for this examination shall be one roll of tape. A minimum of five rolls shall be randomly selected throughout the lot and measured for length (see Table ~~S1-5~~ S1.5).

S1.1.4.5 *Inspection of Preparation for Delivery Requirements*—An inspection shall be made to determine that the packaging, packing, and marking requirements comply with S1.2.

S1.2. Preparation for Delivery

S1.2.1 *Packaging*—Packaging shall be Level A, B, or C, as specified.

S1.2.1.1 *Level A*—Each roll of tape shall be packaged in a snug fitting paperboard box conforming to Federal Specification PPP-B-566. The box shall be closed to prevent accidental opening.

S1.2.1.2 *Level B*—Each roll of tape shall be packaged in a cellophane or plastic wrap with the identification label secured to the outside of the wrap, or each roll shall be packaged in a printed cellophane or plastic wrap. The printed wrap shall contain the information normally required for the label or unit container. The wrap shall be secured to prevent accidental opening.

S1.2.1.3 *Level C*—Each roll of tape shall be packaged to prevent damage during shipment from the supplier to the initial destination.

S1.2.2 *Packing*—Packing shall be Level A, B, or C, as specified.

S1.2.2.1 *Level A*—One hundred rolls of tape shall be packed in a snug fitting fiberboard box conforming to Federal Specification PPP-B-636, weather-resistant class, and closure shall be in accordance with Method II of the appendix to Federal Specification PPP-B-636.

S1.2.2.2 *Level B*—One hundred rolls of tape shall be packed in snug-fitting fiberboard box conforming to Federal Specification PPP-B-636, domestic class. Closure shall be in accordance with Method I of the appendix to Federal Specification PPP-B-636.

S1.2.2.3 *Level C*—The insulation tape shall be packed in such a manner to ensure carrier acceptance and safe delivery to the destination at the lowest transportation cost for such supplies. Containers shall be in accordance with the Uniform Freight Classification or National Motor Freight Classification, as applicable.

TABLE S1.1 Inspection and Acceptable Quality Levels for Sampling Examinations

Supplementary Requirement	Table	Inspection Level	AQL
S1.1.4.1	S1.2	I	2.5
S1.1.4.2	S1.3	S-3	4.0
S1.1.4.3	S1.4	S-3	2.5
S1.1.4.5	S1.5	S-2	2.5



TABLE S1.2 Examination of the End Item for Nonconformities in Workmanship and Appearance

Examine	Nonconformity
<i>Appearance:</i>	Any tear, cut or break, lumps, knots or unevenness to tape. Dirt, foreign material or imbedded particles. Adhesive not uniform, areas not coated.
<i>Workmanship:</i>	Raveling or frayed edges. Splice in tape. Not uniform texture or finish.

S1.2.3 *Marking:*

S1.2.3.1 *Civil Agencies*—In addition to markings required by the contract or purchase order, the unit package and the shipping container shall be marked in accordance with Fed. Std. No. 123.

S1.2.3.2 *Military Agencies* —In addition to markings required by the contract or purchase order, the unit package and shipping container shall be marked in accordance with MIL-STD-129.

**TABLE S1.3 Examination of the Assembly of the
Roll of Tape**

Examine	Nonconformity
<i>Appearance:</i>	Tape not evenly, neatly, or tightly wound. Any telescoping of roll. Core missing or damaged

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).

**TABLE S1.4 Examination of the End Item for
Dimensional Nonconformities**

Examine	Nonconformity
<i>Thickness:</i>	Thickness not in accordance with this specification.
<i>Width:</i>	Width not in accordance with this specification.

**TABLE S1.5 Examination of the End Item for Average Length of
Tape per Roll**

Examine	Nonconformity
<i>Length of Roll:</i>	Length not in accordance with this specification.