



Designation: **D 5638 – 9500**

An American National Standard

## Standard Test Method for Chemical Resistance of Electrical Insulating Varnishes<sup>1</sup>

This standard is issued under the fixed designation D 5638; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This test method covers the mechanical performance of insulating varnishes after exposure to various chemicals.

1.2 The values stated in SI units are the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. See 7.1.*

NOTE 1—There is no IEC/ISO equivalent.

### 2. Referenced Documents

2.1 *ASTM Standards:*

---

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee ~~D-9~~ D09 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.01 on Electrical Insulating Varnishes, Powders, and Encapsulating Compounds.

Current edition approved ~~Jan. 15, 1995~~; Apr. 10, 2000. Published ~~March 1995~~; June 2000. Originally published as D 5638 – 94. Last previous edition D 5638 – ~~94~~ 5.

2519 Test Method for Bond Strength of Electrical Insulating Varnishes by the Helical Coil Test<sup>2</sup>

### 3. Terminology

3.1 See Test Method D 2519.

### 4. Summary of Test Method

4.1 Flexural strength tests are made on varnish-treated helical coils to determine the force required to break the coil under specified conditions both before and after exposure to liquid chemicals.

### 5. Significance and Use

5.1 This test method is useful for the evaluation of insulating varnish performance in chemical exposure.

### 6. Apparatus

6.1 *Tensile Testing Machine*—See Test Method D 2519.

6.2 *Test Fixture*—See Test Method D 2519.

6.3 *Chemical Containers*—Sealable 1000 mL containers of suitable material and design for containing the chemicals to be used.

### 7. Safety Precautions

~~7.1 Do not~~

~~7.1 It is unsafe to use varnish, solvents and reagents varnish at temperatures above their the flash point when without adequate ventilation, especially if the possibility of exists that flames or sparks exist. are present. Store varnish, solvents and reagents varnish in sealed containers.~~

### 8. Test Specimens

8.1 Prepare a minimum of five test specimens for each chemical solution to be tested and five to determine unconditioned bond strength in accordance with Test Method D 2519 using a wire mutually agreed upon by supplier and purchaser.

### 9. Procedure

9.1 Condition a minimum of five test specimens in each chemical. Chemicals, test temperature and conditioning time are mutually agreed upon by supplier and purchaser.

9.2 Test specimens both conditioned and unconditioned as described in Test Method D 2519 at standard laboratory conditions. Test conditioned within 15 min of removal from container. Rinse conditioned specimens with water and pat dry when water soluble chemicals were used for conditioning. ~~Otherwise pat dry wipe specimens~~ to remove excess chemical.

NOTE 2—When using volatile chemicals, the time between removal from the chemical and testing may affect test results.

### 10. Report

10.1 Report the following information:

10.1.1 Description of varnish,

10.1.2 Identification of wire used,

10.1.3 Cure time and temperature and number of dips used to prepare the coils,

10.1.4 Average bond strength in newtons (pounds-force) of unconditioned coils,

10.1.5 Average bond strength in newtons (pounds-force) of conditioned coils,

10.1.6 Description of chemical, exposure temperature, and exposure time to which the specimens were subjected, and

10.1.7 Percent retention of bond strength after conditioning ( $\text{Percent Retained Bond} = \frac{\text{Average Bond Strength [conditioned]}}{\text{Average Bond Strength [unconditioned]}} \times 100$ ).

### 11. Precision and Bias

~~11.1 Precision—No information has been presented to ASTM upon which to base a statement of this test method precision. No activity has not been evaluated, planned to develop such information.~~

11.2 *Bias*—This test method has no bias ~~since~~ because the value for chemical resistance is determined solely in terms of this test method.

### 12. Keywords

12.1 bond strength; chemical resistance; helical coils; varnish—

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 10.02.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)).*