



# Standard Specification for In-Service Care of Insulating Line Hose and Covers<sup>1</sup>

This standard is issued under the fixed designation F 478; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification covers the in-service care, inspection, testing, and use voltage of insulating line hose and covers for protection from electrical shock.

1.2 The following safety hazards caveat applies only to the test method portion, Section 7, of this specification: *This standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* Specific precautionary statements are given in Note 1.

## 2. Referenced Documents

### 2.1 ASTM Standards:

- D 1049 Specification for Rubber Insulating Covers<sup>2</sup>
- D 1050 Specification for Rubber Insulating Line Hose<sup>2</sup>
- D 2865 Practice for Calibration of Standards and Equipment for Electrical Insulating Materials Testing<sup>3</sup>
- F 819 Definitions of Terms Relating to Electrical Protective Equipment for Workers<sup>2</sup>

### 2.2 ANSI Standards:

- C 84.1 Voltage Ratings for Electric Power Systems and Equipment (60 Hz)<sup>4</sup>

### 2.3 IEEE Standard:

- IEEE Standard 4, Techniques for High Voltage Testing<sup>5</sup>

## 3. Terminology

3.1 *breakdown*—the electrical discharge or arc occurring between the electrodes and through the equipment being tested.

3.2 *bulk storage*—the storage of hose or covers together with one or more layers piled neatly, but without the benefit of spacers, supports, or special protective containers.

3.3 *cover*—an electrically insulated enclosure designed to be installed temporarily on various types of irregularly shaped

electrical equipment to protect personnel and equipment working in the close proximity.

3.4 *designated person*—an individual who is qualified by experience or training to perform an assigned task.

3.5 *distorted*—physically changed from the natural and original shape, caused by stress of any type.

3.6 *electrical testing facility*—a location with qualified personnel, testing equipment, and procedures for the inspection and electrical testing of electrical insulating protective equipment.

3.7 *electrode*—the energized or grounded conductor portion of electrical test equipment which is placed near or in contact with the material or equipment being tested.

3.8 *flashover*—the electrical discharge or arc occurring between electrodes and over or around, but not through, the equipment being tested.

3.9 *hose*—an electrical insulating tube with a longitudinal slit designed to be installed temporarily on energized electrical wires.

3.10 *ozone*—a very active form of oxygen that may be produced by corona, arcing, or ultraviolet rays.

3.11 *ozone cutting and checking*—cracks produced by ozone in a material under mechanical stress.

3.12 *retest*—the tests given after the initial acceptance test, usually performed at regular periodic intervals or as required because of physical inspection.

3.13 *voltage, maximum use*—the a-c voltage (rms) classification of the protective equipment that designates the maximum nominal design voltage of the energized system that may be safely worked. The nominal design voltage is equal to phase-to-phase voltage on multiphase circuits.

3.13.1 If there is no multiphase exposure in a system area, and the voltage exposure is limited to phase (polarity on d-c systems) to ground potential, the phase (polarity on d-c systems) to ground potential shall be considered to be the nominal design voltage.

3.13.2 If electrical equipment and devices are insulated, or isolated, or both, such that the multiphase exposure on a grounded wye circuit is removed, then the nominal design voltage may be considered as the phase-to-ground voltage on that circuit.

3.14 *voltage, maximum retest*—voltage, either a-c rms or d-c average, that is equal to the proof test voltage for new protective equipment.

3.15 *voltage, nominal design*—a nominal value consistent

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee F-18 on Electrical Protective Equipment for Workers and is the direct responsibility of Subcommittee F18.25 on Insulating Cover-up Equipment.

Current edition approved Feb. 11, 1992. Published April 1992. Originally published as F 478 – 76. Last previous edition F 478 – 87.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 10.03.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 10.02.

<sup>4</sup> Available from the American National Standards Institute, 1430 Broadway, New York, NY 10018.

<sup>5</sup> Available from Institute of Electrical and Electronics Engineers, Inc., 445 Hoes Lane, Piscataway, NJ 08854-4150.

with the latest revision of ANSI C84.1, assigned to the circuit or system for the purpose of conveniently designating its voltage class.

3.16 *voltage, retest*—voltage, either a-c rms or d-c average, that used protective equipment must be capable of withstanding for a specific test period without breakdown.

**4. Significance and Use**

4.1 Compliance with this specification should continue to provide personnel with insulating line hose and covers of known and acceptable quality after initial acceptance in accordance with Specifications D 1050 and D 1049. The standards herein are to be considered as minimum requirements.

4.2 A margin of safety shall be provided between the maximum use voltage and their class proof voltage in accordance with Specifications D 1050 and D 1049, as shown in Table 1.

4.3 The user of this type of protective equipment shall be knowledgeable of and instructed in the correct and safe inspection and use of this equipment.

**5. Classification**

5.1 Line hose covered in this specification are designed as Type I or Type II; Class 0, Class 1, Class 2, Class 3 or Class 4; Style A, Style B, Style C or Style D. Covers covered in this standard are designated as Type I or Type II; Class 0, Class 1, Class 2, Class 3 or Class 4; Style A, Style B, Style C, Style D or Style E.

5.1.1 *Type I*—High-grade *cis*-1,4-polyisoprene rubber compound of natural or synthetic origin, properly vulcanized.

5.1.2 *Type II*—Ozone resistant, made of any elastomer or combination of elastomeric compounds.

5.1.3 The class designations are based on the electrical properties in Specifications D 1050 and D 1049.

5.1.4 The style designations are based on the designs and descriptions in Specifications D 1050 and D 1049.

**6. Washing and Inspection**

6.1 The recommended sequence of washing and inspection of contaminated insulating line hose and covers is as follows:

- 6.1.1 Washing,
- 6.1.2 Drying,
- 6.1.3 Inspection,
- 6.1.4 Marking, and

6.1.5 Packing for storage and shipment.

6.2 The hose and covers may be washed with a soap, mild non-bleaching detergent, or a cleaner recommended by the equipment manufacturer. After washing, the hose and covers shall be rinsed thoroughly with water.

6.2.1 The cleaning agent shall not degrade the insulating qualities of the line hose and covers.

6.2.2 A commercial tumble-type washing machine may be used, where practicable, but caution must be observed to eliminate any interior surfaces or edges that will cut, abrade, puncture, or pinch the hose or covers.

6.3 The hose and covers shall be air dried. The air temperature shall not be over 150°F (65.5°C). They may be suspended to allow drainage and air circulation or dried in a commercial tumble-type automatic dryer. In an automatic dryer, caution must be observed to eliminate any ozone-producing lamps and interior surfaces that will cut, abrade, puncture, or pinch the hose and covers.

6.4 Insulating line hose and covers shall be given a detailed inspection over the entire inner and outer surface for punctures, cuts, severe ozone cutting, or any other obvious condition that would adversely affect performance.

6.5 The hose and covers shall be marked in accordance with Section 12.

**7. Electrical Tests**

7.1 Where the inspection specified in Section 6 indicates that there may be reason to suspect the electrical integrity of a line hose or cover, an electrical test shall be performed before reissuing the line hose or cover for service.

7.2 Both a-c and d-c voltage retest methods are included in this section and either or both methods may be selected for electrical test.

**NOTE 1—Precaution:** In addition to other precautions, it is recommended that the test apparatus be designed to afford the operator full protection in the performance of duties. Reliable means of de-energizing and grounding the high-voltage circuit should be provided. It is particularly important to incorporate positive means of grounding the high-voltage section of d-c test apparatus due to the likely presence of high-voltage capacitance charges at the conclusion of the test.

7.3 Any electrical retest shall be performed at normal room temperatures and on clean hose or covers at an electrical testing facility.

7.4 *Electrodes:*

7.4.1 The entire area of each hose and cover shall be tested, as nearly as practicable, between electrodes that apply the electrical stress uniformly over the test area without producing damaging corona or mechanical strain in the hose or cover. The electrodes shall be of such dimensions and so placed as to avoid flashover at the edges.

7.4.2 For hose, the inside electrode shall be a metal mandrel of the size in Table 2. The outer electrode should be a close-fitting wet sponge or wet fabric blanket, metal foil, or a smooth metal form; extending to within 1/2 in. (13 mm) of the edge of the lip of the hose, and extending to a distance from the end of the hose as specified in Table 3. If the hose has a connector end, the form should extend to within 1/2 in. (13 mm) of the connector end. When Style C line hose is tested, the outer electrode may fit around the outside diameter of the hose,

**TABLE 1 Voltage Requirements Line Hose and Covers**

Class Designation of Hose and Covers	A-C Use Voltage, rms, max <sup>A</sup>	A-C Retest Voltage, rms	D-C Retest Voltage, avg
0	1000	5000	20 000
1	7500	10 000	40 000
2	17 000	20 000	50 000
3	26 500	30 000	60 000
4	36 000	40 000	70 000

<sup>A</sup> The maximum use voltage is based on the following equations:  
 1. Maximum use voltage = 0.95 a-c and d-c retest voltage – 2 000, Classes 1, 2, 3, and 4.  
 2. Maximum use voltage = 0.95 a-c and d-c reset voltage – 30 500, Classes 1, 2, 3, and 4.  
 3. Maximum use voltage 1 0.95 a-c and d-c retest voltage – 18 000, Class 0.

**TABLE 2 Line Hose Test Mandrel Size**

Hose Size, Inside Diameter, in. (mm)	Recommended Test Mandrel Size, Outside Diameter, in. (mm)
1/4 (6.4)	3/16 (4.8)
5/8 (16)	9/16 (14.3)
1 (25)	15/16(23.8)
1 1/4 (32)	1 3/16(30)
1 1/2 (38)	1 1/4 (31.8)
2 (51)	1 3/4 (44.4)
2 1/2 (63.5)	2 1/4 (57.2)

**TABLE 3 Flashover Clearances Between Electrodes<sup>A</sup>**

Class Designation, Glove or Sleeve	A-C Retest		D-C Retest	
	in.	mm	in.	mm
0	3	76	3	76
1	3	76	4	102
2	5	127	6	152
3	7	178	8	203
4	10	254	12	305

<sup>A</sup> Flashover clearances are stated in terms of the shortest electrical air path between electrodes around the edge of the item being tested. In those cases where atmospheric conditions make the specified clearances impractical, the distance may be increased by the maximum of 2 in. (51 mm).

but not the extended lip (Note 2).

NOTE 2—These end clearances are intended to serve as a guide and under some conditions may have to be increased to prevent flashover.

7.4.3 For covers, the electrodes shall be one of those described in the following methods:

7.4.3.1 *Method 1 for Types I and II*—Water as inner and outer electrodes.

7.4.3.2 *Method 2 for Types I and II*—Wet sponge or wet felt inner electrode; and wet sponge, wet felt, or metal foil outer electrode.

7.4.3.3 *Method 3 for Type II*—Fixed form metal or metal foil inner or outer electrodes, or both.

NOTE 3—Method 3 electrodes shall not be used with Type I materials when testing with alternating current due to the possibility of corona cutting.

**7.5 A-C Test:**

7.5.1 *Voltage Supply and Regulation*—The voltage supply and control equipment should be of such size and design that, with the test specimens in the circuit, the crest factor (ratio of peak to mean effective) of the test voltage shall differ by not more than 5 % from that of a sinusoidal wave over the upper half of the range of the test voltage. The correct rms value of the sinusoidal voltage waveform applied to the hose or cover may be measured by one of the following methods:

7.5.1.1 A voltmeter used in conjunction with a calibrated instrument transformer connected directly across the high voltage circuit,

7.5.1.2 A calibrated electrostatic voltmeter connected directly across the high voltage circuit,

7.5.1.3 An a-c meter connected in series with appropriate high voltage type resistors directly across the high voltage circuit.

7.5.1.4 The accuracy of the voltage measuring circuit shall be ±2 % of full scale. To ensure the continued accuracy of the

test voltage, as indicated by the test equipment voltmeter, the test equipment shall be calibrated at least annually in accordance with the latest revision of Practice D 2865 or IEEE Standard 4. The crest factor may be checked by the use of a peak reading voltmeter connected directly across the high-voltage circuit.

7.5.2 *A-C Retest*—Electrical retest of a hose or cover shall be in accordance with the requirements of Section 8.

NOTE 4—It is recommended that the retest voltage be applied initially at a low value and increased gradually at a constant rate-of-rise of approximately 1000 V/s a-c until the prescribed test voltage level is reached. Unless an electrical puncture has occurred already, the applied voltage should be reduced to at least half value at the end of the test period before opening the test circuit.

**7.6 D-C Test:**

**7.6.1 Voltage Supply and Regulation:**

7.6.1.1 The d-c test voltage can be obtained from a source capable of supplying a d-c voltage whose peak-to-peak a-c ripple component does not exceed 2 % of the average voltage value under no-load conditions.

7.6.1.2 The d-c test voltage shall be measured by a method that provides the average value of the voltage applied to the hose or cover. It is recommended that the voltage be measured by the use of a d-c meter connected in series with appropriate high-voltage type resistors across the high-voltage circuit, or by an electrostatic voltmeter of proper range. The accuracy of the voltage measuring circuit shall be within ±2 % of full scale. The test equipment shall be calibrated at least annually, in accordance with the latest revision of Practice D 2865 or the latest revision of IEEE Standard 4.

7.6.2 *D-C Retest*—Electrical retest of a hose or cover shall be in accordance with the requirements of Section 8.

NOTE 5—It is recommended the d-c retest voltage should be applied in the same manner as for a-c retest voltage, with the exception of a rate-of-rise of approximately 3000 V/s.

**8. Rejection Criteria**

8.1 Any hose or cover that fails to comply with the electrical retest requirements as indicated in this section shall be rejected.

8.2 Each hose or cover shall withstand the 60-Hz a-c retest voltage (rms value) or the d-c retest voltage (average value) specified in Table 1. The test voltage shall be applied continuously for not less than 1 min and not more than 3 min.

8.3 Any hose or cover that upon inspection is found to have punctures, deep cuts, severe corona or ozone cutting, contamination from injurious materials, or has lost its normal elasticity, shall be rejected.

8.4 Minor surface corona cutting or ozone checking need not be cause for rejection.

**9. Precision and Bias**

9.1 No statement is made about either the precision or the bias of the test methods in this specification for measuring the dielectric strength since the results merely state whether there is conformance to the criteria for success specified in the procedure.

**10. Repairs**

10.1 Hose and covers shall not be repaired. Hose may be

used in shorter lengths if the defective portion is cut off.

## 11. Field Care, Inspection, and Storage

11.1 The field care and inspection of electrical insulating line hose and covers, performed by the individual, is an important requirement in providing protection from electrical shock. Defective or suspected defective line hose and covers shall not be used. They shall not be re-issued for use until they have been inspected and retested at an electrical testing facility, and meet the requirements of Section 8.

11.2 Before use and installation on energized conductors, devices, or equipment, line hose and covers shall be inspected visually for defects and at other times if there is cause to suspect any damage.

11.3 Line hose and covers shall be wiped clean of any oil, grease, or other damaging substances as soon as practicable. Line hose and covers whose surface becomes otherwise contaminated shall be set aside and cleaned in accordance with Section 6.

11.4 Loose bulk storage or packaging may be used for hose or covers in transit or in temporary holding operations provided such storage is limited to periods not in excess of 1 month, and there is not severe distortion.

11.5 Line hose and covers shall be stored without distortion and mechanical stress in a location as cool, dark, and dry as possible. They shall be stored or packaged in a suitable compartment or in containers such as boxes or bags. The area shall be as free as possible of ozone, chemicals, oils, solvents,

damaging vapors and fumes, and away from electrical discharges and sunlight.

11.6 Line hose and covers shall not have any identifying adhesive tapes or labels applied to them by other than authorized personnel. Tape shall not be used to secure line hose and covers for shipment or storage.

11.7 Line hose and covers with any of the following defects shall not be used:

11.7.1 Holes other than factory produced openings on the top, sides, or lips of the line hose or covers, tears and punctures, serious cuts, and rope or wire burns that extend more than one third the depth of the thickness of the rubber.

11.7.2 Texture changes: swelling, softening, hardening, and becoming sticky or inelastic.

11.7.3 Other defects that damage the insulating properties.

11.8 Line hose and cover should be left in service on energized lines for minimum necessary periods of time as exposure may result in ozone checking, corona cutting, or excessive weathering.

## 12. Marking

12.1 If the hose and covers are not readily identifiable as to class, they shall be marked.

12.2 Hose or covers that have been rejected and are not suitable for electrical service shall be defaced, cut, or otherwise marked and identified to indicate that they are not to be used for electrical service.

*The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.*

*This standard is copyrighted by ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (<http://www.astm.org>).*