



Standard Practice for Temper Designations of Magnesium Alloys, Cast and Wrought¹

This standard is issued under the fixed designation B 296; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice covers a system for designating the tempers of magnesium alloys, cast and wrought. The designations used in ASTM specifications under the jurisdiction of Committee B07 for magnesium alloy castings and wrought products conform to this practice.²

2. Basis of Codification

2.1 The designations for temper are used for all forms of magnesium and magnesium-alloy products except ingots and are based on the sequence of basic treatments used to produce the various tempers.

2.2 The temper designation follows the alloy designation, the two being separated by a dash.

2.3 Basic temper designations consist of letters. Subdivisions of the basic tempers, where required, are indicated by a digit or digits following the letter. These designate specific sequences of basic treatments, but only operations recognized as significantly influencing the characteristics of the product are indicated. Should some other variation of the same sequence of basic operations be applied to the same alloy, resulting in different characteristics, then additional digits are added to the designation.

NOTE 1—In material specifications containing reference to two or more tempers of the same alloy which result in identical mechanical properties, the distinction between the tempers should be covered in suitable explanatory notes.

2.4 The temper designations and the subdivisions are fully defined and explained in Table 1. A brief outline for quick reference is given in Table 2.

¹ This practice is under the jurisdiction of the ASTM Committee B07 on Light Metals and Alloys and is the direct responsibility of Subcommittee B07.04 on Magnesium Alloy Cast and Wrought Products.

Current edition approved Dec. 1, 2003. Published December 2003. Originally approved in 1954. Last previous edition approved in 1996 as B 296 – 96.

² The designations used in ASTM Committee B07 specifications for aluminum-alloy wrought and cast products conform to the American National Standard H 35.1.

TABLE 1 Temper Designations

F	<i>As Fabricated</i> —Applies to products that acquire some temper from shaping processes not having special control over the amount of strain hardening or thermal treatment.
O	<i>Annealed, Recrystallized</i> —Applies to the softest temper of wrought products.
H	<i>Strain Hardened (Wrought Products Only)</i> —Applies to products that have their strength increased by strain hardening with or without supplementary thermal treatments to produce partial softening. Two or more digits always follow the H.

Subdivisions of the "H" Temper:

- | | |
|----|--|
| H1 | <i>Strain Hardened Only</i> —Applies to products that are strain hardened to obtain the desired mechanical properties without supplementary thermal treatment. The number following this designation indicates the final degree of strain hardening. |
| H2 | <i>Strain Hardened and Then Partially Annealed</i> —Applies to products that are strain hardened more than the desired final amount and then reduced in strength to the desired final amount by partial annealing.
The number following this designation indicates the final degree of strain hardening remaining after the product has been partially annealed. |
| H3 | <i>Strain Hardened and Then Stabilized</i> —Applies to products that are strain hardened and then stabilized by a low temperature heating to slightly lower their strength and increase ductility. This designation applies only to alloys which, unless stabilized, gradually age soften at room temperature.
The number following this designation indicates the degree of strain hardening remaining after the product has been strain hardened a specific amount and then stabilized. |

Subdivisions of the "H1," "H2," and "H3" Tempers:

The digit following the designations "H1," "H2," and "H3" indicates the final degree of strain hardening. Tempers between 0 (annealed) and 8 (full hard) are designated by numerals 1 through 7. Material having a strength about midway between that of the 0 temper and that of the 8 temper is designated by the numeral 4 (half hard); between 0 and 4 by the numeral 2 (quarter hard); between 4 and 8 by the numeral 6 (three-quarter hard); and so forth.

The third digit, when used, indicates a variation of a two-digit H temper. It is used when the degree of control of temper or the mechanical properties are different from but close to those for the two-digit H temper to which it is added. Numerals 1 through 9 may be arbitrarily assigned for an alloy and product to indicate a specific degree of control of temper or specified mechanical property limits.

W	<i>Solution Heat-Treated</i> —An unstable temper applicable only to alloys that spontaneously age at room temperature after solution heat treatment. This designation is specific only when the period of natural aging is indicated: for example, W ½ hour.
T	<i>Thermally Treated to Produce Stable Tempers Other Than F, O, or H</i> —Applies to products that are thermally treated, with or without supplementary strain hardening, to produce stable tempers. One or more digits always follow the T. Numerals 1 through 10 have been assigned to indicate specific sequence of basic treatments as follows:

Subdivisions of the "T" Tempers:

- | | |
|-----|---|
| T1 | <i>Cooled From an Elevated Temperature Shaping Process and Naturally Aged to a Substantially Stable Condition</i> —Applies to products for which the rate of cooling from an elevated temperature shaping process, such as casting, or extruding, is such that their strength is increased by room temperature aging. |
| T3 | <i>Solution Heat Treated and Then Cold Worked</i> —Applies to products that are cold worked to improve strength, or in which the effect of cold work in flattening and straightening is recognized in applicable mechanical properties. |
| T4 | <i>Solution Heat Treated and Naturally Aged to a Substantially Stable Condition</i> —Applies to products that are not cold worked after solution heat treatment, or in which the effect of cold work in flattening or straightening may not be recognized in applicable mechanical properties. |
| T5 | <i>Cooled From an Elevated-Temperature Shaping Process and Then Artificially Aged</i> —Applies to products that are cooled from an elevated temperature shaping process, such as casting or extruding, and then artificially aged to improve mechanical properties or dimensional stability or both. |
| T6 | <i>Solution Heat Treated and Then Artificially Aged</i> —Applies to products that are not cold worked after solution heat treatment, or in which the effect of cold work is flattening or straightening may not be recognized in applicable mechanical properties. |
| T7 | <i>Solution Heat Treated and Then Stabilized</i> —Applies to products that are stabilized to carry them beyond the point of maximum strength to provide control of some special characteristics. |
| T8 | <i>Solution Heat Treated, Cold Worked, and Then Artificially Aged</i> —Applies to products that are cold worked to improve strength, or in which the effect of cold work in flattening or straightening is recognized in applicable mechanical properties. |
| T9 | <i>Solution Heat Treated, Artificially Aged, and Then Cold Worked</i> —Applies to products that are cold worked to improve strength. |
| T10 | <i>Cooled From an Elevated Temperature Shaping Process, Artificially Aged, and Then Cold Worked</i> —Applies to products that are artificially aged after cooling from an elevated temperature shaping process, such as casting or extruding, and then cold worked to further improve strength. |

A period of natural aging at room temperature may occur between or after the operations listed for tempers T3 through T10. Control of this period is exercised when it is metallurgically important.

Additional digits may be added to designations T1 through T10 to indicate a variation in treatment that significantly alters the characteristics of the product.

TABLE 2 Basic Temper Designations and Subdivisions

F	As fabricated.
O	Annealed, recrystallized (wrought products only).
H	Strain hardened.
Subdivisions of the "H" Temper:	
H1, plus one or more digits... Strain hardened only.	
H2, plus one or more digits... Strain hardened and then partially annealed.	
H3, plus one or more digits... Strain hardened and then stabilized.	
W	Solution heat treated. Unstable temper.
T	Thermally treated to produce stable tempers other than F, O, or H.
Subdivisions of the "T" Temper:	
T1	Cooled and naturally aged.
T3	Solution heat treated and then cold worked.
T4	Solution heat treated.
T5	Cooled and artificially aged.
T6	Solution heat treated and artificially aged.
T7	Solution heat treated and stabilized.
T8	Solution heat treated, cold worked, and artificially aged.
T9	Solution heat treated, artificially aged, and cold worked.
T10	Cooled, artificially aged, and cold worked.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).