



Standard Test Methods for Backing Fabric Characteristics of Pile Yarn Floor Coverings¹

This standard is issued under the fixed designation D 2646; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 These test methods cover the procedures listed as follows for testing woven, knitted and nonwoven backing fabrics designed for use in the manufacture of pile yarn floor coverings. The procedures appear in the following order:

	Section
Bow and Skewness of Woven Fabrics	8
Breaking Force of Woven and Nonwoven Fabrics	15
Breaking Force After Tufting of Woven and Nonwoven Fabrics	16
Extractable Matter	9
Fabric Count of Woven Fabrics	12
Fabric Count of Knitted Fabrics	13
Length of Woven Fabrics	11
Mass per Unit Area (Weight) of Woven Fabrics	14
Shrinkage—Hot Wet Method	17
Shrinkage—Hot Dry Method	18
Width of Woven Fabrics	10

1.2 The values stated in SI units are to be regarded as standard. The values in inch-pound units are provided as information only and are not exact equivalents. In case of referee decisions, the SI units will prevail.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

- D 123 Terminology Relating to Textiles²
- D 1776 Practice for Conditioning and Testing Textiles²
- D 2257 Test Method for Extractable Matter in Textiles²
- D 3773 Test Methods for Length of Woven Fabric³
- D 3774 Test Methods for Width of Woven Fabrics³
- D 3775 Test Method for Fabric Count of Woven Fabric³
- D 3776 Test Methods for Mass per Unit Area (Weight) of Fabric³
- D 3882 Test Method for Bow and Skews in Woven and Knitted Fabrics³

¹ These test methods are under the jurisdiction of ASTM Committee D-13 on Textiles and are the direct responsibility of Subcommittee D13.21 on Pile Yarn Floor Covering.

Current edition approved Sept. 10, 2002. Published November 2002. Originally published as D 2646 – 67 T. Last previous edition D 2646 – 87.

² Annual Book of ASTM Standards, Vol 07.01.

³ Annual Book of ASTM Standards, Vol 07.02.

- D 3887 Specification for Tolerances for Knitted Fabrics³
- D 5034 Test Methods for Breaking Force and Elongation of Textile Fabrics (Grab Test)³
- D 5684 Terminology Relating to Pile Floor Covering³

3. Terminology

3.1 For definitions of pile yarn floor covering related to terms used in this practice, refer to Terminology D 5684. For definitions of other textile terms used in this practice refer to Terminology D 123.

4. Summary of Test Methods, General

4.1 A summary of the directions prescribed for the determination of specific properties is stated in the appropriate sections of specific test methods.

5. Significance and Use

5.1 These test methods may be used for acceptance testing of commercial shipments; however, caution is advised because information about between interlaboratory precision is incomplete. Comparative tests as directed in 5.1.1 may be advisable.

5.1.1 If there are differences of practical significance between reported test results for two laboratories (or more), comparative tests should be performed to determine if there is statistical bias between them using competent statistical assistance. As a minimum, use test samples for such comparative tests that are as homogeneous as possible, drawn from the same lot of material as the samples that resulted in the disparate results during initial testing, and that are randomly assigned in equal numbers to each laboratory for testing. The test results from the laboratories should be compared using statistical test for unpaired data at a probability level chosen prior to the testing series. If a bias is found either its cause must be found and corrected, or future test results for that material must be adjusted in consideration of the known bias.

5.2 These test methods are useful to evaluate quality and cost control during the manufacture of pile yarn floor covering.

5.3 The significance and uses of particular properties and test methods are discussed in the appropriate sections of the specified test methods.

6. Sampling

6.1 *Lot Sample*—As a lot sample for acceptance testing, take at random the number of rolls or pieces, as directed in an applicable material specification or other agreement between

the purchaser and the supplier. Consider the rolls or pieces of material to be the primary sampling units. In the absence of such agreement, take one roll or piece from the lot to be tested.

NOTE 1—An adequate specification or other agreement between the purchaser and the supplier requires taking into account the variability between rolls or pieces of floor covering and between specimens from a roll or pieces of floor covering to provide a sampling plan with a meaningful producer's risk, consumer's risk, acceptable quality level, and limiting quality level.

6.2 *Laboratory Sample*—For acceptance testing, take a sample from a roll approximately 1.5 m (1.5 yd) long extending the width of the material from each roll or piece in the lot, unless otherwise specified in the specific test method. For rolls of floor covering, take a sample that will exclude fabric from the outer wrap of the roll or the inner wrap around the core.

6.3 *Test Specimens*—From each laboratory sampling unit, take three specimens with the longer direction parallel to the machine direction, unless otherwise specified in the specific test method. Consider the long direction as the direction of test.

7. Conditioning

7.1 Condition the specimens as directed in Practice D1776 in the standard atmosphere for testing textiles, which is $21 \pm 1^\circ\text{C}$ ($70 \pm 2^\circ\text{F}$) and $65 \pm 2\%$ relative humidity, for 24 h or until the specimen mass changes no more than 0.1 % in 2 h, except the specimens used for the determination of bow and skew (Section 8), width (Section 10), length (Section 11), and fabric count (Section 12), which may be tested without either preconditioning or conditioning. Specimens for the tests listed may be merely air-dried under prevailing room conditions.

NOTE 2—Using these conditions may not result in the product obtaining moisture and temperature equilibrium.

TEST METHODS

8. Bow and Skewness in Woven and Knitted Fabrics

8.1 Determine the bow and skewness of backing fabrics for pile yarn floor coverings as directed in Test Method D 3882.

9. Extractable Matter

9.1 Determine the extractable matter that was added to the backing fabric for pile yarn floor covering as directed in Test Method D 2257.

10. Width of Woven Fabrics

10.1 Determine the width of woven backing fabrics for pile yarn floor coverings as directed in Test Methods D 3774. The choice of the test options of measurement in determining width shall be agreed upon between the purchaser and the supplier.

10.2 For knitted fabrics, refer to Test Method D 3887.

11. Length of Woven Fabrics

11.1 Determine the length of woven fabrics used as backing fabrics in pile yarn floor coverings as directed in Test Methods D 3773. The choice of the test options of measurement in determining the fabric length shall be agreed upon between the purchaser and the supplier.

11.2 For knitted fabrics, refer to Test Method D 3887.

12. Fabric Count of Woven Fabrics

12.1 Determine the fabric count for woven backing fabrics for pile yarn floor coverings as directed in Test Method D 3775.

13. Fabric Count of Knitted Fabrics

13.1 Determine the fabric count for knitted backing fabrics for pile yarn floor coverings as directed in Test Method D 3887.

14. Mass Per Unit Area (Weight) of Woven Fabrics

14.1 Determine the mass per unit area (weight) of woven fabric for backing fabrics for pile yarn floor coverings as directed in Test Methods D 3776.

14.2 For knitted fabrics, refer to Test Method D 3887.

15. Breaking Force of Woven and Nonwoven Fabrics

15.1 Determine the breaking force of woven and nonwoven backing fabrics, of pile yarn floor coverings as directed in Test Methods D 5034 using a constant-rate-of-extension (CRE) type tensile testing machine with the speed of the pulling jaw 300 ± 10 mm/min (12 ± 0.5 in./min).

16. Breaking Force After Tufting of Woven and Nonwoven Fabrics

16.1 Determine the breaking force of woven and nonwoven backing fabrics of pile yarn floor coverings as directed in Test Methods D 5034 using a constant-rate-of-extension (CRE) type tensile testing machine with the speed of the pulling jaw 300 ± 10 mm/min (12 ± 0.5 in./min).

NOTE 3—The tuft conditions with respect to pile height, gage, stitches per millimetre (stitches per inch), pile yarn characteristics, and tufting needles style must be agreed upon by all parties concerned. Using agreed-upon conditions, tuft sufficient backing fabric to secure the required number of test specimens.

17. Shrinkage—Hot Wet Method

17.1 *Scope:*

17.1.1 This test method determines the shrinkage of woven, nonwoven, or knitted backing fabrics for pile yarn floor covering after exposure to hot wet conditions.

17.2 *Summary of Test Method:*

17.2.1 The backing fabric warp yarns and filling picks are first measured to a specific length. The fabric then is immersed in hot distilled or deionized water and remeasured. The shrinkage is calculated as the change in length expressed as a percentage of the length before immersion.

17.3 *Significance and Use:*

17.3.1 Test Methods D 2646 for testing backing fabric shrinkage in hot wet conditions is considered satisfactory for acceptance testing of commercial shipments of fabric because the test method has been used extensively in the trade for that purpose.

17.4 *Apparatus:*

17.4.1 *Metal or Glass Pan*, approximately 330 by 330 mm (13 by 13 in.) by 25 mm (1 in.) deep.

17.4.2 *Circulating Air Oven*, controlled at $70 \pm 2^\circ\text{C}$ ($158 \pm 4^\circ\text{F}$).

17.4.3 *Staple Gun*, such as those used for stapling stationery or any other device that will produce a suitable waterproof mark.

17.4.4 *Reagent*, anionic wetting agent such as sodium lauryl sulphate.

17.5 *Number of Specimens:*

17.5.1 Take three specimens approximately 300 by 300 mm (12 by 12 in.). Take no specimen closer than 250 mm (10 in.) to the selvage and no closer than 1 m (yd) from the end of the roll. For woven fabrics take no specimen containing the same warp yarns or the same filling picks and cut all specimens parallel to the warp and the filling.

17.6 *Preparation of Specimens:*

17.6.1 Lay out the specimens without tension on a flat, horizontal surface, taking care that there are no wrinkles or creases. Place a staple in the specimen or a waterproof mark about 25 mm (1 in.) on it from one edge. Measure 250 ± 2 mm (10 ± 0.1 in.) directly along one principle direction of the specimen and place a second staple or mark. Repeat this procedure along the other principle direction.

17.7 *Procedure:*

17.7.1 Place the specimens in the pan and cover them with a solution of 0.1 % wetting agent in distilled or deionized water at $77 \pm 2^\circ\text{C}$ ($170 \pm 4^\circ\text{F}$) to a depth of approximately 25 mm (1 in.), and soak the specimens for 1 h.

17.7.2 Drain off the wetting solution. Place the specimens on paper towels or blotting paper to remove the excess solution. **Do not squeeze or press.**

17.7.3 Place the specimens flat on a screen and dry in an oven for at least 4 h at $70 \pm 2^\circ\text{C}$ ($158 \pm 4^\circ\text{F}$). Remove the specimens from the oven and recondition as directed in Practice D 1776. Remeasure the specimens in both directions as directed in 22.1.

17.8 *Calculation:*

17.8.1 Average the measurements of the distance between the marks for each direction of the specimen before and after treatment. Calculate the shrinkage in percent by Eq 1 and Eq 2 as follows:

$$\text{Shrinkage, \%} = [(L_1 - L_f)/L_1] \times 100 \quad (1)$$

$$\text{Shrinkage, \%} = [(W_1 - W_f)/W_1] \times 100 \quad (2)$$

where:

L_1 = average original length,

L_f = average final length,

W_1 = average original width, and

W_f = average final width.

17.9 *Report:*

17.9.1 State that the tests were performed as directed in Test Methods D 2646 for shrinkage to hot wet conditions and report the following information:

17.9.2 The shrinkage in the form of shrinkage or growth, and

17.9.3 The percent change in length and in width for each laboratory sample.

17.10 *Precision and Bias:*

17.10.1 *Precision*—Based on limited information from within (one) laboratory, two technicians, the repeatability standard deviation and the 95 % repeatability limits are ap-

proximately 0.153 and 0.429 respectively. The intermediate precision standard deviations and the 95 % intermediate precision limits are approximately 0.197 and 0.552 respectively.

17.10.2 *Bias*—The procedure for shrinkage—hot wet method for backing fabrics of pile yarn floor coverings has no known bias and may be used for referee purposes.

18. Shrinkage—Hot Dry Method

18.1 *Scope:*

18.1.1 This test method determines the shrinkage of woven, nonwoven, or knitted backing fabrics for pile yarn floor covering after exposure to hot dry conditions.

18.2 *Summary of Test Method:*

18.2.1 The backing fabric warp yarns and filling picks are first measured to a specific length. The fabric is then exposed to dry heat and remeasured. The shrinkage is calculated as the change in length expressed as a percentage of the length before exposure.

18.3 *Significance and Use:*

18.3.1 Test Methods D 2646 for testing backing fabric shrinkage in hot dry conditions is considered satisfactory for acceptance testing of commercial shipments of fabric because the test method has been used extensively in the trade for that purpose.

18.4 *Apparatus:*

18.4.1 *Circulating Air Oven*, maintained at specified temperature within $\pm 2^\circ\text{C}$ ($\pm 4^\circ\text{F}$).

18.4.2 *Staple Gun*, such as those used for stapling stationery or any other device that will produce a suitable waterproof mark.

18.5 *Number of Specimens:*

18.5.1 Take three specimens as directed in 17.5.1.

18.6 *Preparation of Specimens:*

18.6.1 Prepare specimens as directed in 17.6.1.

18.7 *Procedure:*

18.7.1 Place the specimens on a perforated shelf in an oven controlled at a specified or agreed-upon temperature within $\pm 2^\circ\text{C}$ ($\pm 4^\circ\text{F}$) and heat for 15 min. In the absence of a specified or agreed-upon temperature, use $125 \pm 2^\circ\text{C}$ ($257 \pm 4^\circ\text{F}$).

18.7.2 Remove specimens from the oven and condition as directed in Test Method D 1776.

18.7.3 Remeasure the specimens as directed in 17.6.1.

18.8 *Calculation:*

18.8.1 Calculate the results as directed in 17.8.1.

18.9 *Report:*

18.9.1 Report the information and results as directed in 17.9.

18.10 *Precision and Bias:*

18.10.1 *Precision*—Based on limited information from three laboratories, one technician per laboratory, the repeatability standard deviation and the 95 % repeatability limits are 0.191 and 0.535 respectively. The reproducibility standard deviation and the 95 % reproducibility limits are 0.337 and 0.944.

18.10.2 *Bias*—The procedure for shrinkage—hot dry method for backing fabrics of pile yarn floor coverings has no known bias and may be used for referee purposes.

19. Keywords

backing; shrinkage; woven fabric

19.1 carpet; extractable matter; knitted fabric; nonwoven fabric; pile yarn floor covering; primary backing; secondary

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).