



Standard Practice for Creating Surface Appearance Changes in Pile Yarn Floor Covering from Foot Traffic¹

This standard is issued under the fixed designation D 6119; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice covers the trafficking of pile yarn floor coverings in a laboratory in order to effect a change in surface appearance as a result of exposure to foot traffic under controlled conditions. A separate test method covers the assessment of surface appearance change using the CRI Reference Scales.

1.2 This practice is applicable to most changes in surface appearance observed in all types of carpet that are intended for residential or commercial use. It eliminates change in appearance associated with soiling by focusing on appearance change due to matting, flattening, or change in pile fiber configuration. Although “pile reversal” or “watermarking” is occasionally visible, this practice is not a reliable method for producing this phenomenon.

1.3 This practice may be used by mutual agreement between the purchaser and supplier to set purchasing specifications.

1.4 The values stated in SI units are to be regarded as the standard. The inch-pound units given in parentheses are for information only.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* Specific precautionary statements are given in Section 7.

2. Referenced Documents

2.1 ASTM Standards:

D 123 Terminology Related to Textiles²

D 5684 Terminology Relating to Pile Yarn Floor Coverings³

2.2 TM-101 CRI Technical Bulletin:

Assessment of Carpet Surface Appearance Change Using CRI Reference Scales⁴

3. Terminology

3.1 Definitions:

¹ Precision and Bias This practice is under the jurisdiction of ASTM Committee D-13 on Textiles and is the direct responsibility of Subcommittee D13.21 on Pile Floor Coverings.

Current edition approved May 10, 1997. Published September 1997.

² Annual Book of ASTM Standards, Vol 07.01.

³ Annual Book of ASTM Standards, Vol 07.02.

⁴ Available from CRI, P.O. Box 2048, Dalton, GA 30722.

3.1.1 *change in surface appearance, n*—for pile yarn floor coverings, the cumulative change in surface appearance between unexposed and exposed specimens due to crushing, loss of tuft definition, and matting.

3.1.2 *foot traffic units, n*—for pile yarn floor coverings, the number of passes by human walkers over a specific group of specimens.

3.1.2.1 *Discussion*—Foot traffic units should not be taken as the actual number of times each specimen is stepped on, but rather as the number of times that persons pass a designated spot on the walking course.

3.1.3 For definitions of other terms relating to pile yarn floor coverings, refer to Terminology D 5684. For definitions of other textile terms used in this test method, refer to Terminology D 123.

4. Summary of Practice

4.1 Specimens are exposed to a specified number of foot traffics under controlled conditions.

5. Significance and Use

5.1 By exposure to sufficient traffic, this practice can be applied to any pile yarn floor covering which undergoes changes in surface appearance.

5.1.1 This practice does not simulate surface appearance changes due to soiling, pivoting, or rolling traffic, or traffic on stairs.

6. Apparatus

6.1 *Area for Foot Traffic*—A room that meets the following conditions:

6.1.1 The floor must be level, rigid, and free of high and low areas. Tile, concrete, or wood are satisfactory. This area should be kept free of pedestrian traffic other than the designated walkers.

6.1.2 The length of the test area shall be adequate for the specimens plus the carpet walk-off areas at both ends of each row of specimens. These areas are necessary to align the walkers to avoid twisting motion while stepping on the specimens, and shall be a minimum of 2 m (2 yards) long.

6.1.3 The width of the test area shall be adequate to layout a pattern with an odd number of lanes of specimens that require the walkers to automatically reverse their direction with each pass through the course. See Fig. 1 for typical traffic pattern.



to assure uniform traffic density from one site to another. The specimen length can be varied with no affect on test results.

8.3 *Marking Specimen*—To orient the carpet specimen with respect to machine direction, place a distinguishing mark such as an arrow on the back of the carpet. Place any other required identification on the back of each specimen before installation in the test area.

9. Conditioning

9.1 Specimens need not be conditioned in the standard atmosphere (70°F, 65 % RH) for testing textiles.

10. Procedure

10.1 Choose a traffic level high enough to produce a noticeable change in surface appearance. 20 000 foot traffic units is recommended for household applications.

10.2 Place the specimens adjacent to one another with the 560 mm (22 in.) dimension perpendicular to the traffic flow.

10.2.1 Group carpet specimens to minimize thickness variation from one specimen to another.

10.3 Secure the individual specimens in place. Do not use any cushioning material with the specimens, unless the test is specifically designed to test the effect of a specific cushion.

10.4 Walkers shall start at the designated start point and follow a walk path in accordance with the layout in Fig. 1.

10.4.1 Walkers shall use a normal walking pace without scuffing.

10.5 Vacuum all specimens uniformly every 1000 foot traffic units, normally while walkers are resting, and at completion of the exposure.

10.5.1 If significant contamination appears in the test area, the source shall be defined and eliminated.

10.6 Remove specimens without stacking. Allow all specimens to recover for a minimum of 16 h.

11. Report

11.1 Report the following information:

11.1.1 Carpet specimens were exposed in accordance with this practice,

11.1.2 Identify the material or product sampled and the method of sampling used,

11.1.3 The number of foot traffic units, and

11.1.4 Detail any deviations from this practice.

12.

13. Keywords

13.1 appearance; carpet; foot traffic units; textile floor covering

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).