



Designation: **D 5021 – 9500**

An American National Standard

Standard Specification for Thermoplastic Elastomer–Chlorinated Ethylene Alloy (TECEA)¹

This standard is issued under the fixed designation D 5021; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

INTRODUCTION

This specification is intended to be a means of calling out materials used in the fabrication of end items or parts. It is not intended for the selection of materials. Material selection should be made by those having expertise in the plastics field after careful consideration of the design and the performance required of the part, the environment to which it will be exposed, the fabrication process to be employed, the inherent properties of the materials other than those covered by this specification, and the economics.

1. Scope*

1.1 This specification covers alloys of chlorinated ethylene elastomers suitable for injection molding, extrusion, blow molding, thermoforming, and other plastics processing methods.

1.2 This specification allows for the use of those TECEA materials that can be recycled, regrounded, and reprocessed, provided that the requirements as stated in this specification are met. The proportions of recycled material used, as well as the nature and amount of any contaminant, however, cannot be covered practically in this specification.

1.3 The properties included in this specification are those required to identify the compositions covered. There may be other requirements necessary to identify particular characteristics important to specialized application. These shall be agreed upon between the user and the supplier, by using the suffixes given in Section 5.

1.4 The values stated in SI units are to be regarded as the standard. The practices, as detailed in Practice ~~E-380~~, IEEE/ASTM SI 10, are incorporated herein.

1.5 The following precautionary caveat pertains only to the test methods portion, Section ~~12~~, 10, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—There is no similar or equivalent ISO standard.

2. Referenced Documents

2.1 ASTM Standards:

D 412 Test Methods for Vulcanized Rubber and Thermoplastic Rubbers and Thermoplastic Elastomers—~~Tension Elastomers—~~
Tension²

¹ This specification is under the jurisdiction of ASTM Committee D-20 on Plastics and is the direct responsibility of Subcommittee D20.15 on Thermoplastic Materials. Current edition approved Feb. 15, 1995; Nov. 10, 2000. Published April 1995; February 2001. Originally published as D 5021 – 89. Last previous edition ~~D 5021 – 89~~. In this revision, a recycle statement was added to the Scope, an ISO equivalency statement was added in Note 1, Tables TECEA and A were revised, and the text was revised in accordance with Classification System D 4000. D 5021 – 95.

*A Summary of Changes section appears at the end of this standard.

- ~~D 618 Practice for Conditioning Plastics and Electrical Insulating Materials for Testing³~~
- ~~D 883 Terminology Relating to Plastics³~~
- ~~D 2240 Test Method for Rubber Property—Durometer Hardness²~~
- ~~D 3892/641 Practice for Packaging/Packing Injection Molding Test Specimens of P Thermoplastic Molding and Extrusion Materials⁴~~
- ~~D 3892 Practice for Packaging/Packing of Plastics⁴~~
- ~~D 4000 Classification System for Specifying Plastic Materials⁴~~
- ~~E 29 Practice for Using Significant Digits in Test Data to Determine Conformance With Specifications⁵~~
- ~~E 380 Practice~~
- ~~IEEE/ASTM SI 10 Standard for Use of the International System of Units (SI) (the Modernized (SI): The Modern Metric System)^{5, 6}~~

3. Terminology

3.1 *Definitions*—For definitions of technical terms pertaining to plastics used in this specification, see Terminology D 883.

4. Classification

4.1 Alloys of chlorinated ethylene elastomers are classified into groups according to processing method. These groups are subdivided into classes by hardness and are further subdivided into grades by purpose as shown in the basic property table (Table TECEA).

NOTE 2—An example of this classification system is as follows; the designation TECEA 112 would indicate:

TECEA	=	thermoplastic elastomer—chlorinated ethylene alloy,
1 (group)	=	extrusion grade,
1 (class)	=	low hardness, and
2 (grade)	=	general purpose—neutral.

4.1.1 To facilitate the incorporation of future or special materials not covered by the basic property table, the “other/unspecified” category (0) for group, class, and grade is shown in Table TECEA. The basic properties can be obtained from Table A.

4.2 Specific requirements shall be shown by a six-character designation. The designation will consist of the letter A and the five digits comprising the cell numbers for the property requirements in the order as they appear in Table A.

² Annual Book of ASTM Standards, Vol 09.01.
³ Annual Book of ASTM Standards, Vol 08.01.
⁴ Annual Book of ASTM Standards, Vol 08.02.
⁵ Annual Book of ASTM Standards, Vol 14.02.
⁶ Annual Book of ASTM Standards, Vol 14.04.

TABLE TECEA Requirements for Thermoplastic Elastomers of Chlorinated Ethylene Alloys

Group	Description	Class	Description	Grade	Description	Hardness Shore A, min	Tensile Strength Test Method D 412, MPa, min	Elongation, % min	Tensile Strength Test Method D 412 at 100°C, MPa, min	Tensile Stress Test Method D 412 at 100 % Elongation, MPa, min		
1	extrusion	1	low hardness	1	black	50	9.0	250	2.0	2.8		
				2	neutral	50	7.2	325	1.2	2.3		
				0	other							
		2	medium hardness	1	black	60	11.6	200	2.4	4.3		
				2	neutral	60	8.3	300	1.3	3.4		
				0	other							
	3	high hardness	1	black	70	12.1	130	2.9	6.2			
			2	neutral	70	9.0	200	1.5	4.8			
			0	other								
	2	molding and extrusion	1	low hardness	1	black	50	6.2	350	1.0	2.4	
					2	neutral	50	6.6	325	1.0	2.4	
					3	translucent	45	5.0	335		1.8	
0					other							
2					medium hardness	1	black	60	6.9	275	1.4	3.4
						2	neutral	60	7.2	330	1.2	3.4
			3	translucent		60	8.6	425	1.6	2.9		
3			high hardness	1	1	black	70	10.4	250	1.8	5.5	
					2	neutral	70	8.6	350	1.6	4.7	
					0	other						
0			other	0	other	0	other					
						0	other					
	0	other										

TABLE A Detail Requirements

Designation Order Number	Property											
		0	1	2	3	4	5	6	7	8	9	
4	Hardness, Test Method D 2240, A/D Durometer, min	unspecified	40A	50A	60A	70A	80A	40D	50D	60D	specify value	
1	Hardness, Test Method D 2240, A/D Durometer, min	unspecified	45A	50A	55A	60A	65A	70A	75A	80A	specify value	
2	Tensile Strength, Test Method D 412, MPa, min	unspecified	4.0	5.5	7.0	8.5	10.0	11.5	13.0	14.5	specify value	
2	Tensile Strength, Test Method D 412, MPa, min	unspecified	4.0	5.0	6.0	7.0	8.0	9.0	10.0	11.0	specify value	
3	Tensile Strength, Test Method D 412, MPa, min at 100°C	unspecified	0.5	1.0		1.5		2.0	2.5	3.0	3.5	
3	Tensile Strength, Test Method D 412, MPa, min at 100°C	unspecified	0.7	1.0	1.2	1.5	1.7	2.0	2.5	3.0	3.5	
4	Tensile Modulus, Test Method D 412, at 100%, MPa	unspecified	2.5	3.5	4.5	5.5	6.5	7.5	8.5	9.5	specify value	
4	Tensile Modulus, Test Method D 412, at 100% elongation, MPa	unspecified	3.0	3.5	4.0	4.5	5.0	5.5	6.0	6.5	specify value	
5	Elongation, Test Method D 412, %, min	unspecified		150	200	250	300	350	400	450	500	specify value
5	Elongation, Test Method D 412, %, min	unspecified	100	150	200	250	300	350	400	450	500	specify value

4.2.1 Although the values listed are necessary to include the range of properties available in existing materials, users should not infer that every possible combination of the properties exists or can be obtained.

4.2.2 An example of this classification system is as follows; the designation TECEA 110 A22400 would indicate the following with the material requirements from Table A:

TECEA 110	=	thermoplastic elastomer chlorinated ethylene alloy from Table TECEA.
A	=	Table A property requirements,
2	=	50 Durometer A hardness, min,
2	=	5.5 MPa tensile, min,
2	=	5.0 MPa tensile, min,
4	=	2.0 MPa tensile, min at 100°C,
4	=	1.5 MPa tensile, min at 100°C,
0	=	unspecified, and
0	=	unspecified.

If no properties are specified, the designation would be TECEA 110.

5. Suffix Requirements

5.1 When requirements are needed that supersede or supplement the property table requirements, they shall be specified through the use of suffixes. In general, the first suffix letter indicates the special requirement needed and the second letter indicates that condition, or test method, or both, with a three-digit number indicating the specific requirement. The suffixes that may be used are listed in Table 3 of Classification System D 4000.

5.1.1 Additional suffixes will be added to this specification as test methods and requirements are developed or requested, or both.

6. Basic General Requirements

6.1 Basic requirements from the property or cell table, as they apply, are always in effect unless these requirements are superseded by specific suffix requirements, which always take precedence.

6.2 The material composition shall be uniform and shall conform to the requirements specified herein.

7. General Requirements

~~7.1 The material composition shall be uniform and shall conform to the requirements specified herein.~~

8. Detail Requirements

~~8.1 The material shall conform to the requirements prescribed in Tables TECEA and A and suffix requirements as they apply.~~

87.2 For the purposes of determining conformance, all specified limits in this specification are absolute limits, as defined in Practice E 29.

87.2.1 With the absolute method, an observed or calculated value is not rounded, but is to be compared directly to the specified limiting value. Conformance or nonconformance with this specification is based on this comparison.

98. Sampling

98.1 Sampling shall be statistically adequate to satisfy the requirements of 142.4. A lot of resin shall be considered to be a unit of manufacture as prepared for shipment and may consist of a blend of two or more product runs or batches of material.

10. Number of Tests

~~10.1 The number of tests conducted shall be consistent with the requirements of Section 9 and 14.4.~~

~~11.~~

9. Specimen Preparation

~~H9.1 The test specimens shall be molded prepared by an injection-molding process as specified in the *Annual Book of ASTM Standards* for the specific products tested, Practice D 3641, or they shall be molded as specified by the resin supplier.~~

120. Conditioning

120.1 Test specimens shall be conditioned in the standard laboratory atmosphere in accordance with Procedure A of Practice D 618 before performing the required tests.

120.2 Conduct tests in the standard laboratory atmosphere of $23 \pm 2^\circ\text{C}$ and $50 \pm 5\%$ relative humidity.

131. Test Methods

131.1 Determine the properties enumerated in this specification by means of the test methods referenced.

~~11.2 The number of tests shall be consistent with the requirements of Section 8 and 12.4.~~

12. Inspection and Certification

142.1 Inspection and certification of the material supplied under this specification shall be in accordance with the requirements specified herein.

142.2 Lot-acceptance inspection shall be the basis on which acceptance or rejection of the lot is made. The lot-acceptance inspection shall consist of the tests listed as they apply: hardness, tensile strength, and elongation.

142.3 Periodic-check inspection shall consist of the tests specified for all requirements of the material under this specification. Inspection frequency shall be adequate to ensure the material is certifiable in accordance with 142.4.

142.4 Certification shall be that the material was manufactured, sampled, tested, and inspected in accordance with this specification and that average values meet the requirements at a confidence level of 95 %.

142.5 Reports of the test results shall be furnished when requested. The report shall consist of the lot-acceptance inspection for the shipment and results of the most recent periodic-check inspection.

153. Packaging and Marking

153.1 For packing, packaging, and marking, the provisions of Practice D 3892 apply.

164. Keywords

164.1 -chlorinated ethylene alloy; elastomers; line callout; recycled

SUMMARY OF CHANGES

This section identifies the location of selected changes to this specification. For the convenience of the user, Committee D20 has highlighted those changes that may impact the use of this specification. This section may also include descriptions of the changes or reasons for the changes, or both.

D 5021 – 00:

(1) Revised cell values in Table A.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).