



Designation: D 6098 – 97

## Standard Specification for Extruded and Compression Molded Shapes Made from Polycarbonate (PC)<sup>1</sup>

This standard is issued under the fixed designation D 6098; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### INTRODUCTION

This specification is intended to be a means of calling out mechanical grade plastic product used in the fabrication of end items or parts.

#### 1. Scope

1.1 This specification covers requirements and test methods for the material, dimensions, and workmanship, and the properties of extruded and compression molded plate, rod, and tubular bar manufactured from polycarbonate.

1.2 This specification is not intended to cover materials used in glazing and signage as defined in 3.2.1 and 3.2.6. It is intended to be a means of calling out mechanical grade plastic products used for fabrication of end items or parts as defined in 3.2.2.

1.3 The properties included in this specification are those required for the compositions covered. Requirements necessary to identify particular characteristics important to specialized applications may be described by using the classification system given in Section 4.

1.4 This specification allows for the use of recycled plastics as defined in Guide D 5033.<sup>2</sup>

1.5 The values stated in inch-pound units are to be regarded as the standard in all property and dimensional tables. For reference purposes, SI units are also included in Table S-PC and Table 1 only.

1.6 The following precautionary caveat pertains only to the test method portions, Section 12, of this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—There is no similar or equivalent ISO standard.

#### 2. Referenced Documents

##### 2.1 ASTM Standards:

- D 256 Test Methods for Determining the Pendulum Impact Resistance of Notched Specimens of Plastics<sup>3</sup>
  - D 618 Practice for Conditioning Plastics for Testing<sup>3</sup>
  - D 638 Test Method for Tensile Properties of Plastics<sup>3</sup>
  - D 790 Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Materials<sup>3</sup>
  - D 883 Terminology Relating to Plastics<sup>3</sup>
  - D 3892 Practice for Packaging/Packing of Plastics<sup>4</sup>
  - D 3935 Specification for Polycarbonate (PC) Unfilled and Reinforced Material<sup>4</sup>
  - D 4000 Classification System for Specifying Plastic Materials<sup>4</sup>
  - D 5033 Guide for the Development of Standards Relating to the Proper Use of Recycled Plastics<sup>5</sup>
- 2.2 ANSI Standard:
- Z1.4-1993 Sampling Procedures and Tables for Inspection by Attributes<sup>6</sup>

#### 3. Terminology

##### 3.1 Definitions:

3.1.1 For definitions of other technical terms pertaining to plastics used in this specification, see Terminology D 883 or Guide D 5033.

3.1.2 *regrind plastic, n*—a product or scrap such as sprues and runners and edge trim that have been reclaimed by shredding and granulating for use in-house.

##### 3.2 Definitions of Terms Specific to This Standard:

3.2.1 *glazing product, n*—a finished product which is glazed or set in frame or sash and not held by mechanical fasteners which pass through the product.

3.2.2 *mechanical grade plastic product, n*—extruded or compression molded shapes made from polycarbonate used for fabrication of end items or parts.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D-20 on Plastics and is the direct responsibility of Subcommittee D20.20 on Plastic Products (Section D20.20.02).

Current edition approved April 10, 1997. Published May 1998.

<sup>2</sup> As defined in Guide D 5033.

<sup>3</sup> Annual Book of ASTM Standards, Vol 08.01.

<sup>4</sup> Annual Book of ASTM Standards, Vol 08.02.

<sup>5</sup> Annual Book of ASTM Standards, Vol 08.03.

<sup>6</sup> Available from American National Standards Institute, 11 W. 42nd St., 13th Floor, New York, NY 10036.



- 3.2.3 *plate, n*—flat stock greater than ¼ in.
- 3.2.4 *recycled-plastic shape, n*—a product made from up to 100 % recycled plastic.
- 3.2.5 *rod, n*—an extruded solid cylindrical shape with a minimum diameter of ⅛in.
- 3.2.6 *signage product, n*—a fabricated sign or outdoor/indoor structure, consisting of any letter, figure, character, mark, point, plane, marquee sign, design, poster, pictorial, picture, stripe, line, trademark, reading matter or illuminating device, which is constructed, attached, erected, fastened, or manufactured in any manner so that the same shall be used for the attraction of the public to any place, subject, person, firm, corporation, public performance, article, machine or merchandise, and displayed in any manner for recognized advertising purposes.
- 3.2.7 *tubular bar, n*—an extruded annular shape with minimum inside diameter of ⅜in. and minimum wall thickness of ⅛in.

#### 4. Classification and Material

- 4.1 Product shape and size as defined in the applicable purchase order.
- 4.2 This specification covers product extruded and compression molded as listed in Table S-PC. Products included in the designations reference Specification D 3935 callouts where applicable.
  - 4.2.1 The type of polycarbonate shape product may be categorized by type, grade and class depending on resin and filler compositions as defined in Table S-PC.
  - 4.2.2 Each type of polycarbonate shape may be categorized into one of several grades as follows:
    - 4.2.2.1 *Grade 1—General Purpose*—Extruded or compression molded product made using only 100 % virgin polycarbonate resin.
    - 4.2.2.2 *Grade 2—Recycled*—Extruded or compression molded product made using any amount up to 100 % recycled polycarbonate plastics.
- 4.3 The type, class and grade is further differentiated based on dimensional stability (elevated temperature excursion test), Table S-PC, and dimensional requirements, Tables A and B.
- 4.4 *Property Tables:*
  - 4.4.1 Table S-PC may be used to describe both extruded or compression molded products.
  - 4.4.2 Table 1 may also be used to describe extruded or compression molded products not included in Table S-PC via a cell callout that includes the applicable Table S-PC polycarbonate type and specific properties (Designations 1–7).
  - 4.4.3 To facilitate the incorporation of future or special materials not covered by Table S-PC, the “as specified” category (00) for type, class and grade is shown in the table with the basic properties to be obtained from Table 1, as they apply.
  - 4.4.4 *Reinforcements and Additive Materials*—A symbol (single-letter) will be used for the major reinforcement or combination, or both, along with two numbers that indicate the percentage of addition by mass with the tolerances as tabulated below. This must be included in all Table 1 callouts.

Symbol	Material	Tolerance (Based on the Total Mass)
C	Carbon and graphite fiber reinforced	±2 %
G	Glass-reinforced	
	<15 % glass content	±2 %
	>15 % glass content	±3 %
L	Lubricants (for example, PTFE, graphite, and silicone)	by agreement between the supplier and the user
M	Mineral	±2 %
R	Combinations of reinforcements or fillers, or both	±3 % for the total reinforcement

4.5 *Callout Designation*—A one-line system shall be used to specify polycarbonate materials covered by this specification. The system uses pre-defined cells to refer to specific aspects of this specification as illustrated below:

##### 4.5.1 Examples:

4.5.1.1 *Example 1*—Product made from general purpose polycarbonate:

CELL CALLOUT: S-PC0111  
 S-PC01 = Product made from PC in accordance with Table S-PC  
 1 = Unfilled class  
 1 = General purpose grade product

4.5.1.2 *Example 2*—Product made from 20 % glass reinforced general purpose polycarbonate:

CELL CALLOUT: S-PC0100G20I3454430  
 S-PC0100 = Product made from PC in accordance with Table S-PC  
 G20 = 20 % glass  
 1 = Table 1 properties  
 3 = Tensile strength (10,000 psi)  
 4 = Elongation at break (10 %)  
 5 = Tensile Modulus (500,000 psi)  
 4 = Dimensional stability (0.4 %)  
 4 = Flexural Modulus (550,000 psi)  
 3 = Izod Impact (1.0 ft-lb/in. of notch)  
 0 = Unspecified

4.5.2 These two examples illustrate how a one-line, alpha-numeric sequence can identify the product composition, commercial parameters and physical characteristics of extruded or compression molded product. A space must be used as a separator between the specification number and the type designation. No separators are needed between type, class and grade. When special notes are to be included, such information should be preceded by a comma. Special tolerances must be noted at the time of order and are inserted after the grade in parenthesis and preceded by a comma.

#### 5. Ordering Information

5.1 All shapes covered by this specification shall be ordered using the proper callout designation (see 4.5).

#### 6. Physical Property Requirements

6.1 The physical property values listed within this specification’s tables are to be considered minimum specification values. Any requirement for specific test data for a given production lot should be specified at the time of order. Physical properties for products not yet included in Table S-PC may be specified using Table 1 for extruded or compression molded products.

#### 7. Dimensional Requirements

7.1 The type, class and grade is differentiated based on dimensional stability (elevated temperature excursion test), as

indicated in Table S-PC.

7.2 Products shall be produced within commercial tolerances and with the lowest stress levels for machined parts as delineated in Tables A-1, B-1, and B-2.

7.3 Tubular bar dimensions shall be supplied in the unfinished condition, unless otherwise specified at time of order, sufficient to finish to the nominal dimension ordered.

7.4 The maximum allowable camber and/or bow shall be within the limits referenced in Tables A-1, B-1, and B-2.

## 8. Workmanship, Finish, and Appearance

8.1 *Appearance*—The resin material color is transparent with water-white or light straw color. Natural resin is also offered with various amounts of blue tinting. The product color shall be as published by the shapes manufacturer. They shall be uniform in color throughout the thickness. Specific colors and color matching only as agreed to by order.

8.1.1 Physical properties, although unaffected by tinting, may be affected by other colors.

8.2 *Finish*—All products shall be free of blisters, wrinkles, cracks, gouges and defects that restrict commercial use of the product. Special surface finish shall be supplied only when specified in the purchase order or contract.

8.3 *Defects*—All products shall be free of voids, dirt, foreign material and embedded particles exceeding 0.040 in. maximum diameter as defined in 8.3.1.

8.3.1 The criteria for determining the internal cleanliness shall be external visual inspection. A maximum number of two internal defects per square foot of plate and one foot length of rod and tubular bar are allowed. Clusters of defects less than 0.040 in. diameter are to be counted as a single defect.

8.3.2 For compression molded products, four defects up to 0.080 in. diameter per square foot of plate are allowed.

## 9. Sampling

9.1 Sampling shall be statistically adequate to satisfy the requirements of this specification as applicable (see ANSI Z1.4 - 1993).

9.2 For purposes of sampling, an inspection lot for examination and tests shall consist of all material of the same type, class, grade and nominal size submitted for inspection at one time.

## 10. Number of Tests

10.1 Routine lot inspection shall consist of all the criteria specified in the applicable product tables.

10.2 The criteria listed in these product tables and definitions are sufficient to establish conformity of the sheet, plate, rod or tubular bars to this specification. When the number of test specimens is not stated in the test method, a single determination may be made. If more than single determinations and separate portions of the same sample are made, the results shall be averaged. The final result shall conform to the requirements prescribed in this specification.

## 11. Test Conditions

11.1 *Conditioning of Specimens*—The specification values and dimensions are based on conditioning techniques outlined in Procedure A of Practice D 618.

11.2 *Standard Temperature*—The tests shall be conducted at the standard laboratory temperature of  $73.4 \pm 3.6^\circ\text{F}$  ( $23 \pm 2^\circ\text{C}$ ) and  $50 \pm 5\%$  relative humidity.

## 12. Test Methods

12.1 Test tensile strength at break, elongation at break, and tensile modulus (tangent) in accordance with Test Method D 638, at the rate of 0.2 in./min.

12.1.1 Test all plate specimens in accordance with Type I of Test Method D 638.

12.1.2 Test all rod specimens in accordance with Test Method D 638.

12.1.3 Test all tubular bar specimens in accordance with Test Method D 638.

12.2 *Dimensional Stability:*

12.2.1 *Specimen Preparation (a Minimum of Three Test Samples Required):*

12.2.1.1 *Rods and Tubular Bar*—Prepare each specimen by cutting a 1.5 in. long slice from the shape to be tested. Machine the slice using a coolant and good machining practices to a length of  $1.000 \pm 0.005$  in. Each end of the specimen shall have a machined surface.

12.2.1.2 *Plate*—Each specimen shall consist of a 2 in. diameter disc machined from the flat (diameter shall equal test specimen thickness with a minimum of 2.0 in.). The same care shall be used in the machining as described in 12.1.1. The thickness of the specimen shall be that of the original flat from which it was cut, no machining being done on the top or bottom faces.

12.2.2 *Testing Procedure*—Measure the outside diameter and thickness or length of the specimen as applicable at  $73.4 \pm 1.8^\circ\text{F}$  ( $23 \pm 1^\circ\text{C}$ ) to the nearest 0.0001 in. All measurements shall be done on the centerline and  $90^\circ$  from the center line for plate. Also take measurements for thickness halfway to center, and for diameter at mid-point. Place the specimen in a bath consisting of polyalkylene glycol or an air circulating oven heated to  $250 \pm 5^\circ\text{F}$  ( $121 \pm 3^\circ\text{C}$ ). After 6 h, allow the specimen to slowly cool to room temperature at a rate not to exceed  $40^\circ\text{F}$  ( $22^\circ\text{C}$ ) / h. Measure the specimen at  $73.4 \pm 1.8^\circ\text{F}$  ( $23 \pm 1^\circ\text{C}$ ) and calculate the percent change in each dimension.

12.3 *Lengthwise Camber and Widthwise Bow*—

12.3.1 Make all measurements for camber and bow using the maximum distance rod, sheet or plate deviates from the straight line extended from edge to edge when measured in accordance with 12.3.2. The shape shall be oriented such that the weight of the product does not influence the results.

12.3.2 *Rod and Plate:*

12.3.2.1 *Rod*—Lay each rod on its side and measure it with concave side facing a straight edge. Measure camber from the straight edge to the maximum concave point on the rod. Camber may not exceed the values of Table A-1.

12.3.2.2 *Plate*—Plate shall not exceed the requirements of Tables B-1 and B-2 on the lengthwise ends and widthwise edges when laid on a flat surface (crown side up).

12.4 *Squareness (Based on a 4 ft Nominal Length):*

12.4.1 Measure and compare diagonal lengths (corner to corner). Accept the product if the difference is  $\frac{1}{16}$  in. or less



and the measured minimums diagonal meets the following requirements:

- 12.4.1.1 1 ft wide is 49 1/2 in. minimum,
- 12.4.1.2 2 ft wide is 53 3/4 in. minimum, and
- 12.4.1.3 4 ft wide is 68 in. minimum.

12.4.2 If the diagonal difference exceeds 1/16 in., proceed to measure the gap (that is, the deviation from a 2 ft square). The maximum allowable gap shall not exceed 1/8 in. except for the 1 ft wide sizes of sheet and plate which should not exceed 1/16 in.

12.5 Test flexural modulus in accordance with Test Method D 790, specimen 1/4 in. thick maximum, testing speed 0.11 in./min.

12.6 Test Izod impact, in accordance with Test Method D 256, Method A, Fig 4, notched, 1/4 in. thick maximum specimen.

### 13. Certification

13.1 When requested at the time of order, the purchaser shall be furnished a certification that the lot is made from the

required polycarbonate plastic (percent recycle, if applicable) and meets the requirements of this specification.

### 14. Packing, Packaging, and Package Marking

14.1 All packing, packaging, and marking provisions of Practice D 3892 shall apply to this specification.

### 15. Ordering Information

15.1 All shapes covered by this specification shall be ordered using the proper callout designation (see 4.5).

### 16. Keywords

16.1 polycarbonate; plates, polycarbonate; rod, polycarbonate; shapes, polycarbonate; tubular bar, polycarbonate; recycled plastic, polycarbonate

**TABLE S-PC Requirements for Polycarbonate (PC) Shapes**

Type	Description	Class	Description	Grade	Resin Type <sup>A</sup>	Description	Ultimate Tensile Strength, min, psi (MPa)	Tensile Elongation, % at break, min	Tensile Modulus, min, psi (MPa)	Dimensional Stability, max, %
01	Polycarbonate	1	Unfilled	1	PC111, <sup>B</sup> PC112, <sup>B</sup> PC113, <sup>B</sup> PC114, <sup>B</sup> PC115, <sup>B</sup> PC116, <sup>B</sup> PC117, <sup>B</sup> or PC110B34720 <sup>B</sup>	General Purpose	8000 (55)	50	300 000 (2070)	0.4
				2	As Specified <sup>C</sup>	Recycled	...	...	...	...
		2	UV Stabilized	0	As Specified <sup>C</sup>	As Specified	...	...	...	...
				1	PC0135 <sup>B</sup> or PC0136	General Purpose	8000 (55)	50	300 000 (2070)	0.4
				0	As Specified <sup>C</sup>	Recycled	...	...	...	...
0	As Specified	0	As Specified <sup>C</sup>	As Specified	...	...	...	...		
00	Other Polycarbonates	0	As Specified	1	As Specified	General Purpose	...	...	...	...
				2	As Specified	Recycled	...	...	...	...
				0	As Specified <sup>C</sup>	As Specified	...	...	...	...

<sup>A</sup>In accordance with Specification D 3935.

<sup>B</sup>Applicable Specification D 3935 resin type to be specified on purchase order.

<sup>C</sup>Alphanumeric sequence indicating filler type and quantity must precede Table 1 callouts for modified products (see 4.4.4).

**TABLE A-1 Dimensional Requirements for Polycarbonate Rod<sup>A</sup>**

Size, in.	Diameter Tolerance, in.	Roundness TIR, in.	Camber, in./ft
1/8 to 7/8	+0.002/-0.001	0.002	2 1/2/8
1	+0.005/-0	0.002	1 1/4/8
1 1/8 to 1 1/4	+0.005/-0	0.004	1 1/4/8
1 3/8 to 1 7/8	+0.005/-0	0.005	1 1/4/8
2	+0.005/-0	0.010	1 1/4/8
2 1/8 to 2 1/2	+0.030/-0	0.025	1 1/4/8
2 5/8 to 6	+0.250/-0	0.050	1/4/4

<sup>A</sup>To convert inches to millimetres multiply by 25.40.

**TABLE B-1 Dimensional Requirements for Extruded Polycarbonate Plates (Grade 1)<sup>A</sup>**

Size, in.	Thickness Tolerances, in.	Length Camber, in./ft	Width Bow, in./ft
1/4 to 2	+0.025/-0	3/4/4	3/16/2
2 1/8 to 3	+0.050/-0	1/4/4	1/16/2
3 1/8 and over	+0.050/-0	1/4/4	1/16/1

<sup>A</sup>To convert inches to millimetres multiply by 25.40.



**TABLE B-2 Dimensional Requirements for Compression Molded Polycarbonate Plates<sup>A,B</sup>**

Size, in.	Thickness Tolerance, in.	Length Camber, in./ft	Width Bow, in./ft
3/8 to 7/8	+0.090/-0	3/64	3/32/2
1 and over	+0.090/-0	1/8/4	3/64/2

<sup>A</sup>To convert inches to millimetres multiply by 25.40.

<sup>B</sup>Compression molded plate is supplied sufficiently oversize to finish to nominal dimension listed.

**TABLE 1 Additional Detail Requirements—Reinforced/Unreinforced Extruded and Compression Molded Polycarbonates**

NOTE 1—The applicable table polycarbonate type (including fillers in accordance with 4.4.4 ) must precede this table designation.

Designa- tion Order Number	Property	0	1	2	3	4	5	6	7	8	9
1	Tensile strength, Test Method D 638, min, psi (MPa)	Unspecified	6000 (41)	8000 (55)	10 000 (69)	12 000 (83)	14 000 (97)	16 000 (110)	20 000 (138)	25 000 (172)	Specify Value
2	Elongation at Break Test Method D 638, %, min	Unspecified	1	3	5	10	20	50	100	200	Specify Value
3	Tensile Modulus, min, Test Method D 638 min, psi (MPa)	Unspecified	100 000 (690)	200 000 (1379)	300 000 (2073)	400 000 (2760)	500 000 (3448)	600 000 (4137)	800 000 (5516)	1 000 000 (6895)	Specify Value
4	Dimensional Stability, % max, per 12.2	Unspecified	0.1	0.2	0.3	0.4	0.6	0.8	1.0	1.5	Specify Value
5	Flexural Modulus,  Test Method D 790, min, psi (MPa)	Unspecified	250 000 (1649)	350 000 (2400)	450 000 (3100)	550 000 (3792)	650 000 (4482)	750 000 (5171)	1 000 000 (6895)	1 500 000 (10 343)	Specify Value
6	Izod impact, Test Method D 256, min ft-lb/in. of notch (J/m of notch)	Unspecified	0.5 (27)	0.75 (40)	1.0 (53)	2.5 (133)	5.0 (266)	10.0 (533)	15.0 (800)	18.0 (960)	Specify Value
7	To be determined	Unspecified	...	...	...	...	...	...	...	...	...

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).*