



# Standard Specification for Ozone-Resisting Silicone Rubber Insulation for Wire and Cable<sup>1</sup>

This standard is issued under the fixed designation D 2526; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification covers an ozone-resisting crosslinked silicone rubber insulating compound for electrical wires and cables.

1.2 This type of insulation is considered suitable for continuous operation at conductor temperatures up through 125°C for power cable applications. It is considered suitable for conductor sizes up to and including 1000 kcmil (507 mm<sup>2</sup>) at a maximum of 5000 V for both single-and-multiple-conductor cables. Minimum conductor sizes and insulation thicknesses are given in Table 1.

1.3 ~~Whenever two sets of values stated are presented, in inch-pound units different units, the values in the first set are the standard, except while those in cases where SI units are more appropriate. The values in parentheses are for information only.~~

~~1.4 This specification pertains to an insulation material. In~~

1.4 In many instances the insulation material cannot be tested unless it has been formed around a conductor or cable. Therefore, tests are done on insulated wire or cable in this specification document are solely to determine the relevant property of the insulation material and not to test the insulated conductor or completed conductor cable.

## 2. Referenced Documents

2.1 *ASTM Standards:*

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee ~~D-9~~ D09 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.18 on Solid Insulations, Non-metallic Sheildings, and Coverings for Electrical and Telecommunications Wires and Cables.

Current edition approved ~~Sept. 10, 1997~~ March 10, 1997; 2002. Published ~~March 1998~~ June 2002. Originally published as D 2526 – 66 T. Last previous edition D 2526 – 907.

**TABLE 1 Minimum Conductor Size and Insulation Thicknesses**

Rated Circuit Voltage, Phase to Phase, V	Size, AWG or kcmil (mm <sup>2</sup> )	100 % Insulation Level, Grounded Neutral or 133 % Insulation Level, Ungrounded Neutral			
		mils	mm	A-C Test Voltage, kV	D-C Test Voltage, kV
0 to 600	18 to 16 (0.823 to 1.31)	30	0.76	1.0	
	14 to 9 (2.08 to 6.63)	45	1.14	4.5	13.5
	8 to 2 (8.37 to 33.6)	60	1.52	6.0	18.0
	1 to 4/0 (42.4 to 107)	80	2.03	7.5	22.5
	225 to 500 (114 to 253)	95	2.41	8.5	25.5
601 to 1000	525 to 1000 (266 to 507)	110	2.79	10.0	30.0
	14 to 8 (2.08 to 8.37)	60	1.52	6.0	18.0
	7 to 2 (10.6 to 33.6)	80	2.03	7.5	22.5
	1 to 4/0 (42.4 to 107)	95	2.41	8.5	25.5
	225 to 500 (114 to 253)	110	2.79	10.0	30.0
1001 to 2000	525 to 1000 (266 to 507)	125	3.18	11.5	34.5
	14 to 8 (2.08 to 8.37)	80	2.03	7.5	22.5
	7 to 2 (10.6 to 33.6)	95	2.41	8.5	25.5
	1 to 4/0 (42.4 to 107)	110	2.79	10.0	30.0
	225 to 500 (114 to 253)	125	3.18	11.5	34.5
2001 to 5000	525 to 1000 (266 to 507)	140	3.66	11.5	34.5
	8 to 4/0 (8.37 to 107)	155	3.94	13.0	35.0
	225 to 1000 (114 to 507)	170	4.32	13.0	35.0

D 470 Test Methods for Crosslinked Insulations and Jackets for Wire and Cable<sup>2</sup>

D 1711 Terminology Relating to Electrical Insulation<sup>2</sup>

2.2 ICEA Standard:

T-24-380 Guide for Partial-Discharge Procedure<sup>3</sup>

### 3. Terminology

3.1 *Definitions:* For definitions of terms used in this specification, refer to Terminology D 1711.

3.2 *Definition of Term Specific to This Standard:*

3.2.1 *aging (act of), n*—exposure of material to air at  $200 \pm 2^\circ\text{C}$  for 168 h.

### 4. Physical Properties Requirements

4.1 The crosslinked insulation shall conform to the requirements for physical properties listed in Table 2.

### 5. Electrical Requirements

5.1 *Order of Testing*—Perform the partial discharge, ac voltage, insulation resistance, and dc voltage tests in that order when any of these tests are specified. The sequence of other testing is not specified.

5.2 *Partial-Discharge (Corona) Extinction Level*—When tested in accordance with ICEA T-24-380 as modified in Test Methods D 470, each length of completed power cable rated for service at 2001 to 5000 V with insulation shielding on the individual conductors shall have a partial discharge (corona) extinction level of 4.0 kV for an insulation level of 100 % (grounded neutral) and 5.0 kV for an insulation level of 133 % (ungrounded neutral).

5.3 *AC Voltage Test*—Each insulated conductor in the completed cable shall withstand for 5 min the ac test voltage specified in Table 1. Unless otherwise specified, omit this test if the dc voltage test described in 5.5 is to be performed.

5.4 *Insulation Resistance*—The insulated conductor shall have an insulation-resistance value equal to or greater than that corresponding to a constant of  $4000 \left( \frac{\text{M}\Omega}{1000 \text{ ft or } 305 \text{ m basis}} \right) (305 \text{ m})$  at  $60^\circ\text{F}$  ( $15.6^\circ\text{C}$ ). When the temperature of the water in which the insulation is tested differs from  $60^\circ\text{F}$ , apply a correction factor. Table 2, titled “Temperature Correction Factors for Insulation Resistance at  $60^\circ\text{F}$ ,” of Test Methods D 470 contains the correction factors. Each insulation manufacturer can furnish

<sup>2</sup> Annual Book of ASTM Standards, Vol 10.01.

<sup>3</sup> Available from Insulated Cable Engineers Association, PO Box 440, South Yarmouth, MA 02664.

**TABLE 2 Requirements for Physical Properties**

<i>Unaged Requirements:</i>	
Tensile strength, min, psi (MPa)	800 (5.5)
Elongation at rupture, min, %	250
<i>Aged Requirements:</i>	
After air oven test at $200 \pm 2^\circ\text{C}$ for 168 h:	
Tensile strength, min, psi (MPa)	500 (3.4)
Elongation at rupture, min, %	125

the 1°F coefficient for the insulation material by using the procedure given in Test Methods D 470. Multiply the measured value by the correction factor to obtain the insulation resistance value corrected to 60°F.

5.4.1 Where a nonconducting separator is applied between the conductor and insulation, or where an insulated conductor is covered with a nonmetallic sheath so that the insulation resistance can be measured only on the completed assembly, the required insulation resistance shall be at least 60 % of that required for the primary insulation based on the thickness of that insulation.

5.5 *DC Voltage Test*—Upon completion of the insulation resistance test, each insulated conductor in the completed cable shall withstand for 5 min the dc test voltage specified in Table 1. Unless otherwise specified, omit this test if the ac voltage test described in 5.3 has been performed.

5.6 *Capacitance and Dissipation Factor*— Test a specimen of insulated conductor rated for service at 2001 V and above for capacitance and dissipation factor. Conduct the test in room temperature water using suitable 60 Hz equipment at the working voltage. The increase in capacitance between the initial reading (within 1 h of immersion) and the 24 h reading shall not exceed 5 %. The dissipation factor shall not exceed 0.035 after 24 h.

**6. Ozone Resistance**

6.1 The insulation shall show no visible cracksing after exposure for 3 h to an ozone concentration not less than 0.025 nor more than 0.030 by volume %.

**7. Accelerated Water Absorption**

7.1 The insulation shall conform to the requirements for accelerated water absorption, specified in Table 3. Maintain the water at  $75 \pm 1^\circ\text{C}$  ~~in the Electrical Method and  $70 \pm 1^\circ\text{C}$  in the Gravimetric Method.~~ 1°C.

**8. Sampling**

8.1 Unless otherwise instructed, sample the insulation in accordance with Test Methods D 470.

**9. Test Methods**

9.1 Unless otherwise instructed, test the insulation in accordance with Test Methods D 470.

**10. Keywords**

10.1 –accelerated water absorption; ac voltage test; capacitance; dc voltage test; dissipation factor; ozone-resisting; partial discharge; silicone-rubber insulation

**TABLE 3 Accelerated Water Absorption Requirements**

<i>Electrical Method:</i>	
Increase in capacitance, max %	
From 1 to 14 days	10.0
From 7 to 14 days	–3.0
<i>Gravimetric Method:</i>	
–Water absorption, max, mg/in. <sup>2</sup> (g/m <sup>2</sup> )	15.0 (23.3)

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)).*