



Designation: **D 3144 – 9500**

An American National Standard

Standard Specification for Crosslinked Poly(Vinylidene Fluoride) Heat-Shrinkable Tubing for Electrical Insulation¹

This standard is issued under the fixed designation D 3144; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers semirigid, flame-retardant, crosslinked poly(vinylidene fluoride) heat-shrinkable tubing for electrical insulation purposes. It is supplied in an expanded form and will shrink to its extruded diameter when heated.

NOTE 1—This standard is similar but not identical to IEC 60684-3-228.

1.2 The values stated in inch-pound units are to be regarded as the standard, except temperature which shall be stated in degrees Celsius. Values in parentheses are for information only.

2. Referenced Documents

2.1 *ASTM Standards:*

D 910 Specification for Aviation Gasolines²

¹ This specification is under the jurisdiction of ASTM Committee ~~D-9~~ D09 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.07 on Flexible and Rigid Insulating Materials.

Current edition approved ~~Feb. 15, 1995~~ Apr. 10, 2000. Published ~~April 1995~~ July 2000. Originally published as D 3144 – 73. Last previous edition ~~D 3144 – 90¹~~ D 3144 – 95.

~~D-2671 Test Methods for Heat-Shrinkable Tubing for 1711 Terminology Relating to Electrical-Use Insulation³~~

~~D-3636 Practice 2671 Test Methods for Heat-Shrinkable Tubing for Electrical Use⁴~~

~~D 3636 Practice for Sampling and Judging Quality of Solid Electrical Insulating Materials⁴~~

~~E 176 Terminology of Fire Standards⁵~~

~~2.2 Military Standards:⁶~~

~~MIL-H-5606 Hydraulic Fluid, Petroleum Base, Aircraft, Missile and Ordnance~~

~~MIL-T-5624 Turbine Fuel, Aviation, Grades JP-4 and JP-5~~

~~MIL-L-7808 Lubrication Oil, Aircraft, Turbine Engine, Synthetic Base~~

~~MIL-L-23699 Lubrication Oil, Aircraft, Turbine Engines, Synthetic Base~~

~~MIL-A-8243 Anti-Icing and Deicing—Defrosting Fluid~~

~~2.3 Federal Standards:~~

~~SS-S-550 Sodium Chloride, Technical, for Water-Softening Units⁷~~

~~2.4 IEC Standards:~~

~~60684-3-228 Flexible insulating sleeving, Part 3, Sheet 228: Heat-shrinkable, semi-rigid, polyvinylidene fluoride sleeving, flame retarded, fluid resistant, shrink ratio 2:1⁸~~

3. Ordering Information

~~3.1 When tubings are ordered Terminology~~

~~3.1 Definitions:~~

~~3.1.1 For definitions pertaining to this specification, the purchaser should define the size and color of the required tubing. electrical insulation, refer to Terminology D 1711.~~

~~3.1.2 For definitions pertaining to fire standards, refer to Terminology E 176.~~

4. Materials and Manufacture

~~4.1 The compound used in Ordering Information~~

~~4.1 When tubings are ordered to this specification, the manufacture of heat-shrinkable tubing shall be modified poly(vinylidene fluoride), and purchaser should define the finished compound shall be free of all foreign matter other than intended formulation additives as appropriate.~~

~~4.2 The tubing shall be extruded, crosslinked, size and then expanded to color of the required dimensions. tubing.~~

5. Materials and Manufacture

~~5.1 The compound used in the manufacture of heat-shrinkable tubing shall be modified poly(vinylidene fluoride), and the finished compound shall be free of all foreign matter other than intended formulation additives as appropriate.~~

~~5.2 The tubing shall be extruded, crosslinked, and then expanded to the required dimensions.~~

6. Chemical Property Requirements

~~56.1 The material shall conform to the chemical property requirements specified in Table 1.~~

~~56.2 Every lot of material manufactured shall be tested for flammability (when applicable). Other chemical requirements may be tested less frequently or at a frequency agreed upon between the purchaser and the seller.~~

67. Physical Property Requirements

~~67.1 The material shall conform to the mechanical, thermal, and electrical requirements of Table 2.~~

~~67.2 Every lot of material manufactured shall be tested for restricted shrinkage, heat shock, tensile strength, and elongation. Other physical requirements may be tested less frequently or at a frequency agreed upon between the purchaser and seller.~~

78. Dimensional Requirements

~~78.1 The material shall conform to the dimensional requirements of Table 3.~~

~~78.2 Tubing with non-standard dimensions may be supplied when agreed upon between purchaser and seller. Tubing with non-standard dimensions shall be considered to comply with this specification if the requirements of Table 1 and Table 2 are~~

² Annual Book of ASTM Standards, Vol 05.01.

³ Annual Book of ASTM Standards, Vol 10.02¹.

⁴ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

⁴ Annual Book of ASTM Standards, Vol 10.02.

⁵ Available from Superintendent

⁵ Annual Book of Documents, U.S. Government Printing Office, Washington, DC 20402; ASTM Standards, Vol 04.07.

⁶ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

⁷ Available from Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

⁸ Available from American National Standards Institute, 11 W. 42nd St., New York, NY 10036.

TABLE 1 Chemical Property Requirements

| Property | Requirement |
|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|-------------|
| Fluid resistance, 24 h at 23 ± 3°C (73 ± 6°F) JP-4 fuel, MIL-T-5624 Lubricating oil, MIL-L-7808 Lubricating oil, MIL-L-23699 Hydraulic fluid, MIL-H-5606 5% NaCl, SS-S-550 Aviation gasoline, Grade 100, min octane 130, Specification D 910 Deicing fluid, MIL-A-8243 | |
| Followed by tests for: | |
| Dielectric strength, min, V/mil (kV/mm) | 500 (19.7) |
| Tensile strength, min, psi (MPa) at 2 in. (50 mm)/min | 5000 (34.5) |
| Flammability, Procedure A, max, s | 15 |
| Water absorption, 24 h at 23 ± 3°C (73 ± 6°F), max % | 0.5 |

TABLE 2 Physical Property Requirements

| Property | Requirement |
|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|-----------------------------------------|
| Restricted shrinkage, Procedure A, 175 ± 3°C (347 ± 6°F) 2000 V | no cracking, no dielectric breakdown |
| Dielectric strength, min, V/mil (kV/mm) | 600 (23.6) |
| Heat shock, 300 ± 4°C (572 ± 7°F) | no cracking, flowing, or dripping |
| Low-temperature flexibility, -55 ± 2°C (-67 ± 4°F) (see Table 4 for mandrels) Use Procedure A of Methods D 2671 for sizes 3/64 through 1/2 Use Procedure C of Methods D 2671 for sizes 3/4 through 1 | no cracking |
| Tensile strength, min, psi (MPa), using 1-in. (25-mm) bench marks and 1-in. (25-mm) jaw separation at 2 in. (50 mm)/min | 5000 (34.5) |
| Elongation, min %, using 1-in. (25-mm) bench marks and 1-in. (25-mm) jaw separation at 2 in. (50 mm)/min | 150 |
| Heat resistance, 168 h at 250 ± 3°C (482 ± 6°F) | |
| Elongation, min, % | 50 |
| Volume resistivity, min, Ω-cm | 10 ¹³ |
| Secant modulus, min, psi (MPa) | 10 ⁵ (690) |
| Specific gravity, max | 1.8 |

TABLE 3 Dimensional Requirements

| Nominal Size, in. | As Supplied | | After Heat Shrinking | | Longitudinal Change, % |
|-------------------|-----------------------------------|-------------------------|-----------------------------------|-----------------------------|---------------------------|
| | Inside Diameter, min. in. (mm) | Eccentricity, max, % | Inside Diameter, max, in. (mm) | Wall Thickness, in. (mm) | |
| 3/64 | 0.046 (1.16) | 40 | 0.023 (0.59) | 0.010 ± 0.002 (0.25 ± 0.05) | ±10 |
| 1/16 | 0.063 (1.60) | 40 | 0.031 (0.76) | 0.010 ± 0.002 (0.25 ± 0.05) | ±10 |
| 3/32 | 0.093 (2.34) | 40 | 0.046 (1.16) | 0.010 ± 0.002 (0.25 ± 0.05) | ±10 |
| 1/8 | 0.125 (3.18) | 40 | 0.062 (1.60) | 0.010 ± 0.002 (0.25 ± 0.05) | ±10 |
| 3/16 | 0.187 (4.75) | 40 | 0.093 (2.34) | 0.010 ± 0.002 (0.25 ± 0.05) | ±10 |
| 1/4 | 0.250 (6.35) | 40 | 0.125 (3.18) | 0.012 ± 0.003 (0.31 ± 0.08) | ±10 |
| 3/8 | 0.375 (9.50) | 40 | 0.187 (4.75) | 0.012 ± 0.003 (0.31 ± 0.08) | ±10 |
| 1/2 | 0.500 (12.7) | 40 | 0.250 (6.35) | 0.012 ± 0.003 (0.31 ± 0.08) | ±10 |
| 3/4 | 0.750 (19.1) | 40 | 0.375 (9.50) | 0.017 ± 0.003 (0.43 ± 0.08) | ±10 |
| 1 | 1.000 (25.4) | 40 | 0.500 (12.7) | 0.019 ± 0.003 (0.48 ± 0.09) | ±10 |

satisfied and the minimum recovered wall thickness equals or exceeds that of the identical or next largest nominal size. The wall for sizes greater than 1 in. shall be at least as thick as that of the 1 in. size.

8. Workmanship

8.1 The tubing shall be homogeneous and essentially free of flaws, defects, pinholes, bubbles, seams, cracks, or inclusions.

8.2 Clear tubing shall be transparent to translucent light tan or in a color as agreed between purchaser and seller.

9. Workmanship

9.1 The tubing shall be homogeneous and essentially free of flaws, defects, pinholes, bubbles, seams, cracks, or inclusions.

9.2 Clear tubing shall be transparent to translucent light tan or in a color as agreed between purchaser and seller.

10. Sampling

910.1 A lot shall consist of all material which is processed at the same time and under the same conditions and submitted for inspection at one time.

910.2 Properties may be tested at any stage in processing when they are unaffected by subsequent processing.

910.3 Select a quantity of the product at random from each lot in accordance with Practice D 3636 and Table 5.

910.4 Statistical process control measurements may be used to demonstrate conformance in lieu of the sampling plan noted herein when the demonstrated process capability is greater than the specified AQL.

10. Number of Tests and Retests

10.1 The methods of test define the number of specimens and length required for each test.

10.2 If the results of any test, except for attributes listed in Table 3, do not conform to the requirements prescribed in this specification, perform two additional tests on different specimens from the same lot. Nonconformance to Table 3 requirements on first inspection shall be cause for rejection.

10.3 If either of the two additional tests result in nonconformance, the lot of material may be rejected at the option of the purchaser. Notice of nonconformances observed by the purchaser based on tests made according to this specification shall be reported to the manufacturer within 60 days from receipt of the material.

10.4 Tubing that has been rejected may be replaced or reworked to correct the nonconformances and resubmitted for inspection. Before resubmitting, full particulars concerning previous rejection and action taken to correct the nonconformances shall be furnished to the inspector.

11. Test Methods

11.1 Use the test Number of Tests and Retests

11.1 The methods of test define the number of specimens and length required for each test.

11.2 If the results of any test, except for attributes listed in Test Methods D 2671 unless stated otherwise Table 3, do not conform to the requirements prescribed in this specification, perform two additional tests on different specimens from the same lot. Nonconformance to Table 1 or Table 2.

11.2 Use a time of 3 min and a temperature requirements on first inspection shall be cause for rejection.

11.3 If either of 200 ± 2°C (392 ± 4°F) to recover (shrink) tubings the two additional tests result in nonconformance, the lot of material may be rejected at the option of the purchaser. Notice of nonconformances observed by the purchaser based on tests made according to this specification shall be reported to the manufacturer within 60 days from receipt of the material.

11.4 Tubing that has been rejected may be replaced or reworked to correct the nonconformances and resubmitted for inspection. Before resubmitting, full particulars concerning previous rejection and action taken to correct the nonconformances shall be furnished to the inspector.

12. Inspection

12.1 The manufacturer or purchaser or both shall have available all Test Methods

12.1 Use the facilities test methods described in Test Methods D 2671 unless stated otherwise in Table 1 or Table 2.

12.2 Use a time of 3 min and a temperature of 200 ± 2°C (392 ± 4°F) to enable the complete testing to recover (shrink) tubings in this specification.

13. Inspection

13.1 The manufacturer or purchaser or both shall have available all the facilities to enable the complete testing to this specification.

14. Certification

134.1 When specified in the purchase order or contract, the manufacturer's or supplier's certification shall be furnished to the purchaser stating that samples representing each lot have been manufactured, tested, and inspected in accordance with this specification and the requirements have been met. When specified in the purchase order or contract, a report of the test results shall be furnished.

TABLE 4 Mandrel Sizes

| Heat-Shrinkable Tubing Inside Diameter As Supplied, in. | Mandrel Diameter, in. (mm) |
|---------------------------------------------------------|----------------------------|
| 3/64 to 1/4 | 0.312 (7.94) |
| 3/8 to 1/2 | 0.375 (9.53) |
| 3/4 to 1 | 0.438 (11.1) |

TABLE 5 Sampling Table for Lot Acceptance Tests

| Property | Requirement | Inspection Level | AQL | Sampling Unit, ft (m) |
|----------------------------------------------|--------------------|------------------|------------|-------------------------------|
| Inside diameter as supplied | Table 3 | S-3 | 1.0 | 4 (1.2) |
| Inside diameter after unrestricted shrinkage | Table 3 | S-3 | 1.0 | 4 (1.2) |
| Wall thickness after shrinkage | Table 3 | S-3 | 1.0 | 4 (1.2) |
| Longitudinal change | Table 3 | S-2 | 1.0 | 4 (1.2) |
| <u>Straight length size, min</u> | <u>14.1 herein</u> | <u>S-3</u> | <u>1.0</u> | <u>single straight</u> |
| <u>Straight length size, min</u> | <u>15.1 herein</u> | <u>S-3</u> | <u>1.0</u> | <u>single straight length</u> |
| Workmanship | 8.1 herein | I | 2.5 | 4 (1.2) |

145. Packaging, Marking, and Shipping

145.1 The tubing shall be supplied in lengths of 48 + 1, –0 in. (1219 + 25, –0 mm) unless otherwise specified.

145.2 The tubing shall be packaged in conformance with standard commercial practice unless otherwise specified. Individual sizes shall be neatly bundled or boxed. The exterior shipping container shall be acceptable by parcel post or common carrier.

145.3 Each bundle or container of tubing shall be distinctly identified by a tag or label. The name of the manufacturer, the expanded and recovered dimension of the tubing, the length, quantity, and other appropriate information shall be shown thereon.

156. Keywords

156.1 crosslinked poly(vinylidene fluoride) heat-shrinkable tubing; electrical insulation; heat-shrinkable tubing; poly(vinylidene fluoride)

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).