

This document is not an ASTM standard and is intended only to provide the user of an ASTM standard an indication of what changes have been made to the previous version. Because it may not be technically possible to adequately depict all changes accurately, ASTM recommends that users consult prior editions as appropriate. In all cases only the current version of the standard as published by ASTM is to be considered the official document.



Designation: D 4730 – 93 (Reapproved 1998)


Designation: D 4730 – 02

An American National Standard

Standard Specification for Flooding Compounds for Telecommunications Wire and Cable¹

This standard is issued under the fixed designation D 4730; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers a variety of compounds used for flooding the shields and armors of telecommunications wires and cables (both electrical and fiber optic) for the purpose of preventing water and other undesirable fluids from entering or migrating along or through the cable sheath. (For related standards see Specifications D 4731 and D 4732.)

2. Referenced Documents

2.1 ASTM Standards:

D 6 Test Method for Loss on Heating of Oil and Asphaltic Compounds²

D 92 Test Method for Flash and Fire Points by Cleveland Open Cup³

D 482 Test Method for Ash from Petroleum Products³

D 1321 Test Method for Needle Penetration of Petroleum Waxes³

D 3236 Test Method for Apparent Viscosity of Hot Melt Adhesives and Coating Materials⁴

D 4565 Test Methods for Physical and Environmental Performance Properties of Insulations and Jackets for Telecommunications Wire and Cable⁵

D 4568 Test Methods for Evaluating Compatibility Between Cable Filling and Flooding Compounds and Polyolefin Wire and Cable Materials⁵

D 4731 Specification for Hot-Application Filling Compounds for Telecommunications Wire and Cable⁵

D 4732 Specification for Cool-Application Filling Compounds for Telecommunications Wire and Cable⁵

E 28 Test Method for Softening Point of Resins Derived from Naval Stores by Ring-and-Ball Apparatus⁶

3. Terminology

3.1 Descriptions of Terms Specific to this Standard:

3.1.1 *flooding compounds*—any of several materials used to fill the air spaces between the sheath elements of single and multi-conductor insulated wires and cables or optical cables for the purpose of excluding water and other undesirable fluids; especially with regard to telecommunications wire and cable, including optical cable, intended for outside aerial or underground installations.

3.1.2 *producer*—the primary manufacturer of the material.

3.1.3 *suppliers*—jobbers and distributors as distinct from producers.

4. Ordering Information

4.1 Orders for material under this specification shall include the following information:

4.1.1 Quantity (mass or volume) of each item,

4.1.2 Generic name of the material, such as cable flooding compound,

4.1.3 How furnished (drums or barrels, blocks, etc.),

4.1.4 Certification, if required (see Section 11).

4.1.5 This specification designation, and

4.1.6 Any special requirements, as listed in 8.2 and 9.2, that apply.

¹ This specification is under the jurisdiction of ASTM Committee D-9 D09 on Electrical and Electronic Insulating Materials and is under the direct responsibility of Subcommittee D09.18 on Solid Insulations, Non-Metallic Shieldings and Coverings for Electrical and Telecommunication Wires and Cables.

Current edition approved July 15, 1993; Sept. 10, 2002. Published October 1993, 2002. Originally published as D 4730-87. Last previous edition D 4730-93 (19987).

² Annual Book of ASTM Standards, Vol 04.04.

³ Annual Book of ASTM Standards, Vol 05.01.

⁴ Annual Book of ASTM Standards, Vol 05.02.

⁵ Annual Book of ASTM Standards, Vol 10.02.

⁶ Annual Book of ASTM Standards, Vol 06.03.

5. Materials and Manufacture

5.1 The material and manufacturing methods used shall be such that the resulting products will conform to the properties and characteristics prescribed in this specification.

6. Compatibility with Other Materials

6.1 It is the responsibility of the purchaser to ensure that the flooding compound ordered is suitable for the intended application and is compatible with any other components that may come into contact with the flooding compound.

6.2 The purchaser shall specify the materials ~~with which~~ that the compound must be compatible with when tested in accordance with Test Method D 4568.

7. Chemical Composition

7.1 The chemical composition of these materials is not specified. The material may be of any chemical composition suitable for the intended purpose and which meets the requirements of this specification as hereinafter stated.

7.2 Once established, the producer shall not change the composition of the compound in successive lots of material without prior approval of the purchaser.

8. Physical Properties

8.1 Flooding compound furnished under this specification shall inhibit the corrosion of any metallic wire and cable elements with which it comes in contact, while serving as a radial and longitudinal barrier to moisture transmission. Contact of the flooding compound with any cable component shall not cause degradation of performance of the cable component. The flooding compound shall display adhesive properties to provide adhesion between metallic sheath elements and the outer jacket materials of wire and cable.

8.2 Other Properties:

8.2.1 Other physical properties requirements such as Viscosity (for example, Test Method D 3236), Flash Point (for example, Test Method D 92), Needle Penetration (for example, Test Method D 1321), Ring-and-Ball Softening Point (for example, Test Method E 28), and Heat Stability/Viscosity Change (for example, Test Method D 3236), may be specified, if needed, and shall be as agreed-upon between the producer and the purchaser.

8.3 The purchaser (individual cable manufacturer or other) shall specify any other expected requirements needed to ensure compliance with such end-product requirements as cold-bend, low-temperature flexibility, and the like (for example, Test Methods D 4565).

9. General Requirements

9.1 All flooding compounds manufactured in conformance to this specification shall meet the following requirements:

9.1.1 *Homogeneity*—The compound shall be homogeneous and uniformly mixed.

9.1.2 *Foreign Material*—The compounds shall be free of dirt, metallic particles, and other foreign matter.

9.2 Other Properties:

9.2.1 Other raw material requirements such as ~~Viscosity (for example, Test Method D 3236), Flash Point (for example, Test Method D 92), Needle Penetration (for example, Test Method D 1321), Ring-and-Ball Softening Point (for example, Test Method E 28),~~ Volatility (for example, Test Method D 6), Metals Content (for example, Test Method D 482), ~~Heat Stability/Viscosity Change (for example, Test Method D 3236);~~ adhesive property measurements, and corrosion inhibiting characteristics may be specified, if needed, and shall be as agreed-upon between the producer and the purchaser.

9.3 The purchaser (individual cable manufacturer or other) shall specify any other expected requirements needed to ensure compliance with such end-product requirements as ~~cable drip-out temperature, jacket slip, cold-bend, low-temperature flexibility, temperature and the like (for example, Test Methods D 4565);~~ jacket slip.

10. Quality Assurance

10.1 *Responsibility for Inspection and Tests*—Unless otherwise specified in the contract or purchase order, the producer is responsible for the performance of all inspection and test requirements specified herein. The producer may use his own or any other suitable facilities for the performance of the inspection and test requirements specified herein, unless otherwise stated by the purchaser in the order or at the time of the contract signing. The purchaser shall have the right to perform any of the inspections and tests set forth in this specification where such inspections are deemed necessary to assure that the material conforms to prescribed requirements.

10.2 Each producer shall establish written nominal values and tolerances for the material properties routinely checked. For properties not routinely checked, typical values shall be specified. Once these values have been accepted by the purchaser, the producer shall not ship material which deviates from these limits without prior notification to and approval by the purchaser.

10.3 An inspection lot shall consist of an identifiable quantity of the same material subjected to inspection at one time.

11. Certification

11.1 The producer or supplier shall, on request, furnish to the purchaser a certificate stating that each lot has been sampled,

tested, and inspected in accordance with this specification, and has met the requirements.

12. Packaging and Package Marking

12.1 *Packaging*—The flooding compound shall be packaged in a manner that protects the material from contamination during shipment.

12.2 *Package Marking*—Shipping containers shall be marked with the name of the manufacturer, trade name, type of material, lot number, mass or volume, and date of manufacture.

13. Keywords

13.1 adhesive; compatibility; flooding compound; moisture barrier; telecommunications wire and cable

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).