



Standard Specification for 42 % Nickel-6 % Chromium-Iron Sealing Alloy ¹

This standard is issued under the fixed designation F 31; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers an iron-nickel-chromium alloy (UNS K94760) used primarily for glass-sealing applications in electronic devices.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 The following safety hazards caveat applies only to Section 13. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

- E 18 Test Methods for Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials ²
- E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications ³
- E 38 Methods for Chemical Analysis of Nickel-Chromium and Nickel-Chromium-Iron Alloys ⁴
- E 112 Test Methods for Determining the Average Grain Size ²
- E 228 Test Method for Linear Thermal Expansion of Solid Materials with a Vitreous Silica Dilatometer ³
- F 14 Practice for Making and Testing Reference Glass-Metal Bead-Seal ⁵
- F 140 Practice for Making Reference Glass-Metal Butt Seals and Testing for Expansion Characteristics by Polarimetric Methods ⁵
- F 144 Practice for Making Reference Glass-Metal Sandwich Seal and Testing for Expansion Characteristics by

Polarimetric Methods ⁵

3. Ordering Information

3.1 Orders for material under this specification shall include the following information:

- 3.1.1 Size,
- 3.1.2 Temper (Section 6),
- 3.1.3 Surface finish (Section 8),
- 3.1.4 Marking and packaging (Section 13), and
- 3.1.5 Certification if required.

4. Chemical Composition

4.1 The material shall conform to the requirements of Table 1 as to chemical composition.

TABLE 1 Chemical Composition

Element	Composition, %
Nickel, nominal	42.0
Chromium, nominal	5.6
Carbon, max	0.07
Manganese, max	0.25
Phosphorus, max	0.025
Sulfur, max	0.025
Silicon, max	0.30
Aluminum, max	0.20
Iron	remainder

NOTE 1—The major constituents of this alloy may be adjusted by the manufacturer so that the alloy meets the requirement for thermal expansion.

5. Chemical Analysis

5.1 Chemical analysis shall be made, when desired, in accordance with Methods E 38.

6. Surface Lubricants

6.1 All lubricants used during cold-working operations such as drawing, rolling, or spinning, shall be capable of being removed readily by any of the common organic degreasing solvents.

7. Temper

7.1 The desired temper of the material shall be specified on the purchase order. Unless otherwise specified, wire, rod, and

¹ This specification is under the jurisdiction of ASTM Committee F-1 on Electronics and is the direct responsibility of Subcommittee F01.03 on Metallic Materials.

Current edition approved April 15, 1994. Published June 1994. Originally published as F 31 – 63 T. Last previous edition F 31 – 68 (1989) ^{ε1}.

² Annual Book of ASTM Standards, Vol 03.01.

³ Annual Book of ASTM Standards, Vol 14.02.

⁴ Discontinued; see 1988 Annual Book of ASTM Standards, Vol 03.05.

⁵ Annual Book of ASTM Standards, Vol 15.02.

TABLE 2 Permissible Variations in Thickness of Cold-Rolled Strip

NOTE 1— Measurement shall be made at least 3/8 in. (9.5 mm) from the edge of strip over 1-in. (25.4 mm) wide.

Specified Thickness		Permissible Variations in Thickness for Width Given, ±							
in.	(mm)	Under 3 in.	(Under 76 mm)	Over 3 to 6 in.	(76 to 150 mm)	Over 6 to 12 in.	(150 to 300 mm)	Over 12 to 16 in.	(300 to 400 mm)
0.160 to 0.100, incl	(4.06 to 2.54)	0.002	(0.05)	0.003	(0.076)	0.004	(0.10)	0.004	(0.10)
0.099 to 0.069, incl	(2.51 to 1.75)	0.002	(0.05)	0.003	(0.076)	0.003	(0.076)	0.004	(0.10)
0.068 to 0.050, incl	(1.73 to 1.27)	0.002	(0.05)	0.003	(0.076)	0.003	(0.076)	0.003	(0.076)
0.049 to 0.035, incl	(1.24 to 0.89)	0.002	(0.05)	0.0025	(0.064)	0.003	(0.076)	0.003	(0.076)
0.034 to 0.029, incl	(0.86 to 0.74)	0.0015	(0.038)	0.002	(0.05)	0.0025	(0.064)	0.0025	(0.064)
0.028 to 0.026, incl	(0.71 to 0.66)	0.0015	(0.038)	0.0015	(0.038)	0.002	(0.05)	0.002	(0.05)
0.025 to 0.020, incl	(0.64 to 0.51)	0.001	(0.025)	0.0015	(0.038)	0.002	(0.05)	0.002	(0.05)
0.019 to 0.017, incl	(0.48 to 0.43)	0.001	(0.025)	0.001	(0.025)	0.0015	(0.038)	0.002	(0.05)
0.016 to 0.012, incl	(0.41 to 0.30)	0.001	(0.025)	0.001	(0.025)	0.0015	(0.038)	0.0015	(0.038)
0.011 to 0.0101, incl	(0.28 to 0.256)	0.001	(0.025)	0.001	(0.025)	0.001	(0.025)	0.0015	(0.038)
0.010 to 0.0091, incl	(0.254 to 0.231)	0.001	(0.025)	0.001	(0.025)	0.001	(0.025)	0.001	(0.025)
0.009 to 0.006, incl	(0.228 to 0.152)	0.00075	(0.019)	0.00075	(0.019)
Under 0.006	(0.152)	0.0005	(0.013)	0.0005	(0.013)

TABLE 3 Permissible Variation in Thickness Across Width of Strip

Specified Thickness		Maximum Variation in Thickness Across Width of Strip, Within Those Provided for in Table 1 for Edge Measurements for Widths and Thicknesses Given,					
in.	(mm)	5 in. and Under	(127 mm and Under)	Over 5 to 12 in.	(Over 127 to 300 mm)	Over 12 to 24 in., incl	(Over 300 to 600 mm)
0.005 to 0.010, incl	(0.13 to 0.25)	0.00075	(0.019)	0.001	(0.025)	0.0015	(0.038)
Over 0.010 to 0.025, incl	(0.25 to 0.64)	0.001	(0.025)	0.0015	(0.038)	0.002	(0.051)
Over 0.025 to 0.065, incl	(0.64 to 1.65)	0.0015	(0.038)	0.002	(0.051)	0.0025	(0.064)
Over 0.065 to 3/16, excl	(1.65 to 4.74)	0.002	(0.051)	0.0025	(0.064)	0.003	(0.076)

tubing shall be given a final bright anneal by the manufacturer. Strip and sheet shall be annealed properly to develop drawing properties. For deep drawing, the hardness shall not exceed Rockwell B90 when determined in accordance with Test Methods E 18.

8. Grain Size

8.1 Strip and sheet for deep drawing applications shall have an average grain size not larger than ASTM No. 5 (Note 2), with no more than 10 % of the grains larger than No. 5 when measured in accordance with Test Methods E 112. For materials less than 0.005 in. (0.13 mm) in thickness, the grain size shall be such that there are no less than 4 grains across the thickness.

NOTE 2—This corresponds to a grain size finer than 0.065 mm or 16 grains/in.² of image at 100X.

9. Dimensional Tolerances

9.1 *Cold-Rolled Strip*—Cold-rolled strip shall conform to the permissible variations in dimensions prescribed in Table 2, Table 3, and Table 4.

TABLE 5 Permissible Variations in Diameter of Wire and Rod

Specified Diameter		Permissible Variations in Diameter, ±	
in.	(mm)	in.	(mm)
Wire (Coiled, Spooled or Straight Lengths)			
0.002 to 0.0043	(0.051 to 0.109)	0.0002	(0.005)
0.0044 to 0.0079	(112 to 0.200)	0.00025	(0.0064)
0.008 to 0.0149	(0.203 to 0.378)	0.0003	(0.0076)
0.015 to 0.0199	(0.381 to 0.505)	0.0004	(0.0102)
0.020 to 0.0309	(0.508 to 0.785)	0.0005	(0.0127)
0.031 to 0.0409	(0.787 to 1.039)	0.0006	(0.0152)
0.041 to 0.0609	(1.041 to 1.547)	0.0007	(0.0178)
0.061 to 0.0809	(1.549 to 2.055)	0.0008	(0.0203)
0.081 to 0.1259	(2.057 to 3.198)	0.001	(0.0254)
0.126 to 0.1569	(3.200 to 3.985)	0.0015	(0.038)
0.157 to 0.250	(3.988 to 6.35)	0.002	(0.051)
Rod, Centerless Ground Finish (Straight Lengths)			
0.030 to 0.0549	(0.766 to 1.394)	0.0005	(0.0127)
0.055 to 0.1249	(1.397 to 3.172)	0.001	(0.0254)
0.125 to 0.499	(3.175 to 12.67)	0.0015	(0.038)
0.500 to 0.999	(12.70 to 25.37)	0.002	(0.051)
1.000 to 1.625	(25.4 to 41.27)	0.0025	(0.064)
1.626 to 1.749	(41.3 to 44.42)	0.003	(0.076)
1.750 to 1.999	(44.45 to 50.17)	0.004	(0.010)
2.000 to 4.000	(50.8 to 101.6)	0.005	(0.013)

TABLE 4 Permissible Variations in Width of Cold-Rolled Strip Supplied in Coils

Specified Thickness		Permissible Variations in Width for Widths Given, ±											
in.	(mm)	Under 1/2 to 3/16 in.	(Under 12.7 to 4.75 mm)	1/2 to 6 in.	(12.7 to 150 mm)	Over 6 to 9 in.	(150 to 225 mm)	Over 9 to 12 in.	(225 to 300 mm)	Over 12 to 20 in.	(300 to 500 mm)	Over 20 to 23 1/16 in.	(500 to 600 mm)
0.187 to 0.161	(4.75 to 4.09)	...	(0.016)	(0.41)	0.020	(0.51)	0.020	(0.51)	0.031	(0.79)	0.031	(0.79)	
0.160 to 0.100	(4.06 to 2.54)	0.010	(0.25)	0.010	(0.25)	0.016	(0.41)	0.016	(0.41)	0.020	(0.51)	0.020	(0.51)
0.099 to 0.069	(2.51 to 1.75)	0.008	(0.20)	0.008	(0.20)	0.010	(0.25)	0.010	(0.25)	0.016	(0.41)	0.020	(0.51)
0.068 and under	(1.73)	0.005	(0.13)	0.005	(0.13)	0.005	(0.13)	0.010	(0.25)	0.016	(0.41)	0.020	(0.51)

TABLE 6 Permissible Variations in Dimensions of Standard Tubing

Specified Outside Diameter,		Permissible Variations ^A				
in.	(mm)	Outside Diameter		Inside Diameter		Wall Thickness, plus or minus, %
		in.	(mm)	in.	(mm)	
Under 0.093	(2.36)	+ 0.002	(+ 0.051)	+ 0.000	(+ 0.000)	10
		-0.000	(-0.000)	-0.002	(-0.051)	
0.093 to 0.187, excl	(2.36 to 4.75)	+ 0.003	(+ 0.076)	+ 0.000	(+ 0.000)	10
		-0.000	(-0.000)	-0.003	(-0.076)	
0.187 to 0.550, excl	(4.75 to 12.7)	+ 0.004	(+ 0.102)	+ 0.000	(+ 0.000)	10
		-0.000	(-0.000)	-0.004	(-0.102)	
0.500 to 1.500, excl	(12.7 to 38.1)	+ 0.005	(+ 0.13)	+ 0.000	(+ 0.000)	10
		-0.000	(-0.00)	-0.005	(-0.13)	

^A Any two of the three dimensional tolerances listed may be specified.

TABLE 7 Coefficient of Thermal Expansion^A

Temperature Range, °C	Coefficient, 10 ⁻⁶ /°C
30 to 425	9.7 to 10.4
30 to 350	8.5 to 9.2

^A Typical expansion data up to 700°C are given in the Appendix.

9.2 *Round Wire and Rod*—Wire and rod shall conform to the permissible variations in dimension prescribed in Table 5.

9.3 *Cold-Drawn Tubing*—Cold-drawn tubing, available either as seamless or welded, shall conform to the permissible variations prescribed in Table 6.

10. Surface Finish

10.1 The standard surface finishes available shall be those resulting from the following operations:

- 10.1.1 Hot rolling,
- 10.1.2 Forging,
- 10.1.3 Centerless grinding (rod),
- 10.1.4 Belt polishing,
- 10.1.5 Cold rolling, and drawing, and
- 10.1.6 Wire drawing.

10.2 Care shall be taken to prevent the depletion of surface chromium during processing.

11. Thermal Expansion Characteristics

11.1 The average linear coefficient of thermal expansion shall be within limits specified in Table 7.

12. Test Method for Thermal Expansion

12.1 Heat the specimen for 15 min at 1100°C in a hydrogen or cracked-ammonia atmosphere with a dew point of -40°C and cool to room temperature at a rate not exceeding 5°C/min.

12.2 Determine the thermal expansion characteristics in accordance with Test Method E 228.

12.3 The thermal expansion match between the alloy and a glass may be evaluated by preparing and testing an assembly in accordance with Practice F 14, Practice F 140, or Practice F 144.

13. Test Results

13.1 Observed or calculated values obtained from analysis, measurements, or tests shall be rounded off in accordance with the rounding-off method of Practice E 29, to the nearest unit in the last right-hand place of figures used in expressing the specified limit.

14. General Requirements

14.1 The material shall be commercially smooth, uniform in cross section, in composition, and in temper; it shall be free of scale, corrosion, cracks, seams, scratches, slivers, and other defects as best commercial practice will permit.

15. Packaging and Package Marking

15.1 Packaging shall be subject to agreement between the purchaser and seller.

15.2 The material as furnished under this specification shall be identified by the name or symbol of the manufacturer and by melt number. The lot size for determining compliance with the requirements of this specification shall be one heat.

16. Investigation of Claims

16.1 Where any material fails to meet the requirements of this specification, the material so designated shall be handled in accordance with the agreement mutually agreed upon between the purchaser and the seller.

17. Keywords

17.1 glass-to-metal sealing; iron-nickel-chromium alloy; UNS K94760

APPENDIX**(Nonmandatory Information)****X1. THERMAL EXPANSION DATA**

X1.1 The following typical thermal expansion data for 42 % nickel-6 % chromium-iron sealing alloy (UNS K94760) are given for information only.

Temperature Range. °C	Average Linear Coefficient of Thermal Expansion. $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$
30 to 300	7.9
30 to 400	9.8
30 to 500	11.2
30 to 600	12.1
30 to 700	13.0

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).