



Standard Specification for Electronic Grade Alloys of Copper and Nickel in Wrought Forms¹

This standard is issued under the fixed designation F 96; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers alloys of copper and nickel in a variety of wrought shapes suitable for external and internal use in electron devices.

1.2 The following safety hazards caveat applies to Test Methods Section 8 only: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

- A 342 Test Methods for Permeability of Feebly Magnetic Materials²
- B 122/B122M Specification for Copper-Nickel-Tin Alloy, Copper-Nickel-Zinc Alloy (Nickel Silver) and Copper-Nickel Alloy Plate, Sheet, Strip, and Rolled Bar³
- B 127 Specification for Nickel-Copper Alloy (UNS N04400) Plate, Sheet, and Strip⁴
- B 164 Specification for Nickel-Copper Alloy Rod, Bar, and Wire⁴
- B 165 Specification for Nickel-Copper Alloy (UNS N04400) Seamless Pipe and Tube⁴
- E 75 Test Method for Chemical Analysis of Copper-Nickel and Copper-Nickel-Zinc Alloys⁵

3. Ordering Information

3.1 Orders for material to this specification shall include the following information:

- 3.1.1 Alloy (see 9.1),
- 3.1.2 Shape,
- 3.1.3 Condition (cold-rolled, hot-rolled, etc.),
- 3.1.4 Dimensions,

- 3.1.5 Weight,
- 3.1.6 Packaging (see 10.2), and
- 3.1.7 Special requirements (see 11.1).

4. Manufacture and Workmanship

4.1 The material shall be handled in such a manner that oxide contamination and foreign material such as metal chips and dirt shall be minimized on the surfaces.

4.2 Sheet and strip intended for deep drawing shall be substantially free from directional properties which can cause excessive tearing in the deep drawn product.

5. Chemical Composition

5.1 This material shall conform to the chemical composition shown in Table 1.

5.2 When specifically requested, a certificate of chemical analysis shall be supplied by the manufacturer. Sample for chemical analysis is to be taken from a ladle sample at the time the melt is cast. Each sample shall be individually analyzed to the requirements of 5.1 and the numerical results of analysis reported in the certification.

5.3 In case of disagreement, the analysis shall be made in accordance with Test Method E 75 for the respective materials when such methods of analysis are available. When ASTM methods are not available, the analytical procedures shall be agreed upon by the manufacturer and the purchaser.

6. Physical Properties

6.1 *Alloy 1*—The properties shall be as shown in the applicable basic product specification referenced in 5.1 except for grain size which shall conform to the requirements in Table 2.

6.2 *Alloys 2 and 3*—The mechanical properties shall be as agreed upon between manufacturer and purchaser. The grain size shall conform to the requirements in Table 2.

6.3 *Alloy 4*:

6.3.1 The mechanical properties shall be as agreed upon between manufacturer and purchaser.

6.3.2 Grain size and hardness for deep drawing quality sheet and strip shall conform to the requirements shown in Specification B 127.

6.3.3 The magnetic permeability shall not exceed 1.1 when tested at -3°C and a field strength of 39.8 A/m.

¹ This specification is under the jurisdiction of ASTM Committee F-1 on Electronics and is the direct responsibility of Subcommittee F01.03 on Metallic Materials.

Current edition approved June 24, 1977. Published August 1977. Originally published as F 96 – 68. Last previous edition F 96 – 68 (1973).

² *Annual Book of ASTM Standards*, Vol 03.04.

³ *Annual Book of ASTM Standards*, Vol 02.01.

⁴ *Annual Book of ASTM Standards*, Vol 02.04.

⁵ *Annual Book of ASTM Standards*, Vol 03.05.

TABLE 1 Chemical Requirements^A

Alloy	1	2	3	4	5
Nominal Composition, %	70 Cu-30 Ni	70 Cu-30 Ni	90 Cu-10 Ni	55 Ni-45 Cu	65 Ni-35 Cu
UNS Alloy Number	C71580	C71590	C70690	N04404	N04400
Nickel, %	29–33	29–33	9.0–11.0	52–57	62 min
Cobalt, %	^B	0.05 max	0.02 max	^B	^B
Iron, max, %	0.5	0.005	0.005	0.5	2.5
Zinc, max, %	0.05 ^C	0.001	0.001	0.02 ^C	0.02 ^C
Manganese, max, %	0.3	0.001	0.001	0.1	2.0
Lead, max, %	0.05 ^C	0.001	0.001	0.01 ^C	0.01 ^C
Carbon, max, %	0.07	0.03	0.03	0.15	0.2
Silicon, max, %	0.15	0.02	0.02	0.1	0.5
Sulfur, max, %	0.024	0.003	0.003	0.015	0.015
Aluminum, max, %	0.05	0.002	0.002	0.05	—
Phosphorus, max, %	0.03	0.001	0.001	0.03 ^C	0.02 ^C
Copper, %	65 min	67 ^D min	89.0 ^D min	balance	28.0–34.0

^A By agreement between purchaser and seller, analysis may be required and limits established for elements or compounds not specified in this table.

^B Cobalt counting as nickel. (For these alloys the percentage given for nickel includes any cobalt present, and no separate value is given for cobalt.)

^C Need not be routinely determined and reported unless specifically requested by agreement between purchaser and seller.

^D The following additional requirements shall apply to Alloys 2 and 3; bismuth, arsenic, titanium, tin, and antimony—10 ppm each max; mercury—5 ppm max.

TABLE 2 Grain Size of Annealed Tempers of Alloys 1, 2, and 3

Temper	Average Grain Size, mm					
	Sheet and Strip			Rod and Bar		
	nominal	min	max	nominal	min	max
Soft anneal	0.035	0.025	0.050	0.035	0.025	0.050
Light anneal	0.015	^A	0.025	0.015	^A	0.030

^A Although no minimum grain size is required, this material shall be fully recrystallized.

6.3.3.1 Testing shall be performed in accordance with Method 5 of Test Methods A 342, or by an equivalent procedure. In case of disagreement, Method 5 of Test Methods A 342 shall be used as the referee method.

6.3.3.2 Testing shall be performed on a one per heat basis.

6.4 Alloy 5—The properties shall be as shown in the applicable basic product specifications referenced in 5.1.

7. General Condition

7.1 *Macroscopical*—Edges shall be free from seams, laps, folds, and cracks which would be detrimental to its end use.

7.2 *Microscopical*—The material shall be free of nonmetallic inclusions or discontinuities which would be detrimental to its end use when examined in accordance with 8.1.2.

8. Test Methods

8.1 For Alloys 1 and 2, the properties enumerated in this specification shall be determined on specimens prepared in accordance with the following procedures.

8.1.1 *Macroscopical*:

8.1.1.1 For this examination, usually performed on heat-treated or unheat-treated specimens of large diameter wire, rod, tube, and shaped extrusions, specimens shall be machined to a 63 rms surface finish or smoother on the transverse section and degreased.

8.1.1.2 Prepare a fresh 1 + 1 aqueous solution of commercial nitric acid to which has been added 5 g of copper per litre of solution before use. The solution shall be kept free from dirt and maintained during use at a temperature $24 \pm 3^\circ\text{C}$.

8.1.1.3 Etch the specimens for 3 to 5 min by lowering into the solution and agitating slowly. Remove periodically to determine whether the etching is sufficient. If the specimens tend to stain, adding 25 mL of hydrochloric acid to each litre of solution will minimize the staining. After etching, wash and dry the specimen before examination.

8.1.1.4 Examine at 10 \times magnification.

8.1.2 *Microscopical*:

8.1.2.1 Cut and degrease longitudinal specimens from the finished material. Heat to $850 \pm 25^\circ\text{C}$ for 30 min in an atmosphere containing not less than 10 % hydrogen and rapidly cool but do not necessarily quench.

8.1.2.2 Polish the specimens and etch for microscopical examination in a solution consisting of:

Water	800 mL
Sodium dichromate	16 g
Sulfuric acid (concentrated)	64 mL
Sodium chloride	12 g

8.1.2.3 Examine at 100 \times magnification.

9. General Requirements

9.1 This material shall conform to the requirements of the following applicable ASTM specifications, B122/B122M, B127, B164, and B165, except as modified by the special requirements of this specification. In case of conflict between the requirements of the basic product specification and those contained in this specification, the requirements of this specification shall govern.

10. Packaging and Package Marking

10.1 Each bundle or shipping container shall be marked as follows:

- 10.1.1 Name of material,
- 10.1.2 Specification number,
- 10.1.3 Size,
- 10.1.4 Gross weight,
- 10.1.5 Tare weight,
- 10.1.6 Net weight,
- 10.1.7 Consignor and consignee addresses,

- 10.1.8 Contract or order number, and
- 10.1.9 Other information as may be defined in the contract or order,
- 10.2 Packaging shall be subject to agreement between manufacturer and purchaser.

11. Special Requirements

- 11.1 Special tolerances, analyses, test procedures, mechani-

cal properties, and quality requirements not covered by this specification shall be as agreed upon between manufacturer and purchaser.

12. Keywords

- 12.1 copper nickel alloys; electronic devices; UNS C71580; UNS C71590; UNS C70690; UNS N04404; UNS N04400

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.

This standard is copyrighted by ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (<http://www.astm.org>).