



# Standard Practice for Exposure of Adhesive Specimens to Artificial Light<sup>1</sup>

This standard is issued under the fixed designation D 904; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This practice covers the basic principles and operating procedures for ultraviolet (UV) light aging (with or without water) of adhesive bonded joints having at least one glass or transparent adherend, using fluorescent UV (see Method A) or xenon-arc light sources (see Method B).

1.2 This practice is limited to the apparatus for obtaining, measuring, and controlling the aging conditions, and to the procedures for exposure. Sample preparation, strength, test conditions, and evaluation of the results are described in other ASTM test methods or specifications.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

### 2.1 ASTM Standards:

D 907 Terminology of Adhesives<sup>2</sup>

G 151 Practice for Exposing Nonmetallic Materials in Accelerated Test Devices that Use Laboratory Light Sources<sup>3</sup>

G 154 Practice for Operating Fluorescent Light Apparatus for UV Exposure of Nonmetallic Materials<sup>3</sup>

G 155 Practice for Operating Xenon Arc Light Apparatus for Exposure of Nonmetallic Materials<sup>3</sup>

## 3. Terminology

3.1 *Definitions*—Many of the terms in this practice are defined in Terminology D 907.

### 3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *irradiance, n*—(1) the rate at which light energy falls on a unit area of surface ( $\text{W}/\text{m}^2$ ), or (2) the radiant power incident upon a unit area of surface.

3.2.2 *radiant exposure (or light dosage), n*—(1) the accumulated light energy which has fallen on a unit area over time ( $\text{J}/\text{m}^2$ ), or (2) the irradiance integrated with respect to time.

3.2.3 *spectral irradiance, n*—the distribution of irradiance in accordance with wavelength.

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee D-14 on Adhesives and is the direct responsibility of Subcommittee D14.40 on Adhesives for Plastics. Current edition approved Oct. 10, 1999. Published December 1999. Originally published as D 904 – 46. Last previous edition D 904 – 94.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 15.06.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 14.02.

3.2.3.1 *Discussion*—Spectral irradiance is usually shown as a curve relating irradiance (ordinate) and light wavelength (abscissa). Because shorter wavelength UV is usually more damaging than longer wavelength UV, lamps with different *spectral irradiance* curves can cause drastically different amounts of UV damage, even if they produce the same total *irradiance*.

3.2.4 *spectral power distribution (SPD), n*—the amount of radiation present at each wavelength.

3.2.4.1 *Discussion*—The SPD can be expressed by power in watts, irradiance in watts/square metre, or energy in joules. The shape of the SPD would be identical in all of these units. Fluorescent lamps are frequently described by relative SPD's which show the amount of radiation at each wavelength as a percentage of the amount of radiation at the peak wavelength.

3.2.5 *UV-A, n*—ultraviolet light in the wavelength band between 315 and 400 nm.

3.2.6 *UV-B, n*—ultraviolet light in the wavelength band between 280 and 315 nm.

## 4. Significance and Use

4.1 This practice is for determining the effects of UV light, or UV light and water, on adhesive bonded joints under controlled but artificial conditions. The results of this practice can be used for comparing the relative durability of several adhesives in a specific laboratory UV exposure.

4.2 This practice is not for determining a forecast of the life of an adhesive bond in service. It is only for determining the relative durability of different adhesives compared to each other.

4.3 The results obtained may vary between the different light sources (xenon-arc or fluorescent UV), because of the different spectral-irradiance of the lamps. Adhesives should not be compared to each other based on their performance under different types of light sources.

4.4 The results obtained may vary when operation conditions are varied within the limits of a given method. The results may also vary when exposures are performed on instruments made by different manufacturers. Comparisons between materials must only be made when they are tested at the same time in the same instrument. Be sure to accurately report the operating conditions.

4.5 The type and UV transmittance characteristics of the transparent adherend used can have a significant effect on the rate and type of degradation of the adhesives being tested.

Comparisons between adhesives must only be made when tested on transparent adherends of the same type (preferably the same lot) with the same UV transmission.

4.6 This practice is not for determining the effects of atmospheric pollutants, biological organisms, salt, or freeze/thaw cycles.

## 5. Method A—Fluorescent UV

5.1 *Apparatus*—A fluorescent UV and condensation chamber in accordance with Practices G 151 and G 154.

5.2 *Lamp Type*—Use fluorescent UV-A lamps, with a peak emission at 343 nm.

NOTE 1—UV-A lamps are preferable to UV-B lamps, because UV-A wavelengths can pass through the transparent portion of the test specimen without being absorbed, whereas most of the UV-B wavelengths are filtered out by the glass.

5.2.1 Other fluorescent UV lamps meeting the size and electrical characteristics in 5.2 may be used by prior agreement, provided that the lamp and spectral power distribution are reported in conformance with Section 7. Use of lamps other than those specified in 5.2 may result in significant differences in test results.

5.3 *Specimen Mounting*—Mount the specimens in the specimen holders so that the UV passes through the transparent adherend to reach the adhesive joint or so that the joint is exposed to the effects of condensation (if applicable). Use a suitable backing panel to ensure that vapor does not escape from the test chamber around the test specimen. When the test specimens do not completely fill the racks, fill the empty spaces with blank panels to maintain the test conditions within the chamber.

5.4 *Time/Temperature Cycles*—Program the apparatus to achieve the desired test conditions, as follows:

5.4.1 *Cycle I*—4 h UV at  $60 \pm 3^\circ\text{C}$  followed by 4 h condensation at  $50 \pm 3^\circ\text{C}$ , for applications where the adhesive will be exposed to moisture.

5.4.2 *Cycle II*—24 h UV at  $60 \pm 3^\circ\text{C}$  with no condensation, for applications where moisture is not a factor.

5.4.3 Other temperatures and time cycles are acceptable, as long as they are reported in accordance with Section 7.

NOTE 2—Temperatures are black-panel temperatures measured in the panel rack.

5.5 Operate the apparatus in accordance with Practices G 151 and G 154.

5.6 Expose the specimens for 168 h or multiples thereof, unless a significant change is observed in a shorter time.

## 6. Method B—Xenon Arc

6.1 *Apparatus*—Any xenon arc apparatus in accordance with Practices G 151 and G 155.

6.2 Filter configuration in accordance with Practices G 151 and G 155.

6.3 *Irradiance Level*—Set the irradiance level to a level selected by mutual agreement.

6.4 *Time/Temperature Cycles*—Program the unit for one of the following light/spray cycles:

6.4.1 *Cycle I*—40 min of light followed by 20 min of light and specimen spray followed by 60 min of light followed by 60 min of dark. During the light cycle operate at a  $63 \pm 3^\circ\text{C}$  black-panel temperature and  $50 \pm 5\%$  relative humidity. During the dark cycle operate at  $38 \pm 2^\circ\text{C}$  black-panel temperature and  $95 \pm 5\%$  relative humidity.

6.4.2 *Cycle II*—Continuous light without water at a black-panel temperature of  $60 \pm 3^\circ\text{C}$ .

6.5 Other filters, irradiance levels, relative humidities, temperatures, and time cycles are acceptable, as long as they are reported in accordance with Section 7.

6.6 Operate the apparatus in accordance with Practices G 151 and G 155.

6.7 Expose the specimens for either (1) 168 h or multiples thereof, unless a significant change is observed in a shorter time, or (2) a given amount of radiant exposure.

## 7. Report

7.1 Report the following information:

7.1.1 Type and model of exposure apparatus and the manufacturer's designation.

7.1.2 Type of light source and the manufacturer's designation. If a xenon-arc device is used, report the filter combination and irradiance setting.

7.1.3 Specimen temperature setting.

7.1.4 Time cycle.

7.1.5 Relative humidity if controlled.

7.1.6 Number of hours of exposure, or radiant exposure.

7.1.7 Type of specimen and property evaluated for change due to light effects.

7.1.8 Type, thickness, and (optionally) UV transmission characteristics of transparent adherend used. If UV transmission is reported, describe how it was measured.

7.1.9 Mean and precision of property measured before exposure.

7.1.10 Mean and precision of property measured after exposure.

7.2 Follow the section on Report contained in Practices G 151 and G 154 or Practice G 155, as appropriate.

## 8. Precision and Bias

8.1 It is not practicable to specify the precision and bias of this practice because this practice limits itself to the relative durability of different adhesives compared to each other.

## 9. Keywords

9.1 adhesive; artificial light; ultraviolet light

 **D 904**

*The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.*

*This standard is copyrighted by ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website (<http://www.astm.org>).*