

## ASTM E 1300 GLASS LOAD RESISTANCE REPORT

### JOB DETAILS:

Project Name: RIVER CHASE - SHEET 4 - GL2 - 57 x 23 (Inner & Outer)

### WINDOW GLASS DETAILS: 1-” Insulated Window

Lite Support: 4 Edges  
Rectangular Dimensions: Long: 57” : Short: 23”  
Window Construction: Insulated - ¼” Glass / 1/2” Gas/ 1/4 ” Glass  
Window Orientation: Sloped at 0° from Vertical

#### Outer Lite

Product: SNX on CrystalGray #2  
Glass Type: Tempered  
Construction: Monolithic  
Nominal Thickness: Plate thicknesses -- 0.250”

#### InnerLite

Product: Clear: Medium Gray Frit #4  
Glass Type: Tempered  
Construction: Monolithic  
Nominal Thickness: Plate thicknesses -- 0.250”

### SHORT DURATION LOAD, RESISTANCE AND DEFLECTION DATA:

Load (<=60 sec.) : 45 psf  
Load Deflection (Inner Lite): : 0.071 in  
Load Deflection (Outer Lite): : 0.071 in  
Maximum Allowable Glass Deflection: : L/175

### CONCLUSION:

This glass configuration is below the maximum L/175 deflection for the specified loading.

### STATEMENT OF COMPLIANCE:

Procedures followed in determining the resistance of this window glass configuration are in accordance with ASTM E 1300-97.

### Disclaimer:

The load resistance of specified glass types exposed to uniform lateral loads of short or long duration subject to the following conditions:

- The glass is free of edge and surface damage and has been properly glazed in the opening in conformance with the manufacturers recommendations.
- The glass is supported on all sides by a framing system sufficiently stiff to limit lateral deflection of glass less than to 1/175 of the glass edge length; Center of glass deflection in excess of 19- and does not affect glass strength;
- The laminated glass factors for short term loads are representative of roof temperature data 1

For other limiting conditions that may apply, refer to Section 5 of ASTM E1300 and local building codes.

Prepared by : Brian A. Mistich

Date: 1/9/2017

